



Designation: **A866—14 A866 – 18**

Standard Specification for Medium Carbon Anti-Friction Bearing Steel¹

This standard is issued under the fixed designation A866; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

- 1.1 This specification covers medium carbon bearing quality steel to be used in the manufacture of anti-friction bearings.
- 1.2 Supplementary requirements of an optional nature are provided and when desired shall be so stated in the order.
- 1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.
- 1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

- [A29/A29M Specification for General Requirements for Steel Bars, Carbon and Alloy, Hot-Wrought](#)
- [A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products](#)
- [E45 Test Methods for Determining the Inclusion Content of Steel](#)
- [E112 Test Methods for Determining Average Grain Size](#)
- [E381 Method of Macroetch Testing Steel Bars, Billets, Blooms, and Forgings](#)
- [E1019 Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel, Iron, Nickel, and Cobalt Alloys by Various Combustion and Fusion Techniques](#)
- [E1077 Test Methods for Estimating the Depth of Decarburization of Steel Specimens](#)

2.2 ISO Standard:³

- [ISO 683 Part 17: Ball and Roller Bearing Steels](#)

3. Ordering Information

- 3.1 Orders for material under this specification should include the following information:
 - 3.1.1 Quantity (weight or pieces),
 - 3.1.2 Grade identification,
 - 3.1.3 ASTM designation and year of issue,
 - 3.1.4 Dimensions, and
 - 3.1.5 Supplementary requirements, if included.

4. Materials and Manufacture

4.1 Process:

- 4.1.1 The steel shall be made by a process that is capable of providing a high quality product meeting the requirements of this specification.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.28 on Bearing and Power Transmission Steels.

Current edition approved Oct. 1, 2014 May 1, 2018. Published November 2014 May 2018. Originally approved in 1987. Last previous edition approved in 2009 2014 as A866—09: A866 – 14. DOI: 10.1520/A0866-14.10.1520/A0866-18.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from International Organization for Standardization (ISO), 1, ch. de la Voie-Creuse, CP 56, CH-1211 Geneva 20, ISO Central Secretariat, BIBC II, Chemin de Blandonnet 8, CP 401, 1214 Vernier, Geneva, Switzerland, http://www.iso.org.

*A Summary of Changes section appears at the end of this standard

5. Chemical Composition and Analysis

5.1 Typical examples of chemical composition are shown in **Table 1**. Other compositions may be specified.

5.2 An analysis of each heat of steel shall be made by the steel manufacturer in accordance with Test Methods, Practices, and Terminology **A751**. The chemical composition thus determined shall conform to the requirements specified in **Table 1** for the ordered grade or to other requirements agreed upon between the manufacturer and the purchaser.

5.3 Product analysis may be made by the purchaser in accordance with Test Methods, Practices, and Terminology **A751**. Permissible variations in product analysis shall be in accordance with Specification **A29/A29M**.

6. Sizes, Shapes, and Dimensional Tolerances

6.1 The physical size and shape of the material shall be agreed upon between the manufacturer and the purchaser.

6.2 Dimensional tolerances for hot-rolled or hot-rolled and annealed bars, in straight lengths or coils, and cold-finished bars 0.500 in. (12.7 mm) and larger in diameter furnished under this specification shall conform to the requirements specified in the latest edition of Specification **A29/A29M**.

6.3 Dimensional tolerances for cold-finished coils for ball and roller material shall be as shown in **Table 2**.

6.4 Coil tolerances also apply to cold-finished straight lengths under 0.500 in. in diameter.

7. Quality Tests

7.1 The supplier shall be held responsible for the quality of the material furnished and shall make the necessary tests to ensure this quality. The supplier shall be required to report on the results of the micro-inclusion rating tests detailed below. Quality tests shown in **7.2** through **7.3** are based upon procedures established in Test Methods **E45**.

7.2 *Sampling*—Samples taken in accordance with the following paragraphs shall be obtained from 4 by 4 in. (102 by 102 mm) rolled billets or forged sections. Tests may be made on smaller or larger sections by agreement with the purchaser. A minimum 3 to 1 reduction of rolled billets or forged sections is required for strand cast products.

TABLE 1 Chemical Composition^{A,B}

Number ^C	Name	C	Mn	P (max)	S (max)	Si	Cr	Mo	V	Cu (max)	O (max) ^D	Al (max)
...	1030	0.28 to 0.34	0.60 to 0.90	0.025	0.025	0.15 to 0.35	0.30	0.0020	0.050
...	1040	0.37 to 0.44	0.60 to 0.90	0.025	0.025	0.15 to 0.35	0.30	0.0020	0.050
...	1050	0.48 to 0.55	0.60 to 0.90	0.025	0.025	0.15 to 0.35	0.30	0.0020	0.050
...	1541	0.36 to 0.44	1.35 to 1.65	0.025	0.025	0.15 to 0.35	0.30	0.0020	0.050
...	1552	0.47 to 0.55	1.20 to 1.50	0.025	0.025	0.15 to 0.35	0.30	0.0020	0.050
...	4130	0.28 to 0.33	0.40 to 0.60	0.025	0.025	0.15 to 0.35	0.80 to 1.10	0.15 to 0.25	...	0.30	0.0020	0.050
...	4140	0.38 to 0.43	0.75 to 1.00	0.025	0.025	0.15 to 0.35	0.80 to 1.10	0.15 to 0.25	...	0.30	0.0020	0.050
...	4150	0.48 to 0.53	0.75 to 1.00	0.025	0.025	0.15 to 0.35	0.80 to 1.10	0.15 to 0.25	...	0.30	0.0020	0.050
...	5140	0.38 to 0.43	0.70 to 0.95	0.025	0.025	0.15 to 0.35	0.70 to 0.90	0.30	0.0020	0.050
...	5150	0.48 to 0.53	0.70 to 0.90	0.025	0.025	0.15 to 0.35	0.70 to 0.90	0.30	0.0020	0.050
...	6150	0.48 to 0.53	0.70 to 0.90	0.025	0.025	0.15 to 0.35	0.80 to 1.10	...	0.15 min	0.30	0.0020	0.050
B40	C56E2	0.52 to 0.60	0.60 to 0.90	0.025	0.015	0.40 max	0.30	0.0020	0.050
B41	56Mn4	0.52 to 0.60	0.90 to 1.20	0.025	0.015	0.40 max	0.30	0.0020	0.050
B43	43CrMo4	0.40 to 0.46	0.60 to 0.90	0.025	0.015	0.40 max	0.90 to 1.20	0.15 to 0.30	...	0.30	0.0020	0.050

TABLE 1 Chemical Composition^{A,B}

ISO ^C	Name	C	Mn	P (max)	S (max)	Si	Cr	Mo	V	Cu (max)	O (max) ^D	Al (max)
...	1030	0.28 to 0.34	0.60 to 0.90	0.025	0.025	0.15 to 0.35	0.30	0.0020	0.050
...	1040	0.37 to 0.44	0.60 to 0.90	0.025	0.025	0.15 to 0.35	0.30	0.0020	0.050
...	1050	0.48 to 0.55	0.60 to 0.90	0.025	0.025	0.15 to 0.35	0.30	0.0020	0.050
...	1541	0.36 to 0.44	1.35 to 1.65	0.025	0.025	0.15 to 0.35	0.30	0.0020	0.050
...	1552	0.47 to 0.55	1.20 to 1.50	0.025	0.025	0.15 to 0.35	0.30	0.0020	0.050
...	4130	0.28 to 0.33	0.40 to 0.60	0.025	0.025	0.15 to 0.35	0.80 to 1.10	0.15 to 0.25	...	0.30	0.0020	0.050
...	4140	0.38 to 0.43	0.75 to 1.00	0.025	0.025	0.15 to 0.35	0.80 to 1.10	0.15 to 0.25	...	0.30	0.0020	0.050
...	4150	0.48 to 0.53	0.75 to 1.00	0.025	0.025	0.15 to 0.35	0.80 to 1.10	0.15 to 0.25	...	0.30	0.0020	0.050
...	5140	0.38 to 0.43	0.70 to 0.95	0.025	0.025	0.15 to 0.35	0.70 to 0.90	0.30	0.0020	0.050
...	5150	0.48 to 0.53	0.70 to 0.90	0.025	0.025	0.15 to 0.35	0.70 to 0.90	0.30	0.0020	0.050
...	6150	0.48 to 0.53	0.70 to 0.90	0.025	0.025	0.15 to 0.35	0.80 to 1.10	...	0.15 min	0.30	0.0020	0.050
ISO	C56E2	0.52 to 0.60	0.60 to 0.90	0.025	0.015	0.40 max	0.30	0.0020	0.050
ISO	56Mn4	0.52 to 0.60	0.90 to 1.20	0.025	0.015	0.40 max	0.30	0.0020	0.050
ISO	70Mn4	0.65 to 0.75	0.80 to 1.10	0.025	0.015	0.40 max	0.30	0.0020	0.050
ISO	43CrMo4	0.40 to 0.46	0.60 to 0.90	0.025	0.015	0.40 max	0.90 to 1.20	0.15 to 0.30	...	0.30	0.0020	0.050

^A Elements not quoted shall not be intentionally added to the steel without the agreement of the purchaser.

^B Intentional additions of calcium or calcium alloys for deoxidation or inclusion shape control are not permitted unless specifically approved by the purchaser.

^C Steels B40, B41, and B43 listed as ISO meet the requirements of ISO 683, Part 17, Second Third Edition, Table 3.

^D Oxygen content applies to product analysis and shall be determined in accordance with Test Methods **E1019**.