



Designation: **B439—12 B439 – 18**

## Standard Specification for Iron-Base Powder Metallurgy (PM) Bearings (Oil- Impregnated)<sup>1</sup>

This standard is issued under the fixed designation B439; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

### 1. Scope\*

1.1 This specification covers the requirements for porous iron-base metallic sleeve, flange, thrust, and spherical bearings that are produced from metal powders utilizing powder metallurgy (PM) technology and then impregnated with oil to supply operating lubrication.

1.2 Listed are the chemical, physical, and mechanical specifications for those standardized ferrous PM materials that have been developed specifically for the manufacture of self-lubricating bearings.

1.3 This standard is a companion to Specification **B438** that covers the requirements for porous ~~oil-impregnated~~ oil-impregnated bronze-base bearings.

1.4 Typical applications for self-lubricating iron-base PM bearings are discussed in **Appendix X1**.

1.5 Commercial bearing dimensional tolerance data are shown in ~~Appendix~~ **Appendix X2**, while engineering information regarding installation and operating parameters of PM bearings is included in ~~Appendix~~ **Appendix X3**. Additional useful information on self-lubricating bearings can be found in MPlF Standard 35 (Bearings), ISO 5755 and the technical literature.<sup>2</sup>

1.6 *Units*—With the exception of ~~density values for~~ the values for density and the mass used to determine density, for which the use of the  $g/cm^3$  unit is the long-standing practice of the PM industry, the values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not to be regarded as standard

1.7 *The following safety hazards caveat pertains only to the test methods described in this specification. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and ~~health~~ environmental practices and determine the applicability of regulatory limitations prior to use.*

1.8 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>3</sup>

**B243** Terminology of Powder Metallurgy

**B438** Specification for Bronze-Base Powder Metallurgy (PM) Bearings (Oil-Impregnated)

**B939** Test Method for Radial Crushing Strength, **K**, of Powder Metallurgy (PM) Bearings and Structural Materials

**B962** Test Methods for Density of Compacted or Sintered Powder Metallurgy (PM) Products Using Archimedes' Principle

**B963** Test Methods for Oil Content, Oil-Impregnation Efficiency, and Surface-Connected Porosity of Sintered Powder Metallurgy (PM) Products Using Archimedes' Principle

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee **B09** on Metal Powders and Metal Powder Products and is the direct responsibility of Subcommittee **B09.04** on Bearings.

Current edition approved April 1, 2012/April 1, 2018. Published September 2012/May 2018. Replaces portions of B612 and B782. Originally approved in 1966 to replace portions of B202. Last previous edition approved in 2008/2012 as ~~B439—08~~ **B439 – 12**. DOI: 10.1520/B0439-12.10.1520/B0439-18.

<sup>2</sup> *Machine Design Magazine*, Vol 54, No. 14, June 17, 1982, pp. 130–142.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard

- ~~B966 Test Method for Permeability of Powder Metallurgy (PM) Bearings Using Nitrogen Gas (Withdrawn 2015)~~<sup>4</sup>  
~~B970 Test Method for Cleanliness of Powder Metallurgy (PM) Bearings and Structural Parts (Withdrawn 2016)~~<sup>4</sup>  
**E9 Test Methods of Compression Testing of Metallic Materials at Room Temperature**  
**E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications**  
**E1019 Test Methods for Determination of Carbon, Sulfur, Nitrogen, and Oxygen in Steel, Iron, Nickel, and Cobalt Alloys by Various Combustion and Fusion Techniques**  
2.2 *MPIF Standard*:<sup>4</sup>  
**MPIF Standard 35 Materials Standards for PM Self-Lubricating Bearings**  
2.3 *ISO Standards*:<sup>5</sup>  
**ISO 2795 Plain bearings from sintered metal—Dimensions and tolerances**  
**ISO 5755 Sintered Metal Materials – Specifications,**

### 3. Terminology

3.1 *Definitions*—The definitions of the terms used in this specification are found in Terminology **B243**. Additional descriptive information is available in the Related Materials section of Volume 02.05 of the *Annual Book of ASTM Standards*.

### 4. Classification

4.1 The following list of standardized iron-base oil-impregnated PM bearing material compositions classified by composition are included in this specification. Their complete chemical, physical and mechanical requirements can be found in the specification tables. Typical applications are discussed in **Annex A1**.

4.2 The three-part alphanumeric PM Material Designation Code, developed by the PM industry, is used to identify these materials. A complete explanation of this classification system is presented in **Annex A1**.

4.2.1 *Iron and Iron-Carbon Bearing Materials, (Prefix F)*

4.2.1.1 *Iron Materials*

F-0000-K15

F-0000-K23

4.2.1.2 ~~Iron-Carbon Materials~~ *Iron-Carbon Materials*

F-0005-K20

F-0005-K28

~~F-0008-K20~~ *F-0008-K20*

~~F-0008-K32~~ *F-0008-K32*

4.2.2 *Iron-Copper Bearing Materials (Prefix FC)*

4.2.2.1 *Low-Copper Materials*

FC-0200-K20

FC-0200-K34

4.2.2.2 *Medium-Copper Materials*

FC-1000-K20

FC-1000-K30

FC-1000-K40

4.2.2.3 *High-Copper Materials*

FC-2000-K25

FC-2000-K30

FC-2000-K40

4.2.3 *Iron-Copper-Carbon Bearing Materials (Prefix FC)*

4.2.3.1 ~~Low-Copper-Carbon~~ *Low-Copper-Carbon Materials.*

FC-0205-K20

FC-0205-K35

FC-0208-K25

FC-0208-K40

4.2.3.2 *Medium-Copper-Carbon Materials.*

FC-0508-K35

FC-0508-K46

4.2.3.3 *High-Copper-Carbon Materials.*

FC-2008-K44

FC-2008-K46

<sup>4</sup> Available from Metal Powder Industries Federations, 105 College Road East, Princeton, NJ 08540, <http://www.info@mpif.org>.

<sup>5</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

#### 4.2.4 Iron-Graphite Bearing Materials (Prefix FG)

FG-0303-K10  
 FG-0303-K12  
 FG-0308-K16  
 FG-0308-K22

#### 4.2.5 Iron-Bronze-Graphite (Diluted Bronze) Bearing Materials (Prefix FCTG)

FCTG-3604-K16  
 FCTG-3604-K22

#### 4.2.6 Diffusion Alloyed Iron-Bronze Bearing Materials (Prefix FDCT)

~~FDCT-1802-K22~~ FDCT-1802-K22  
~~FDCT-1802-K31~~ FDCT-1802-K31  
~~FDCT-1802-K39~~ FDCT-1802-K39

### 5. Ordering Information

5.1 Purchase orders or contracts for iron-base oil-impregnated PM bearings covered by this purchasing specification shall include the following information:

- 5.1.1 A copy of the bearing print showing dimensions and tolerances (Section 10),
- 5.1.2 Reference to this ASTM specification, including date of issue,
- 5.1.3 Identification of bearing material by the *PM Material Designation Code* (Section 4),
- 5.1.4 Request for certification and test report documents, if required (Section 16),
- 5.1.5 Type and grade of special lubricating oil, if required (6.2.3), and
- 5.1.6 Instructions for special packaging, if required (Section 17).

### 6. Materials and Manufacture

#### 6.1 Porous Metallic Bearing:

6.1.1 Porous iron-base bearings shall be processed from a mixture of elemental, prealloyed or diffusion-alloyed metal powders with or without the additions of copper, tin, bronze or graphite powder that together meet the specified chemical composition of the material.

6.1.2 The powder mixture shall be compacted to produce a green bearing of the required dimensions, shape and density

6.1.3 The green bearings shall then be sintered in a furnace having a protective atmosphere for a time and temperature cycle that will produce the required sintered ferrous-base PM material.

6.1.4 After sintering, the iron-base bearings are normally sized to achieve the density, dimensional characteristics, concentricity, and surface finish required of the finished metallic bearing.

#### 6.2 Oil for Operating Lubrication:

6.2.1 The ~~interconnected or open~~ surface-connected porosity in the bearings shall be filled to the required volume with lubricating oil, either by an extended soaking in the hot oil or preferably by a vacuum impregnation operation.

6.2.2 A medium viscosity petroleum oil is the lubricant used for most bearing applications, but extreme operating conditions such as elevated temperatures, intermittent rotation, extremely low speeds, or heavy loads may require a synthetic lubricant or an oil with a different viscosity.

6.2.3 Unless otherwise specified by the purchaser, a high-grade turbine oil with antifoaming additives and containing corrosion and oxidation inhibitors, having a kinematic viscosity of 280 to 500 SSU [(60 × 10<sup>-6</sup> to 110 × 10<sup>-6</sup> m<sup>2</sup>/s), (60 to 110 cSt)] at 100 °F (38 °C) is normally used as the general purpose lubricating oil.

### 7. Chemical Composition

7.1 *Chemical Composition Specifications*—Each iron-base PM bearing material shall conform to the chemical composition requirements prescribed in **Table 1** when determined on a clean test sample obtained from oil-free bearings.

7.2 *Limits on Nonspecified Elements*—By agreement between the purchaser and the supplier/producer, limits may be established and chemical analyses required for elements or compounds not specified in **Table 1**.

### 8. Physical Properties

8.1 *Oil Content*—For each bearing material, the oil content of the as-received bearing shall not be less than the minimum percentage listed in **Table 2**.

8.2 *Impregnation Efficiency*—A minimum of 90 % of the ~~interconnected~~ surface-connected porosity in the as-received bearings shall be impregnated with lubricating oil.

8.3 *Impregnated Density*—The density of the sample bearings, when fully impregnated with lubricating oil, shall meet the requirements specified in **Table 2** for each bearing material.

**TABLE 1 Compositional Specifications for Iron-Base PM Bearing Materials**

Material Designation Code	Chemical Composition Requirements						
	Iron mass %	Total Carbon mass %	Combined Carbon <sup>A</sup> mass %	Graphitic Carbon <sup>B</sup> mass %	Copper mass %	Tin mass %	All Others mass %
<b>Iron and Iron-Carbon</b>							
F-0000-K15	bal.	0 to 0.3			0 to 1.5		0 to 2.0
F-0000-K23	bal.	0 to 0.3			0 to 1.5		0 to 2.0
F-0005-K20	bal.		0.3 to 0.6		0 to 1.5		0 to 2.0
F-0005-K28	bal.		0.3 to 0.6		0 to 1.5		0 to 2.0
F-0008-K20	bal.		0.6 to 0.9		0 to 1.5		0 to 2.0
F-0008-K32	bal.		0.6 to 0.9		0 to 1.5		0 to 2.0
<b>Iron-Copper</b>							
FC-0200-K20	bal.	0 to 0.3			1.5 to 3.9		0 to 2.0
<del>FC-0200-K34</del>	<del>bal.</del>	<del>0 to 0.3</del>			<del>1.5 to 3.9</del>		<del>0 to 2.0</del>
FC-0200-K34	bal.	0 to 0.3			1.5 to 3.9		0 to 2.0
FC-1000-K20	bal.	0 to 0.3			9.0 to 11.0		0 to 2.0
FC-1000-K30	bal.	0 to 0.3			9.0 to 11.0		0 to 2.0
FC-1000-K40	bal.	0 to 0.3			9.0 to 11.0		0 to 2.0
FC-2000-K25	bal.	0 to 0.3			18.0 to 22.0		0 to 2.0
FC-2000-K30	bal.	0 to 0.3			18.0 to 22.0		0 to 2.0
FC-2000-K40	bal.	0 to 0.3			18.0 to 22.0		0 to 2.0
<b>Iron-Copper-Carbon</b>							
FC-0205-K20	bal.		0.3 to 0.6		1.5 to 3.9		0 to 2.0
FC-0205-K35	bal.		0.3 to 0.6		1.5 to 3.9		0 to 2.0
FC-0208-K25	bal.		0.6 to 0.9		1.5 to 3.9		0 to 2.0
FC-0208-K40	bal.		0.6 to 0.9		1.5 to 3.9		0 to 2.0
FC-0508-K35	bal.		0.6 to 0.9		4.0 to 6.0		0 to 2.0
FC-0508-K46	bal.		0.6 to 0.9		4.0 to 6.0		0 to 2.0
FC-2008-K44	bal.		0.6 to 0.9		18.0 to 22.0		0 to 2.0
FC-2008-K46	bal.		0.6 to 0.9		18.0 to 22.0		0 to 2.0
<b>Iron-Graphite</b>							
FG-0303-K10	bal.		0 to 0.5	2.0 to 3.0			0 to 2.0
FG-0303-K12	bal.		0 to 0.5	2.0 to 3.0			0 to 2.0
FG-0308-K16	bal.		0.5 to 1.0	1.5 to 2.5			0 to 2.0
FG-0308-K22	bal.		0.5 to 1.0	1.5 to 2.5			0 to 2.0
<b>Iron-Bronze (Diluted Bronze)</b>							
FCTG-3604-K16	bal.	0.5 to 1.3	0.5 max	<sup>C</sup>	34.0 to 38.0	3.5 to 4.5	0 to 2.0
FCTG-3604-K22	bal.	0.5 to 1.3	0.5 max	<sup>C</sup>	34.0 to 38.0	3.5 to 4.5	0 to 2.0
<b>Diffusion Alloyed Iron-Bronze</b>							
FDCT-1802-K22	bal.	0 to 0.1		<sup>D</sup>	17.0 to 19.0	1.5 to 2.5	0 to 1.0
FDCT-1802-K31	bal.	0 to 0.1		<sup>D</sup>	17.0 to 19.0	1.5 to 2.5	0 to 1.0
FDCT-1802-K39	bal.	0 to 0.1		<sup>D</sup>	17.0 to 19.0	1.5 to 2.5	0 to 1.0

<sup>A</sup>The combined carbon value listed is based on the mass percent of the iron content, not the mass percent of the alloy.

<sup>B</sup>Graphitic Carbon is also known as Free Graphite.

<sup>C</sup>These compositions usually contain 0.5 to 1.3% graphite.

<sup>D</sup>These compositions have no added graphite

## 9. Mechanical Properties

9.1 *Radial Crushing Strength*—The radial crushing strength of the oil-impregnated bearing material determined on a plain sleeve bearing or a test specimen prepared from a flange or spherical bearing shall meet the minimum and maximum (if required) strength values listed in [Table 2](#).

## 10. Dimensions, Mass, and Permissible Variations

10.1 This specification is applicable to iron-base PM sleeve and flange bearings having a 3 to 1 maximum length to inside diameter ratio and a 20 to 1 maximum length to wall thickness ratio.

10.2 Standard sleeve, flange, thrust, and spherical PM bearings covered by this specification are illustrated by [Figs. 1-4](#). Most PM bearings are small and weigh less than one-quarter pound (~100 g) but they can be produced in sizes that will accommodate shafts up to approximately 8 in. (200 mm) in diameter.

10.3 Permissible variations in dimensions shall be within the limits specified on the bearing drawing accompanying the order or shall be within the limits specified in the purchase order or contract.

10.4 Recommended commercial tolerances for iron-base PM bearings are referenced throughout the tables in [Appendix X2](#).

10.5 Chamfers of 30 to 45° are generally used on PM bearings to break the corners.

TABLE 2 Physical and Mechanical Property Specifications for Iron-Base PM Bearing Materials

Material Designation Code	Physical Requirements		Mechanical Requirements <sup>4</sup>			
	Oil Content vol %	Impregnated Density g/cm <sup>3</sup>	Radical Crushing Strength, (K)			
			10 <sup>3</sup> psi		MPa	
			min	max	min	max
<b>Iron and Iron-Carbon</b>						
F-0000-K15	21	5.6 to 6.0	12		100	
F-0000-K23	17	6.0 to 6.4	23		160	
F-0005-K20	21	5.6 to 6.0	20		140	
F-0005-K28	17	6.0 to 6.4	28		190	
F-0008-K20	21	5.6 to 6.0	20		140	
F-0008-K32	17	6.0 to 6.4	32		220	
<b>Iron-Copper</b>						
FC-0200-K20	22	5.6 to 6.0	20		140	
<del>FC-0200-K34</del>	<del>17</del>	<del>6.0 to 6.4</del>	<del>34</del>		<del>230</del>	
FC-0200-K34	17	6.0 to 6.4	34		230	
FC-1000-K20	22	5.6 to 6.0	20		140	
FC-1000-K30	19	5.8 to 6.2	30		210	
FC-1000-K40	17	6.0 to 6.4	40		280	
FC-2000-K25	22	5.6 to 6.0	25		170	
FC-2000-K30	19	5.8 to 6.2	30		210	
FC-2000-K40	17	6.0 to 6.4	40		280	
<b>Iron-Copper-Carbon</b>						
FC-0205-K20	22	5.6 to 6.0	20		140	
FC-0205-K35	17	6.0 to 6.4	35		240	
FC-0208-K25	22	5.6 to 6.0	25		170	
<del>FC-0208-K40</del>	<del>17</del>	<del>6.0 to 6.4</del>	<del>40</del>		<del>280</del>	
FC-0208-K40	17	6.0 to 6.4	40		280	
FC-0508-K35	22	5.6 to 6.0	35		240	
FC-0508-K46	17	6.0 to 6.4	46		320	
FC-2008-K44	22	5.6 to 6.0	44		300	
FC-2008-K46	17	6.0 to 6.4	46		320	
<b>Iron-Graphite</b>						
FG-0303-K10	18	5.6 to 6.0	10	25	70	170
FG-0303-K12	12	6.0 to 6.4	12	35	80	240
FG-0308-K16	18	5.6 to 6.0	16	45	110	310
FG-0308-K22	12	6.0 to 6.4	22	55	150	380
<b>Iron-Bronze (Diluted Bronze)</b>						
FCTG-3604-K16	22	5.6 to 6.0	16	36	110	250
FCTG-3604-K22	17	6.0 to 6.4	22	50	150	340
<b>Diffusion Alloyed Iron-Bronze</b>						
FDCT-1802-K22	24	5.6 to 6.0	22		150	
FDCT-1802-K31	19	6.0 to 6.4	31		215	
FDCT-1802-K39	13	6.4 to 6.8	39		270	

<sup>4</sup>These requirements are based on bearings in the finished, oil-impregnated condition.




FIG. 1 Standard Sleeve Bearing

## 11. Workmanship, Finish, and Appearance

11.1 The bearings should have a matte surface, and not show oxidation. The surfaces of sized bearings should have a smooth bright finish.

11.2 When cut or fractured, the exposed surface shall exhibit a uniform appearance.




FIG. 2 Standard Flange Bearing




FIG. 3 Standard Thrust Bearing




FIG. 4 Standard Spherical Bearing

11.3 If metallographic examination is performed to determine degree of sintering, it should be done at 200 to 400 $\times$  magnification. The iron materials should show a predominantly ferritic or pearlitic phase with uniformly dispersed graphitic carbon (if present). High copper content Iron-Copper materials should show evidence of melted copper as a copper rich skeletal network around a ferrous interior structure. Diluted Bronze material should show a bronze phase with no visible free tin, dispersed throughout an iron matrix. The structure should not show an excessive number of original particle boundaries.

11.4 To verify the presence of oil in the bearing, the as-received bearing may be heated to approximately 300 °F (150 °C) for approximately 5 min. If oil is present, the surfaces will show beads of oil being exuded from the open porosity.

11.5 When bearings are ordered as being “dry-to-the-touch” to allow automated handling by the purchaser, the excess surface oil is normally removed by a centrifugal tumbling operation. It is important that the Oil Content test (13.3.1) be performed after the surface drying treatment to make certain that the required volume of lubricating oil is present.