



Designation: **C1248 – 08 (Reapproved 2012) C1248 – 18**

## Standard Test Method for Staining of Porous Substrate by Joint Sealants<sup>1</sup>

This standard is issued under the fixed designation C1248; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method covers four types of laboratory tests to determine if a joint sealant has a probability of staining a porous substrate (such as marble, limestone, sandstone, and granite). The tests are on compressed samples and include (1) storage under standard laboratory conditions, (2) storage in an oven, and (3) exposure in a fluorescent UV/condensation device, and (4) exposure in a xenon arc device.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety ~~problems, concerns,~~ if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate ~~safety~~ safety, health, and health environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 The committee with jurisdiction over this standard is not aware of any comparable standards published by other organizations.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[C717 Terminology of Building Seals and Sealants](#)

[C1442 Practice for Conducting Tests on Sealants Using Artificial Weathering Apparatus](#)

[G113 Terminology Relating to Natural and Artificial Weathering Tests of Nonmetallic Materials](#)

[G151 Practice for Exposing Nonmetallic Materials in Accelerated Test Devices that Use Laboratory Light Sources](#)

[G154 Practice for Operating Fluorescent Ultraviolet \(UV\) Lamp Apparatus for Exposure of Nonmetallic Materials](#)

[G155 Practice for Operating Xenon Arc Light Apparatus for Exposure of Non-Metallic Materials](#)

### 3. Terminology

3.1 *Definitions:*

3.1.1 Refer to Terminology [C717](#) and [G113](#) for definitions of terms used in this test method.

### 4. Summary of Test Method

4.1 In this test method standard joint specimens are compressed and clamped at the manufacturer's rated movement capability and subjected to the following treatments; (a) four of the specimens are stored at standard conditions while under compression for up to 28 days; (b) four of the specimens are exposed in an oven while under compression for up to 28 days; (c) four of the specimens are exposed either in a fluorescent UV/condensation device or in a xenon arc device while under compression for up to 28 days.

4.1.1 This test method allows for additional exposure beyond the minimum 28 day exposure period as described in 4.1. If it is desired to extend the exposure period beyond 28 days, prepare an additional six specimens for each extended exposure period. Of these six specimens prepared, two specimens each should be stored as described in the three conditions named in 4.1.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee [C24](#) on Building Seals and Sealants and is the direct responsibility of Subcommittee [C24.40](#) on Weathering.

Current edition approved Dec. 1, 2012; June 1, 2018. Published December 2012; June 2018. Originally approved in 1993. Last previous edition approved in 2008 as [C1248C1248-08\(2012\)-08](#). DOI: [10.1520/C1248-08R12](#); [10.1520/C1248-18](#).

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4.2 The effects of the test are evaluated by visual inspection for changes in surface appearance and average measurements of any stain depth and stain width.

4.3 This test method is applicable to any type of elastomeric joint sealant and any type of porous substrate.

## 5. Significance and Use

5.1 Staining of building materials is an aesthetically undesirable occurrence. This test method evaluates the likelihood of a sealant causing an early stain on a porous substrate due to exudation of materials from the sealant. Since this is an accelerated test, it does not necessarily predict that the tested sealants will not stain or discolor porous substrates over longer periods of time.

## 6. Apparatus

6.1 *Forced-Draft Oven.*

6.2 *Exposure Apparatus:*

6.2.1 Fluorescent UV/condensation apparatus that conforms to the requirements in Practices **G151** and **G154** with UVA-340 type lamps.

6.2.2 Xenon-Arc apparatus that conforms to the requirements in Practices **G151** and **G155** with daylight type filters.

6.3 *TFE-Fluorocarbon Spacers.*

6.4 *Masking Tape.*

## 7. Test Specimens

7.1 Substrates shall be 25 by 25 by 75 mm (1 by 1 by 3 in.). A total of 24 substrates are required to make the twelve test specimens.

7.1.1 If testing beyond the minimum 28 day exposure period, prepare an additional twelve substrates to make the six additional test specimens as required in **4.1.1**.

NOTE 1—The precision and bias statement is based on Vermont white marble and Bethel white granite substrates.

7.2 *Primers*—When a primer is recommended by the sealant manufacturer, apply the primer to one substrate block of each test specimen. Apply the primer where the sealant will be in contact with the substrate.

7.3 *Preparation of Test Specimens:*

7.3.1 Standard conditions of temperature and relative humidity used throughout this test method are defined as  $23 \pm 2^\circ\text{C}$  ( $73.4 \pm 3.6^\circ\text{F}$ ) and  $50 \pm 5\%$ , respectively.

7.3.1 *Multi-Component Sealants*—Prepare twelve test specimens for each substrate that is to be used in the test. After maintaining the unopened sample for at least 24 h at standard conditions, mix thoroughly for 5 min at least 250 g of base compound with the appropriate amount of curing agent. Apply a bead of sealant 13 by 13 by 50 mm ( $\frac{1}{2}$  by  $\frac{1}{2}$  by 2 in.) between parallel 25 by 75 mm (1 by 3 in.) faces of substrates (see **Fig. 1**). Use appropriate spacers to form the proper size bead. Use adhesive tape, rubber bands, or clamps to hold the test specimen together before and after filling it with the sealant. In the case of a self leveling sealant, use masking or other suitable tape to retain the sealant. Use masking tape on the top surface of substrates to prevent sealant from curing on the finished surface. Remove the tape immediately following filling of the specimen joint cavity.

7.3.2 *Single-Component Sealants*—Prepare the specimens as described in **7.3.27.3.1** except that no mixing is required. Condition the sealed cartridge or bulk container at standard conditions for at least 24 h before use.

## 8. Conditioning

8.1 Cure specimens for 21 days at standard conditions. Separate the TFE-fluorocarbon spacers from the sealant as soon as practical during the curing period without damaging the sealant.

NOTE 2—The producer may request conditions other than standard conditions for the curing of single-component sealants provided they meet the following requirements: the curing period shall extend for 21 days; and the temperature during the curing period shall not exceed  $50^\circ\text{C}$  ( $122^\circ\text{F}$ ).

## 9. Procedure

9.1 Compress all test specimens and clamp them at the manufacturer's rated movement capability for the sealant being tested.

9.2 Store four compressed specimens at standard conditions. Remove two after 14 days and two after 28 days.

9.2.1 If testing beyond the minimum 28 day exposure period, prepare an additional two compressed specimens at standard conditions for each extended period, and remove those two compressed specimens at the end of each extended period.

9.3 Place four compressed specimens in an oven at  $70 \pm 2^\circ\text{C}$  ( $158 \pm 3.6^\circ\text{F}$ ). Remove two after 14 days and two after 28 days.

9.3.1 If testing beyond the minimum 28 day exposure period, place an additional two compressed specimens in an oven at  $70 \pm 2^\circ\text{C}$  ( $158 \pm 3.6^\circ\text{F}$ ) for each extended period, and remove those two compressed specimens at the end of each extended period.

9.4 Expose four compressed samples in one of the laboratory accelerated exposure devices listed below. Choice of type of apparatus shall be by mutual agreement among the interested parties. Because of differences in type of light source and test