



Designation: **D4527 – 99 (Reapproved 2016) D4527 – 18**

Standard Test Method for Carbon Black—Solvent Extractables¹

This standard is issued under the fixed designation D4527; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the procedure for measuring carbon black solvent extractables.

1.1.1 This test method determines the total material extracted from carbon black by toluene under specified conditions. The procedure is also applicable to other solvents such as cyclohexane, etc.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* For a specific precautionary statement, see Section 7.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

~~D3051~~~~D4483~~ Practice for Carbon Black—~~Stating the Precision of ASTM Test Methods~~Evaluating Precision for Test Method Standards in the Rubber and Carbon Black Manufacturing Industries (Withdrawn 1990)

~~D3396~~ Practice for Carbon Black—~~Measuring the Precision of ASTM Test Methods~~ (Withdrawn 1990)³

3. Summary of Test Method

3.1 A specimen of carbon black is extracted for 48 h (or other specified time) in a Soxhlet extractor, the solvent removed by controlled temperature evaporation, and the extracted residue determined gravimetrically. If the carbon black extractables are to be subjected to additional analysis, see Section 7.

4. Significance and Use

4.1 The carbon black extract test procedure provides a uniform and precise method for the gravimetric determination of organic-solvent extractables on carbon black. Accuracy and precision are acceptable for most specification or regulatory purposes, or both. However, carbon black with very low extract (less than 0.02 %) may require a more rigorous extraction procedure. The actual chemical composition of the extract can vary significantly with the type and origin of the carbon black.

5. Apparatus

5.1 *Soxhlet Extraction Apparatus*, with interchangeable ground joints, 40 mm I.D. extraction tube, and 250-cm³ flask.³

5.2 *Extraction Thimble*, glass, 35-mm diameter by 90-mm height, with coarse porosity fritted disc.⁴ When filled with 50 cm³ of toluene, drainage time for the first 40 cm³ should not exceed 95 s. Discard thimbles taking longer.

¹ This test method is under the jurisdiction of ASTM Committee D24 on Carbon Black and is the direct responsibility of Subcommittee D24.31 on Non-Carbon Black Components of Carbon Black.

Current edition approved June 1, 2016; June 1, 2018. Published July 2016; July 2018. Originally approved in 1985. Last previous edition approved in 2011 as D4527 – 99 (2011); (2016). DOI: 10.1520/D4527-99R16.10.1520/D4527-18.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Fisher Scientific No. 9-556B available from Fisher Scientific Co., 203 Fisher Ave., Pittsburgh, PA 15219, has been found satisfactory. The use of Kontas K-586100 (glass jacketed) available from Kontas Glass Co., 8000 Spruce St., Vineland, NJ 08360, simplifies insulating the apparatus and reduces the possibility of breakage.

⁴ Fisher Scientific 9-653B available from Fisher Scientific Co., has been found satisfactory.

5.3 *Heater*, for extraction flask, with adjustable heat input. A hot plate extraction heater or hemispherical heating mantle is preferred.

5.4 *Filter Funnel*, glass fritted disc type, with medium porosity fritted disc.

5.5 *Filter Flask*, 125 or 250 cm³.

5.6 *Water Bath*, or other suitable warming means for evaporating solvent from extract at a controlled temperature of 40 to 50°C.

5.7 *Container*, suitable for final solvent removal and weighing of residue. A lightweight aluminum dish 63 by 17.5 mm, a TFE-fluorocarbon cup or a 50-cm³ glass beaker is suggested.⁵

5.8 *Vacuum Oven*, gravity-convection type, capable of temperature regulation within $\pm 1^\circ\text{C}$ at 125°C and temperature uniformity within $\pm 5^\circ\text{C}$.

5.9 *Oven*, gravity-convection type, capable of temperature regulation within $\pm 1^\circ\text{C}$ at 125°C and temperature uniformity within $\pm 5^\circ\text{C}$.

5.10 *Desiccator*.

5.11 *Analytical Balance*, with a sensitivity of ± 0.1 mg.

6. Reagents and Materials

6.1 *Toluene*, having a residue after evaporation less than 10 ppm (preferably less than 2 ppm).⁶

6.2 *Nitrogen*.

6.3 *Glass wool*, extracted with toluene, air-dried, followed by drying in a convection oven at 125°C for 1 h. Store in a closed container until ready to use.

6.4 *Aluminum Foil*.

7. Precautions

7.1 For safety reasons, conduct the extraction and solvent evaporation in an approved fume hood. Carbon blacks may contain polynuclear aromatic compounds, some of which are carcinogens. These compounds, when present, are so strongly bound to the carbon black that they are biologically inactive. However, they may be removed by extraction with toluene or other appropriate solvents. Avoid skin contact with solvent extracts from such carbon blacks.

7.2 For most pelleted blacks, the depth of 60 mm in the thimble should provide a sample of 15 to 25 g. Unpelleted blacks should be predensified sufficiently that this depth will require a sample of at least 10 g.

7.3 Do not use joint lubricant on the ground joints. To minimize vapor loss by leakage, the joints may be sealed with TFE-fluorocarbon inserts or wrapped with TFE-fluorocarbon laboratory tape.

7.4 New thimbles should be washed before use by suction with hot HCl and then rinsed with distilled or deionized water to remove loose particles of foreign matter such as dust. Thimbles are conveniently cleaned by back washing under suction with appropriate media (water, acetone, etc.). If the fritted disc becomes fouled with carbon black, it may be necessary to burn it out by slowly heating the thimble from room temperature to 500°C in a muffle furnace. One hour is usually sufficient. The use of chromic acid cleaning solution is not recommended. The permeability of the clean thimble should be checked periodically. Discard thimbles with drainage times exceeding the 95 s specified under 5.2.

7.5 To prevent contamination, it is recommended that all glassware used in this procedure be reserved for the extraction of carbon black. If this is not feasible, the glassware must be extracted before use in accordance with 7.6.

7.6 New glassware, including thimbles, must be extracted, repeatedly if necessary, with toluene or other solvent until the blank is acceptable (preferably less than 0.3 mg/150 cm³ solvent).

7.7 Two or three glass beads may be added to the extraction flask to promote smooth boiling. Do not use porous boiling chips.

7.8 An extraction must be discarded if there is any visible carbon black in the extraction flask or if the thimble does not drain properly and overflows at any time during the extraction.

7.9 The nitrogen should be delivered through a glass or metal tip. Do not allow plastic or rubber to contact the solvent.

7.10 To protect from dust, a loose cover over the evaporation vessel is recommended.

⁵ Fisher Scientific No. 8-732-5C (aluminum dish) available from Fisher Scientific Co., and Ventron No. 2034 (teflon cup) available from Ventron Instrument Corp., Cahn Division, 16707 S. Carmenita Rd., Cerritos, CA 90701, have been found to be satisfactory.

⁶ Distilled-in-glass toluene available from Burdick and Jackson, 1953 T.S. Harvey, Muskegan, MI 49442 and Photrex grade available from J.T. Bauer Chemical Co., 223 Red School Ln., Phillipsburg, NJ 08865 are preferred products. Analytical reagent grade available from Mallinckrodt, Inc., 675-T McDonnell Blvd., St. Louis, MO 63134 has generally been found acceptable.