

INTERNATIONAL STANDARD

NORME INTERNATIONALE

iTeh STANDARD

Ferrite cores – Guidelines on dimensions and the limits of surface
irregularities –

PREVIEW

Part 6: ETD-cores for use in power supplies

(standards.iteh.ai)

Noyaux ferrites – Lignes directrices relatives aux dimensions et aux limites
des irrégularités de surface – IEC 63093-6:2018

Partie 6: Noyaux ETD utilisés dans les alimentations électriques

c10d-429e-8d25-609a64df9929/iec-63093-6-2018





THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2018 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Secretariat
3, rue de Varembé
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 300 terminological entries in English and French, with equivalent terms in 19 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Recherche de publications IEC - webstore.iec.ch/advsearchform

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études, ...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

Découvrez notre puissant moteur de recherche et consultez gratuitement tous les aperçus des publications. Avec un abonnement, vous aurez toujours accès à un contenu à jour adapté à vos besoins.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

Electropedia - www.electropedia.org

Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 300 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 19 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch



IEC 63093-6

Edition 1.0 2018-06

INTERNATIONAL STANDARD

NORME INTERNATIONALE

iTeh STANDARD

Ferrite cores – Guidelines on dimensions and the limits of surface
irregularities –

Part 6: ETD-cores for use in power supplies

[PREVIEW
\(standards.iteh.ai\)](http://standards.iteh.ai)

Noyaux ferrites – Lignes directrices relatives aux dimensions et aux limites
des irrégularités de surface – [IEC 63093-6:2018](http://standards.iteh.ai)

Partie 6: Noyaux ETD utilisés dans les alimentations électriques
[c10d-429e-8d25-609a64df9929/iec-63093-6-2018](http://standards.iteh.ai)

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 29.100.10

ISBN 978-2-8322-1088-2

Warning! Make sure that you obtained this publication from an authorized distributor.

Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

CONTENTS

FOREWORD	4
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Primary dimensions	6
4.1 General.....	6
4.2 Dimensions of ETD-cores	7
4.2.1 Principal dimensions	7
4.2.2 Effective parameter and A_{\min} values	7
4.3 Dimensional limits for coil formers.....	8
4.4 Pin locations and base outlines	9
4.5 Pin diameter	12
5 Marking	12
6 Mounting	12
7 Limits of surface irregularities.....	12
7.1 General.....	12
7.2 Examples of surface irregularities	12
7.3 Chips and ragged edges	13
7.3.1 General.....	13
7.3.2 Chips and ragged edges on the mating surfaces	13
7.3.3 Chips and ragged edges on the other surfaces.....	13
7.4 Cracks	16
7.5 Flash	16
7.6 Pull-outs	16
7.7 Crystallites	17
7.8 Pores	18
Annex A (normative) Derived standards	19
Annex B (normative) Example of dimensions for gauges to check the dimensions of ETD-cores complying with this document	22
B.1 General.....	22
B.2 Procedure and requirements	22
Annex C (informative) Reference of allowable areas of chips	23
Bibliography.....	24
Figure 1 – Dimensions of ETD-cores.....	7
Figure 2 – Essential dimensions of coil formers	8
Figure 3 – Pin locations and base outlines viewed from the upper-side of the board	10
Figure 4 – Examples of surface irregularities	13
Figure 5 – Chip location for ETD-cores	14
Figure 6 – Crack and pull-out locations for ETD-cores	16
Figure 7 – Crystallite location for ETD-cores	17
Figure 8 – Pore location for ETD-cores	18
Figure A.1 – Main dimensions of coil formers.....	20
Figure B.1 – Gauge dimensions	22

Table 1 – Dimensions of ETD-cores	7
Table 2 – Effective parameter and A_{\min} values	8
Table 3 – Dimensional limits for coil formers	9
Table 4 – Area and length reference for visual inspection	15
Table 5 – Limits for cracks	17
Table A.1 – Main dimensions of coil formers	21
Table B.1 – Gauge dimensions	22
Table C.1 – Allowable areas of chips for ETD-cores.....	23

iTeh STANDARD PREVIEW (standards.iteh.ai)

[IEC 63093-6:2018](#)

<https://standards.iteh.ai/catalog/standards/sist/2efbb7cd-c10d-429e-8d25-609a64df9929/iec-63093-6-2018>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FERRITE CORES – GUIDELINES ON DIMENSIONS AND THE LIMITS OF SURFACE IRREGULARITIES –

Part 6: ETD-cores for use in power supplies

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
<http://standards.iec.ch/care/iec-standards/structure-and-use-of-iec-publications/iec-63093-6-2018>
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 63093-6 has been prepared by IEC technical committee 51: Magnetic components, ferrite and magnetic powder materials.

This first edition cancels and replaces the first edition of IEC 62317-6 published in 2015 and the second edition of IEC 60424-3 published in 2015. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to IEC 62317-6:2015 and IEC 60424-3:2015:

- a) This document integrates IEC 62317-6:2015 and IEC 60424-3:2015;
- b) Table 1 – Allowable areas of chips for ETD-cores, of IEC 60424-3:2015, has been moved to Annex C (informative) of this document.

The text of this standard is based on the following documents:

CDV	Report on voting
51/1215/CDV	51/1234/RVC

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 63093 series, published under the general title *Ferrite cores – Guidelines on dimensions and the limits of surface irregularities*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[IEC 63093-6:2018](#)

<https://standards.iteh.ai/catalog/standards/sist/2efbb7cd-c10d-429e-8d25-609a64df9929/iec-63093-6-2018>

FERRITE CORES – GUIDELINES ON DIMENSIONS AND THE LIMITS OF SURFACE IRREGULARITIES –

Part 6: ETD-cores for use in power supplies

1 Scope

This part of IEC 63093 specifies the dimensions that are of importance for mechanical interchangeability for a preferred range of ETD-cores made of ferrite and the essential dimensions of coil formers to be used with them, as well the effective parameter values to be used in calculations involving them. It also gives guidelines on allowable limits of surface irregularities applicable to ETD-cores.

The specifications contained in this document are useful in negotiations between ferrite core manufacturers and users about surface irregularities.

The use of derived standards which give more detailed specifications of component parts while still permitting compliance with this document is discussed in Annex A.

iTeh STANDARD

2 Normative references

PREVIEW

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 63093-6:2018

IEC 60205, *Calculation of the effective parameters of magnetic piece parts*

<https://standards.iec.ch/catalog/standards/2018/iec-63093-6-2018-c10d-429e-8d25-609a64df9929/iec-63093-6-2018>

IEC 60401-1, *Terms and nomenclature for cores made of magnetically soft ferrites – Part 1: Terms used for physical irregularities*

IEC 60424-1, *Ferrite cores – Guidelines on the limits of surface irregularities – Part 1: General specification*

3 Terms and definitions

For the purpose of this document, the terms and definitions given in IEC 60401-1 and IEC 60424-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Primary dimensions

4.1 General

Compliance with the following requirements ensures the mechanical interchangeability of complete assemblies and coil formers.

4.2 Dimensions of ETD-cores

4.2.1 Principal dimensions

The principal dimensions of ETD-cores shall be those given in Figure 1 and Table 1. The dimensions of the cores can be checked by means of gauges. By way of example, possible dimensions for these gauges are given in Annex B. In order to facilitate production, it can be necessary to use gauges with dimensions that differ from those given in Annex B, although no relaxation of the requirements for the dimensions of the cores given in Table 1 is permitted. The dimensions specified in Table 1 are illustrated in Figure 1.




Figure 1 – Dimensions of ETD-cores
<https://standards.iteh.ai/catalog/standards/sist/2efbb7cd-c10d-429e-8425-609a641f9929/iec-63093-6-2018>

Table 1 – Dimensions of ETD-cores

Size	A mm		B mm		C mm		D mm		E mm		F mm	
	Min.	Max.										
ETD 19	19,1	20,1	13,5	13,8	7,2	7,6	9,2	9,6	14,4	15,4	7,2	7,6
ETD 24	23,8	25,0	14,3	14,6	8,2	8,8	9,9	10,3	18,0	19,2	8,2	8,8
ETD 29	29,0	30,6	15,6	16,0	9,2	9,8	10,7	11,3	22,0	23,4	9,2	9,8
ETD 34	33,4	35,0	17,1	17,5	10,5	11,1	11,8	12,4	25,6	27,0	10,5	11,1
ETD 39	38,2	40,0	19,6	20,0	12,2	12,8	14,2	15,0	29,3	30,9	12,2	12,8
ETD 44	43,0	45,0	22,1	22,5	14,4	15,2	16,1	16,9	32,5	34,1	14,4	15,2
ETD 49	47,6	49,8	24,5	24,9	15,9	16,7	17,7	18,5	36,1	37,9	15,9	16,7
ETD 54	53,2	55,8	27,4	27,8	18,5	19,3	19,8	20,6	40,1	42,3	18,5	19,3
ETD 59	58,4	61,2	30,8	31,2	21,2	22,1	22,0	22,9	43,6	45,8	21,2	22,1

4.2.2 Effective parameter and A_{\min} values

The effective parameter values of a pair of cores whose dimensions comply with 4.2.1 shall be as given in Table 2. For the definitions of these parameters and their calculations, reference shall be made to IEC 60205.

Table 2 – Effective parameter and A_{\min} values

Size	C_1 mm ⁻¹	C_2 mm ⁻³	L_e mm	A_e mm ²	V_e mm ³	A_{\min}^a mm ²
ETD 19	1,253 9	$28,412 \times 10^{-3}$	55,3	44,1	2 440	39,5
ETD 24	1,053 7	$17,811 \times 10^{-3}$	62,3	59,2	3 690	55,0
ETD 29	0,927 07	$12,139 \times 10^{-3}$	70,8	76,4	5 410	70,9
ETD 34	0,814 49	$8,387 9 \times 10^{-3}$	79,1	97,1	7 680	91,6
ETD 39	0,742 00	$5,940 1 \times 10^{-3}$	92,7	125	11 600	123
ETD 44	0,599 18	$3,462 8 \times 10^{-3}$	104	173	17 900	172
ETD 49	0,542 45	$2,569 2 \times 10^{-3}$	115	211	24 200	209
ETD 54	0,455 01	$1,625 1 \times 10^{-3}$	127	280	35 700	280
ETD 59	0,382 24	$1,038 9 \times 10^{-3}$	141	368	51 700	366

NOTE 1 Manufacturers can indicate more precise values in their catalogues than those given in Table 2.

NOTE 2 The above values have been calculated using the method given in IEC 60205.

^a IEC 60205 shall be referred to for the definition of A_{\min} .

iTeh STANDARD 4.3 Dimensional limits for coil formers

The essential dimensions of coil formers suitable for use with a pair of ETD-cores shall be as given in Figure 2 and Table 3.

(standards.iteh.ai)


**Figure 2 – Essential dimensions of coil formers**

Table 3 – Dimensional limits for coil formers

Size	<i>e</i> mm	<i>f</i> ₁ mm	<i>f</i> ₂ mm	<i>d</i> ₁ mm	<i>d</i> ₂ mm
	Max.	Max.	Min.	Max.	Min.
ETD 19	14,1	9,8	7,8	18,2	15,9
ETD 24	17,6	11,0	9,0	19,6	17,1
ETD 29	21,6	12,0	10,0	21,2	18,7
ETD 34	25,2	13,6	11,3	23,4	20,9
ETD 39	28,8	15,3	13,0	28,2	25,7
ETD 44	32,0	17,7	15,4	32,0	29,5
ETD 49	35,5	19,5	17,0	35,2	32,2
ETD 54	39,5	22,1	19,6	39,3	36,3
ETD 59	43,0	24,9	22,4	43,7	40,7


4.4 Pin locations and base outlines

These shall be as shown in Figure 3, in which the base is viewed in the mounting direction, i.e. from the upper side of the printed wiring board.

**ITen STANDARD
PREVIEW
(standards.iteh.ai)**


[IEC 63093-6:2018](#)

<https://standards.iteh.ai/catalog/standards/sist/2efbb7cd-c10d-429e-8d25-609a64df9929/iec-63093-6-2018>



The module, designated as m , as shown in the grid plan, may be 2,50 mm or 2,54 mm.

Figure 3 – Pin locations and base outlines viewed from the upper-side of the board (1 of 2)



The module, designated as m , as shown in the grid plan, may be 2,50 mm or 2,54 mm.

Figure 3 (2 of 2)

4.5 Pin diameter

Coil former terminations (pins) shall be accepted by a gauge with 1,2 mm holes on a true position.

5 Marking

Where a coil former is fitted with termination pins conforming to a 2,50 mm module, it shall be clearly and indelibly marked with the letter *m*, in such a position that it can be readily seen in the completed component.

6 Mounting

According to their sizes and respective weights, it is recommended that two of the largest cores (ETD 54 and ETD 59) be fixed on the printed board by means of screws located at two opposite sides of their coil formers.

Concerning smaller sizes such as ETD 19 and ETD 24, no mounting assemblies are defined. It is recommended that the two cores be fixed by glue or adhesive tape.

7 Limits of surface irregularities

IEH STANDARD

7.1 General

Surface irregularities are defined in IEC 60424-1.

PREVIEW (standards.iteh.ai)

7.2 Examples of surface irregularities

Figure 4 shows different examples of surface irregularities of an ETD-core.

<https://standards.iteh.ai/catalog/standards/sist/2efbb7cd-c10d-429e-8d25-609a64df9929/iec-63093-6-2018>




Figure 4 – Examples of surface irregularities

<https://standards.iteh.ai/catalog/standards/sist/2efbb7cd-10d4-49c8-8d25-609a64df9929/iec-63093-6-2018>

7.3 Chips and ragged edges

7.3.1 General

The minimum area is taken as $0,5 \text{ mm}^2$, to be distinguishable to the naked eye.

Examples of allowable areas of chips are given in Annex C.

7.3.2 Chips and ragged edges on the mating surfaces

The areas of the chips located on the mating surfaces (chip 1 and chip 1' irregularities in Figure 5) shall not exceed the following limits:

- the cumulative area of the chips shall be less than 6 % of the mating surface (whether gapped or ungapped) of the centre pole;
- the total length of the ragged edges shall be less than 25 % of the perimeter of the relevant surface.

7.3.3 Chips and ragged edges on the other surfaces

The allowable areas of chips on the other surfaces are doubled as compared to the limits for the mating surface (see Figure 5).

The rule for ragged edges is the same as that for the mating surface.