



Designation: E2824 – 18

# Standard Test Method for Determination of Beryllium in Copper-Beryllium Alloys by Phosphate Gravimetric Method<sup>1</sup>

This standard is issued under the fixed designation E2824; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method describes the determination of beryllium in copper-beryllium alloys in percentages from 0.1 % to 3.0 % by the phosphate gravimetric method.

1.2 *Units*—The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* Specific hazard statements are given in Section 9.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E50 Practices for Apparatus, Reagents, and Safety Considerations for Chemical Analysis of Metals, Ores, and Related Materials

E135 Terminology Relating to Analytical Chemistry for Metals, Ores, and Related Materials

E173 Practice for Conducting Interlaboratory Studies of

Methods for Chemical Analysis of Metals (Withdrawn 1998)<sup>3</sup>

E255 Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition

E1601 Practice for Conducting an Interlaboratory Study to Evaluate the Performance of an Analytical Method

## 3. Terminology

3.1 For definitions of terms used in this method, refer to Terminology E135.

## 4. Summary of Test Method

4.1 Beryllium is precipitated as the phosphate, which is filtered, ignited, and weighed as beryllium pyrophosphate. Interfering elements, if present, may be complexed with (ethylenedinitrilo) tetraacetate solution.

## 5. Significance and Use

5.1 This test method is primarily intended to test such materials for compliance with compositional specifications. It is assumed that all who use these test methods will be trained analysts capable of performing common laboratory procedures skillfully and safely. It is expected that work will be performed in a properly equipped laboratory.

## 6. Interferences

6.1 The elements ordinarily present in beryllium-copper alloys do not interfere.

## 7. Apparatus

7.1 *Electrodes for Electroanalysis*—Recommended stationary type platinum electrodes are described in 7.1.1 and 7.1.2. The surface of the platinum electrode should be smooth, clean, and bright to promote uniform deposition and good adherence. Deviations from the exact size and shape are allowable. In instances where it is desirable to decrease the time of deposition, a generally available rotating type of electrode may be employed. Cleaning of the electrode by sandblasting is not recommended.

<sup>3</sup>The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

<sup>1</sup>This test method is under the jurisdiction of ASTM Committee E01 on Analytical Chemistry for Metals, Ores, and Related Materials and is the direct responsibility of Subcommittee E01.05 on Cu, Pb, Zn, Cd, Sn, Be, Precious Metals, their Alloys, and Related Metals.

Current edition approved April 15, 2018. Published June 2018. Originally approved in 2011. Last previous edition approved in 2011 as E2824–11. DOI: 10.1520/E2824-18.

<sup>2</sup>For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.