



Edition 1.0 2020-09

TECHNICAL SPECIFICATION



Nanomanufacturing - Key control characteristics - VIEW Part 3-3: Luminescent nanomaterials – Determination of fluorescence lifetime of semiconductor quantum dots using time correlated single photon counting (TCSPC)

<u>IEC 1S 62607-3-3:2020</u> https://standards.iteh.ai/catalog/standards/sist/0e1f821d-a5fd-4461-b4e7b575bee0b526/iec-ts-62607-3-3-2020





THIS PUBLICATION IS COPYRIGHT PROTECTED Copyright © 2020 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office 3, rue de Varembé CH-1211 Geneva 20 Switzerland

Tel.: +41 22 919 02 11 info@iec.ch www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email. ı i en

IEC Customer Service Centre - webstore iec ch/csc If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch. IEC TS 62607-3-3:2020

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

https://standards.iteh.ai/catalog/standards/sist/0e1f821d-a5fd-4461-b4e7 b575bee0b526/iec-ts-62607-3-3-2020





Edition 1.0 2020-09

TECHNICAL SPECIFICATION



Nanomanufacturing • Key control characteristics EVIEW Part 3-3: Luminescent nanomaterials – Determination of fluorescence lifetime of semiconductor quantum dots using time correlated single photon counting (TCSPC) IEC TS 62607-3-3:2020

<u>IFC_1S_62607-3-3:2020</u> https://standards.iteh.ai/catalog/standards/sist/0e1f821d-a5fd-4461-b4e7b575bee0b526/iec-ts-62607-3-3-2020

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ICS 07.030, ICS 07.120

ISBN 978-2-8322-8881-8

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD	3
INTRODUCTION	5
1 Scope	6
2 Normative references	6
3 Terms, definitions, and abbreviated terms	6
3.1 Terms and definitions	6
3.2 Abbreviated terms	7
4 Test principle	7
5 Sample preparation	8
6 Measurement	8
6.1 TCSPC fluorescence spectrometer	8
6.2 Measurement procedure	8
6.2.1 Instrument preparation	8
6.2.2 Fluorescence lifetime decay curve measurement	9
6.2.3 IRF measurement	10
6.2.4 Data analysis	10
7 Test reports	10
8 Uncertainty sourceTeh.STANDARD.PREVIEW	10
Annex A (informative) Case study for determining fluorescence lifetime of semiconductor quantum dots cancer of semiconductor guantum dots cancer of semiconduc	11
A 1 General	11
A.2 QDs sample <u>IEC TS 62607-3-3:2020</u>	11
A.3 Instruments	11
A.4 Measurement conditions for TCSPC	11
A.5 Procedures for measurement	11
A.5.1 Instrument preparation	11
A.5.2 Fluorescence lifetime decay curve measurement	11
A.5.3 IRF measurement	12
A.6 Results of fluorescence lifetime decay curve	12
A.7 Data analysis	13
Annex B (informative) Typical laser input excitation sources used in TCSPC	14
Bibliography	15
Figure 1 – The schematic of start-stop times in time-resolved fluorescence	
measurement with TCSPC	7
Figure 2 – The working schematic of TCSPC fluorescence spectrometer	8
Figure 3 – Examples for typical single exponential decay curves obtained in different measurement ranges	9
Figure A.1 – Typical fluorescence lifetime decay curve	12
Figure A.2 – Fitting result curve and IRF curve	13
	-
Table B.1 – Typical laser input excitation sources used in TCSPC	14
Table B.2 – Fluorescence lifetime of commonly used semiconductor QDs	14

INTERNATIONAL ELECTROTECHNICAL COMMISSION

NANOMANUFACTURING - KEY CONTROL CHARACTERISTICS -

Part 3-3: Luminescent nanomaterials – Determination of fluorescence lifetime of semiconductor quantum dots using time correlated single photon counting (TCSPC)

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user. (Standards.iten.al)
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. In exceptional circumstances, a technical committee may propose the publication of a Technical Specification when

- the required support cannot be obtained for the publication of an International Standard, despite repeated efforts, or
- the subject is still under technical development or where, for any other reason, there is the future but no immediate possibility of an agreement on an International Standard.

Technical Specifications are subject to review within three years of publication to decide whether they can be transformed into International Standards.

IEC TS 62607-3-3, which is a Technical Specification, has been prepared by IEC technical committee 113: Nanotechnology standardization for electrotechnical products and systems.

The text of this Technical Specification is based on the following documents:

Enquiry draft	Report on voting
113/490/DTS	113/529/RVDTS

Full information on the voting for the approval of this Technical Specification can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 62607 series, published under the general title *Nanomanufacturing – Key control characteristics*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

b575bee0b526/iec-ts-62607-3-3-2020

IEC TS 62607-3-3:2020 © IEC 2020 - 5 -

INTRODUCTION

Fluorescence lifetime is considered as the average time that luminescent materials spend in the excited state before emitting a photon and returning to the ground state. Fluorescence lifetime can vary widely from picoseconds to hundreds of nanoseconds, even to microseconds or milliseconds, depending on the type of luminescent nanomaterials.

Fluorescence lifetime is an important property of luminescent materials. Fluorescence lifetime does not depend on fluorophore concentration, absorption by the sample, thickness of the sample, method of measurement, fluorescence intensity, photo-bleaching, and/or excitation intensity. It is affected by external factors, such as temperature, polarity of solvent, and the presence of fluorescence quenchers. Fluorescence lifetime is sensitive to internal factors that are dependent on fluorophore structure.

The possible applications of measuring fluorescence lifetime include the following:

- a) determine the environment that the sample molecules inhabit, e.g. viscosity, pH value, temperature, polarity, and solvation, etc.;
- b) uncover the size and shape of the sample molecules, and the distances between different parts of the molecules:
- c) learn about the contributions of each component in a mixture of sample molecules, through time-resolved spectra of overlapping emissions;
- d) reveal the molecular interactions;
- e) obtain the kinetic and dynamic rates.

Time-correlated single photon counting (TCSPC) is a widely used, sensitive, reproducible and precise technique to measure the photon arrival time in applications characterized by a strong demand in terms of temporal resolution such as fluorescence lifetime spectroscopy and imaging, photon migration and time of flight measurements/sist/0e1f821d-a5fd-4461-b4e7-

b575bee0b526/jec-ts-62607-3-3-2020

NANOMANUFACTURING – KEY CONTROL CHARACTERISTICS –

Part 3-3: Luminescent nanomaterials – Determination of fluorescence lifetime of semiconductor quantum dots using time correlated single photon counting (TCSPC)

1 Scope

This part of IEC 62607, which is a Technical Specification, provides a method for determining the fluorescence lifetime of semiconductor quantum dots (QDs) using the time correlated single photon counting (TCSPC) technique. TCSPC is suitable for testing fluorescence lifetime in the range from picoseconds to nanoseconds. This document is only applicable to liquid samples that are stable dispersions of QDs. It is not applicable to solid samples.

This document includes:

- outlines of the experimental procedures,
- data processing, and
- case study.

iTeh STANDARD PREVIEW (standards.iteh.ai)

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references anthes latestated tion dates the referenced 4 (document (including any amendments) applies. b575bce0b526/icc-ts-62607-3-3-2020

ISO 3696, Water for analytical laboratory use – Specification and test methods

ISO 385, Laboratory glassware – Burettes

ISO 648, Laboratory glassware – Single-volume pipettes

ISO 1042, Laboratory glassware – One-mark volumetric flasks

3 Terms, definitions, and abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at http://www.iso.org/obp

3.1.1

time correlated single photon counting TCSPC

technique based on detecting single photons of periodical light signal, measuring the detection times, and building up the distribution of the photon numbers with respect to the detection time

3.1.2

fluorescence lifetime

parameter describing the time evolution of the decay of the fluorescent radiant intensity

Note 1 to entry: For a single exponential decay, the decay means that fluorescent radiant intensity decreases along the time axis to 1/e of the initial maximum value.

[SOURCE: "Glossary of terms used in photochemistry, 3rd edition (IUPAC Recommendations 2006)" *Pure Appl. Chem.* 79, 293-465 (2007)]

3.2 Abbreviated terms

- TCSPC time correlated single photon counting
- IRF instrumental response function
- OPO optical parametric oscillator
- QDs quantum dots
- SHG second harmonic generation
- THG third harmonic generation
- FHG fourth harmonic generation
- YAG yttrium aluminium garnet
- EHT extra-high tension

4 Test principle **iTeh STANDARD PREVIEW**

TCSPC is an established technique for the measurement of fluorescence lifetimes in the picosecond and nanosecond time scale. Detection of single photon delay times following multiple pulsed excitations yields a distribution that is equivalent to a fluorescence intensity decay that would be observed following a single pulse excitation of an ensemble of fluorophores in the same sample. The TCSPC technique requires a high repetition rate light source to accumulate a sufficient number of photon events for precise statistics in the probability histogram of arrival times.

Figure 1a is an illustration of how the histogram is formed over multiple cycles. In the example, fluorescence is excited repetitively by short laser pulses. The time difference between excitation and emission is measured by electronics that act like stopwatches. In Figure 1b, the typical result in time-resolved fluorescence experiments is a histogram with an exponential drop of counts towards later times.



Figure 1 – The schematic of start-stop times in time-resolved fluorescence measurement with TCSPC

5 Sample preparation

For the measurement of fluorescence lifetimes of QDs with TCSPC, a homogeneous and stable dispersion of QDs sample is needed. The solvent should be compatible with the surface chemistry of QDs sample to produce a clear dispersion, while not interfering with the fluorescence lifetime of QDs sample.

When performing the dilution, care should be taken to avoid QDs aggregation due to desorption of ligand molecules from QDs. Compatible solvent with 0,1 % to 0,5 % mass fraction of ligand molecules dissolved can be employed to dilute the QDs samples, which ensures the diluted QDs are stable and well-dispersing.

Measure the lifetime of QDs samples with different concentrations and assure that it does not change significantly with concentration. If the lifetime varies significantly, QDs aggregation may take place. To avoid aggregation, increase the concentration of ligand molecules or use a more compatible solvent.

During the analysis, reagents shall be recognized analytical grade, water shall be at least Grade 2, in accordance with ISO 3696 as appropriate.

All volumetric glassware shall be class A, in accordance with ISO 385, ISO 648 or ISO 1042 as appropriate.

A case study for determining fluorescence lifetime of semiconductor QDs is shown in Annex A.

6 Measurement

(standards.iteh.ai)

6.1 TCSPC fluorescence spectrometer

https://standards.iteh.ai/catalog/standards/sist/0e1f821d-a5fd-4461-b4e7-

TCSPC is based on the detection of the arrival times of individual photons after optical excitation of a sample. A TCSPC fluorescence spectrometer usually contains light source, detector, constant fraction discriminator (CFD), time-to-amplitude converter (TAC), analog-to-digital converter (ADC) and memorizer (MEM), as shown in Figure 2.



Figure 2 – The working schematic of TCSPC fluorescence spectrometer

The wavelength of the light source is selected to match excitation wavelength of the QDs sample. Table B.1 shows typical laser input excitation sources used in TCSPC.

6.2 Measurement procedure

6.2.1 Instrument preparation

Prepare the instrument following the user manual and operation instructions.

6.2.2 Fluorescence lifetime decay curve measurement

- a) The absorption spectrum of QDs sample is recorded and the absorption peak wavelength is measured.
- b) The emission spectrum is recorded with QDs sample excited at the absorption peak or a shorter wavelength.

NOTE Take CdTe QDs as an example. The absorption peak of CdTe QDs is located below 500 nm; so, set the excitation wavelength below 500 nm (e.g. 474 nm), with an emission wavelength of 620 nm.

c) According to the absorption peak wavelength, choose the appropriate light source and set the appropriate instrument parameters.

NOTE Take CdTe QDs as example. Choose the picosecond pulsed diode lasers light source in the range 200 nm to 400 nm, pulse width of < 1 ns, pulse repetition rate of 0 MHz to 80 MHz, and power of 0,2 mW to 2 mW.

- d) An appropriate volume of sample (50 μ L to 2 000 μ L) is added into a quartz cuvette. Then the cuvette is put into the instrument sample holder. Make sure the position of the sample is in the excitation beam.
- e) Estimate the expected lifetime and review the pulse repetition rate. The pulse repetition period of the light source should not be shorter than 10 times the longest lifetime to be measured. The pulse width should be set to 50 ps to 300 ps; and the light source (CW) power should be set to 0,2 mW to 2 mW.
- f) Check the detector signal (in counts per second). Ensure that the signal is below saturation and pulse pile-up level. With TCSPC, the signal count rate from the detector should not exceed 5 % of the rate of the exciting light source.
- g) Set up the measurement parameters and ensure to gain a proper spectrum with a short trailing stretch, as shown in Figure 3b. To obtain a proper fitting result, the far end of the tail that only contains detector background, noise and no valuable information on the decay kinetics should be excluded.



a) narrow measurement range

b) suitable measurement range

c) broad measurement range



NOTE For single exponential decay, the number of collected photons is set as 2 000 to 10 000. It is enough for most luminescent materials to set the number of collected photons as 2 000 to 10 000. A higher number of collected photons needs more unnecessary testing time.

h) Start the measurement, and record the fluorescence decay curve. The measurement will stop manually or automatically when the number of collected photons reaches the set value.