



Designation: D7481 – 18

Standard Test Methods for Determining Loose and Tapped Bulk Densities of Powders using a Graduated Cylinder¹

This standard is issued under the fixed designation D7481; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the apparatus and procedures for determining the bulk densities of free flowing and moderately cohesive powders and granular materials up to 3.5 mm in size in their loose (Method A) and tapped (Method B) states.

1.2 This test method should be performed in a laboratory under controlled conditions of temperature and humidity.

1.3 This test method is similar to those of Test Methods [B212](#), [B329](#), [B417](#), [D29](#), and [D2854](#).

1.4 All observed and calculated values shall conform to the guidelines for significant digits and rounding established in Practice [D6026](#).

1.4.1 The procedures used to specify how data are collected/recorded or calculated in this standard are regarded as the industry standard. In addition they are representative of the significant digits that generally should be retained. The procedures used do not consider material variations, purpose for obtaining the data, special purpose studies, or any considerations for the user's objectives; and it is common practice to increase or reduce significant digits of reported data to be commensurate with these considerations. It is beyond the scope of this standard to consider significant digits used in analysis methods for engineering design.

1.5 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the*

Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 *ASTM Standards:*²

[B212](#) Test Method for Apparent Density of Free-Flowing Metal Powders Using the Hall Flowmeter Funnel

[B329](#) Test Method for Apparent Density of Metal Powders and Compounds Using the Scott Volumeter

[B417](#) Test Method for Apparent Density of Non-Free-Flowing Metal Powders Using the Carney Funnel

[B527](#) Test Method for Tap Density of Metal Powders and Compounds

[C29/C29M](#) Test Method for Bulk Density (“Unit Weight”) and Voids in Aggregate

[D29](#) Test Methods for Sampling and Testing Lac Resins (Withdrawn 2005)³

[D653](#) Terminology Relating to Soil, Rock, and Contained Fluids

[D2216](#) Test Methods for Laboratory Determination of Water (Moisture) Content of Soil and Rock by Mass

[D2854](#) Test Method for Apparent Density of Activated Carbon

[D3740](#) Practice for Minimum Requirements for Agencies Engaged in Testing and/or Inspection of Soil and Rock as Used in Engineering Design and Construction

[D4164](#) Test Method for Mechanically Tapped Packing Density of Formed Catalyst and Catalyst Carriers

[D4753](#) Guide for Evaluating, Selecting, and Specifying Balances and Standard Masses for Use in Soil, Rock, and Construction Materials Testing

[D6026](#) Practice for Using Significant Digits in Geotechnical Data

[D6683](#) Test Method for Measuring Bulk Density Values of Powders and Other Bulk Solids as Function of Compressive Stress

¹ This test method is under the jurisdiction of ASTM Committee [D18](#) on Soil and Rock and is the direct responsibility of Subcommittee [D18.24](#) on Characterization and Handling of Powders and Bulk Solids.

Current edition approved June 1, 2018. Published July 2018. Last previous edition approved in 2009 as D7481 - 09, which was withdrawn January 2018 and reinstated in June 2018. DOI: 10.1520/D7481-18.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

*A Summary of Changes section appears at the end of this standard

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

ifying national authority that inspects agencies that perform this standard.

3. Terminology

3.1 Definitions:

3.1.1 For common definitions of technical terms in this standard, refer to Terminology [D653](#).

4. Summary of Test Method

4.1 Loose bulk density (Method A) is determined by measuring the volume of a known mass of powder that has been passed through a screen or funnel into a graduated cylinder.

4.2 Tapped bulk density (Method B) is achieved by mechanically tapping a measuring cylinder containing a powder. After observing the initial volume, the cylinder is mechanically tapped, and volume readings are taken until little further volume change is observed.

5. Significance and Use

5.1 The data from the loose bulk density test can be used to estimate the size of bags, totes, small bins or hoppers for the storage of a fixed mass of powder in its loose condition. It can also be used to estimate the mass of powder that will fit in small size containers such as drums. It cannot be used to estimate powder quantities of large vessels such as silos.

5.2 Values of loose bulk density obtained using this test method should be used with caution, since they can vary considerably depending on the initial state of dispersion of the test specimen, height-to-diameter ratio of specimen in graduated cylinder, dryness of powder, and other factors.

5.3 The data from the tapped bulk density test can be used to estimate the needed volume of small containers holding a fixed mass of powder that has been compacted. An example would be a packing line where vibration is used to tamp powders into a small container for effective packing purposes.

5.4 Bulk density values can vary significantly if the particle size of the actual material to be handled is different than tested. A bulk solid consisting of large and small particles often has higher bulk densities than the fine particles by themselves. For powders, lower densities are possible if the fine particles are fluidized or aerated.

5.5 The results of this test method are most applicable to containers with volumes up to about one cubic meter. Another method (such as [D6683](#)) should be used when considering larger silos.

NOTE 1—The quality of the results produced by this standard is dependent on the competence of the personnel performing it, and the suitability of the equipment and facilities used. Agencies that meet the criteria of Practice [D3740](#) are generally considered capable of competent and objective testing/sampling/inspection/etc. Users of this standard are cautioned that compliance with Practice [D3740](#) does not in itself assure reliable results. Reliable results depend on many factors; Practice [D3740](#) provides a means of evaluating some of those factors. Practice [D3740](#) was developed for agencies engaged in the testing or inspection (or both) of soil and rock. As such it is not totally applicable to agencies performing this standard. However, users of this standard should recognize that the framework of Practice [D3740](#) is appropriate for evaluating the quality of an agency performing this standard. Currently there is no known quali-

6. Apparatus

6.1 Balance having a minimum capacity of 400 g and meeting the requirements of Guide [D4753](#) for a balance of 0.1 g readability.

6.2 250 mL or 100 mL standard glass graduated cylinder. See [7.3](#).

6.3 Two screens: 1.7 mm (No. 12 U.S. sieve), 4.00 mm (No. 5 U.S. sieve). Each screen should be full height and 200 mm (8 in.) diameter (see Specification [E11](#)).

6.4 Suitable mechanical tapped density tester that provides a fixed drop of 14 ± 2 mm at a nominal rate of 300 drops per minute or a fixed drop of $3 \text{ mm} \pm 0.2 \text{ mm}$ at a nominal rate of 250 drops per minute. A typical tester is shown in [Fig. 1](#).

7. Preparation of Apparatus

7.1 Check that the balance is set on a sturdy table or bench, leveled and zeroed.

7.2 Make sure that the graduated cylinder is clean of any and all foreign material (including water or other liquids) prior to starting each test.

7.3 Depending on the untapped apparent volume of the test specimen and its particle size gradation, choose either a 250 mL or 100 mL standard glass graduated cylinder using the table below.

Graduated cylinder size, mL	Untapped apparent volume of test specimen, mL		Upper limit on particle size, mm	
	Min.	Max.	d_{50}	Absolute max.
100	50	100	1.3	2.5
250	150	250	1.7	3.5

8. Procedure

8.1 Loose Bulk Density (Method A):

8.1.1 Determine and record the mass of the graduated cylinder to the nearest 0.1 g.

8.1.2 Choose an appropriate dispersion method to ensure that the material hasn't agglomerated from transit. If this test is being conducted on a fine powder with particles much smaller than 1 mm, pass a sufficient quantity through a 1.00 mm (18 mesh) screen to break up agglomerates that may have formed during storage. Oversized particles should not be excluded from the test. Should any particles not pass through the screen, an alternate dispersion method is required, such as selecting a screen slightly larger than the largest particle to pass the material through, or stirring the material in a mixing bowl with a spatula. Maximum limits on particle size for this test are provided in [7.3](#). Avoid agglomeration and segregation of material. Describe method used on Test Data Sheet.

8.1.3 If necessary, carefully level the powder without compacting, and read the unsettled apparent volume to the nearest graduated unit. Determine and record the volume of the powder in the cylinder to the nearest graduated unit; that is, 1 mL for the 100-mL cylinder and 2 mL for the 250-mL cylinder, noting that 1 mL is equal to 1 cm^3 .