



Designation: A434/A434M – 18

Standard Specification for Steel Bars, Alloy, Hot-Wrought or Cold-Finished, Quenched and Tempered¹

This standard is issued under the fixed designation A434/A434M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers hot-wrought and cold-finished quenched and tempered alloy steel bars.

1.2 Hot-wrought bars are available in three strength level classes designated BB, BC, and BD, and cold-finished bars in two strength level classes designated BB and BC. The bars are available in the conditions specified in 4.4 subject to the size limitations shown.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[A29/A29M Specification for General Requirements for Steel Bars, Carbon and Alloy, Hot-Wrought](#)

[A108 Specification for Steel Bar, Carbon and Alloy, Cold-Finished](#)

[A370 Test Methods and Definitions for Mechanical Testing of Steel Products](#)

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.15 on Bars.

Current edition approved July 1, 2018. Published July 2018. Originally approved in 1959. Last previous edition approved in 2017 as A434/A434M-17. DOI: 10.1520/A0434_A0434M-18.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. Ordering Information

3.1 Orders for material under this specification should include the following information:

3.1.1 Quantity (weight or number of pieces),

3.1.2 Name of material (heat-treated alloy steel bars),

3.1.3 Method of finish (condition) (4.4),

3.1.4 Dimensions, including length (if hot-wrought bars are for cold finishing, the cold-finished size should also be specified),

3.1.5 ASTM designation and date of issue,

3.1.6 Chemical composition grade (Section 5),

3.1.7 Strength class (Table 1),

3.1.8 Test report, if required (Section 11),

3.1.9 Supplementary Requirements or Special Requirements, if required, and

3.1.10 End use.

NOTE 1—A typical ordering description is as follows: 10 000 lb, Heat-Treated Alloy Steel Bars, Hot Rolled, 1.000 in. diameter \times 10 ft, ASTM A434 dated ____, Grade 4140, Class BB, Test Report Required, Motor Shafts.

4. Materials and Manufacture

4.1 *Melting Practice*—The steel shall be made by any commercially viable primary steelmaking process. The primary melting may incorporate separate degassing or refining and may be followed by secondary melting using electroslag remelting or vacuum arc remelting. Where secondary melting is employed, the heat shall be defined as all of the ingots remelted from a single primary heat.

4.2 *Discard*—Sufficient discard shall be made to secure freedom from injurious piping and undue segregation.

4.3 *Slow Cooling*—Hot-wrought alloy bars shall, immediately after rolling, be allowed to cool to a temperature below the critical range under suitable conditions to prevent injury by too rapid cooling.

4.4 *Condition*—Bars shall be furnished in one of the following conditions, as specified by the purchaser. Generally, size limits for various methods of processing round bars are:

*A Summary of Changes section appears at the end of this standard

TABLE 1 Tensile Properties

NOTE 1—The mechanical properties of hot-wrought bars ordered for cold finishing, shall be governed by the cold-finished size.

Class	Diameter, in. [mm]	Yield Strength, min, ksi [MPa] ^A	Tensile Strength, min, ksi [MPa]	Elongation in 2 in. or 50 mm, min, %	Reduction of Area, min, %	SAE or AISI Representative Grade Types ^B
BB ^C	1½ [38.1] and under	90 [620]	110 [760]	20	50	3100, 4100, 8600, 8700
	Over 1½ to 2½ [38.1 to 63.5], incl	80 [550]	105 [720]	20	50	
	Over 2½ to 4 [63.5 to 102], incl	75 [520]	100 [690]	20	50	
	Over 4 to 7 [102 to 178], incl	75 [520]	95 [660]	20	50	
	Over 7 to 10 [178 to 254], incl	65 [450]	90 [620]	18	40	
BC ^C	1½ [38.1] and under	110 [760]	130 [900]	16	50	3100, 4100, 6100, 8600, 8700
	Over 1½ to 2½ [38.1 to 63.5], incl	105 [720]	125 [860]	16	50	
	Over 2½ to 4 [63.5 to 102], incl	95 [660]	115 [790]	16	45	3100, 4100, 4300, 9800
	Over 4 to 7 [102 to 178], incl	85 [590]	110 [760]	16	45	
	Over 7 to 10 [178 to 254], incl	80 [550]	105 [720]	15	40	
BD ^C	1½ [38.1] and under	130 [900]	155 [1070]	14	35	4100, 4300, 9800
	Over 1½ to 2½ [38.1 to 63.5], incl	120 [830]	150 [1030]	14	35	
	Over 2½ to 4 [63.5 to 102], incl	110 [760]	140 [960]	14	35	
	Over 4 to 7 [102 to 178], incl	105 [720]	135 [930]	14	35	
	Over 7 to 10 [178 to 254], incl	100 [690]	130 [900]	14	35	

^A Determined by the 0.2 % offset method.

^B The carbon content of all steels listed in this column may vary up to 0.55 % max, as agreed upon by the manufacturer and the purchaser.

^C Class BB, BC, BD hot-wrought; Class BB, BC cold-finished.

Hot-wrought or hot-wrought descaled	9½ in. [241.3 mm], max
Cold-drawn	⅛ to 4 in. [3.2 to 102 mm], incl
Cold-drawn, ground, and polished	⅛ to 4 in. [3.2 to 102 mm], incl
Turned and polished	¾ to 9 in. [19.1 to 229 mm], incl
Turned, ground, and polished	¾ to 9 in. [19.1 to 229 mm], incl

4.5 Heat Treatment:

4.5.1 Heat treatment shall include quenching and tempering for all classes of material. The material shall be uniformly heated to the austenitizing temperature, soaked for a sufficient length of time to produce the desired structure (a lot thus heated being known as a “quenching charge”), and quenched in a suitable medium under substantially uniform conditions for each quenching charge. The material shall then be uniformly reheated to the proper temperature for tempering (a lot thus reheated being known as a “tempering charge”), and allowed to cool uniformly. The temperature selected for tempering shall be not less than 800 °F [427 °C].

4.5.2 Material cold drawn after heat treatment shall be stress relieved, when this is necessary, in order to meet the specified mechanical properties.

4.5.3 Cold-finished bars may be stress relieved after straightening.

4.5.4 For heat-treated hot-wrought bars, where it is desirable to minimize internal stresses introduced by machine straightening, the purchaser may specify a stress relief as a final operation.

4.5.5 If warpage occurs in the stress-relieving operation, the bars may be restraightened without further stress-relieving, provided they meet the required mechanical properties.

5. Chemical Composition

5.1 The grade of steel furnished shall be specified by the purchaser and shall be selected from the standard alloy grades in Table 2 of Specification A29/A29M, or to such other compositions as may be specified using the ranges and limits in Table 4 of Specification A29/A29M.

5.2 In all cases, the grade specified shall be capable of developing the required mechanical properties. If, in the opinion of the manufacturer, the grade specified is not capable of developing the mechanical properties, the manufacturer shall notify the purchaser and whenever possible suggest an alternative grade.

5.3 Representative grade types listed for the respective classes and bar sizes in Table 1 are for information only.

6. Grain Size

6.1 Requirement—The steel shall conform to the fine austenitic grain size requirement of Specification A29/A29M.

7. Mechanical Properties

7.1 Requirements—The material, as represented by test specimens, shall conform to the tensile properties in Table 1 for the class specified.

7.2 Specimens:

7.2.1 Test specimens shall be taken longitudinally after final processing.

7.2.2 Test specimens shall be selected from the locations and prepared for testing as specified in Test Methods and Definitions A370.

7.3 Number of Tests—One tension test shall be made from each tempering or stress-relieving charge. If more than one quenching charge is represented, one tension test shall be made from each quenching charge. If more than one heat is represented in a quenching charge, one tension test shall be made from each heat and size. For continuous-type treatment, one tension test shall be made for each 25 tons [22.7 Mg] of each heat or size.

7.4 Test Method—Tension tests shall be made in accordance with Test Methods and Definitions A370 using the 0.2 % offset method when determining yield strength.