

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Electrical installations in ships –
Part 354: Single- and three-core power cables with extruded solid insulation for
rated voltages 6 kV ($U_m = 7,2$ kV) up to 30 kV ($U_m = 36$ kV)

Installations électriques à bord des navires –
Partie 354: Câbles d'énergie unipolaires et tripolaires à isolement massif extrudé
pour des tensions assignées allant de 6 kV ($U_m = 7,2$ kV) jusqu'à 30 kV
($U_m = 36$ kV)



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2020 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22,000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67,000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Recherche de publications IEC -

webstore.iec.ch/advsearchform

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: sales@iec.ch.

Electropedia - www.electropedia.org

Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 000 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 16 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

Glossaire IEC - std.iec.ch/glossary

67 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Electrical installations in ships –
Part 354: Single- and three-core power cables with extruded solid insulation for
rated voltages 6 kV ($U_m = 7,2$ kV) up to 30 kV ($U_m = 36$ kV)**

**Installations électriques à bord des navires –
Partie 354: Câbles d'énergie unipolaires et tripolaires à isolement massif
extrudé pour des tensions assignées allant de 6 kV ($U_m = 7,2$ kV) jusqu'à 30 kV
($U_m = 36$ kV)**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 29.060.20; 47.020.60

ISBN 978-2-8322-7840-6

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

FOREWORD	4
1 Scope	6
2 Normative references	6
3 Terms and definitions	7
4 General requirements	7
4.1 Rated voltage	7
4.2 Markings	8
4.2.1 Indication of origin and voltage identification	8
4.2.2 Continuity of marking	8
4.2.3 Core identification for three-cores	8
5 Constructional requirements	8
5.1 General cable description	8
5.1.1 Overview	8
5.1.2 Armoured single-sheathed cable with outer sheath only	8
5.1.3 Armoured double-sheathed cable with inner and outer sheath	8
5.1.4 Armoured single-sheathed cable with inner sheath only	9
5.1.5 Unarmoured single-sheathed cable	9
5.2 Conductors	9
5.3 Insulation	9
5.3.1 Material	9
5.3.2 Application	10
5.3.3 Thickness of insulation	10
5.4 Screening of cores	10
5.4.1 General	10
5.4.2 Conductor screening	10
5.4.3 Insulation screening	10
5.5 Metallic screen	11
5.5.1 Construction	11
5.5.2 Requirements	11
5.6 Assembly of three-core cables, inner coverings and fillers	11
5.7 Inner covering	11
5.7.1 General	11
5.7.2 Thickness of inner covering	11
5.8 Inner sheath	12
5.8.1 Material	12
5.8.2 Application	12
5.8.3 Thickness of inner sheath	12
5.9 Braid armour	12
5.9.1 General	12
5.9.2 Braid wire armour	13
5.9.3 Braid wire diameter	13
5.10 Outer sheath	13
5.10.1 Material	13
5.10.2 Application	13
5.10.3 Thickness of outer sheath	13
5.10.4 Colour of outer sheath	14

6 Tests – Methods and requirements	14
Annex A (normative) Electrical tests after installation	17
Bibliography	18
Table 1 – Insulation thickness	10
Table 2 – Thickness of extruded inner covering for calculation of fictitious diameters	12
Table 3 – Tests applicable to all cables	14
Table 4 – Additional tests for halogen-free cables	15
Table 5 – Additional test for low smoke cables	16
Table 6 – Additional tests when required	16

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[IEC 60092-354:2020](https://standards.iteh.ai/catalog/standards/sist/2fbc5b3b-3638-4c73-85e5-84307bdaa2d8/iec-60092-354-2020)

<https://standards.iteh.ai/catalog/standards/sist/2fbc5b3b-3638-4c73-85e5-84307bdaa2d8/iec-60092-354-2020>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ELECTRICAL INSTALLATIONS IN SHIPS –

**Part 354: Single- and three-core power cables
with extruded solid insulation for rated voltages
6 kV ($U_m = 7,2$ kV) up to 30 kV ($U_m = 36$ kV)**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60092-354 has been prepared by subcommittee 18A: Electric cables for ships and mobile and fixed offshore units, of IEC technical committee 18: Electrical installations of ships and of mobile and fixed offshore units.

This fourth edition cancels and replaces the third edition published in 2014. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) Editorial adaptations have been made.

The text of this International Standard is based on the following documents:

CDV	Report on voting
18A/419/CDV	18A/424/RVC

Full information on the voting for the approval of this document can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

The list of all the parts of the IEC 60092 series, under the general title *Electrical installations in ships*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[IEC 60092-354:2020](#)

<https://standards.iteh.ai/catalog/standards/sist/2fbc5b3b-3638-4c73-85e5-84307bdaa2d8/iec-60092-354-2020>

ELECTRICAL INSTALLATIONS IN SHIPS –

Part 354: Single- and three-core power cables with extruded solid insulation for rated voltages 6 kV ($U_m = 7,2$ kV) up to 30 kV ($U_m = 36$ kV)

1 Scope

This part of IEC 60092 is applicable to shipboard and offshore power cables with extruded solid insulation, conductor and core screening, having a voltage rating of one of the following: 3,6/6 (7,2) kV, 6/10 (12) kV, 8,7/15 (17,5) kV, 12/20 (24) kV, 18/30 (36) kV.

NOTE 1 Subclause 4.1 gives more details.

The cables are intended for fixed installations.

The various types of power cables are given in 5.1. The constructional requirements and test methods are aligned with those indicated in IEC 60092-350, unless otherwise specified in this document.

The object of this document is:

- to standardize cables whose safety and reliability is ensured when they are installed in accordance with the requirements of IEC 60092-352 or IEC 61892-4;
- to lay down standard manufacturing requirements and characteristics of such cables directly or indirectly bearing on safety;
- to specify test methods for checking conformity with those requirements.

NOTE 2 Only radial field cables are covered.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60038, *IEC standard voltages*

IEC 60228, *Conductors of insulated cables*

IEC 60092-350:—, *Electrical installations in ships – Part 350: General construction and test methods of power, control and instrumentation cables for shipboard and offshore applications*¹

IEC 60092-360, *Electrical installations in ships – Part 360: Insulating and sheathing materials for shipboard and offshore units, power, control, instrumentation and telecommunication cables*

¹ Under preparation. Stage at the time of publication: IEC/BPUB 60092-350:2019.

IEC 60332-1-2, *Tests on electric and optical fibre cables under fire conditions – Part 1-2: Test for vertical flame propagation for a single insulated wire or cable – Procedure for 1 kW pre-mixed flame*

IEC 60332-3-22, *Tests on electric cables under fire conditions – Part 3-22: Test for vertical flame spread of vertically-mounted bunched wires or cables – Category A*

IEC 60684-2, *Flexible insulating sleeving – Part 2: Methods of test*

IEC 60754-1, *Test on gases evolved during combustion of materials from cables – Part 1: Determination of the halogen acid gas content*

IEC 60754-2, *Test on gases evolved during combustion of materials from cables – Part 2: Determination of acidity (by pH measurement) and conductivity*

IEC 60885-2, *Electrical test methods for electric cables. Part 2: Partial discharge tests*

IEC 61034-1, *Measurement of smoke density of cables burning under defined conditions – Part 1: Test apparatus*

IEC 61034-2, *Measurement of smoke density of cables burning under defined conditions – Part 2: Test procedure and requirements*

3 Terms and definitions

ITeH STANDARD PREVIEW
(standards.iteh.ai)

For the purpose of this document, the definitions given in IEC 60092-350 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:
http://www.iso.org/iso/iso_catalogue/catalogue_tc/catalogue_tc.htm
<http://www.iec.ch/iec-60092-354-2020>

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 General requirements

4.1 Rated voltage

The standard method of designating the rated voltages of cables covered by this document shall take the form

$$U_0/U (U_m)$$

where

U_0 is the rated power-frequency voltage between phase conductor and earth or metallic screen, for which the cable is designed;

U is the rated power-frequency voltage between phase conductors for which the cable is designed;

U_m is the maximum value of the “highest system voltage” for which the equipment (including cable) may be used (see IEC 60038).

All voltages are given as RMS values.

The standard rated voltages $U_0/U (U_m)$ of the cables considered in this document are:

$$U_0/U(U_m) = 3,6/6 (7,2) - 6/10 (12) - 8,7/15 (17,5) - 12/20 (24) - 18/30 (36) \text{ kV}$$

4.2 Markings

4.2.1 Indication of origin and voltage identification

Cables shall comply with 4.1.3 of IEC 60092-350:2019 with respect to:

- b) indication of origin;
- c) rated voltage and cable construction (number of cores and cross-sectional area of the construction);
- d) continuity of marking;
- e) durability/legibility.

4.2.2 Continuity of marking

The marking is deemed to be continuous if the distance between the end of any marking and the beginning of the next does not exceed:

- a) 550 mm if the marking is on the outer surface of the cable;
- b) 275 mm in all other cases.

4.2.3 Core identification for three-cores

Cores of cables shall be provided with a suitable method of identification. Each core shall be easily distinguishable from the other cores in the cable.

5 Constructional requirements

5.1 General cable description

[IEC 60092-354:2020](https://standards.iteh.ai/catalog/standards/sist/2fbc5b3b-3638-4c73-85e5-84307bdaa2d8/iec-60092-354-2020)

<https://standards.iteh.ai/catalog/standards/sist/2fbc5b3b-3638-4c73-85e5-84307bdaa2d8/iec-60092-354-2020>

5.1.1 Overview

Shipboard and offshore cables for fixed installations shall be single or multicore cables generally constructed as indicated in 5.1.2 to 5.1.5.

5.1.2 Armoured single-sheathed cable with outer sheath only

The armoured single-sheathed cables having only an outer sheath are constructed as follows:

- copper conductor, see 5.2;
- conductor semi-conducting screen, see 5.4.2;
- insulation, see 5.3;
- insulation screening, see 5.4;
- cabling (for three-core cables), see 5.6;
- inner covering, see 5.7;
- braid armour, see 5.9;
- outer sheath applied as either one or two layer systems, see 5.10.

5.1.3 Armoured double-sheathed cable with inner and outer sheath

The armoured double-sheathed cables having both an inner and an outer sheath are constructed as follows:

- copper conductor, see 5.2;
- conductor semi-conducting screen, see 5.4.2;

- insulation, see 5.3;
- insulation screening, see 5.4;
- cabling (for three-core cables), see 5.6;
- inner sheath, see 5.8;
- braid armour, see 5.9;
- outer sheath applied as either one or two layer systems, see 5.10.

The use of a thermoplastic inner sheath (ST2 or SHF1) is not recommended if the outer sheath consists of an elastomeric cross-linked material.

5.1.4 Armoured single-sheathed cable with inner sheath only

The armoured single-sheathed cables having only an inner sheath are constructed as follows:

- copper conductor, see 5.2;
- conductor semi-conducting screen, see 5.4.2;
- insulation, see 5.3;
- insulation screening, see 5.4;
- inner sheath, see 5.8;
- braid armour, see 5.9.

The cables for installation in spaces where corrosion may occur, for example weather decks, wet locations, battery compartments, refrigeration rooms, etc., should have an outer sheath over the braid, if any, unless the braid itself is corrosion-resistant

5.1.5 Unarmoured single-sheathed cable

The unarmoured single-sheathed cables are constructed as follows:

- copper conductor, see 5.2;
- conductor semi-conducting screen, see 5.4.2;
- insulation, see 5.3;
- insulation screening, see 5.4;
- cabling (for three-core cables), see 5.6;
- inner covering (optional), see 5.7;
- outer sheath applied as either one or two layer systems, see 5.10.

5.2 Conductors

Material, metal coating, class and form of the conductors shall be in accordance with IEC 60092-350. The form of the conductor shall be round circular stranded, non-compacted or compacted, in accordance with Class 2 of IEC 60228. To aid installation, a conductor of Class 5 may be used. Cables with such Class 5 conductors should not be regarded as suitable for repeated flexing in service.

The minimum cross-sectional area shall be 10 mm² for 3,6/6 (7,2) kV cables, 16 mm² for 6/10 (12) kV cables, 25 mm² for 8,7/15 (17,5) kV cables, 35 mm² for 12/20 (24) kV cables and 50 mm² for 18/30 (36) kV cables.

5.3 Insulation

5.3.1 Material

The insulation system shall be EPR, HEPR or XLPE compounds as defined in IEC 60092-360.

5.3.2 Application

The application shall be as detailed in 4.3.2 of IEC 60092-350:2019.

5.3.3 Thickness of insulation

The thickness of the insulation shall be as specified in Table 1 and meet the requirements of 4.3.3 of IEC 60092-350:2019 so that the following applies:

- a) the thickness at any point may be less than the specified value provided the difference does not exceed 0,1 mm + 10 % of the specified value;
- b) the thickness of the semi-conducting screen on the conductor, or over the insulation, shall not be included in the thickness of insulation.

Table 1 – Insulation thickness

Nominal cross sectional area of conductor mm ²	Nominal thickness of insulation at rated voltage $U_0/U (U_m)$				
	3,6/6 (7,2) kV	6/10 (12) kV	8,7/15 (17,5) kV	12/20 (24) kV	18/30 (36) kV
	mm	mm	mm	mm	mm
10	2,5	-	-	-	-
16	2,5	3,4	-	-	-
25	2,5	3,4	4,5	-	-
35	2,5	3,4	4,5	5,5	-
50 to 185	2,5	3,4	4,5	5,5	8,0
240	2,6	3,4	4,5	5,5	8,0
300	2,8	3,4	4,5	5,5	8,0
400	3,0	3,4	4,5	5,5	8,0
500 to 630	3,2	3,4	4,5	5,5	8,0

Any smaller conductor cross-section than those given in this table is not recommended. However, if a smaller cross-section is needed, either the diameter of the conductor shall be increased by a conductor screen (see 5.4.2), or the insulation thickness shall be increased in order to limit, at the values calculated with the smallest conductor size given in this table, the maximum electrical stresses applied to the insulation under test voltage.

5.4 Screening of cores

5.4.1 General

Screening of individual cores in single- or three-core cables shall consist of a conductor screen and an insulation screen.

5.4.2 Conductor screening

The conductor screen shall be non-metallic and shall consist of an extruded semi-conducting compound, which may be applied on top of a semi-conducting tape. Where tape is not applied, the extruded semi-conducting compound shall be firmly bonded to the insulation.

5.4.3 Insulation screening

The insulation screening is designed as follows.

- a) The insulation screen shall consist of a non-metallic semi-conducting layer in combination with a metallic layer.

- b) The non-metallic layer shall be extruded directly upon the insulation of each core and consist of either a bonded or strippable semi-conducting compound.

NOTE A layer of semi-conducting tape can then be applied over the individual cores.

- c) The metallic layer shall be applied over the individual cores and shall comply with the requirements of 5.5.

5.5 Metallic screen

5.5.1 Construction

The metallic screen shall consist of one or more tapes, or a braid, or a concentric layer of wires, or a combination of tape(s) and wires.

If a metallic braid screen is applied, the fictitious diameter over the screen is given by:

$$D_c + 5d_w, \text{ in mm}$$

where

D_c is the fictitious diameter of core;

d_w is the nominal diameter of the braid wire.

5.5.2 Requirements

The dimensional, physical and electrical requirements of the metallic screen shall be determined taking into account any other requirements (e.g. national or approval authority regulations and standards), including the value of the current to be carried in case of fault.

5.6 Assembly of three-core cables, inner coverings and fillers

Cores of a three core cable shall be laid up, and the interstices filled if necessary with fillers, inner covering or inner sheath (outer sheath in the case of unarmoured cables) according to 4.6 of IEC 60092-350:2019.

5.7 Inner covering

5.7.1 General

The inner covering shall be extruded. The relevant material and characteristics shall be in accordance with extruded inner coverings in 4.6 of IEC 60092-350:2019.

5.7.2 Thickness of inner covering

The values of the (approximate) thickness of extruded inner covering for the calculation of fictitious diameters are given in Table 2.