



Designation: B556 – 90 (Reapproved 2018)

Standard Guide for Measurement of Thin Chromium Coatings by Spot Test¹

This standard is issued under the fixed designation B556; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide covers the use of the spot test for the measurement of thicknesses of electrodeposited chromium coatings over nickel and stainless steel with an accuracy of about $\pm 20\%$ (Section 9). It is applicable to thicknesses up to $1.2\ \mu\text{m}$.²

NOTE 1—Although this test can be used for coating thicknesses up to $1.2\ \mu\text{m}$, there is evidence that the results obtained by this method are high at thicknesses greater than $0.5\ \mu\text{m}$.³ In addition, for coating thicknesses above $0.5\ \mu\text{m}$, it is advisable to use a double drop of acid to prevent depletion of the test solution before completion of the test.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*⁴

B504 Test Method for Measurement of Thickness of Metallic Coatings by the Coulometric Method

B568 Test Method for Measurement of Coating Thickness by X-Ray Spectrometry

B588 Test Method for Measurement of Thickness of Transparent or Opaque Coatings by Double-Beam Interference

¹ This guide is under the jurisdiction of ASTM Committee B08 on Metallic and Inorganic Coatings and is the direct responsibility of Subcommittee B08.10 on Test Methods.

Current edition approved Aug. 1, 2018. Published August 2018. Originally approved in 1971. Last previous edition approved in 2013 as B556 – 90 (2013). DOI: 10.1520/B0556-90R18.

² Blum, W., and Olson, W. A., *Proceedings*, Am. Electroplaters Soc., Vol 28, 1940, p. 25.

³ DuRose, A. H., and Pierce, W. J., *Metal Finishing*, Vol 57, March 1959, p. 54.

⁴ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

Microscope Technique (Withdrawn 2016)⁵

3. Summary of Guide

3.1 A drop of hydrochloric acid (test solution) is deposited on the surface of the test specimen, and the time required for the hydrochloric acid to penetrate through the chromium coating (penetration time) is measured. The coating thickness is proportional to this time.

4. Significance and Use

4.1 The thickness of a decorative chromium coating is often critical to its performance.

4.2 This procedure is useful for an approximate determination when the best possible accuracy is not required. For more reliable determinations, the following methods are available: Methods **B504**, **B568**, and **B588**.

4.3 This test assumes that the rate of dissolution of the chromium by the hydrochloric acid under the specified conditions is always the same.

5. Test Solutions

5.1 For chromium on nickel the test solution is reagent grade hydrochloric acid having a specific gravity at 16°C of 1.180 ± 0.002 . (This corresponds to $11.5\ \text{N} \pm 0.2\ \text{N}$, which may be checked by titration.) For chromium on stainless steel the test solution is 20 g/L of antimony trioxide dissolved in reagent grade hydrochloric acid having a specific gravity at 16°C of 1.160.

NOTE 2—As received, reagent grade hydrochloric acid is normally more concentrated than $11.5\ \text{N}$.

6. Preparation of Test Area

6.1 The test area must be free of foreign material. Clean by rubbing the test area with a paste of magnesium oxide, rinse it, and dry it with a clean cloth or filter paper. Draw a ring with a diameter of about 6 mm on the test area with melted paraffin or with a wax pencil.

7. Procedure

7.1 Let the test specimen, the test solution, and the dropper stand long enough to reach room temperature, which should be

⁵ The last approved version of this historical standard is referenced on www.astm.org.