



## Designation: D822/D822M – 13 (Reapproved 2018)

# Standard Practice for Filtered Open-Flame Carbon-Arc Exposures of Paint and Related Coatings<sup>1</sup>

This standard is issued under the fixed designation D822/D822M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope

1.1 This practice covers the selection of test conditions for accelerated exposure testing of coatings and related products in filtered open-flame carbon-arc devices conducted according to Practices [G151](#) and [G152](#). This practice also covers the preparation of test specimens, the test conditions suited for coatings, and the evaluation of test results. [Table 1](#) describes commonly used test conditions.

1.2 This practice does not cover enclosed carbon-arc exposures of paints and related coatings, which is described in Practice [D5031/D5031M](#). Another procedure for exposing these products is covered by Practice [D3361/D3361M](#), in which the specimens are subjected to radiation from an unfiltered open-flame carbon arc that produces shorter wavelengths and higher levels of short wavelength radiation than filtered open-flame or enclosed carbon arcs.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee [D01](#) on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee [D01.27](#) on Accelerated Testing.

Current edition approved Sept. 1, 2018. Published September 2018. Originally approved in 1945. Last previous edition approved in 2013 as D822/D822M – 13. DOI: 10.1520/D0822\_D0822M-13R18.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- [D358](#) Specification for Wood to Be Used as Panels in Weathering Tests of Coatings (Withdrawn 2014)<sup>3</sup>
- [D523](#) Test Method for Specular Gloss
- [D609](#) Practice for Preparation of Cold-Rolled Steel Panels for Testing Paint, Varnish, Conversion Coatings, and Related Coating Products
- [D610](#) Practice for Evaluating Degree of Rusting on Painted Steel Surfaces
- [D659](#) Method for Evaluating Degree of Chalking of Exterior Paints (Withdrawn 1990)<sup>3</sup>
- [D660](#) Test Method for Evaluating Degree of Checking of Exterior Paints
- [D662](#) Test Method for Evaluating Degree of Erosion of Exterior Paints
- [D714](#) Test Method for Evaluating Degree of Blistering of Paints
- [D772](#) Test Method for Evaluating Degree of Flaking (Scaling) of Exterior Paints
- [D823](#) Practices for Producing Films of Uniform Thickness of Paint, Coatings and Related Products on Test Panels
- [D1005](#) Test Method for Measurement of Dry-Film Thickness of Organic Coatings Using Micrometers
- [D1186](#) Test Methods for Nondestructive Measurement of Dry Film Thickness of Nonmagnetic Coatings Applied to a Ferrous Base (Withdrawn 2006)<sup>3</sup>
- [D1400](#) Test Method for Nondestructive Measurement of Dry Film Thickness of Nonconductive Coatings Applied to a Nonferrous Metal Base (Withdrawn 2006)<sup>3</sup>
- [D1729](#) Practice for Visual Appraisal of Colors and Color Differences of Diffusely-Illuminated Opaque Materials
- [D1730](#) Practices for Preparation of Aluminum and Aluminum-Alloy Surfaces for Painting

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

**TABLE 1 Test Cycles Commonly Used for Filtered Open-Flame Carbon-Arc Exposure Testing of Paints and Related Coatings<sup>A</sup>**

Cycle Number	Cycle Description <sup>B,C</sup>	Uninsulated Black Panel Temperature <sup>B,C,D</sup>		Typical Uses <sup>E</sup>
		°C	°F	
1	Continuous light 102 min light only at 50 ± 10 % RH 18 min light and water spray <sup>G</sup> Repeat continuously	63 ± 2.5	145 ± 5	General coatings and historical convention <sup>F</sup>
2	18 h continuous light using: 102 min light only at 50 ± 10 % RH 18 min light and water spray 6 h dark using: 95 % relative humidity (no water spray) Repeat continuously	63 ± 2.5 24 ± 1.5	145 ± 5 75 ± 3	General coatings
3	48 min light at 50 ± 10 % RH 12 min light and water spray Repeat continuously	63 ± 2.5	145 ± 5	Coatings used in original equipment manufacturing
4	4 h light at 50 ± 10% RH 4 h dark with water spray Repeat continuously	63 ± 2.5	145 ± 5	Exterior pigmented stains
5	12 h light at 50 ± 10 % RH 12 h dark water spray Repeat continuously	63 ± 2.5	145 ± 5	Exterior wood stains and clears
6	8 h light at 50 ± 10 % RH 10 h light and water spray 6 h dark with water spray Repeat continuously	63 ± 2.5	145 ± 5	Marine enamels

<sup>A</sup> The cycles described are not listed in any order indicating importance, and are not necessarily recommended for the applications listed.

<sup>B</sup> Unless otherwise specified, operate the device so that the allowable deviations about the set points given in Table 1 are within the specified limits specified in the corresponding entry. If the actual operating conditions do not agree with the machine settings after the equipment has stabilized, discontinue the test and correct the cause of the disagreement before continuing.

<sup>C</sup> Set points and operational fluctuations are listed as set point ± operational fluctuation in Table 1. They are sometimes listed in separate columns. The set point is the target condition for the sensor used at the operational control point as programmed by the user. Operational fluctuations are deviations from the indicated set point at the control point indicated by the readout of the calibrated control sensor during equilibrium operation and do not include measurement uncertainty. At the operational control point, the operational fluctuation can exceed no more than the listed value at equilibrium. Therefore, when a standard calls for a particular set point, the user programs that exact number. The operational fluctuations specified with the set point do not imply that the user is allowed to program a set point higher or lower than the exact set point specified.

<sup>D</sup> Unless otherwise indicated, black panel temperatures apply during the light-only portion of the cycle. The equilibrium black panel temperature is obtained without a spray period. For light intervals less than 30 min, the black panel temperature might not reach equilibrium.

<sup>E</sup> Typical uses do not imply that results from exposures of these materials according to the cycle described will correlate to those from actual use conditions.

<sup>F</sup> Historical convention has established this as a very commonly used test cycle. This cycle may not adequately simulate the effects of outdoor exposure.

<sup>G</sup> Unless otherwise specified, water spray refers to water sprayed on the exposed surfaces of the test specimens.

### ASTM D822/D822M-13(2018)

<https://standards.iteh.ai/catalog/standards/sist/88dda408-b86e-41c6-ba4a-4bdcd2ec8113/astm-d822-d822m-132018>

**D2244** Practice for Calculation of Color Tolerances and Color Differences from Instrumentally Measured Color Coordinates

**D2616** Test Method for Evaluation of Visual Color Difference With a Gray Scale

**D3361/D3361M** Practice for Unfiltered Open-Flame Carbon-Arc Exposures of Paint and Related Coatings

**D4214** Test Methods for Evaluating the Degree of Chalking of Exterior Paint Films

**D5031/D5031M** Practice for Enclosed Carbon-Arc Exposure Tests of Paint and Related Coatings

**D5870** Practice for Calculating Property Retention Index of Plastics

**E691** Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

**E1347** Test Method for Color and Color-Difference Measurement by Tristimulus Colorimetry

**G113** Terminology Relating to Natural and Artificial Weathering Tests of Nonmetallic Materials

**G141** Guide for Addressing Variability in Exposure Testing of Nonmetallic Materials

**G147** Practice for Conditioning and Handling of Nonmetallic Materials for Natural and Artificial Weathering Tests

**G151** Practice for Exposing Nonmetallic Materials in Accelerated Test Devices that Use Laboratory Light Sources

**G152** Practice for Operating Open Flame Carbon Arc Light Apparatus for Exposure of Nonmetallic Materials

**G169** Guide for Application of Basic Statistical Methods to Weathering Tests

### 3. Terminology

3.1 The definitions given in Terminology **G113** are applicable to this practice.

### 4. Significance and Use

4.1 The ability of a paint or coating to resist deterioration of its physical and optical properties caused by exposure to light, heat, and water can be very significant for many applications. This practice is intended to induce property changes associated with end-use conditions, including the effects of sunlight, moisture, and heat. The exposure used in this practice is not intended to simulate the deterioration caused by localized weather phenomena such as atmospheric pollution, biological attack, and saltwater exposure.

4.2 *Cautions*—Variation in results may be expected when different operating conditions are used. Therefore, no reference

to the use of this practice shall be made unless accompanied by a report prepared according to Section 10 that describes the specific operating conditions used. Refer to Practice G151 for detailed information on the caveats applicable to use of results obtained according to this practice.

NOTE 1—Additional information on sources of variability and on strategies for addressing variability in the design, execution, and data analysis of laboratory accelerated exposure tests is found in Guide G141.

4.2.1 The spectral power distribution of light from an open-flame carbon-arc is significantly different from that produced in light and water exposure devices using other carbon-arc configurations or other light sources. The type and rate of degradation and the performance rankings produced by exposures to filtered open-flame carbon-arcs can be much different from those produced by exposures to other types of laboratory light sources.

4.2.2 Interlaboratory comparisons are valid only when all laboratories use the same type of carbon-arc, filters, and exposure conditions.

4.3 Reproducibility of test results between laboratories has been shown to be good when the stability of materials is evaluated in terms of performance ranking compared to other materials or to a control.<sup>4,5</sup> Therefore, exposure of a similar material of known performance (a control) at the same time as the test materials is strongly recommended. It is recommended that at least three replicates of each material be exposed to allow for statistical evaluation of results.

4.4 Test results will depend upon the care that is taken to operate the equipment according to Practice G152. Significant factors include regulation of line voltage, freedom from salt or other deposits from water, temperature and humidity control, and conditions of the electrodes.

4.5 All references to exposures in accordance with this practice must include a complete description of the test cycle used.

## 5. Apparatus

5.1 Use filtered open-flame carbon-arc apparatus that conforms to the requirements defined in Practices G151 and G152.

5.2 Unless otherwise specified, the spectral power distribution of the filtered open-flame carbon-arc shall conform to the requirements in Practice G152 for carbon arc with daylight filters.

## 6. Hazards

6.1 **Warning**—In addition to other precautions, never look directly at the carbon arc because UV radiation can damage the eye. Most carbon-arc machines are equipped with door safety switches, but users of old equipment must be certain to turn off the power to the carbon arc before opening the test-chamber door.

6.2 The burning carbon rods used in these devices become very hot during use. Make sure to allow at least 15 min for the arcs to cool after the device is turned off before attempting to change the carbon rods.

6.3 Carbon residue and ash are known respiratory irritants. Wear an appropriate high-efficiency dust respirator, gloves, and safety glasses when handling or changing carbon rods. Make sure to wash any carbon residue from hands or arms prior to eating or drinking.

## 7. Test Specimens

7.1 Apply the coating to flat (plane) panels with the substrate, method of preparation, method of application, coating system, film thickness, and method of drying consistent with the anticipated end use, or as mutually agreed upon between the producer and user.

7.2 Panel specifications and methods of preparation include but are not limited to Practices D609 or D1730, or Specification D358. Select panel sizes suitable for use with the exposure apparatus.

7.3 Coat test panels in accordance with Test Methods D823, then measure the film thickness in accordance with an appropriate procedure selected from Test Methods D1005, D1186, or D1400. Nondestructive methods are preferred because panels so measured need not be repaired.

7.4 Prior to exposing coated panels in the apparatus, condition them at  $23 \pm 2^\circ\text{C}$  [ $73 \pm 3^\circ\text{F}$ ] and  $50 \pm 10\%$  relative humidity for one of the following periods in accordance with the type of coating:

Baked coatings	24 h
Radiation-cured coatings	24 h
All other coatings	7 days

7.4.1 Other procedures for preparation of test specimens may be used if agreed upon between all interested parties.

7.5 Mount specimens in holders so that only the minimum specimen area required for support by the holder is covered. Do not use this covered area of the specimen as part of the test area.

7.6 Unless otherwise specified, expose at least three replicate specimens of each test and control material.

7.7 Follow the procedures described in Practice G147 for identification and conditioning and handling of specimens of test, control, and reference materials prior to, during, and after exposure.

7.8 Do not mask the face of a specimen for the purpose of showing on one panel the effects of various exposure times. Misleading results may be obtained by this method, since the masked portion of the specimen is still exposed to temperature and humidity cycles that in many cases will affect results.

7.9 Retain a supply of unexposed file specimens of all materials evaluated.

7.9.1 When destructive tests are run, it is recommended that a sufficient number of file specimens be retained so that the property of interest can be determined on unexposed file specimens each time exposed materials are evaluated.

<sup>4</sup> Fischer, R., "Results of Round-Robin Studies of Light- and Water-Exposure Standard Practices," *Accelerated and Outdoor Durability Testing of Organic Materials*, ASTM STP 1202, ASTM, 1993.

<sup>5</sup> Ketola, W., and Fischer, R., "Characterization and Use of Reference Materials in Accelerated Durability Tests," *VAMAS Technical Report No. 30*, NIST, June 1997.