



Edition 2.0 2021-06 REDLINE VERSION

INTERNATIONAL STANDARD



Resin based reactive compounds used for electrical insulation – Part 3-8: Specifications for individual materials – Resins for cable accessories

Document Preview

IEC 60455-3-8:2021

https://standards.iteh.ai/catalog/standards/iec/d1df4fe3-30d5-4ea1-af78-2b7e55cd16d2/iec-60455-3-8-2021





THIS PUBLICATION IS COPYRIGHT PROTECTED Copyright © 2021 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office 3, rue de Varembé CH-1211 Geneva 20 Switzerland

Tel.: +41 22 919 02 11 info@iec.ch www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC online collection - oc.iec.ch

Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 18 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.







Edition 2.0 2021-06 REDLINE VERSION

INTERNATIONAL STANDARD



Resin based reactive compounds used for electrical insulation – Part 3-8: Specifications for individual materials – Resins for cable accessories

Document Preview

IEC 60455-3-8:2021

https://standards.iteh.ai/catalog/standards/iec/d1df4fe3-30d5-4ea1-af78-2b7e55cd16d2/iec-60455-3-8-2021

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ICS 29.035.01

ISBN 978-2-8322-9916-6

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOF	REWO	RD	3
ΙΝΤΙ	RODU	ICTION	5
1	Scop	e	6
2	Norm	ative references	6
3	Term	s and definitions	7
4	Desig	gnation	7
5	Туре	testing	8
5	5.1	General	8
5	.2	Sampling	9
5	.3	Preparation and conditioning	9
	5.3.1	General	9
	5.3.2	Individual components prior to mixing	9
	5.3.3	, 300 ,	
	5.3.4		
	5.3.5	5 5 () ,	
	.4	Sequence of tests	
-	.5	Test report	
6		methods	
7		mation on supply, packaging, marking and labelling	19
7	. 1	Packaging	19
7	.2	Marking and labelling	19
	7.2.1		
	7.2.2	IEC 60455 3 8:2021	
s://sta	7.2.3		
		normative) Examination grid Idt4le3-30d5-4ea1-at78-2b7e55cd16d2/iec-604	
Bibl	iograp	bhy	21
Figu	ire A.	1 – Examination grid	20
Figu	ire A.2	2 – Position of examination grid on the specimen	20
Tah	_ 1 ما	Categories of resins	Q
		-	
		Type tests: test methods and requirements for Polyurethane resins	
		Type tests: test methods and requirements for Polybutadiene resins	
		Type tests: test methods and requirements for Epoxy resins	
Tab	le 5 –	Type tests: test methods and requirements for Silicone resins	18

INTERNATIONAL ELECTROTECHNICAL COMMISSION

RESIN BASED REACTIVE COMPOUNDS USED FOR ELECTRICAL INSULATION –

Part 3-8: Specifications for individual materials – Resins for cable accessories

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- https 6) All users should ensure that they have the latest edition of this publication. 257e55cd16d2/lec-60455-3-8-2021
 - 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
 - 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
 - 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition IEC 60455-3-8:2013. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

International Standard IEC 60455-3-8 has been prepared by IEC technical committee 15: Solid electrical insulating materials.

This second edition cancels and replaces the first edition published in 2013. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) Clause 1: a link to assemblies according to IEC 60502-4 and EN 50393 was introduced;
- b) designation: the categories, especially the mechanical ones, were redefined;
- c) type tests: the testing was updated based on the chemical basis of the material;
- d) type tests: additional materials were introduced;
- e) Annex A: an examination grid was established.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
15/937/FDIS	15/941/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/standardsdev/publications.

A list of all parts in the IEC 60455 series, published under the general title Resin based reactive compounds used for electrical insulation, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

This part of IEC 60455 is one of a series which deals with specifications for reactive compounds and their components for electrical insulation. This series consists of three parts:

Part 1: Definitions and general requirements (IEC 60455-1);

Part 2: Methods of test (IEC 60455-2);

Part 3: Specifications for individual materials (IEC 60455-3)

IEC 60455-3-8 is one of the specification sheets comprising Part 3 as follows:

Sheet 8: Resins for cable accessories

iTeh Standards (https://standards.iteh.ai) Document Preview

IEC 60455-3-8:2021

https://standards.iteh.ai/catalog/standards/iec/d1df4fe3-30d5-4ea1-af78-2b7e55cd16d2/iec-60455-3-8-2021

RESIN BASED REACTIVE COMPOUNDS USED FOR ELECTRICAL INSULATION –

Part 3-8: Specifications for individual materials – Resins for cable accessories

1 Scope

This part of IEC 60455 gives the requirements for resins for power cable accessories that conform to this specification and meet established levels of performance. However, the selection of a material by a user for a specific application should will be based on the actual requirements necessary for adequate performance in that application and not on this specification alone.

These materials are designed to be used in low and medium voltage cable accessories and as such, electrical performance is proven as part of the assembly. Examples of this are described in EN 50393 and IEC 60502-4.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60093, Methods of test for volume resistivity and surface resistivity of solid electrical insulating materials

IEC 60212, Standard conditions for use prior to and during the testing of solid electrical insulating materials

IEC 60243-1, *Electric strength of insulating materials – Test methods – Part 1: Tests at power frequencies*

IEC 60250, Recommended methods for the determination of the permittivity and dielectric dissipation factor of electrical insulating materials at power, audio and radio frequencies including metre wavelengths

IEC 60455-2:2015, Resin based reactive compounds used for electrical insulation – Part 2: *Methods of test*-4

IEC 62631-2-1, Dielectric and resistive properties of solid insulating materials – Part 2-1: Relative permittivity and dissipation factor – Technical Frequencies (0,1 Hz – 10 MHz) – AC Methods

IEC 62631-3-1, Dielectric and resistive properties of solid insulating materials – Part 3-1: Determination of resistive properties (DC methods) – Volume resistance and volume resistivity – General method

¹—Third edition to be published.

IEC 60455-3-8:2021 RLV © IEC 2021 - 7 -

IEC 62631-3-2, Dielectric and resistive properties of solid insulating materials – Part 3-2: Determination of resistive properties (DC methods) – Surface resistance and surface resistivity

ISO 179 (all parts), *Plastics – Determination of Charpy impact properties*

ISO 527 (all parts), Plastics – Determination of tensile properties

ISO 868, Plastics and ebonite – Determination of indentation hardness by means of a durometer (Shore hardness)

ISO 1183-1, Plastics – Methods for determining the density of non-cellular plastics – Part 1: Immersion method, liquid pycnometer method and titration method

ISO 2137, Petroleum products and lubricants – Determination of cone penetration of lubricating greases and petrolatum

ISO 2555, Plastics — Resins in the liquid state or as emulsions or dispersions — Determination of apparent viscosity-by the Brookfield Test using a single cylinder type rotational viscometer method

ISO 4895, Plastics – Liquid epoxy resins – Determination of tendency to crystallize

3 Terms and definitions **iTeh** Standards

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

• IEC Electropedia: available at http://www.electropedia.org/

http://www.iso.org/obp_sed16d2/jec-60455-3-8-2021

3.1

tendency to crystallization

measurement of the ability of epoxy based resin not to change from a liquid to a solid state at a certain temperature close to water freezing point for a fixed time

3.2

type test

test made on materials or components of a cable accessory in order to demonstrate satisfactory performance characteristics to meet the intended application

3.3

outer protection

cured resinous compound to protect the connections from damage by external mechanical forces

4 Designation

Resins for cable accessories are classified in categories according to their application as follows (see Table 1):

Voltage Class	Function	Characteristic
Low Voltage (L)	Outer Protection (OP)	Cures in presence of
Medium Voltage (M)	Insulation (I)	water ^a (W)

Table 1 – Categories of resins

^a Low foaming during curing when in contact with water as described in the subclause dealing with curing under water in IEC 60455-2.

Voltage class	Mechanical classification	Characteristic
Low voltage (L)	Rigid (R)	
Madium valtaga (M)	Soft (S)	Suitable for applications in presence of water ^a (W)
Medium voltage (M)	Gel-like (G)	p
^a Low foaming during IEC 60455-2:2015, 5.2	curing when in contact w 6.	ith water as described in

A resin is identified by a combination of categories.

For example: Low voltage compound for outer protection: L-OP;

Low voltage compound for insulation, curing in presence of water: L-I-W;

Low voltage compound for insulation and mechanical protection: L-OP-I.

For the purposes of this document:

- rigid is defined as Shore D > 30, the material has self-supporting properties,
- soft is defined as Shore $D \le 30$ and Shore $A \ge 10$,
- gel-like is defined as Shore A < 103C 60455 3 82021

A resin is identified by a combination of categories, for example:

- low voltage compound soft: L-S
- low voltage compound rigid, suitable for application in presence of water: L-R-W

Resins without specific information about application temperature are suitable for applications between 5 °C and 40 °C. Otherwise the application temperature shall be stated by the manufacturer on the packaging.

Tests for type testing are carried out in accordance with each of the resin categories.

Low voltage:	0,6/1,0 (1,2) kV
Medium voltage:	20,8/36 (42) kV

5 Type testing

5.1 General

Tests shall be carried out based on the category of the resins as defined in Table 1. These tests are of such nature that, once successfully completed, they need not to be repeated unless changes are made in the material, component formulation or manufacturing process, which might change the performance characteristics.

IEC 60455-3-8:2021 RLV © IEC 2021 - 9 -

5.2 Sampling

Samples for type testing shall be taken from material stored under conditions-prescribed specified by the manufacturer. The type testing of resins shall be carried out-either:

- as a stand-alone test. Samples used for the type test shall be taken from material available as agreed between supplier and user, or
- in combination with an accessory type test. Samples used for the resins type test shall be taken from the same batch as used in the accessory type test. In the event that no material from the same batch is available, then the samples used for the resins type test shall be taken from material available as agreed between supplier and user.

5.3 Preparation and conditioning

5.3.1 General

5.3.3

For all tests, unless otherwise specified, conditioning shall be made in accordance with IEC 60212 using standard atmosphere B.

5.3.2 Individual components prior to mixing

Components (resin and reactive component) shall be individually prepared, conditioned and tested in accordance with the relevant test method as specified in stage 1 of the sequence of tests given in Table 2 to Table 5. Filler, when supplied as a separate item, shall not be tested as a component.

Resin just after mixing (curing stage)

Compounds shall be prepared and mixed according to the supplier's instructions and tested as specified in stage 2 of the sequence of tests specified in Table 2 to Table 5.

5.3.4 Cured resin (original)

Compounds shall be prepared according to the supplier's instructions and cured for 24 h at room temperature unless otherwise specified in the test method referred to in stage 3 of the 021 sequence of tests given in Table 2 to Table 5. The specimens shall be post-cured at (80 ± 2) °C for 24 h unless otherwise specified in the test method, and then cooled in a desiccator for 24 h at room temperature.

NOTE If degassing is needed, it will be indicated in the relevant test method and the conditions for the degassing will also be indicated.

5.3.5 Cured resin after thermal ageing (dry and wet)

Cured resin shall be prepared according to the supplier's instructions and cured for 24 h at room temperature unless otherwise specified in the test method referred to in stage 4 of the sequence of tests given in Table 2 to Table 5. The specimens shall be post-cured at (80 ± 2) °C for 24 h unless otherwise specified in the test method, and then cooled in a desiccator for 24 h at room temperature.

NOTE If degassing is needed, it will be indicated in the relevant test method and the conditions for the degassing will also be indicated.

5.4 Sequence of tests

Tests shall be carried out on the resin in the following four stages, in accordance with Table 2 to Table 5:

- stage 1: Reactive components prior to mixing;
- stage 2: Resin just after mixing (curing stage);
- stage 3: Cured resin (original);

stage 4: Cured resin after heat exposure (dry and wet).

5.5 Test report

The test report shall include the following data:

- 1) resin category and identification;
- 2) lot number or identification;
- 3) marking and labelling according to the material safety data sheet (MSDS);
- test results;
- 5) major test parameters, including conditioning and calibration, if any;
- 6) processing conditions used to mix the compound;
- 7) copy of the technical data sheet (TDS) and MSDS.

6 Test methods

International test methods are specified within this document where available; for those tests where there is no international test method available or the test method needs some adaptation of conditions, the method or specific conditions are specified in IEC 60455-2.

For special applications, water temperature in Table 2 to Table 5, stage 4-2 (Wet heat resistance), may can be insufficient to ensure the satisfactory performance of the resinous compound. In such cases, upon agreement between manufacturer and user, the compound shall be tested using an increased temperature of 90 °C. The chosen temperature shall be recorded in the test report.

Compliance at 90 °C also includes compliance at 70 °C.

IEC 60455-3-8:2021

https://standards.iteh.ai/catalog/standards/iec/d1df4fe3-30d5-4ea1-af78-2b7e55cd16d2/iec-60455-3-8-2021

Number		nonnani reat		vedanienie	CVIPILIAN
+	Viscosity at 5 °C	ISO 2555	Pas	<u>≤ 50</u>	
Ş	Tendency to crystallization	ISO 4895	1	5 No turbidity after 7 days	Epoxy resin part only.
Stage 2 – Re	-Resins just after mixing (curing stage)	1		30c	
£	Pot life (0,3 I at 5 °C)	HEC 60455-2	min	e3-)21 ≮75	
	Pot life (0,3 l at 40 °C)		min	1f4 f 3-20	
4	Curing in presence of water, gas volume	IEC 60455-2	ie ₽	/d1- -3 ←10	For PUR resin type W only-
	Curing in presence of water, physical structure	laro ds.i	rev	No blisters or cracks, small amount of individual bubbles or inclusions acceptable.	Include picture of cut resin surface with scale in report.
Stage 3 – Cu	Stage 3 – Cured resins (original)	n c a r	P	ind:	
Φ	Density	ISO 1183-1	g/cm ³	g/sta 5d2 Record value	Density should be > 1,05 g/cm ³
θ	Impact strength (without notch)	150 179	<mark>kJ/m</mark> ²	talo cd1) €	No break is also acceptable.
t	Hardness (Shore)	180 868	n	1/ca Record value	
ф	Tensile strength	1 SO 527	MPa	h.a b7e Record value	
0	Elongation at break	ISO 527	~ %	s. ita 8-2 Record value	
10	Dissipation factor at room temperature .ª	HEC 60250	Do	tandard eal- <mark>M:</mark> dissipation factor ≤ 0,1	Using conductive silver varnish as electrode material Using 500 V/mm at 50 Hz
#	Dielectric constant at room temperature ^e	HEC 60250		https://s M⊡relative permittivity ≤ 6	Using conductive silver varnish as electrode material Using 500 V/mm at 50 Hz
12	Volume resistivity at room temperature.ª	IEC 60093	Ω cm	MI: ≥ 1 × 10¹³ LI: ≥ 1 × 10¹⁴	Using conductive silver varnish as electrode material Using 500 V/mm at 50 Hz
^a According	 According IEC 60212 atmosphere B. 				

Table 2 – Type tests: test methods and requirements for Polyurethane resins

	4-1 Dry heat resistance: 28 days at 120 °C (vented oven) - IEC 60455-2	; (vented oven) – IE (60455-	Þ			
1 3	Mass loss	IEC 60455-2		%		<u>5</u>	
4	Impact strength (without notch)	ISO 179		kJ/m²		<u>≥</u> 4	No break is also acceptable.
	4-2 Wet heat resistance: 28 days at 70 °C ^b in water – IEC 60455-2	^b in water – IEC 604	;5-2				
15	Hardness (retention/original)	838 OSI		%	5-	<u>≥ 80</u>	
16	Tensile strength (retention/original)	ISO 527	i)	%	30c	<u>≥ 65</u>	
7	Elongation at break (retention/original)	ISO 527		%	e3-)21	<mark>≥ 65</mark>	
18	Dielectric strength (resin type-LI)	IEC 60243-1	eh	kV/mm	1f41 8-2	<u>≥ 2</u>	For resin type I only.
	Dielectric strength (resin type MI)	ls	•			I∕ 5	
See also	See also Clause 6 regarding test at 90 °C.						
		da		202	dards		