

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Resin based reactive compounds used for electrical insulation –
Part 3-8: Specifications for individual materials – Resins for cable accessories**

**Composés réactifs à base de résines utilisés comme isolants électriques –
Partie 3-8: Spécifications pour matériaux particuliers – Résines pour
accessoires de câble**



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2021 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC online collection - oc.iec.ch

Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 18 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Recherche de publications IEC - webstore.iec.ch/advsearchform

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études, ...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: sales@iec.ch.

IEC online collection - oc.iec.ch

Découvrez notre puissant moteur de recherche et consultez gratuitement tous les aperçus des publications. Avec un abonnement, vous aurez toujours accès à un contenu à jour adapté à vos besoins.

Electropedia - www.electropedia.org

Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 000 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 16 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Resin based reactive compounds used for electrical insulation –
Part 3-8: Specifications for individual materials – Resins for cable accessories**

**Composés réactifs à base de résines utilisés comme isolants électriques –
Partie 3-8: Spécifications pour matériaux particuliers – Résines pour
accessoires de câble**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 29.035.01

ISBN 978-2-8322-9895-4

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	7
4 Designation	7
5 Type testing.....	8
5.1 General.....	8
5.2 Sampling.....	8
5.3 Preparation and conditioning.....	8
5.3.1 General	8
5.3.2 Individual components prior to mixing	8
5.3.3 Resin just after mixing (curing stage).....	8
5.3.4 Cured resin (original)	9
5.3.5 Cured resin after thermal ageing (dry and wet)	9
5.4 Sequence of tests	9
5.5 Test report	9
6 Test methods.....	9
7 Information on supply, packaging, marking and labelling.....	16
7.1 Packaging.....	16
7.2 Marking and labelling.....	16
7.2.1 General.....	16
7.2.2 Components	16
7.2.3 Accessory kit	16
Annex A (normative) Examination grid	17
Bibliography.....	18
Figure A.1 – Examination grid.....	17
Figure A.2 – Position of examination grid on the specimen	17
Table 1 – Categories of resins	7
Table 2 – Type tests: test methods and requirements for Polyurethane resins	10
Table 3 – Type tests: test methods and requirements for Polybutadiene resins.....	12
Table 4 – Type tests: test methods and requirements for Epoxy resins	13
Table 5 – Type tests: test methods and requirements for Silicone resins.....	15

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**RESIN BASED REACTIVE COMPOUNDS USED
FOR ELECTRICAL INSULATION –****Part 3-8: Specifications for individual materials –
Resins for cable accessories**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60455-3-8 has been prepared by IEC technical committee 15: Solid electrical insulating materials.

This second edition cancels and replaces the first edition published in 2013. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) Clause 1: a link to assemblies according to IEC 60502-4 and EN 50393 was introduced;
- b) designation: the categories, especially the mechanical ones, were redefined;
- c) type tests: the testing was updated based on the chemical basis of the material;
- d) type tests: additional materials were introduced;
- e) Annex A: an examination grid was established.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
15/937/FDIS	15/941/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/standardsdev/publications.

A list of all parts in the IEC 60455 series, published under the general title *Resin based reactive compounds used for electrical insulation*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/d1df4fe3-30d5-4ea1-af78-2b7e55cd16d2/iec-60455-3-8-2021>

INTRODUCTION

This part of IEC 60455 is one of a series which deals with specifications for reactive compounds and their components for electrical insulation. This series consists of three parts:

Part 1: Definitions and general requirements (IEC 60455-1);

Part 2: Methods of test (IEC 60455-2);

Part 3: Specifications for individual materials (IEC 60455-3)

IEC 60455-3-8 is one of the specification sheets comprising Part 3 as follows:

Sheet 8: Resins for cable accessories

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[IEC 60455-3-8:2021](https://standards.iteh.ai/catalog/standards/sist/d1df4fe3-30d5-4ea1-af78-2b7e55cd16d2/iec-60455-3-8-2021)

<https://standards.iteh.ai/catalog/standards/sist/d1df4fe3-30d5-4ea1-af78-2b7e55cd16d2/iec-60455-3-8-2021>

RESIN BASED REACTIVE COMPOUNDS USED FOR ELECTRICAL INSULATION –

Part 3-8: Specifications for individual materials – Resins for cable accessories

1 Scope

This part of IEC 60455 gives the requirements for resins for power cable accessories that conform to this specification and meet established levels of performance. However, the selection of a material by a user for a specific application will be based on the actual requirements necessary for adequate performance in that application and not on this specification alone.

These materials are designed to be used in low and medium voltage cable accessories and as such, electrical performance is proven as part of the assembly. Examples of this are described in EN 50393 and IEC 60502-4.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

<https://standards.iteh.ai/catalog/standards/sist/d1df4e3-30d5-4ea1-af78-202510062107-60455-3-8-2021>

IEC 60212, *Standard conditions for use prior to and during the testing of solid electrical insulating materials*

IEC 60243-1, *Electric strength of insulating materials – Test methods – Part 1: Tests at power frequencies*

IEC 60455-2:2015, *Resin based reactive compounds used for electrical insulation – Part 2: Methods of test*

IEC 62631-2-1, *Dielectric and resistive properties of solid insulating materials – Part 2-1: Relative permittivity and dissipation factor – Technical Frequencies (0,1 Hz – 10 MHz) – AC Methods*

IEC 62631-3-1, *Dielectric and resistive properties of solid insulating materials – Part 3-1: Determination of resistive properties (DC methods) – Volume resistance and volume resistivity – General method*

IEC 62631-3-2, *Dielectric and resistive properties of solid insulating materials – Part 3-2: Determination of resistive properties (DC methods) – Surface resistance and surface resistivity*

ISO 179 (all parts), *Plastics – Determination of Charpy impact properties*

ISO 527 (all parts), *Plastics – Determination of tensile properties*

ISO 868, *Plastics and ebonite – Determination of indentation hardness by means of a durometer (Shore hardness)*

ISO 1183-1, *Plastics – Methods for determining the density of non-cellular plastics – Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 2137, *Petroleum products and lubricants – Determination of cone penetration of lubricating greases and petrolatum*

ISO 2555, *Plastics — Resins in the liquid state or as emulsions or dispersions — Determination of apparent viscosity using a single cylinder type rotational viscometer method*

ISO 4895, *Plastics – Liquid epoxy resins – Determination of tendency to crystallize*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

tendency to crystallization

measurement of the ability of epoxy based resin not to change from a liquid to a solid state at a certain temperature close to water freezing point for a fixed time

3.2

type test

test made on materials or components of a cable accessory in order to demonstrate satisfactory performance characteristics to meet the intended application

4 Designation

Resins for cable accessories are classified in categories according to their application as follows (see Table 1):

Table 1 – Categories of resins

Voltage class	Mechanical classification	Characteristic
Low voltage (L)	Rigid (R)	Suitable for applications in presence of water ^a (W)
Medium voltage (M)	Soft (S)	
	Gel-like (G)	
^a Low foaming during curing when in contact with water as described in IEC 60455-2:2015, 5.26.		

For the purposes of this document:

- rigid is defined as Shore D > 30, the material has self-supporting properties,
- soft is defined as Shore D ≤ 30 and Shore A ≥ 10,
- gel-like is defined as Shore A < 10.

A resin is identified by a combination of categories, for example:

- low voltage compound – soft: L-S
- low voltage compound – rigid, suitable for application in presence of water: L-R-W

Resins without specific information about application temperature are suitable for applications between 5 °C and 40 °C. Otherwise the application temperature shall be stated by the manufacturer on the packaging.

Tests for type testing are carried out in accordance with each of the resin categories.

Low voltage: 0,6/1,0 (1,2) kV

Medium voltage: 20,8/36 (42) kV

5 Type testing

5.1 General

Tests shall be carried out based on the category of the resins as defined in Table 1. These tests are of such nature that, once successfully completed, they need not to be repeated unless changes are made in the material, component formulation or manufacturing process, which might change the performance characteristics.

5.2 Sampling

Samples for type testing shall be taken from material stored under conditions specified by the manufacturer. The type testing of resins shall be carried out:

- as a stand-alone test. Samples used for the type test shall be taken from material available as agreed between supplier and user, or
- in combination with an accessory type test. Samples used for the resins type test shall be taken from the same batch as used in the accessory type test. In the event that no material from the same batch is available, then the samples used for the resins type test shall be taken from material available as agreed between supplier and user.

5.3 Preparation and conditioning

5.3.1 General

For all tests, unless otherwise specified, conditioning shall be made in accordance with IEC 60212 using standard atmosphere B.

5.3.2 Individual components prior to mixing

Components (resin and reactive component) shall be individually prepared, conditioned and tested in accordance with the relevant test method as specified in stage 1 of the sequence of tests given in Table 2 to Table 5. Filler, when supplied as a separate item, shall not be tested as a component

5.3.3 Resin just after mixing (curing stage)

Compounds shall be prepared and mixed according to the supplier's instructions and tested as specified in stage 2 of the sequence of tests specified in Table 2 to Table 5.

5.3.4 Cured resin (original)

Compounds shall be prepared according to the supplier's instructions and cured for 24 h at room temperature unless otherwise specified in the test method referred to in stage 3 of the sequence of tests given in Table 2 to Table 5. The specimens shall be post-cured at $(80 \pm 2) ^\circ\text{C}$ for 24 h unless otherwise specified in the test method, and then cooled in a desiccator for 24 h at room temperature.

NOTE If degassing is needed, it will be indicated in the relevant test method and the conditions for the degassing will also be indicated.

5.3.5 Cured resin after thermal ageing (dry and wet)

Cured resin shall be prepared according to the supplier's instructions and cured for 24 h at room temperature unless otherwise specified in the test method referred to in stage 4 of the sequence of tests given in Table 2 to Table 5. The specimens shall be post-cured at $(80 \pm 2) ^\circ\text{C}$ for 24 h unless otherwise specified in the test method, and then cooled in a desiccator for 24 h at room temperature.

NOTE If degassing is needed, it will be indicated in the relevant test method and the conditions for the degassing will also be indicated.

5.4 Sequence of tests

Tests shall be carried out on the resin in the following four stages, in accordance with Table 2 to Table 5:

- stage 1: Reactive components prior to mixing;
- stage 2: Resin just after mixing (curing stage);
- stage 3: Cured resin (original);
- stage 4: Cured resin after heat exposure (dry and wet).

5.5 Test report

The test report shall include the following data:

- 1) resin category and identification;
- 2) lot number or identification;
- 3) marking and labelling according to the material safety data sheet (MSDS);
- 4) test results;
- 5) major test parameters, including conditioning and calibration, if any;
- 6) processing conditions used to mix the compound;
- 7) copy of the technical data sheet (TDS) and MSDS.

6 Test methods

International test methods are specified within this document where available; for those tests where there is no international test method available or the test method needs some adaptation of conditions, the method or specific conditions are specified in IEC 60455-2.

For special applications, water temperature in Table 2 to Table 5, stage 4-2 (Wet heat resistance), can be insufficient to ensure the satisfactory performance of the resinous compound. In such cases, upon agreement between manufacturer and user, the compound shall be tested using an increased temperature of $90 ^\circ\text{C}$. The chosen temperature shall be recorded in the test report.

Compliance at $90 ^\circ\text{C}$ also includes compliance at $70 ^\circ\text{C}$.

Table 2 – Type tests: test methods and requirements for Polyurethane resins

Number	Property	Test method	Units	Requirement	Remarks
Stage 1 – Reactive components prior to mixing					
1	Viscosity at 5 °C	ISO 2555 ^b	Pa · s	≤ 50	Resin only
Stage 2 – Resins just after mixing (curing stage)					
2	Pot life (0,3 l at 5 °C) Pot life (0,3 l at 40 °C)	IEC 60455-2 IEC 60455-3-8:2021	min min	< 75 ≥ 5	
3	Curing in presence of water, physical structure	IEC 60455-2 IEC 60455-3-8:2021		No blisters or cracks, small amount of individual bubbles or inclusions acceptable	For PUR resin type W only. See Annex A Include picture of cut resin surface with scale in report
Stage 3 – Cured resins (original)					
4	Density	ISO 1183-1	g/cm ³	> 1,05 g/cm ³	Only for category W
5	Impact strength (without notch)	ISO 179 (all parts)	kJ/m ²	≥ 6	No break is also acceptable
6	Hardness (Shore)	ISO 868		For classification purpose	See Clause 4
7	Tensile strength	ISO 527 (all parts)	MPa	Record value	
8	Elongation at break	ISO 527 (all parts)	%	Record value	
9	Dissipation factor at room temperature ^a	IEC 62631-2-1		M: dissipation factor ≤ 0,1	Using conductive silver varnish as electrode material Using 500 V/mm at 50 Hz
10	Dielectric constant at room temperature ^a	IEC 62631-2-1		M: relative permittivity ≤ 6	Using conductive silver varnish as electrode material Using 500 V/mm at 50 Hz
11	Volume resistivity at room temperature ^a	IEC 62631-3-1 and IEC 62631-3-2	Ω cm	M: ≥ 1 × 10 ¹³ L: ≥ 1 × 10 ¹¹	Using conductive silver varnish as electrode material Using 500 V/mm at 50 Hz

^a According IEC 60212 atmosphere B.

^b Use spindle 2 min⁻¹ and 10 min⁻¹ for viscosities up to 4 Pa·s; use spindle 3 min⁻¹ and 10 min⁻¹ for viscosities > 4 Pa·s up to 10 Pa·s; use spindle 4 min⁻¹ and 10 min⁻¹ for viscosities > 10 Pa·s up to 20 Pa·s; use spindle 5 min⁻¹ and 10 min⁻¹ for viscosities > 20 Pa·s up to 40 Pa·s; use spindle 7 min⁻¹ and 50 min⁻¹ for viscosities > 40 Pa·s. Reading when indication is stable.

Number	Property	Test method	Units	Requirement	Remarks
Stage 4 – Cured resins after heat exposure					
	4-1 Dry heat resistance: 28 days at 120 °C (vented oven) – IEC 60455-2				
12	Mass loss	IEC 60455-2	%	≤ 5	
13	Impact strength (without notch)	ISO 179 (all parts)	kJ/m ²	≥ 4	No break is also acceptable
	4-2 Wet heat resistance: 28 days at 70 °C^c in water – IEC 60455-2				
14	Hardness (retention/original)	ISO 868	%	≥ 80	
15	Tensile strength (retention/original)	ISO 527 (all parts)	%	≥ 65	
16	Elongation at break (retention/original)	ISO 527 (all parts)	%	≥ 65	
17	Dielectric strength (resin type L)	IEC 60243-1	kV/mm	≥ 2	
	Dielectric strength (resin type M)			≥ 5	
^c See also Clause 6 regarding the test at 90 °C.					