



Designation: C615/C615M – 18

Standard Specification for Granite Dimension Stone¹

This standard is issued under the fixed designation C615/C615M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers the material characteristics, physical requirements, and sampling appropriate to the selection of granite for general building and structural purposes. Refer to Guides C1242 and C1528 for the appropriate selection and use of granite dimension stone.

1.2 Granite dimension stone shall include stone that is sawed, cut, split, or otherwise finished or shaped, and shall specifically exclude molded, cast, or otherwise artificially aggregated units composed of fragments, crushed and broken stone.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C97/C97M Test Methods for Absorption and Bulk Specific Gravity of Dimension Stone

C99/C99M Test Method for Modulus of Rupture of Dimension Stone

C119 Terminology Relating to Dimension Stone

C170/C170M Test Method for Compressive Strength of Dimension Stone

C241/C241M Test Method for Abrasion Resistance of Stone Subjected to Foot Traffic

C1242 Guide for Selection, Design, and Installation of Dimension Stone Attachment Systems

C880/C880M Test Method for Flexural Strength of Dimension Stone

C1353 Test Method for Abrasion Resistance of Dimension Stone Subjected to Foot Traffic Using a Rotary Platform Abraser

C1528 Guide for Selection of Dimension Stone

3. Terminology

3.1 *Definitions*—All definitions are in accordance with Terminology C119.

4. Classification

4.1 Granite dimension stone under this specification shall be granite used for:

4.1.1 Exterior and interior cladding of buildings and structures;

4.1.2 Curbstone, paving, and landscape features;

4.1.3 Structural components having established dimensions;

4.1.4 Grade separations and retaining walls; and

4.1.5 Monuments.

5. Physical Properties

5.1 Granite supplied under this specification shall conform to the physical requirements prescribed in Table 1. See Footnote^B for possible variations from this table.

5.1.1 The minimum compressive strength, flexural strength, and modulus of rupture shall be based upon the minimum average strength of specimens tested in four conditions: wet or dry and parallel or perpendicular to rift.

5.1.2 The physical properties given in Table 1 represent properties of granite that have a history of successful use for general building and structural purposes. Granite with strength or abrasion resistance less than the minimum values prescribed in Table 1 may be used provided that competent engineering authority has evaluated relevant characteristics of the granite. This evaluation shall consider both structural effects and material characteristics such as durability, permanent volume change, modulus of elasticity, thermal expansion, and the like.

¹ This specification is under the jurisdiction of ASTM Committee C18 on Dimension Stone and is the direct responsibility of Subcommittee C18.03 on Material Specifications.

Current edition approved Sept. 1, 2018. Published September 2018. Originally approved in 1968. Last previous edition approved in 2011 as C 615/C 615M– 11. DOI:10.1520/C615_C615M-18.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.