



Designation: **B416 – 98 (Reapproved 2013) B416 – 98 (Reapproved 2018)**

Standard Specification for Concentric-Lay-Stranded Aluminum-Clad Steel Conductors¹

This standard is issued under the fixed designation B416; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers bare concentric-lay-stranded conductors made from bare, hard-drawn, round, aluminum-clad steel wires of 20.3 % conductivity for general use of electrical purposes. This specification does not apply to stranded conductors for reinforcement in ACSR conductors.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 The following documents of the issue in effect on date of material purchase form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards:*²

B354 Terminology Relating to Uninsulated Metallic Electrical Conductors

B415 Specification for Hard-Drawn Aluminum-Clad Steel Wire

2.3 *Other Documents:*

C8.1 Definitions and General Standards for Wires and Cables³

NBS Handbook 100 Handbook 100—Copper—Copper Wire Tables of the National Institute of Standards and Technology⁴

3. Description of Conductor

3.1 The designation of the finished conductor shall be expressed as the number of wires and the diameter of these individual wires, usually expressed as the AWG size of the wires.

4. Ordering Information

4.1 Orders for material under this specification shall include the following information:

4.1.1 Quantity of each size,

4.1.2 Conductor size expressed as number and AWG size of individual wires (Section 3 and Table 1),

4.1.3 Direction of lay of outer layer, if other than left-hand (see 6.3),

4.1.4 Package size (see 15.1),

4.1.5 Special package markings if required (see 15.3),

4.1.6 Special lagging if required (see 15.2), and

4.1.7 Place of inspection if other than place of manufacture (Section 13).

5. Joints

5.1 Joints or splices may be made in the finished individual aluminum-clad steel wires composing concentric-lay stranded conductors using more than three wires, provided that such joints or splices have a protection and electrical conductance equivalent

¹ This specification is under the jurisdiction of ASTM Committee B01 on Electrical Conductors and is the direct responsibility of Subcommittee B01.06 on Bi-Metallic Conductors.

Current edition approved April 1, 2013/Oct. 1, 2018. Published April 2013/October 2018. Originally approved in 1964. Last previous edition approved in 2007/2013 as B416 – 98 (2007) (2013). DOI: 10.1520/B0416-98R13; 10.1520/B0416-98R18.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁴ Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Stop 1070, Gaithersburg, MD 20899-1070, <http://www.nist.gov>.

TABLE 1 Construction Requirements and Breaking Strength of Concentric-Lay Stranded Aluminum-Clad Steel Conductors^A

Size Designation ^B	Number and Diameter of Individual Wires		Conductor Diameter, in. ^C	Rated Breaking Strength min, lb ^D
	Number	Nominal Diameter, in.		
37 No. 5 AWG	37	0.1819	1.27	142 800
37 No. 6 AWG	37	0.1620	1.13	120 200
37 No. 7 AWG	37	0.1443	1.01	100 700
37 No. 8 AWG	37	0.1285	0.899	84 200
37 No. 9 AWG	37	0.1144	0.801	66 770
37 No. 10 AWG	37	0.1019	0.713	52 950
19 No. 5 AWG	19	0.1819	0.910	73 350
19 No. 6 AWG	19	0.1620	0.810	61 700
19 No. 7 AWG	19	0.1443	0.721	51 730
19 No. 8 AWG	19	0.1285	0.642	43 240
19 No. 9 AWG	19	0.1144	0.572	34 290
19 No. 10 AWG	19	0.1019	0.509	27 190
7 No. 5 AWG	7	0.1819	0.546	27 030
7 No. 6 AWG	7	0.1620	0.486	22 730
7 No. 7 AWG	7	0.1443	0.433	19 060
7 No. 8 AWG	7	0.1285	0.385	15 930
7 No. 9 AWG	7	0.1144	0.343	12 630
7 No. 10 AWG	7	0.1019	0.306	10 020
7 No. 11 AWG	7	0.0907	0.272	7 945
7 No. 12 AWG	7	0.0808	0.242	6 301
3 No. 5 AWG	3	0.1819	0.392	12 230
3 No. 6 AWG	3	0.1620	0.349	10 280
3 No. 7 AWG	3	0.1443	0.311	8 621
3 No. 8 AWG	3	0.1285	0.277	7 206
3 No. 9 AWG	3	0.1144	0.247	5 715
3 No. 10 AWG	3	0.1019	0.220	4 532

^A For metric equivalents: Diameter (mm)—multiply diameter in inches by 25.4 (round to 4 significant figures).

Breaking Strength (kg)—multiply breaking strength in pounds by 0.45359 (round to 4 significant figures).

^B The designation is a combination of the number of wires each of the AWG size indicated by "No."

^C Diameter of circumscribing circle. See Table 3 for complete table of properties.

^D See Section 7.

ASTM B416-98(2018)

to that of the wire itself and that they do not decrease the strength of the finished stranded conductor below the minimum breaking strength shown in Table 1. Such joints or splices shall be not closer than 50 ft (15 m) to any other joint in the same layer in the conductor.

NOTE 1—Joints are made by electrical butt-welding. The ends must be cut and the end of each wire must be straightened for a distance of 12 to 15 in. (300 to 380 mm). The proper sleeve is slipped over the end of one of the wires. The wires are then butt-welded and dressed off to a finished diameter equal to that of the wire. The weld area is then tempered, the sleeve centered over the weld area and compressed to provide a finished joint that is smooth and neat in appearance. This joint has a tensile strength of approximately 90 % of rated breaking strength of the wire, but an allowance is made for this in the rated strength of the conductor as a whole. The completed conductor when containing such joints is required to have the full rated strength.

6. Lay

6.1 For 3-wire conductors, the preferred lay is 16½ times the outside diameter, but the lay shall not be less than 14 times nor more than 20 times this diameter.

6.2 For 7, 19, and 37-wire conductors, the preferred lay is 13½ times the diameter of that layer, but the lay shall not be less than 10 nor more than 16 times this diameter.

6.3 The direction of lay of the outer layer shall be left-hand unless the direction of lay is specified otherwise by the purchaser.

6.4 The direction of lay shall be reversed in consecutive layers.

6.5 All wires in the conductor shall lie naturally in their true positions in the completed conductor. They shall tend to remain in position when the conductor is cut at any point and shall permit restranding by hand after being forcibly unraveled at the end of the conductor.

7. Strength of Conductor

7.1 The breaking strength of the completed conductors composed of 7 wires, 19 wires, and 37 wires shall be taken as 90 % of the sum of the breaking strengths of the aluminum-clad wires, calculated from their nominal diameter and the appropriate specified