

Edition 2.0 2021-02 REDLINE VERSION

INTERNATIONAL STANDARD



Terrestrial photovoltaic (PV) modules – Design qualification and type approval – Part 1-2: Special requirements for testing of thin-film Cadmium Telluride (CdTe) based photovoltaic (PV) modules

Document Preview

IEC 61215-1-2:2021

https://standards.iteh.ai/catalog/standards/iec/9t6d72d2-86bd-4495-8252-914035964097/iec-61215-1-2-2021





THIS PUBLICATION IS COPYRIGHT PROTECTED Copyright © 2021 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office 3, rue de Varembé CH-1211 Geneva 20 Switzerland

Tel.: +41 22 919 02 11

info@iec.ch www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished
Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC online collection - oc.iec.ch

Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 18 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.





Edition 2.0 2021-02 REDLINE VERSION

INTERNATIONAL STANDARD



Terrestrial photovoltaic (PV) modules – Design qualification and type approval – Part 1-2: Special requirements for testing of thin-film Cadmium Telluride (CdTe) based photovoltaic (PV) modules

Document Preview

IEC 61215-1-2:202

https://standards.iteh.ai/catalog/standards/iec/9f6d72d2-86bd-4495-8252-914035964097/iec-61215-1-2-202

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ICS 27.160 ISBN 978-2-8322-9422-2

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FORE	EWOF	RD	4
1 5	Scope	e- <mark>and-object</mark>	6
2 N	Norma	ative references	7
3 1	Terms	s and definitions	7
4 T	Test s	samples	7
		ng and documentation	
		ng	
		criteria	
	•	visual defects	
	-	rt	
		ications	
11 1		low and procedures	
11	.1	Visual inspection (MQT 01)	8
11		Maximum power determination (MQT 02)	
11		Insulation test (MQT 03)	
11		Measurement of temperature coefficients (MQT 04)	
		Measurement of nominal module operating temperature (NMOT) (MQT 05)	
11		Placeholder section, formerly NMOT	
11		Performance at STC (MQT 06.1) and NMOT (MQT 06.2)	
11		Performance at low irradiance (MQT 07)	
11		Outdoor exposure test (MQT 08)	
11		Hot-spot endurance test (MQT 09)	
	11.9.1	$\frac{11C \ 01215^{-1}-2.2021}{11C \ 01215^{-1}}$	
//stand	11.9.2 11.9.3	2 Hot-spot effect	
	11.9.3 11.9.4		
	11.9.5 11.9.5		
	11.9.6		
	11.9.7		
		UV preconditioning test (MQT 10)	
		Thermal cycling test (MQT 11)	
		Humidity-freeze test (MQT 12)	
		Damp heat test (MQT 13)	
		Robustness of terminations (MQT 14)	
		Wet leakage current test (MQT 15)	
		Static mechanical load test (MQT 16)	
		Hail test (MQT 17)	
		Bypass diode testing (MQT 18)	
11	.19	Stabilization (MQT 19)	10
	11.19		
1	11.19	.2 Light induced stabilization procedures	10
1	11.19	.3 Other stabilization procedures	10
1	11.19		
	11.19	,	
11	.20	Cyclic (dynamic) mechanical load test (MQT 20)	11

11.21	Potential induced degradation test (MQT 21)	11
11.22	Bending test (MQT 22)	11

iTeh Standards (https://standards.iteh.ai) Document Preview

IEC 61215-1-2:2021

https://standards.iteh.ai/catalog/standards/iec/9f6d72d2-86hd-4495-8252-914035964097/iec-61215-1-2-2021

INTERNATIONAL ELECTROTECHNICAL COMMISSION

TERRESTRIAL PHOTOVOLTAIC (PV) MODULES - DESIGN QUALIFICATION AND TYPE APPROVAL -

Part 1-2: Special requirements for testing of thin-film Cadmium Telluride (CdTe) based photovoltaic (PV) modules

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition IEC 61215-1-2:2016. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

International Standard IEC 61215-1-2 has been prepared by IEC technical committee 82: Solar photovoltaic energy systems.

This second edition cancels and replaces the first edition of IEC 61215-1-2, issued in 2016, and constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) A cyclic (dynamic) mechanical load test (MQT 20) added.
- b) A test for detection of potential-induced degradation (MQT 21) added.
- c) A bending test (MQT 22) for flexible modules added.

Informative Annex A, of 61215-1:2021, explains the background and reasoning behind some of the more substantial changes that were made in the IEC 61215 series in progressing from edition 1 to edition 2.

The text of this standard is based on the following documents:

FDIS	Report on voting
82/1825/FDIS	82/1850/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

This standard is to be read in conjunction with IEC 61215-1:2021 and IEC 61215-2:2021.

A list of all parts in the IEC 61215 series, published under the general title *Terrestrial photovoltaic (PV) modules – Design qualification and type approval*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- · replaced by a revised edition, or
- amended.

TERRESTRIAL PHOTOVOLTAIC (PV) MODULES - DESIGN QUALIFICATION AND TYPE APPROVAL -

Part 1-2: Special requirements for testing of thin-film Cadmium Telluride (CdTe) based photovoltaic (PV) modules

1 Scope and object

This part of IEC 61215 lays down IEC requirements for the design qualification and type approval of terrestrial photovoltaic modules suitable for long-term operation in general openair climates, as defined in IEC 60721-2-1.

This document lays down requirements for the design qualification of terrestrial photovoltaic modules suitable for long-term operation in open-air climates. The useful service life of modules so qualified will depend on their design, their environment and the conditions under which they are operated. Test results are not construed as a quantitative prediction of module lifetime.

In climates where 98th percentile operating temperatures exceed 70 °C, users are recommended to consider testing to higher temperature test conditions as described in IEC TS 63126. Users desiring qualification of PV products with lesser lifetime expectations are recommended to consider testing designed for PV in consumer electronics, as described in IEC 63163 (under development). Users wishing to gain confidence that the characteristics tested in IEC 61215 appear consistently in a manufactured product may wish to utilize IEC 62941 regarding quality systems in PV manufacturing.

This document is intended to apply to all thin-film CdTe based terrestrial flat plate modules. As such, it addresses special requirements for testing of this technology supplementing IEC 61215-1:20162021 and IEC 61215-2:20162021 requirements for testing.

This document does not apply to modules used with concentrated sunlight although it may be utilized for low concentrator modules (1 to 3 suns). For low concentration modules, all tests are performed using the irradiance, current, voltage and power levels expected at the design concentration.

The object of this test sequence is to determine the electrical and thermal characteristics of the module and to show, as far as possible within reasonable constraints of cost and time, that the module is capable of withstanding prolonged exposure in climates described in the scope outdoors. The actual lifetime expectancy of modules so qualified will depend on their design, their environment and the conditions under which they are operated. Accelerated test conditions are empirically based on those necessary to reproduce selected observed field failures and are applied equally across module types. Acceleration factors may vary with product design and thus not all degradation mechanisms may manifest. Further general information on accelerated test methods including definitions of terms may be found in IEC 62506.

Some long-term degradation mechanisms can only reasonably be detected via component testing, due to long times required to produce the failure and necessity of stress conditions that are expensive to produce over large areas. Component tests that have reached a sufficient level of maturity to set pass/fail criteria with high confidence are incorporated into the IEC 61215 series via addition to Table 1 in IEC 61215-1. In contrast, the tests procedures described in this series, in IEC 61215-2, are performed on modules.

This document defines PV technology dependent modifications to the testing procedures and requirements per IEC 61215-1:20162021 and IEC 61215-2:20162021.

2 Normative references

The normative references of IEC 61215-1:20162021 and IEC 61215-2:20162021 are applicable without modifications.

3 Terms and definitions

This clause of IEC 61215-1:20162021 is applicable without modifications.

4 Test samples

This clause of IEC 61215-1:20162021 is applicable without modifications.

5 Marking and documentation

This clause of IEC 61215-1:20162021 is applicable without modifications.

6 Testing

This clause of IEC 61215-1:20162021 is applicable with the following modifications:

Special care has to be taken for stabilizing the power output of the module using MQT 19 procedure with specific requirements stated in 11.19 below.

7 Pass criteria

This clause of IEC 61215-1:20162021 is applicable with the following modifications:

The maximum allowable value of reproducibility is set to r = 2.0 %.

The maximum allowable value of measurement uncertainty is set to $m_1 = 4.0$ % for modules containing single-junction cells, and $m_1 = 5.0$ % for modules containing multi-junction cells.

8 Major visual defects

This clause of IEC 61215-1:20162021 is applicable without modifications.

9 Report

This clause of IEC 61215-1:20162021 is applicable without modifications.

10 Modifications

This clause of IEC 61215-1:20162021 is applicable without modifications.

The test flow from IEC 61215-1:20162021 is applicable.

11.1 Visual inspection (MQT 01)

This test of IEC 61215-2:20162021 is applicable without modifications.

11.2 Maximum power determination (MQT 02)

This test of IEC 61215-2:20162021 is applicable without modifications.

11.3 Insulation test (MQT 03)

This test of IEC 61215-2:20162021 is applicable without modifications.

11.4 Measurement of temperature coefficients (MQT 04)

This test of IEC 61215-2:20162021 is applicable without modifications.

11.5 Measurement of nominal module operating temperature (NMOT) (MQT 05)

This test of IEC 61215-2:2016 is applicable without modifications.

11.5 Placeholder section, formerly NMOT and ard S

This subclause of IEC 61215-2:2021 does not require technology-specific modifications.

11.6 Performance at STC (MQT 06.1) and NMOT (MQT 06.2)

This test of IEC 61215-2:20162021 is applicable without modifications.

11.7 Performance at low irradiance (MQT 07)

This test of IEC 61215-2:20162021 is applicable without modifications.

11.8 Outdoor exposure test (MQT 08)

This test of IEC 61215-2:20162021 is applicable without modifications.

11.9 Hot-spot endurance test (MQT 09)

This test of IEC 61215-2:20162021 is applicable with the following modifications:

CdTe thin-film modules may exhibit performance changes with extended time in storage without light exposure (the "dark soak" effect). In order to minimize the influence of this dark soak effect, limit the time delay between the outdoor exposure or stabilization and the hot spot procedure to within 2 to 3 days. During the first hour after the hot-spot procedure is complete, no additional heating or light beyond room ambient shall be applied. If the time delay is to exceed 1 h, the modules are to be stored in the dark at \leq 25 °C.

11.9.1 **Purpose**

This subclause of IEC 61215-2:20162021, test MQT 09, is applicable without modifications.

11.9.2 Hot-spot effect

This subclause of IEC 61215-2:20162021, test MQT 09, is applicable without modifications.

11.9.3 Classification of cell interconnection

This subclause of IEC 61215-2:20162021, test MQT 09, is applicable without modifications.

11.9.4 Apparatus

This subclause of IEC 61215-2:20162021, test MQT 09, is applicable without modifications.

11.9.5 Procedure

MQT 09.2 of IEC 61215-2:20162021 shall be performed for any MLI module design.

If the module is constructed by interconnection of cell-like substructures, MQT 09.1 of IEC 61215-2:20162021 may be applicable.

11.9.6 Final measurements

This subclause of IEC 61215-2:20162021, test MQT 09, is applicable without modifications.

11.9.7 Requirements

This subclause of IEC 61215-2:20162021, test MQT 09, is applicable without modifications.

11.10 UV preconditioning test (MQT 10)

This test of IEC 61215-2:20162021 is applicable without modifications.

11.11 Thermal cycling test (MQT 11)

This test of IEC 61215-2:20162021 is applicable with the following modifications:

The technology specific current which needs to be applied according to MQT 11 of IEC 61215-2: $\frac{2016}{2021}$ shall be equal to 0,1 × STC peak power current. If 0,1 × STC peak power current is less than 100 mA, then 100 mA may be applied instead.

11.12 Humidity-freeze test (MQT 12)

This test of IEC 61215-2:20162021 is applicable without modifications.

11.13 Damp heat test (MQT 13)

This test of IEC 61215-2:20162021 is applicable without modifications.

11.14 Robustness of terminations test (MQT 14)

This test of IEC 61215-2:20162021 is applicable without modifications.

11.15 Wet leakage current test (MQT 15)

This test of IEC 61215-2:20162021 is applicable without modifications.

11.16 Static mechanical load test (MQT 16)

This test of IEC 61215-2:20162021 is applicable without modifications.

11.17 Hail test (MQT 17)

This test of IEC 61215-2:20162021 is applicable without modifications.