



SLOVENSKI STANDARD
SIST EN ISO 7233:2000
01-december-2000

; i a YbY]b`dc`ja YfbY`Wj]`hYf`Wj b]`df]_`f _]!`I [cHj`Ub`Y`Xcfc bY`cXdcfbcgh]
fIGC`+&`' .% - %L

Rubber and plastics hoses and hose assemblies - Determination of suction resistance
(ISO 7233:1991)

Gummi- und Kunststoffschläuche und -schlauchleitungen - Bestimmung der
Vakuumbeständigkeit (ISO 7233:1991)

Tuyaux et flexibles en caoutchouc et en plastique - Détermination de la résistance a
l'aspiration (ISO 7233:1991)

STANDARD PREVIEW
(standards.iteh.ai)
[https://standards.iteh.ai/catalog/standards/sist/1024467f-8927-4b65-9754-
d7f582d75a53/sist-en-iso-7233-2000](https://standards.iteh.ai/catalog/standards/sist/1024467f-8927-4b65-9754-d7f582d75a53/sist-en-iso-7233-2000)

Ta slovenski standard je istoveten z: EN ISO 7233:1995

ICS:

23.040.70 Gumene cevi in armature Hoses and hose assemblies

SIST EN ISO 7233:2000 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 7233:2000

<https://standards.iteh.ai/catalog/standards/sist/1024467f-8927-4b65-9754-d7f582d75a53/sist-en-iso-7233-2000>

EUROPEAN STANDARD

EN ISO 7233

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 1995

ICS 23.040.70

Descriptors: Rubber products, plastics products, hoses, rubber hoses, tests, pressure tests, determination, pressure resistance

English version

**Rubber and plastics hoses and hose assemblies -
Determination of suction resistance
(ISO 7233:1991)**

Tuyaux et flexibles en caoutchouc et en
plastique - Détermination de la résistance à
l'aspiration (ISO 7233:1991)

Gummi- und Kunststoffschläuche und
-schlauchleitungen - Bestimmung
der
Vakuumbeständigkeit (ISO 7233:1991)

(standards.iteh.ai)

SIST EN ISO 7233:2000

<https://standards.iteh.ai/catalog/standards/sist/1024467f-8927-4b65-9754-d7f582d75a53/sist-en-iso-7233-2000>

This European Standard was approved by CEN on 1995-02-06. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CEN

European Committee for Standardization
Comité Européen de Normalisation
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

© 1995

All rights of reproduction and communication in any form and by any means reserved in all countries to CEN and its members.

Ref. No. EN ISO 7233:1995 E

Foreword

This European Standard has been taken over by the Technical Committee CEN/TC 218 "Rubber and plastics hoses and hose assemblies" from the work of ISO/TC 45 "Rubber and rubber products" of the International Organization for Standardization (ISO).

This European Standard shall be given the status of a National Standard, either by publication of an identical text or by endorsement, at the latest by August 1995, and conflicting national standards shall be withdrawn at the latest by August 1995.

According to the CEN/CENELEC Internal Regulations, the following countries are bound to implement this European Standard: Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland, United Kingdom.

Endorsement notice

The text of the International Standard ISO 7233:1991 has been approved by CEN as a European Standard without any modification.

(standards.iteh.ai)

[SIST EN ISO 7233:2000](https://standards.iteh.ai/catalog/standards/sist/1024467f-8927-4b65-9754-d7f582d75a53/sist-en-iso-7233-2000)

<https://standards.iteh.ai/catalog/standards/sist/1024467f-8927-4b65-9754-d7f582d75a53/sist-en-iso-7233-2000>

INTERNATIONAL STANDARD

ISO
7233

Second edition
1991-12-01

Rubber and plastics hoses and hose assemblies — Determination of suction resistance

iTeh STANDARD PREVIEW

*(Tuyaux et flexibles en caoutchouc et en plastique — Détermination de la
résistance à l'aspiration)*

SIST EN ISO 7233:2000

[https://standards.iteh.ai/catalog/standards/sist/1024467f-8927-4b65-9754-
d7f582d75a53/sist-en-iso-7233-2000](https://standards.iteh.ai/catalog/standards/sist/1024467f-8927-4b65-9754-d7f582d75a53/sist-en-iso-7233-2000)



Reference number
ISO 7233:1991(E)

ISO 7233:1991(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 7233 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Sub-Committee SC 1, *Hoses (rubber and plastics)*.

This second edition cancels and replaces the first edition (ISO 7233:1983), of which it constitutes a technical revision.

© ISO 1991

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

Introduction

Suction testing is applied to hoses to determine that they will withstand the differential pressure encountered in service resulting from a reduced pressure within the hose. The degree of suction for the test will be specified in the relevant product standard.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 7233:2000](https://standards.iteh.ai/catalog/standards/sist/1024467f-8927-4b65-9754-d7f582d75a53/sist-en-iso-7233-2000)

<https://standards.iteh.ai/catalog/standards/sist/1024467f-8927-4b65-9754-d7f582d75a53/sist-en-iso-7233-2000>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

This page intentionally left blank

[SIST EN ISO 7233:2000](#)

<https://standards.iteh.ai/catalog/standards/sist/1024467f-8927-4b65-9754-d7f582d75a53/sist-en-iso-7233-2000>

Rubber and plastics hoses and hose assemblies — Determination of suction resistance

1 Scope

This International Standard specifies two methods for determining the suction resistance of hoses, depending on bore diameter, as follows:

method A — for hoses of nominal bore diameter up to and including 80 mm;

method B — for hoses of nominal bore diameter greater than 80 mm.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 471:1983, *Rubber — Standard temperatures, humidities and times for the conditioning and testing of test pieces*.

ISO 1826:1981, *Rubber, vulcanized — Time-interval between vulcanization and testing — Specification*.

3 Test pieces

A minimum test length, clear of the end fittings, of five times the nominal bore or 1 m, whichever is the greater, shall be used, or the complete hose or hose assembly if less than 1 m long.

4 Conditioning of test pieces

No tests shall be carried out within 24 h of manufacture (see ISO 1826). Test pieces shall be con-

ditioned at standard temperature (see ISO 471) for at least 3 h before testing; this may be part of the 24 h after manufacture, unless otherwise agreed between the purchaser and manufacturer.

5 Procedure (method A)

Lay out the hose as straight as possible on a flat surface and blank off one end to form an airtight seal. Insert into the hose a smooth solid ball having a diameter equal to the nearest whole millimetre below $0,9 \times$ the bore diameter and then connect the open end of the hose to a suction pump and gauge. Reduce the internal pressure in the hose within 60 s to the specified test pressure and maintain this pressure for the required period, which shall not be less than 10 min.

Whilst the specified pressure is being maintained, examine the hose externally for any signs of indentation or collapse and then tilt the hose to permit the solid ball to traverse the full length of the hose to check for any obstructions caused by internal deformation.

6 Procedure (method B)

Fit transparent airtight plates to both ends of the hose, one of which is connected to a suction pump and gauge. Reduce the internal pressure in the hose within 60 s to the specified test pressure and maintain this pressure for the required period, which shall not be less than 10 min.

Whilst the reduced pressure is being maintained, examine the interior of the hose through one of the transparent plates by illumination applied through the other plate, and also examine the exterior of the hose, for signs of delamination, indentation or collapse.