

INTERNATIONAL STANDARD



Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 2: Methods of test

Document Preview

[IEC 60893-2:2023](#)

<https://standards.iteh.ai/catalog/standards/iec/e8bef67b-d159-4654-9046-da1211f244bc/iec-60893-2-2023>



THIS PUBLICATION IS COPYRIGHT PROTECTED
Copyright © 2023 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Secretariat
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 300 terminological entries in English and French, with equivalent terms in 19 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

International Standards
Document Preview
standards.iteh.ai

[IEC 60893-2:2023](#)

<https://standards.iteh.ai/catalog/standards/iec/e8bef67b-d159-4654-9046-da1211f244bc/iec-60893-2-2023>



IEC 60893-2

Edition 3.0 2023-11
REDLINE VERSION

INTERNATIONAL STANDARD



Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 2: Methods of test

Document Preview

[IEC 60893-2:2023](https://standards.iteh.ai/iec/60893-2:2023)

<https://standards.iteh.ai/catalog/standards/iec/e8bef67b-d159-4654-9046-da1211f244bc/iec-60893-2-2023>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.035.01

ISBN 978-2-8322-7858-1

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	5
INTRODUCTION.....	2
1 Scope.....	8
2 Normative references	8
3 Terms and definitions	8
4 Conditioning of test specimens	10
5 Dimensions.....	10
5.1 Thickness	10
5.1.1 General	10
5.1.2 Test apparatus for reference method	10
5.1.3 Procedure for reference method	10
5.1.4 Results	11
5.2 Flatness.....	11
5.2.1 General	11
5.2.2 Test specimens	11
5.2.3 Test method	11
5.2.4 Results	11
6 Mechanical tests.....	11
6.1 Flexural strength.....	11
6.1.1 General	11
6.1.2 Test specimens	11
6.1.3 Test method	11
6.1.4 Results	12
6.2 Modulus of elasticity in flexure.....	12
6.2.1 General	12
6.2.2 Test specimens	12
6.2.3 Test method	12
6.2.4 Results	12
6.3 Compressive strength	12
6.3.1 General	12
6.3.2 Test specimens	12
6.3.3 Test method	12
6.3.4 Results	12
6.4 Impact strength.....	12
6.4.1 General	12
6.4.2 Charpy Impact strength	12
6.4.3 Izod impact strength	13
6.5 Shear strength parallel to laminations	13
6.5.1 General	13
6.5.2 Test specimens	13
6.5.3 Test method	14
6.5.4 Results	14
6.6 Tensile strength	14
6.6.1 General	14
6.6.2 Test specimens	14
6.6.3 Test method	14

6.6.4	Results	14
7	Electrical tests	15
7.1	Electric strength and breakdown voltage	15
7.1.1	General	15
7.1.2	Test specimens	15
7.1.3	Test method	15
7.2	Permittivity and dissipation factor	15
7.2.1	General requirements	15
7.2.2	Methods	16
7.2.3	Principles of the methods	16
7.2.4	Measuring instruments	17
7.2.5	Method A: Direct measurement technique	17
7.2.6	Method B: Air substitution technique	20
7.2.7	Method C: Two fluid immersion technique	22
7.2.8	Test report	25
7.3	Insulation resistance after immersion in water	26
7.3.1	General	26
7.3.2	Test specimens	26
7.3.3	Test method	26
7.3.4	Results	26
7.4	Comparative and proof tracking indices	26
7.4.1	General	26
7.4.2	Test specimens	26
7.4.3	Test method	27
7.4.4	Results	27
7.5	Tracking and erosion resistance	27
7.5.1	General	27
7.5.2	Test specimens	27
7.5.3	Test method	27
7.5.4	Results	27
8	Thermal tests	27
8.1	Thermal endurance	27
8.1.1	General	27
8.1.2	Test specimens	27
8.1.3	Test method	27
8.1.4	Results	27
8.2	Flammability	28
8.2.1	General	28
8.2.2	Test specimens	28
8.2.3	Test method	28
8.2.4	Results	28
9	Other tests	28
9.1	Density	28
9.1.1	General	28
9.1.2	Test specimens	28
9.1.3	Test method	28
9.1.4	Results	28
9.2	Water absorption	28
9.2.1	General	28

9.2.2	Test specimens	28
9.2.3	Test method	28
9.2.4	Results	28
Annex A (informative) Modes of representation of capacitance		34
Annex B (informative) Liquids of known permittivity values		35
Bibliography.....		36
Figure 1 – Test specimens for impact strength test		29
Figure 2 – Device for testing parallel shearing strength.....		30
Figure 3 – Example of electrode system for method A.....		31
Figure 4 – Example of electrode system for method B.....		32
Figure 5 – Example of electrode system for method C		33
Figure A.1 – Equivalent parallel and series representation of a capacitor.....		34
Table 1 – Sequence employed for routine measurements		24
Table B.1 – Liquids of know permittivity values		35

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC 60893-2:2023](#)

<https://standards.iteh.ai/catalog/standards/iec/e8bef67b-d159-4654-9046-da1211f244bc/iec-60893-2-2023>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**INSULATING MATERIALS –
INDUSTRIAL RIGID LAMINATED SHEETS
BASED ON THERMOSETTING RESINS
FOR ELECTRICAL PURPOSES –****Part 2: Methods of test**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition IEC 60893-2:2003. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

IEC 60893-2 has been prepared by IEC technical committee 15: Solid electrical insulating materials. It is an International Standard.

This third edition cancels and replaces the second edition published in 2003. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) removal of reference to withdrawn specification IEC 60167:1964;
- b) inclusion of reference to IEC 62631-3-3:2015, which supersedes IEC 60167:1964. Details in 6.3 have been updated accordingly. The actual performance of the test has not changed;
- c) normative references have been updated.

The text of this International Standard is based on the following documents:

Draft	Report on voting
15/1017/FDIS	15/1023/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

A list of all parts in the IEC 60893 series, published under the general title *Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

IMPORTANT – The "colour inside" logo on the cover page of this document indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

This document is one of a series which deals with industrial rigid laminated sheets based on thermosetting resins for electrical purposes.

This series consists of four parts:

- Part 1: Definitions, designations and general requirements (IEC 60893-1);
- Part 2: Methods of test (IEC 60893-2);
- Part 3: Specifications for individual materials (IEC 60893-3);
- Part 4: Typical values (IEC TR 60893-4).

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC 60893-2:2023](#)

<https://standards.iteh.ai/catalog/standards/iec/e8bef67b-d159-4654-9046-da1211f244bc/iec-60893-2-2023>

INSULATING MATERIALS – INDUSTRIAL RIGID LAMINATED SHEETS BASED ON THERMOSETTING RESINS FOR ELECTRICAL PURPOSES –

Part 2: Methods of test

1 Scope

This part of IEC 60893 describes methods of test for the materials defined in IEC 60893-1 (referred to also as Part 1).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60112, *Method for ~~determining the comparative and the proof tracking indices of solid insulating materials under moist conditions~~ the determination of the proof and the comparative tracking indices of solid insulating materials*

~~IEC 60167:1964, Methods of test for the determination of the insulation resistance of solid insulating materials~~

IEC 60212: ~~1974~~2010, *Standard conditions for use prior to and during the testing of solid electrical insulating materials*

IEC 60216-1: ~~2001~~2013, *Electrical insulating materials – ~~Properties of~~ Thermal endurance properties – Part 1: Ageing procedures and evaluation of test results*

IEC 60243-1: ~~1998~~2013, *Electric strength of ~~solid~~ insulating materials – Test methods – Part 1: Tests at power frequencies*

~~IEC 60250:1969, Recommended methods for the determination of the permittivity and dielectric dissipation factor of electrical insulating materials at power, audio and radio frequencies including metre wavelengths~~

IEC 60296: ~~1982~~2012¹, *~~Specification for unused mineral insulating oils for transformers and switchgear~~ Fluids for electrotechnical applications – Unused mineral insulating oils for transformers and switchgear*

IEC 60587: ~~1984~~2007², *~~Test method for evaluating resistance to tracking and erosion of electrical insulating materials used under severe ambient conditions~~ Electrical insulating materials used under severe ambient conditions – Test methods for evaluating resistance to tracking and erosion*

¹ A fifth edition of this standard has been published in 2020.

² A fourth edition of this standard has been published in 2022.

IEC 60695-11-10:~~1999~~2013, *Fire hazard testing – Part 11-10: Test flames – 50 W horizontal and vertical flame test methods*

IEC 60893-1, *Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 1: Definitions, designations and general requirements*³

IEC 60893-3 (all parts~~3~~), *Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 3: Specifications for individual materials*

IEC TR 60893-4:~~2003~~, *Insulating materials – Industrial rigid laminated sheets based on thermosetting resins for electrical purposes – Part 4: Typical values*

IEC 62631-3-3:2015, *Dielectric and resistive properties of solid insulating materials – Part 3-3: Determination of resistive properties (DC methods) – Insulation resistance*

ISO 62:~~1999~~2008, *Plastics – Determination of water absorption*

ISO 178:~~2004~~2010⁴, *Plastics – Determination of flexural properties*

ISO 179-1:2000⁵, *Plastics – Determination of Charpy impact properties – Part 1: Non-instrumented impact test*

ISO 179-2:1997⁶, *Plastics – Determination of Charpy impact properties – Part 2: Instrumented impact test*

ISO 180:2000⁷, *Plastics – Determination of Izod impact strength*

ISO 527-1:~~1993~~2012⁸, *Plastics – Determination of tensile properties – Part 1: General principles*

ISO 527-4:1997⁹, *Plastics – Determination of tensile properties – Part 4: Test conditions for isotropic and orthotropic fibre-reinforced plastic composites*

ISO 604:2002, *Plastics – Determination of compressive properties*

~~ISO 1183:1987, *Plastics – Methods for determining the density and relative density of non-cellular plastics*~~

ISO 1183-1:2012¹⁰, *Plastics – Methods for determining the density of non-cellular plastics – Part 1: Immersion method, liquid pycnometer method and titration method*

³ ~~Use edition 2 when published.~~

⁴ A sixth edition of this standard has been published in 2019.

⁵ A third edition of this standard has been published in 2023.

⁶ A second edition of this standard has been published in 2020.

⁷ A fifth edition of this standard has been published in 2023.

⁸ A third edition of this standard has been published in 2019.

⁹ A third edition of this standard has been published in 2023.

¹⁰ A third edition of this standard has been published in 2019.

ISO 3611:1978/2010¹¹, ~~Micrometer callipers for external measurement~~ Geometrical product specifications (GPS) – Dimensional measuring equipment: Micrometers for external measurements – Design and metrological characteristics

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

4 Conditioning of test specimens

Unless otherwise specified, test specimens shall be conditioned for at least 24 h in standard atmosphere B according to IEC 60212:2010 (temperature ~~23 °C ± 2 K~~ 23 ± 2 °C, relative humidity (50 ± 5) %).

Unless otherwise specified, each specimen shall be tested in the conditioning atmosphere and at the conditioning temperature, or the tests shall commence within 3 min of removal of each test specimen from the conditioning atmosphere.

Where testing at an elevated temperature is required in one of the specification sheets of IEC 60893-3, test specimens shall be conditioned for 1 h at that elevated temperature immediately before testing.

5 Dimensions

[IEC 60893-2:2023](https://standards.iteh.ai/catalog/standards/iec/e8bef67b-d159-4654-9046-da1211f244bc/iec-60893-2-2023)

5.1 Thickness

5.1.1 General

Any method which enables the thickness of the laminated sheet to be measured at an appropriate number of points may be used, provided that the equipment used and the method of measurement are capable of a precision of 0,01 mm or better.

The following reference method has been shown to be suitable and shall be used in cases of dispute.

5.1.2 Test apparatus for reference method

In case of dispute, an external screw type micrometer in accordance with ISO 3611 having faces with diameters between 6 mm and 8 mm shall be used.

5.1.3 Procedure for reference method

Measure the thickness of the rigid laminated sheet as delivered to the nearest 0,01 mm at eight points, two along each edge but not less than 20 mm from the edge.

¹¹ A third edition of this standard has been published in 2023.

5.1.4 Results

Report the maximum and minimum measured values and the arithmetic mean of all measured values in mm.

5.2 Flatness

5.2.1 General

This test is applicable to all sheets having a thickness of 3 mm or greater.

5.2.2 Test specimens

The test specimen shall be the whole sheet or panel under test in the 'as received' condition.

5.2.3 Test method

When any sheet of nominal thickness 3,0 mm or more is placed without restraint, concave side up, on a flat surface, the departure at any point of the upper surface of the sheet from a light straight edge 1 000 mm or 500 mm in length, laid in any direction upon it, shall not exceed the value given in the relevant sheet of IEC 60893-3 appropriate to the material, its thickness and length of straight edge. The mass of the 1 000 mm straight edge shall not exceed 800 g, and the mass of the 500 mm straight edge shall not exceed 400 g.

5.2.4 Results

Report the maximum measured deviation from flatness in mm.

NOTE—In cases where the sheet deviates from flatness in two directions, is saddle-shaped, measure both deviations and report the highest.

6 Mechanical tests

[IEC 60893-2:2023](https://standards.iteh.ai/catalog/standards/iec/e8bef67b-d159-4654-9046-da1211f244bc/iec-60893-2-2023)

6.1 Flexural strength

6.1.1 General

The flexural strength is defined as the flexural stress at rupture. It shall be determined by the method specified in ISO 178. **Method A shall be used.**

6.1.2 Test specimens

Cut the test specimens from the sheet to be tested with their major axes parallel to the sides of the sheet. Test five test specimens in each direction, except for types with fibres aligned mainly in the same direction. In such cases, cut five specimens only, with their long axis parallel to the direction of the fibres.

If the nominal thickness of the sheet to be tested is more than 10 mm (20 mm in the case of types PF WV), reduce the thickness of the test specimens to 10 mm (20 mm in the case of PF WV).

When it is necessary to reduce the thickness of a test specimen, machine it, leaving one face of the sheet intact. In such cases, test specimens shall be tested with the original surface of the sheet in contact with the two supports.

6.1.3 Test method

The test shall be carried out with the load applied perpendicular to the plane of the laminations. The test speed shall be 5 mm/min with a tolerance of ± 20 %.

6.1.4 Results

Report the arithmetic mean of the results for each direction in MPa. Take the lower of the two mean values as the minimum flexural strength of the sheet under test, except in cases where the reinforcing fibres run mainly in one direction. In such cases, take the mean value obtained in this direction.

6.2 Modulus of elasticity in flexure

6.2.1 General

The following test method shall be used in order to determine the modulus of elasticity in flexure.

6.2.2 Test specimens

The specimens shall be in the same form as described for the flexural strength test described in 6.1.2 above.

6.2.3 Test method

Modulus of elasticity shall be determined by the method specified in ISO 178.

6.2.4 Results

Results shall be expressed in MPa.

6.3 Compressive strength

6.3.1 General

The following test method shall be used in order to determine the compressive strength.

6.3.2 Test specimens

Specimens shall be cut from the sheet under test as described in ISO 604.

6.3.3 Test method

Compressive strength shall be determined by the method specified in ISO 604 with the load applied perpendicular to the plane of the laminations.

6.3.4 Results

Results shall be expressed in MPa.

6.4 Impact strength

6.4.1 General

This test is only applicable to sheets of nominal thickness equal to or greater than 5 mm.

6.4.2 Charpy Impact strength

6.4.2.1 Test specimens

Test specimens shall be cut from the sheet under test in accordance with Figure 1 a). Five specimens, with a thickness between 5 mm and 10 mm, shall be tested in each direction, except for types with fibres aligned mainly in the same direction. In such cases, cut five specimens only, with their longitudinal axis parallel to the direction of the fibres.