



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 28033:2000

<https://standards.iteh.ai/catalog/standards/sist/a1c92ba0-7691-4f6c-b737-bdc67d2287cc/sist-en-28033-2000>

EUROPEAN STANDARD

EN 28033:1993

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 1993

UDC 621.643.3-036:620.179.4

Descriptors: Rubber products, plastic products, rubber hoses, plastic tubes, hoses, adhesion tests, adhesion

English version

**Rubber and plastics hose - Determination of  
adhesion between components (ISO 8033:1991)**

Tuyaux en caoutchouc et en plastique -  
Détermination de l'adhérence entre éléments  
(ISO 8033:1991)

Gummi und Kunststoffschlauch - Bestimmung der  
Haftung zwischen den einzelnen Schichten  
(ISO 8033:1991)

**(standards.iteh.ai)**SIST EN 28033:2000

<https://standards.iteh.ai/catalog/standards/sist/a1c92ba0-7691-4f6c-b737-bdc67d2287cc/sist-en-28033-2000>

This European Standard was approved by CEN on 1993-03-31. CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

The European Standards exist in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

**CEN**

European Committee for Standardization  
Comité Européen de Normalisation  
Europäisches Komitee für Normung

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

## Foreword

This European Standard has been taken over by the Technical Committee CEN/TC 218 "Rubber and plastics hoses and hose assemblies" from the work of ISO/TC 45 "Rubber and rubber products" of the International Organization for Standardization (ISO).

This European Standard EN 28033 was approved by CEN without any modification.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 1993, and conflicting national standards shall be withdrawn at the latest by November 1993.

According to the Internal Regulations of CEN/CENELEC, the following countries are bound to implement this European Standard : Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

### Endorsement notice

The text of the international standard ISO 8033:1991 was approved by CEN without any modification.

<https://standards.iteh.ai/catalog/standards/sist/a1c92ba0-7691-4f6c-b737-bdc67d2287cc/sist-en-28033-2000>

# INTERNATIONAL STANDARD

**ISO**  
**8033**

Second edition  
1991-12-01

---

---

## Rubber and plastics hose — Determination of adhesion between components

**iTeh STANDARD PREVIEW**  
*Tuyaux en caoutchouc et en plastique — Détermination de l'adhérence  
entre éléments*  
**(standards.iteh.ai)**

[SIST EN 28033:2000](#)

[https://standards.iteh.ai/catalog/standards/sist/a1c92ba0-7691-4f6c-b737-  
bdc67d2287cc/sist-en-28033-2000](https://standards.iteh.ai/catalog/standards/sist/a1c92ba0-7691-4f6c-b737-bdc67d2287cc/sist-en-28033-2000)



Reference number  
ISO 8033:1991(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 8033 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Sub-Committee SC 1, *Hoses (rubber and plastics)*.

This second edition cancels and replaces the first edition (ISO 8033:1985), of which it constitutes a minor revision.

© ISO 1991

All rights reserved. No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

# Rubber and plastics hose — Determination of adhesion between components

## 1 Scope

Adequate adhesion between the various components of a hose is essential if it is to perform satisfactorily in service.

This International Standard specifies methods for the determination of the adhesion between lining and reinforcement, between cover and reinforcement and between reinforcement layers. It covers all bore sizes and the following types of hose construction:

- woven textile fabric
- braided yarns
- spiralled yarns
- knitted yarns
- circular woven yarns
- textile cord fabric
- braided wires
- spiralled wires
- hoses containing a supporting helix

## 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 471:1983, *Rubber — Standard temperatures, humidities and times for the conditioning and testing of test pieces.*

ISO 1826:1981, *Rubber, vulcanized — Time-interval between vulcanization and testing — Specification.*

ISO 5893:1985, *Rubber and plastics test equipment — Tensile, flexural and compression types (constant rate of traverse) — Description.*

ISO 6133:1981, *Rubber and plastics — Analysis of multi-peak traces obtained in determinations of tear strength and adhesion strength.*

SIST EN 28033:2000

<https://standards.iteh.ai/catalog/standards/sist/a1c92ba0-7691-4f6c-b737-bdc67d2287cc/sist-en-28033-2000>

## 3 Principle

Using test pieces of standard dimensions, the adhesion strength between lining and reinforcement, between cover and reinforcement and between reinforcement layers is measured under specified conditions.

## 4 Apparatus

A test machine having the following characteristics is required.

**4.1** The machine shall be power driven, equipped with a suitable dynamometer, capable of maintaining a substantially constant rate of traverse of the moving head during the test and fitted with an autographic recorder. It shall comply with the requirement for grade A of ISO 5893.

NOTE 1 An inertialess dynamometer should be used.

**4.2** The grips shall be capable of holding the test piece without slippage.

NOTE 2 Self-tightening grips are recommended.

## ISO 8033:1991(E)

For strip test pieces, provision shall be made to maintain the strip in the appropriate plane of the grips during the test, for example by the attachment of sufficient weights to the free end of the test piece or by fitting a supporting plate, coated with a low friction material such as polytetrafluoroethylene (PTFE), to the non-driven grip.

**4.3** For testing a ring test piece, a mandrel shall be provided that is a close sliding fit in the test piece. This mandrel shall be capable of being fitted into the driven head of the machine so that it will rotate freely during the test (type 6).

## 5 Test pieces

### 5.1 Types of test piece

Seven types of test piece are specified to cover the range of hose construction for methods and bore size normally encountered.

#### 5.1.1 Type 1

Ring, cut from the hose 25 mm  $\pm$  0,5 mm wide and cut transversely to form a strip.

#### 5.1.2 Type 2

Strip, 160 mm  $\times$  half the hose circumference.

#### 5.1.3 Type 3

Ring, cut from the hose 35 mm  $\pm$  2 mm wide and cut transversely to form a strip.

#### 5.1.4 Type 4

Strip, 160 mm  $\times$  half the hose circumference or 10 mm whichever is smaller.

#### 5.1.5 Type 5

Strip, 160 mm long  $\times$  half the hose circumference.

#### 5.1.6 Type 6

Ring, 35 mm  $\pm$  2 mm wide.

#### 5.1.7 Type 7

Strip, cut along a reinforcing helix, 25 mm  $\pm$  0,5 mm wide or the maximum obtainable.

### 5.2 Test piece selection

Unless specified in the particular product standard or otherwise agreed between the interested parties, the type of test piece shall be selected from table 1. Results obtained with different test pieces and/or

hoses of the same construction but of different diameters are not comparable.

### 5.3 Test piece preparation

#### 5.3.1 Type 1

Cut a ring 25 mm  $\pm$  0,5 mm wide from the hose at right angles to its longitudinal axis. Cut the ring transversely and open it out to form a strip (see figure 1).

NOTE 3 The test pieces should be prepared by a method that does not cause high temperatures due to the cutting blade. Where heat build-up might cause a deterioration of properties, type 2, 3, 5 or 6 test pieces should be used.

#### 5.3.2 Type 2

Cut the test piece in half longitudinally. From one of the halves make two cuts parallel to the axis of the test piece 25 mm  $\pm$  0,5 mm, 10 mm  $\pm$  0,5 mm or 5 mm  $\pm$  0,2 mm apart, depending on the width available, taking care not to cut through the yarns.

Separate a layer for a distance sufficient to enable the separated ends to be held in the grips of the test machine (see figure 2).

#### 5.3.3 Type 3

Cut a ring 35 mm  $\pm$  2 mm wide from the hose at right angles to its longitudinal axis. Cut the ring transversely and open it to form a strip.

Make two parallel cuts on the strip 25 mm  $\pm$  0,5 mm apart, taking care not to cut through the yarns.

Separate a layer for a distance sufficient to enable the separated ends to be held in the grips of the test machine (see figure 3).

#### 5.3.4 Type 4

Cut the test piece in half longitudinally. Cut from one of the halves a strip 10 mm  $\pm$  0,5 mm wide, or of the maximum width obtainable if less than 10 mm.

Separate a layer for a distance sufficient to enable the separated ends to be held in the grips of the test machine (see figure 4).

#### 5.3.5 Type 5

Cut the test piece in half longitudinally. Using a twin bladed tool, cut a centrally located longitudinal strip 5 mm  $\pm$  0,2 mm wide through the lining and open up one end of the test piece to form a lip (see figure 5).

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN 28033:2000

<https://standards.iteh.ai/catalog/standards/sist/a1/c2/ba0-7091-1/bc-8737-bdc67d2287cc/sist-en-28033-2000>

Table 1 — Test piece selection

Hose construction	Adhesion between	Hose nominal bore size, $d$ (mm)		
		$d \leq 20$	$20 < d \leq 50$	$d > 50$
Textile woven fabric	Lining and reinforcement	Type 4	Type 1	Type 1
Textile braided	Reinforcement layers	Type 4	Type 1	Type 1
Textile knitted	Cover and reinforcement	Type 4	Type 1	Type 1
Textile circular woven				
Textile spiral	Lining and reinforcement	Type 2	Type 3	Type 3
Textile cord fabric	Reinforcement layers	Type 2 <sup>1)</sup>	Type 2 or 3 <sup>1)</sup>	Type 3 <sup>1)</sup>
	Cover and reinforcement	Type 2	Type 3	Type 3
Wire braid	Lining and reinforcement	Type 5 <sup>2)</sup>	Type 5	Type 5
Wire spiral	Reinforcement layers	— <sup>3)</sup>	— <sup>3)</sup>	— <sup>3)</sup>
	Cover and reinforcement	Type 2 or 6	Type 2 or 6	Type 2 or 6
Hoses containing a supporting helix	Lining and reinforcement	Type 7	Type 7	Type 7
	Reinforcement layers	Type 7	Type 7	Type 7
	Cover and reinforcement	Type 7	Type 7	Type 7

1) If the determination of adhesion is affected by the difficulty of obtaining a cleanly separating interface because of fraying of the yarns, indicate this in the test report.

2) Determination is impracticable below 12,5 mm bore size since insufficient test piece width is available.

3) Determination is impracticable since the wire braid or spiral layers tend to disintegrate and the result is in any case significantly affected by the forces required to bend the wires.

### 5.3.6 Type 6

Cut a ring 35 mm  $\pm$  2 mm wide from the hose at right angles to its longitudinal axis. Make two circumferential cuts through the cover 25 mm  $\pm$  0,5 mm apart and located centrally on the specimen. Make a transverse cut across the 25 mm width through the cover and open up on one side of the cut to form a lip (see figure 6).

### 5.3.7 Type 7

Obtain a strip from the hose wall by cutting along the reinforcing helix and trim to 160 mm long, 25 mm  $\pm$  0,5 mm wide or the maximum obtainable less than 25 mm (see figure 7).

NOTE 4 This is an optional test where helix reinforced hoses are made in long lengths. It does not apply to hoses made to individual lengths, with special ends, built-in fittings, etc. It is only applicable if the spacing between individual helices is greater than 10 mm.

## 5.4 Conditioning of test pieces

No tests shall be carried out within 24 h of manufacture. Test pieces shall be conditioned at standard temperature and humidity (see ISO 471) before testing for at least 16 h; this may be part of the 24 h after manufacture.

## 5.5 Time interval between vulcanization and testing

For evaluations intended to be comparable the tests should, as far as possible, be carried out after the same time interval after manufacture. ISO 1826 shall be followed for time between sample manufacture and testing.

## 6 Procedure

6.1 A separate test piece shall be used for each interface to be tested.

6.2 Take the test piece from the conditioning atmosphere and measure the actual width of the test piece. Fix the separated ends of the test piece in the grips of the testing machine and adjust so that the tension is distributed uniformly and that no twisting of the test piece occurs during the test. Place the test piece in the grips so that the angle of separation is approximately 180° for strip or 90° for ring test pieces.

It is important to ensure that the pulling force acts in the plane of separation.

6.3 The rate of travel of the power-driven grip shall be such as to provide a rate of ply separation of 50 mm/min  $\pm$  5 mm/min.