



Standard Practice for Testing Graphite Materials for Gas-Cooled Nuclear Reactor Components¹

This standard is issued under the fixed designation C781; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This practice covers the application and limitations of test methods for measuring the properties of graphite materials. These properties may be used for the design and evaluation of gas-cooled reactor components.

1.2 The test methods referenced herein are applicable to materials used for replaceable and permanent components as defined in Section 7 and includes fuel elements; removable reflector elements and blocks; permanent side reflector elements and blocks; core support pedestals and elements; control rod, reserve shutdown, and burnable poison compacts; and neutron shield material. Specific aspects with respect to testing of irradiated materials are addressed.

1.3 This practice includes test methods that have been selected from ASTM standards and guides that are specific to the testing of materials listed in 1.2. Comments on individual test methods for graphite components are given in Section 8. The test methods are summarized in Table 1.

1.4 The values stated in SI units are to be regarded as standard. The values given in parentheses after SI units are provided for information only and are not considered standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This practice is under the jurisdiction of ASTM Committee D02 on Petroleum Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee D02.F0 on Manufactured Carbon and Graphite Products.

Current edition approved Oct. 1, 2018. Published November 2018. Originally approved in 1977. Last previous edition approved in 2014 as C781 – 08 (2014). DOI: 10.1520/C0781-18.

2. Referenced Documents

2.1 ASTM Standards:²

- C559 Test Method for Bulk Density by Physical Measurements of Manufactured Carbon and Graphite Articles
- C561 Test Method for Ash in a Graphite Sample
- C577 Test Method for Permeability of Refractories
- C611 Test Method for Electrical Resistivity of Manufactured Carbon and Graphite Articles at Room Temperature
- C625 Practice for Reporting Irradiation Results on Graphite
- C651 Test Method for Flexural Strength of Manufactured Carbon and Graphite Articles Using Four-Point Loading at Room Temperature
- C695 Test Method for Compressive Strength of Carbon and Graphite
- C747 Test Method for Moduli of Elasticity and Fundamental Frequencies of Carbon and Graphite Materials by Sonic Resonance
- C749 Test Method for Tensile Stress-Strain of Carbon and Graphite
- C769 Test Method for Sonic Velocity in Manufactured Carbon and Graphite Materials for Use in Obtaining an Approximate Value of Young's Modulus
- C816 Test Method for Sulfur Content in Graphite by Combustion-Iodometric Titration Method
- C838 Test Method for Bulk Density of As-Manufactured Carbon and Graphite Shapes
- C1039 Test Methods for Apparent Porosity, Apparent Specific Gravity, and Bulk Density of Graphite Electrodes
- C1179 Test Method for Oxidation Mass Loss of Manufactured Carbon and Graphite Materials in Air
- C1233 Practice for Determining Equivalent Boron Contents of Nuclear Materials
- C1274 Test Method for Advanced Ceramic Specific Surface Area by Physical Adsorption
- D346 Practice for Collection and Preparation of Coke Samples for Laboratory Analysis
- D1193 Specification for Reagent Water

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

TABLE 1 Summary of Test Methods for Graphite Components

NOTE 1—Graphite Components include: Fuel, Removable Reflector and Core Support Elements; Pebble Bed Reflector, Key and Sleeves and Dowel Pins, Permanent Side Reflector Elements and Dowel Pins, Core Support Pedestals and Dowels.

	Test Method
Fabrication	
As Manufactured Bulk Density	C838
Mechanical Properties	
Compressive Strength	C695
Tensile Properties	C749
Poisson's Ratio	E132, C747
Flexural Strength	C651, D7972
Fracture Toughness	D7779
Modulus of Elasticity	C747, C769
Physical Properties	
Bulk Density—Machined Specimens	C559
Surface Area (BET)	C1274
Permeability	C577 ^{A,B}
Apparent Porosity	C1039
Spectroscopic Analysis	^B
Electrical Resistivity	C611
Thermal Properties	
Linear Thermal Expansion	E228 ^A
Thermal Conductivity	E1461 ^A
Chemical Properties	
Oxidative Mass Loss	C1179, D7542
Sulfur Concentration	C816
Ash Content	C561 ^A
Equivalent Boron Content ^C	C1233 ^A

^A Modification of this test method is required. See Section 8 for details.

^B New test methods are required. See Section 8 for details.

^C There is no identified need for determining this property for core support pedestals and dowels.

D2854 Test Method for Apparent Density of Activated Carbon

D2862 Test Method for Particle Size Distribution of Granular Activated Carbon

D3104 Test Method for Softening Point of Pitches (Mettler Softening Point Method)

D4175 Terminology Relating to Petroleum Products, Liquid Fuels, and Lubricants

D4292 Test Method for Determination of Vibrated Bulk Density of Calcined Petroleum Coke

D5600 Test Method for Trace Metals in Petroleum Coke by Inductively Coupled Plasma Atomic Emission Spectrometry (ICP-AES)

D7219 Specification for Isotropic and Near-isotropic Nuclear Graphites

D7542 Test Method for Air Oxidation of Carbon and Graphite in the Kinetic Regime

D7775 Guide for Measurements on Small Graphite Specimens

D7779 Test Method for Determination of Fracture Toughness of Graphite at Ambient Temperature

D7846 Practice for Reporting Uniaxial Strength Data and Estimating Weibull Distribution Parameters for Advanced Graphites

D7972 Test Method for Flexural Strength of Manufactured Carbon and Graphite Articles Using Three-Point Loading at Room Temperature

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

E132 Test Method for Poisson's Ratio at Room Temperature

E228 Test Method for Linear Thermal Expansion of Solid Materials With a Push-Rod Dilatometer

E261 Practice for Determining Neutron Fluence, Fluence Rate, and Spectra by Radioactivation Techniques

E639 Test Method for Measuring Total-Radiance Temperature of Heated Surfaces Using a Radiation Pyrometer (Withdrawn 2011)³

E1461 Test Method for Thermal Diffusivity by the Flash Method

E1269 Test Method for Determining Specific Heat Capacity by Differential Scanning Calorimetry

E2716 Test Method for Determining Specific Heat Capacity by Sinusoidal Modulated Temperature Differential Scanning Calorimetry

3. Terminology

3.1 *Definitions*—Terminology D4175 shall be considered as applying to the terms used in this practice.

4. Significance and Use

4.1 Property data obtained with the recommended test methods identified herein may be used for research and development, design, manufacturing control, specifications, performance evaluation, and regulatory statutes pertaining to nuclear reactors that utilize graphite.

4.2 The referenced test methods are applicable primarily to specimens in the non-irradiated and non-oxidized state. Testing irradiated specimens often requires specimen geometries that

³ The last approved version of this historical standard is referenced on www.astm.org.

do not meet the requirements of the standard. Specific instructions or recommendations with respect to testing non-conforming geometries can be found in STP 1578⁴ and/or Guide D7775. When testing irradiated specimens at elevated temperatures, the effects of annealing should be considered (see Note 1).

NOTE 1—Exposure to fast neutron radiation will result in atomic and microstructural changes to graphite. This radiation damage occurs when energetic particles, such as fast neutrons, impinge on the crystal lattice and displace carbon atoms from their equilibrium positions, creating a lattice vacancy and an interstitial carbon atom. The lattice strain that results from displacement damage causes significant structural and property changes in the graphite and is a function of the irradiation temperature and dose. When the temperature of the graphite is brought above the temperature at which it was irradiated, enough energy is provided that the structure of the graphite will anneal back to its original condition. Therefore, measurement techniques that bring the specimen temperature above the irradiation temperature can result in property values that change during the measurement process. For this reason, measurements made on irradiated test specimens below the irradiation temperature will produce results that are representative of the irradiation damage. However, measurements made at temperatures above the irradiation temperature could include the effects of annealing.

4.3 Additional test methods are in preparation and will be incorporated. The user is cautioned to employ the latest revision.

5. Sample Selection

5.1 All test specimens should be selected from materials that are representative of those to be used in the intended application.

6. Test Reports

6.1 Test results should be reported in accordance with the reporting requirements included in the applicable test method. Where relevant, information on grade designation, lot number, billet number, orientation, and location (position of sample in the original billet) shall be provided.

6.2 Information on specimen irradiation conditions shall be reported in accordance with Practices C625 and E261 or referenced to source information of equivalent content.

GRAPHITE COMPONENTS

7. Description and Function

7.1 The following are identified as typical components of a graphite moderated gas-cooled reactor based on historical designs. This list is not intended to be inclusive of all possible components, which will depend upon the particular reactor design.

7.2 Fuel and Removable Reflector Elements:

7.2.1 In manufactured carbons and graphites, a fuel element is a removable graphite element that contains channels for the passage of coolant gas, the fuel material (typically in the form of a compact containing coated particle fuel), the alignment

dowel pins, and for the insertion of a handling machine pickup head. A fuel element may also contain channels for reactivity control material (control rods), reserve shutdown compacts, and burnable poison compacts, and nuclear instrumentation.

7.2.2 The fuel elements serve multiple functions, including (1) vertical and lateral mechanical support for the fuel elements and removable reflector elements above and adjacent to them, and for the fuel, reactivity control materials, and nuclear instrumentation within them, (2) moderation of fast neutrons within the core region, (3) a thermal reservoir and conductor for nuclear heat generated in the fuel, (4) a physical constraint for the flow of coolant gases, and (5) a guide for and containment of fuel material, reactivity control materials, and nuclear instrumentation.

7.2.3 A removable reflector element is a removable graphite element that contains channels for the alignment dowel pins and the insertion of a handling machine pickup head. A removable reflector element may also contain channels for the passage of coolant gas, reactivity control materials (control rods), neutron flux control materials (neutron shield materials), and nuclear instrumentation.

7.2.4 The primary function of the removable reflector elements that are located at the boundaries of the active reactor core (fuel elements) is to provide moderation of fast neutrons escaping from and reflection of thermal neutrons back into the active core region.

7.2.5 Except for support, guide, and containment of fuel material, removable reflector elements may also serve any of the functions listed in 7.2.2.

7.3 Permanent Side Reflector Element:

7.3.1 A permanent side reflector element is a graphite block that is designed to remain permanently in the core but may be removed for inspection and replacement, if necessary. A permanent side reflector element contains channels for alignment dowel pins. It may also contain channels for neutron flux control materials (boronated steel pins) and nuclear instrumentation, and recessed areas along its length on its outer periphery to provide channels for the passage of coolant gas between the element and the metallic lateral restraint for the reactor core.

7.3.2 The permanent side reflector elements encircle the active (fuel) elements and passive (removable reflector) elements of the reactor core and serve multiple functions, including (1) vertical and lateral mechanical support for the permanent side reflector elements above and beside them, (2) lateral mechanical support for the fuel, removable reflector, and core support elements, (3) moderation of fast neutrons within the reflector region, (4) reflection of thermal neutrons back into the core region, and (5) support, guide, and containment of nuclear instrumentation and neutron flux control materials (boronated steel pins) for reducing the neutron flux to metallic structures outside the permanent side reflector boundary.

7.4 Core Support Pedestals and Elements:

7.4.1 A core support pedestal is a graphite column that is designed to remain permanently in the core but can be removed for inspection and replacement, if necessary. A core support pedestal has a central reduced cross-section (dog bone shape) that at its upper end contains channels for the passage of

⁴ Tzelepi, N. and Carroll, M., Eds., *Graphite Testing for Nuclear Applications: The Significance of Test Specimen Volume and Geometry and the Statistical Significance of Test Specimen Population*, STP1578-EB, ASTM International, West Conshohocken, PA, 2014, <https://doi.org/10.1520/STP1578-EB>

coolant gas, alignment dowel pins, and for the insertion of a handling machine pickup head, and at its lower end contains a recessed region for locating it with respect to the metallic structure that supports the graphite core support assembly. A core support element is a graphite element that contains channels for alignment dowel pins and for the insertion of a handling machine pickup head. The core support elements may also contain channels for the passage of coolant gas, neutron flux control materials, and nuclear instrumentation.

7.4.2 The primary function of the core support pedestals is to provide for vertical mechanical support for core support elements and permanent side reflector elements above them. In addition, core support pedestals provide for lateral mechanical support for adjacent core support pedestals and permanent side reflector elements and physical constraint for the flow of coolant gases. The primary function of the core support elements is to provide for vertical mechanical support for core support, fuel, and removable reflector elements above them. In addition, core support elements provide for lateral mechanical support for adjacent core support and permanent side reflector elements and may provide for the physical constraint of coolant gases and for the support, guide, and containment of neutron flux control materials and nuclear instrumentation.

7.5 Pebble Bed Modular Reactor Reflector Blocks:

7.5.1 The fuel form of a pebble bed reactor is typically a 60 mm diameter sphere (pebble) containing graphite-carbon matrix and coated particle fuel.

7.5.2 The Pebble Bed reactor core structure consists of a graphite reflector supported and surrounded by a metallic core barrel. The graphite reflector is comprised of a large number of graphite blocks arranged in circular rings of separate columns. The graphite reflector can be subdivided into three subsystems, namely, the bottom, side, and top reflector. The side reflector may be split into an inner replaceable reflector and an outer permanent reflector. The graphite reflector blocks are interlinked within each circular ring by graphite keys set in machined channels in the reflector blocks. Certain Pebble Bed reactors designs have annular fuelled cores, and thus the reactor contains a central graphite column.

7.5.3 The primary function of the reflector blocks that are located at the boundary of the active reactor core (fuelled region) is to provide for moderation of fast neutrons escaping from, and reflection of thermal neutrons back into, the active core region.

7.5.4 Replaceable reflector blocks contain vertical channels for the reactivity control rods and reserve shutdown system. These channels contain graphite sleeves to eliminate cross flow of reactor coolant gas.

8. Test Methods

8.1 Fabrication:

8.1.1 *Coefficient of Thermal Expansion of Coke*—The method known as the flour-based graphitized rod CTE test is described in [Annex A1](#).

8.1.2 *Bulk Density*—Determine bulk density on as-manufactured or machined specimens in accordance with Test Methods [C838](#) and [C559](#), respectively. Test Method [C838](#) includes shaped articles other than right circular cylinders and

rectangular parallelepipeds. Test Method [C559](#) is used when a higher degree of accuracy is required. The procedures of Test Method [C559](#) are modified in [Annex A2](#) to provide for the measurement of bulk density of non-uniform specimens.

8.1.3 *Graphitization Temperature*—The graphitization temperature of a full-size billet is estimated from a laboratory correlation between Specific Electrical Resistivity (SER) (Test Method [C611](#)) and heat treatment temperature. The method is described in [Annex A3](#).

8.2 Mechanical Properties:

8.2.1 *Compressive Strength*—Determine compressive strength in accordance with Test Method [C695](#).

8.2.2 *Tensile Strength*—Determine tensile strength in accordance with Test Method [C749](#) and Guide [D7775](#).

8.2.3 *Flexural Strength*—Determine flexural strength in accordance with Test Method [C651](#) or [D7972](#).

8.2.4 *Fracture Toughness*—Determine fracture toughness in accordance with Test Method [D7779](#).

8.2.5 *Modulus of Elasticity and Poisson's Ratio*—Determine modulus of elasticity in accordance with Test Method [C747](#). Poisson's ratio can be determined using Test Method [E132](#). Sonic velocity (Test Method [C769](#)) may be used to give an approximate Young's Modulus.

8.3 Physical Properties:

8.3.1 *Bulk Density*—See [8.1.2](#).

8.3.2 *Surface Area*—The determination of the specific surface area (BET) shall be in accordance with Test Method [C1274](#).

8.3.3 *Gaseous Permeability*—Test Method [C577](#) for measuring gaseous permeability must be modified to permit the additional use of helium as the permeating medium and the use of alternative geometries for specimens and specimen holders.

8.3.4 *Apparent Porosity*—The determination of the apparent porosity shall be in accordance with Test Method [C1039](#).

8.4 Thermal Properties:

8.4.1 *Coefficient of Thermal Expansion of Graphite*—Determine the linear coefficient of thermal expansion (CTE) of graphite of all grain sizes in (general) accordance with Test Method [E228](#). Test specimens of cylindrical or prismatic geometry shall be used. The diameter or transverse-edge length, respectively, shall be no less than five times the maximum grain size of the graphite, and in no case smaller than 4 mm. The length of the test specimen shall be at least 25 mm, preferably 50 mm to 125 mm. The report shall include the temperature range over which the CTE was measured.

8.4.2 *Thermal Conductivity*—Calculate the thermal conductivity from the thermal diffusivity as determined by Test Method [E1461](#). The required calculation is described in [Annex A4](#).

8.5 Chemical Properties:

8.5.1 *Oxidation*—Determine the oxidative mass loss in air in accordance with Test Method [C1179](#). (A test method for the determination of oxidation rate in air is in preparation.)

8.5.2 Chemical Impurities:

8.5.2.1 The chemical impurities shall be measured in accordance with [D5600](#). An alternative test method for determining

impurity concentrations in nuclear graphite by spectroscopic methods is in preparation.

8.5.2.2 Determine sulfur concentration in accordance with Test Method **C816**.

8.5.2.3 A method for determining boron levels is described in **Annex A5**.

8.5.3 *Equivalent Boron Content*—Test Method **C1233** shall be used to calculate equivalent boron content. The elements

specified in **D7219** shall be measured for the determination of the equivalent boron content.

9. Keywords

9.1 chemical properties; graphite; gas-cooled nuclear reactors; mechanical properties; neutronic properties; physical properties; thermal properties

ANNEXES

(Mandatory Information)

A1. QUALIFICATION CTE TEST FOR CALCINED COKE

A1.1 *Scope*—This method is applicable to the manufacture of graphite test rods from calcined petroleum or coal tar pitch coke of any origin.

A1.2 Sampling

A1.2.1 Coke samples that are submitted for testing shall properly represent those lots, barges, railcars, or trucks which are received by the manufacturing locations.

A1.2.2 The coke sample shall be collected in accordance with Practice **D346**.

A1.2.3 Approximately 0.5 kg of calcined coke shall be riffled from a larger sample.

A1.3 Procedure

A1.3.1 *Preparation of Green Test Specimen*—The sample of calcined coke shall be split into equal parts and one half retained for possible recheck. The other half is dried at 110 °C for 2 h and then crushed in one cycle to pass through a U.S. Standard 6.35 mm screen. The crushed sample is milled to flour so that at least 95 % passes a U.S. Standard No. 40 screen, and 40 % to 60 % passes a U.S. Standard No. 200 screen. Then appropriate quantities of the flour and a suitable medium coal tar pitch binder (nominal softening point 110 °C according to Test Method **D3104**, crushed to pass a U.S. Standard No. 10 screen) are heated to about 150 °C in a suitable laboratory scale mixer with occasional stirring. An extrusion aid may be added and mixed thoroughly. The mixture is then cooled or placed directly into a suitable heated laboratory scale extrusion press and tamped prior to extrusion. The internal diameter of the laboratory press may be 38 mm to 50 mm. The quantity of mix is sufficient when extruded to produce three test specimens 12 mm to 20 mm in diameter and 100 mm to 150 mm in length. The first test specimen extruded is discarded.

A1.3.2 *Baking*—The duplicate green specimens are packed without touching in a suitable sagger in bed of graphite particles or bed of coke and sand mixture (the pack passes a

U.S. Standard No. 10 screen) then covered with about 50 mm of the same packing media. The sagger is placed into a furnace at 100 °C and heated at about 90 °C/h to 120 °C/h to 850 °C to 900 °C and held for 1 h to 3 h. The sagger shall be furnace cooled to less than 300 °C before opening and unpacking the rods. The rods may be cleaned using coarse sandpaper if required.

A1.3.3 *Graphitizing*—The baked specimens are placed loosely in a graphite capsule and heated at approximately 15 °C/min to a temperature above 2700 °C and held for 30 min. Graphitization shall be conducted under flowing argon and the capsule shall be cooled to less than 300 °C before removing the rods.

A1.4 *Measuring the Coefficient of Thermal Expansion*—The rods will be cleaned and machined so that the end faces are parallel and normal to the longitudinal axis. The bulk density shall be measured according to Test Method **C559**, and the resistivity measured according to Test Method **C611**, and the values recorded. The density and resistivity shall be evaluated to ensure proper processing was achieved. The coefficient of thermal expansion (CTE) of the test specimens shall be measured along the longitudinal axis of the rod between room temperature and 500 °C in accordance with Test Method **E228** and **8.4.1**. The average of a single determination on each of the two specimens shall be recorded. A variation of the method involves measurement of the CTE at the baked stage and the use of an empirical relationship to estimate the CTE of the graphite.

A1.5 *Report*—The average CTE of the individual rods shall be reported in $\mu\text{m}/\text{m}\cdot^\circ\text{C}$ (25 °C to 500 °C). The averages of rod bulk density and resistivity shall also be reported.

A1.6 *Precision and Bias*—No precision statement has been determined for this test method.

A2. BULK DENSITY OF NON-UNIFORM TEST SPECIMENS

A2.1 The bulk density of test specimens other than right circular cylinders or rectangular parallelepipeds may be determined using Test Method C559 provided the specimen volume can be determined within 0.15 %. (See 6.2 of Test Method C559.)

A2.2 The net volume of a nonuniform, axisymmetric test specimen can be calculated if the shape can be broken down into simple geometric elements. Element volumes can be

calculated with the aid of mensuration tables generally found in math and engineering handbooks. Sum the element volumes to obtain the net volume of the test specimen. Calculate the bulk density as in 7.3 of Test Method C559.

A3. ESTIMATION OF THE GRAPHITIZATION TEMPERATURE OF FULL-SIZE BILLETS FROM THE MEASURED SPECIFIC ELECTRICAL RESISTIVITY

A3.1 The estimate of the graphitization temperature of a full-size billet is determined from a laboratory correlation between heat treatment temperature and the specific electrical resistivity (SER) of small specimens.

A3.2 Procedure

A3.2.1 Samples of appropriate dimensions as described in Test Method C611 shall be cut from a full sized billet that has completed all processing steps prior to graphitization. The SER and bulk density of the cut samples shall be measured, using Test Methods C611 and C559, respectively, and reported along with the sampling diagram. At least three samples at each temperature shall be heat treated under controlled laboratory conditions at a minimum of five temperatures covering the range 2400 °C to 3100 °C. A heating rate of 15 °C/min shall be used. The samples shall be held at the heat treatment temperature for a minimum of 30 min. The SER of the heat treated specimens shall be determined at room temperature in accordance with Test Method C611. An SER versus temperature

correlation curve shall be developed and a value shall be established that represents the required full-size billet graphitization temperature, typically 2700 °C. Errors in measurement will be determined from the scatter in the SER versus temperature plot. Typically, the temperature is monitored using an optical pyrometer calibrated by Test Method E639. Note, a new SER value must be established if changes are made in raw materials, mix formulation, or processing procedures.

A3.2.2 The SER of each full-size graphite billet shall be measured at room temperature using a standard procedure developed by the supplier and approved by the purchaser. The value of SER determined on each billet shall be used to establish the graphitization temperature of that billet using the laboratory correlation.

A3.2.3 The SER derived graphitization temperature of each billet shall be reported to the purchaser.

A3.3 *Precision and Bias*—No precision statement has been determined for this test method.

A4. SPECIFIC HEAT CAPACITY OF GRAPHITE AND THE CALCULATION OF THERMAL CONDUCTIVITY FROM MEASUREMENTS OF THERMAL DIFFUSIVITY

A4.1 The thermal conductivity may be calculated from the measurements of thermal diffusivity with the following equation:

$$\lambda = \alpha C_p \rho$$

where:

λ = thermal conductivity, W/m-K,

α = thermal diffusivity,
 ρ = bulk density, and
 C_p = specific heat capacity.

A4.2 The bulk density of polycrystalline graphite at room temperature can be measured by applying 8.1.2 of this practice. If the thermal conductivity is desired at elevated temperatures, it is important to consider how both the density and the specific