



Designation: **D3056—14 D3056 – 14 (Reapproved 2018)**

## Standard Test Method for Gel Time of Solventless Varnishes<sup>1</sup>

This standard is issued under the fixed designation D3056; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

### 1. Scope\*

1.1 This test method covers the determination of the gel time of a solventless varnish mixed with a catalyst, if required, and exposed to elevated temperature.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.* For a specific precaution statement, see Section 6.

NOTE 1—Although this standard and IEC 60455–2 differ in approach or detail, data obtained using either are technically equivalent.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D1711 Terminology Relating to Electrical Insulation

2.2 *IEC Standard:*<sup>3</sup>

IEC 60455–2 Resin Based Reactive Compounds Used for Electrical Insulation—Part 2: Methods of Test

### 3. Terminology

3.1 *Definitions:*

3.1.1 *gel time, n*—of solventless varnish, the time required at a specified temperature for a solventless varnish to be transformed from a liquid state to a gel as measured with a suitable gel time apparatus.

3.1.2 See Terminology D1711 for definitions of other terms relating to electrical insulation.

### 4. Significance and Use

4.1 Gel time is important in determining batch uniformity and some processing characteristics. It is indicative of pot life and shelf life.

### 5. Apparatus

5.1 *Gel Time Apparatus.*<sup>4</sup>

5.2 *Power Supply*, 110 V ac variable.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.01 on Electrical Insulating Varnishes, Powders and Encapsulating Compounds Products.

Current edition approved Nov. 1, 2014; Nov. 1, 2018. Published November 2014; November 2018. Originally approved in 1972. Last previous edition approved in 2010 as D3056–05 (2010); D3056 – 14. DOI: 10.1520/D3056-14.10.1520/D3056-18.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

<sup>4</sup> The sole source of supply of the apparatus known to the committee at this time is Sunshine Gel Time Meter, Catalog No. 22, manufactured by Sunshine Scientific Instruments, 1810 Grant Ave., Philadelphia, PA 19115. If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,<sup>4</sup> which you may attend.

\*A Summary of Changes section appears at the end of this standard