



Designation: D3376 – 18

Standard Test Methods of Sampling and Testing Pulps to be Used in the Manufacture of Electrical Insulation¹

This standard is issued under the fixed designation D3376; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 These test methods cover the sampling and testing of cellulosic pulps for use in the manufacture of electrical insulating papers and boards or in the direct application of pulp fibers as insulation to electrical conductors.

NOTE 1—Consider the significance of any one pulp property test method, as set forth herein, with discretion depending on the product made from the pulp.

1.2 Sections on Reagents, Sampling, and Report are integral parts of each of the individual test methods that follow.

1.3 Each test method is described as being a measure of either a bulk property of the pulp or a property of a handsheet formed from the pulp.

1.3.1 Bulk characteristics determinable by these procedures appear in the following sections:

Procedure	Sections	ASTM Method Reference	TAPPI Method Reference
Aqueous Extract Conductivity	8 & 9	D202	...
Aqueous Extract pH	10 & 11	D202	...
Aqueous Extractable Acidity-Alkalinity	12 & 13	D202	...
Analysis of Ash for Cations by Atomic Absorption Spectrophotometry	70 – 78	D1193 & D2576	...
Ash Content	79 – 82	D202	T 413
Dirt in Pulp	40 & 41	...	T 213
Fiber Analysis	23 & 24	D202 & D1030	...
Fiber Length of Pulp	42 & 43	...	T 232, T 233
Freeness (Canadian Standard Freeness)	53 & 54	...	T 227
Kappa Number/Permanganate Number (Substances Oxidizable by Permanganate)	27 & 28	...	T 236, UM 251
Laboratory Processing of Pulp (Beater Method)	51 & 52	...	T 200
Moisture in Pulp	31 – 33	...	T 210
Neutral Aqueous Extractable Hardness in Pulp	16 – 22	D202, D1126, & D2576	...

¹ These test methods are under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and are the direct responsibility of Subcommittee D09.01 on Electrical Insulating Products.

Current edition approved Nov. 1, 2018. Published November 2018. Originally approved in 1975. Last previous edition approved in 2014 as D3376 – 14. DOI: 10.1520/D3376-18.

Procedure	Sections	ASTM Method Reference	TAPPI Method Reference
Pentosan Content of Pulp	29 & 30	...	T 223
Resistance of Pulp to Disintegration (Standard RPG)	44 – 50	...	T 239, UM 252
Shive Count	34 – 39
Solvent-Soluble Matter in Pulp	25 & 26	D202	...
Tensile Properties	65 – 69	D202	...
Water-Extractable Chlorides	14 & 15	D202	...

1.3.2 Handsheet characteristics determinable by these procedures appear in the following sections:

Procedure	Sections	ASTM Method Reference	TAPPI Method Reference
Air Resistance (Porosity)	57 & 58	D202	T 205
Apparent Density	63 & 64	D202	T 205
Bursting Strength	59 & 60	D202 & D774/D774M	T 205
Folding Endurance (M.I.T.)	51 & 52	D202 & D2176	T 205
Forming Handsheets for Physical Tests of Pulp	55 & 56	...	T 205
Tensile Strength	65 & 66	D202 & D828	T 205

NOTE 2—Methods for Ash, Silica, selected cations from Ash, Heat Stability, α , β , and γ Cellulose, Viscosity, Total Chlorine, Tear, and Dissipation Factor and Relative Permittivity, will be considered for addition as methods are developed.

1.4 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

*A Summary of Changes section appears at the end of this standard

2. Referenced Documents

2.1 ASTM Standards:²

D202 Test Methods for Sampling and Testing Untreated Paper Used for Electrical Insulation

D774/D774M Test Method for Bursting Strength of Paper (Withdrawn 2010)³

D828 Test Method for Tensile Properties of Paper and Paperboard Using Constant-Rate-of-Elongation Apparatus

D1030 Test Method for Fiber Analysis of Paper and Paperboard

D1126 Test Method for Hardness in Water

D1193 Specification for Reagent Water

D1711 Terminology Relating to Electrical Insulation

D2176 Test Method for Folding Endurance of Paper and Plastics Film by the M.I.T. Tester

D2576 Method of Test for Metals in Water and Waste Water by Atomic Absorption Spectrophotometry (Withdrawn 1979)³

D3376 Test Methods of Sampling and Testing Pulps to be Used in the Manufacture of Electrical Insulation

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

2.2 TAPPI Standards:⁴

T 200 Laboratory Processing of Pulp (Beater Method)

T 205 Forming Handsheets for Physical Tests of Pulp

T 210 Weighing, Sampling, and Testing Pulp for Moisture

T 213 Dirt in Pulp

T 221 Drainage Time of Pulp

T 223 Pentosans in Wood and Pulp

T 227 Freeness of Pulp

T 232 Fiber Length of Pulp by Projection

T 233 Fiber Length of Pulp by Classification

T 236 Kappa Number of Pulp

T 413 Ash in Paper and Paperboard

T 445 Identification of Specks and Spots in Paper

T 1002 Drainage Time for Insulating Board

UM 203 Freeness of Pulp (William Tester)

UM 251 Permanganate Number of Pulp

UM 252 Resistance of Pulp and Paper Stock to Disintegration

3. Terminology

3.1 Definitions—For definitions of terms used in these test methods and associated with electrical and electronic insulating materials use Terminology **D1711**.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 aqueous extractable hardness, *n*—the amount of calcium and magnesium present in pulp and which is extracted by hot neutral water under prescribed conditions.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from Technical Association of the Pulp and Paper Industry (TAPPI), 15 Technology Parkway South, Norcross, GA 30092, <http://www.tappi.org>.

3.2.2 hardness, *n*—a characteristic of water that represents the total concentration of calcium and magnesium in the water, expressed as parts per million (ppm) CaCO₃.

3.2.3 pulp, *n*—a fibrous material that is made by chemical or mechanical treatment, or both, of wood, cotton, hemp, or other cellulosic fiber to achieve substantially separate fibers that are suitable for a sheet-forming process.

NOTE 3—Electrical insulation made from pulp are papers or boards used for capacitors, transformer coils, creped papers, and so forth. Pulp is also applied directly onto electrical conductors.

3.2.4 resistance to disintegration, *n*—the amount of work (expressed as revolutions per gram of pulp) required under standard conditions to bring a sample of pulp to a state of complete dispersion of single fibers.

3.2.5 shive, *n*—a particle in pulp or paper that is a bundle of cellulosic fibers bonded together in a parallel arrangement.

NOTE 4—Dark single fibers are not to be counted as shives. Count only bundles of fibers regardless of color.

3.2.6 shive count, *n*—the quantitative expression of the concentration of shives in a quantity of pulp or paper.

3.2.6.1 Discussion—For this method the shive count is restricted to the number of shives that exceed 1.5 mm in length that are present after a specified processing of the pulp to form handsheets for evaluation.

4. Summary of Test Methods

4.1 These test methods describe the specific procedures for testing the properties of pulp, both in its original bulk form and after it has been formed into a handsheet in the testing laboratory.

5. Reagents

5.1 Purity of Reagents—Use reagent grade chemicals in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.⁵ It is acceptable to use other grades, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

5.2 Purity of Water—Unless otherwise indicated, references to water shall be understood to mean water conforming to Specification **D1193**, Type III.

6. Sampling

6.1 Terminology regarding sampling and evaluation terminology shall conform to those in the sampling sections of Test Methods **D202**.

6.2 Obtain the sample of pulp from the lot to be evaluated in a manner that will maximize the probability that a representative sample is collected. Where practicable, use one of the

⁵ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmaceutical Convention, Inc. (USPC), Rockville, MD.

sampling plans shown in Test Methods **D202**. Protect the material sample from contamination during handling and transporting to a laboratory for testing. The instructions for preparation of specimens are given in the sections pertaining to the individual property tests. Take the sample for moisture content in accordance with TAPPI T 210.

6.3 Condition samples in a container suitable for preventing moisture variation over the period of testing. When test specimens are drawn, determine the moisture content of the material to allow correction of weights to moisture-free equivalent weight.

7. Report

7.1 At the completion of any or all of the following tests, report the test results (as defined in 6.1) of the pulp properties with identifying units as follows:

7.1.1 Identification of the pulp sampled and tested by lot number, type, grade, and so forth,

7.1.2 Dates of testing,

7.1.3 Location of the testing laboratory and the person responsible for the testing,

7.1.4 Remarks indicating method or procedures used and the deviation, if any, from the standard test procedures,

7.1.5 Indication of the variance in test measurements (as defined in 6.1) such as high, low, standard deviation, and so forth, and

7.1.6 Any information particular to the cited procedure.

7.2 Report the test results (as defined in 6.1) as calculated or observed values rounded to the nearest unit in the last right-hand place of figures used in the material specification to express the limiting value. (See the rounding method of Practice **E29**.)

AQUEOUS EXTRACT CONDUCTIVITY

8. Significance and Use

8.1 The conductivity of the water extract of electrical grade pulp results from electrolytic impurities in the pulp potentially present as ionizable acids, bases, salts, or a combination of these. The presence of electrolytic impurities in electrical insulation is undesirable as they tend to lower insulation resistance and have corrosion-producing tendencies under conditions of applied potential. When comparing test data, note that the extract conductivity of pulps, especially those of high purity, changes with time after manufacturing in some instances. This test is useful for routine acceptance testing, the comparison of different pulps, and research work.⁶

9. Procedure

9.1 Follow Test Methods **D202** except use a specimen weight equivalent to 1 g of moisture-free pulp.

⁶ For more detailed information see *Paper and Paperboard—Characteristics, Nomenclature, and Significance of Tests*, ASTM STP 60 B, Am. Soc. Testing Mats., 1963, pp. 59–61.

AQUEOUS EXTRACT pH

10. Significance and Use

10.1 The extract pH determination measures the degree to which a pulp alters the hydrogen-hydroxyl equilibrium of pure water. The test gives a measure of the active acidity or alkalinity of the pulp extract. It is possible that the presence of active acidic or alkaline contaminants in a pulp will result in their being incorporated into the electrical insulation made from the pulp, and will lead to a deterioration of the insulation in service. This test is useful for routine acceptance testing, the comparison of different pulps, and research work.²

11. Procedure

11.1 Follow Test Methods **D202**, except use a specimen weight equivalent to 1 g of moisture-free pulp.

AQUEOUS EXTRACTABLE ACIDITY-ALKALINITY

12. Significance and Use

12.1 The extract acidity-alkalinity determination for a pulp measures the quantity of extracted ionizable material, which alters the hydrogen-hydroxyl equilibrium of pure water. It is possible that the presence of active acidic or alkaline contaminants in a pulp will result in their being incorporated into the electrical insulation made from the pulp, and this will lead to a deterioration of the insulation in service. This test is useful for routine acceptance testing, the comparison of different pulps, and research.⁴

13. Procedure

13.1 Follow Test Methods **D202**, except use a specimen weight equivalent to 1 g of moisture-free pulp.

WATER-EXTRACTABLE CHLORIDES

14. Significance and Use

14.1 It is possible that the occurrence of significant amounts of chloride ion in a pulp will lead to the incorporation of the ion in the electrical insulation made from the pulp. It is possible that the presence of chloride ions will adversely affect the electrical properties and service life of the insulation. This test is useful for routine acceptance testing, the comparison of different pulps, and research testing.

15. Procedure

15.1 Follow Test Methods **D202**, except use a specimen weight equivalent to 4 g of moisture-free pulp. For pulps with higher levels of chloride (greater than 30 ppm), 10 min of maseration as in the above method for aqueous extract conductivity is an acceptable way to hasten the extraction, followed by 1 h refluxing as in Test Methods **D202**. When the chloride content is less than 30 ppm, maseration is not permitted. The appropriate extraction time must be determined to give complete extraction of the chloride for each pulp type. Times greater than 1 h will be necessary in some instances.

NEUTRAL AQUEOUS EXTRACTABLE HARDNESS PULP

16. Significance and Use

16.1 Cellulose pulps contain varying amounts of aqueous extractable hardness as supplied to the purchaser. It is possible that the dissolved hardness from the pulp will accumulate in process water used in wet-forming methods and will interfere with the action of process additives and affect product quality adversely.

16.2 Method A is the preferred method and shall be used for reference purposes.

METHOD A

17. Procedure

17.1 Extraction:

17.1.1 Prepare extracts of the pulp specimens in accordance with the Test Methods **D202** method for aqueous extract conductivity, except:

17.1.2 Use a specimen weight equivalent to 2.0 g of moisture-free pulp. Determine the moisture content of the pulp sample on a separate specimen taken at the same time as the test specimen.

17.1.3 The extraction volume shall be 200 mL.

17.1.4 Run a blank determination concurrently with the test specimen determination.

17.1.5 Following extraction and filtration, collect the clear filtrate and adjust the volume to exactly 200 mL.

17.2 Determine the calcium and magnesium concentration of the extract in accordance with Test Method **D2576**.

18. Calculation

18.1 Calculate the hardness of the extracts as follows:

$$\text{Hardness, ppm} = 100[2.497(P_1 - P_a) + 4.117(P_2 - P_b)] \quad (1)$$

where:

P_1 = ppm calcium in the pulp extract,

P_a = ppm calcium in the blank,

P_2 = ppm magnesium in the pulp extract, and

P_b = ppm magnesium in the blank.

METHOD B

19. Procedure

19.1 Follow the procedure of Method A for the preparation of the extract.

19.2 Take two 100-mL aliquots of the extract and titrate for total hardness, following the "low total hardness" procedure of the nonreferee volumetric method of Test Method **D1126**.

20. Calculation

20.1 Calculate the hardness of the specimen extract as follows:

$$\text{Hardness, ppm} = 500(V_1 + V_2 - V_a - V_b) \quad (2)$$

where:

V_1 = standard EDTA solution for titration of first aliquot of extract, mL,

V_2 = standard EDTA solution for titration of second aliquot of extract, mL,

V_a = standard EDTA solution for titration of first blank aliquot, mL, and

V_b = standard EDTA solution for titration of second blank aliquot, mL.

21. Report

21.1 Report the results as neutral aqueous extractable hardness, ppm, expressed as calcium carbonate according to the appropriate method of Test Methods **D3376**.

22. Precision and Bias

22.1 The precision of this test has not been determined. No statement can be made about the bias of this test since standard material is not available.

FIBER ANALYSIS

23. Significance and Use

23.1 The fiber composition of a pulp (fiber source and pulping treatment) strongly affects the ultimate product characteristics. Fiber analysis is useful both as a specification and as a control test, and is acceptable in referee testing or research.

NOTE 5—For accurate results the analyst must have considerable training and experience. It is recommended the analyst make frequent use of standard fiber sources of known composition, or of authentic fiber samples, and be thoroughly familiar with different fibers and their behavior when treated with the various stains.

24. Procedure

24.1 Follow Test Methods **D202** and **D1030** using a specimen weight of 0.2 g of pulp drawn from a composite sample of pulp, equivalent to 30 g of moisture-free pulp disintegrated in 2 L of water, as in Test Method **D1030** and the section on fiber analysis in Test Methods **D202**.

SOLVENT-SOLUBLE MATTER IN PULP

25. Significance and Use

25.1 Since pulping processes usually remove most water-soluble and volatile compounds that are also soluble in organic solvents, consider the solvent extractives in pulp to consist primarily of resin and fatty acids, their esters, waxes, and unsaponifiable substances. No single organic solvent is capable of removing all these substances, and different solvents remove different combinations. The mixture of one part (by volume) of 95 % ethanol and two parts of benzene appears to provide the most complete removal of all solvent-extractable substances in pulp.

25.2 Solvent-extractable materials, if present in sufficient quantity in electrical insulation, will lower the quality of the insulation or have a deleterious effect on the liquid compounds used in contact with insulation in various types of apparatus. Ethanol-soluble materials in capacitor paper have been found to increase the conductivity of chlorinated organic compounds,

which are used as impregnants in capacitors. A combination of ether and alcohol-benzene extractives is reported to represent the quantity of pitch in wood pulp. Pitch in pulp will, in some instances, cause operating problems in the paper mill, such as the plugging of felts, wires, and so forth.

25.3 This method, with solvent or solvents specified, is acceptable for routine acceptance testing, comparing different pulps, and research tests.

26. Procedure

26.1 Test for solvent-soluble matter in accordance with Test Methods **D202**.

KAPPA NUMBER/PERMANGANATE NUMBER (SUBSTANCES OXIDIZABLE BY PERMANGANATE)

27. Significance and Use

27.1 The permanganate consumption of a pulp is a measure of its lignin content and is acceptable as a measure of lot-to-lot uniformity. For a given species of wood or other fibers, the permanganate consumption is a measure of the degree of cooking to which the fiber has been subjected, and relates to the ease of refining of the pulp produced from the cooked fiber. This test is useful for control purposes, specifications, and the comparison of different pulps.

28. Procedure

28.1 *Kappa Number*—Follow TAPPI T 236.

28.2 *Permanganate Number*—Follow TAPPI UM 251.

PENTOSAN CONTENT OF PULP

29. Significance and Use

29.1 The pentosan content of a pulp strongly affects the dissipation factor-temperature relationship of electrical insulation made from it. It is also a potential indicator of lot-to-lot uniformity and is one of several factors related to the bonding power of a pulp, and the amount of energy required to refine the pulp.

30. Procedure

30.1 Follow TAPPI T 223.

MOISTURE IN PULP

31. Significance and Use

31.1 Pulp is purchased on the basis of moisture content. In addition, the moisture content is acceptable for consistency control. It is possible that the moisture content will affect the energy of repulping and the biological degradation of the pulp. This test is useful for control purposes and specifications.

32. Procedure

32.1 Follow TAPPI T 210.

33. Report

33.1 This method gives the percentage moisture content of the pulp. Report percent water and percent moisture-free fiber (equal to 100 minus percent water).

SHIVE COUNT

34. Significance and Use

34.1 Several grades of electrical insulating paper are most effectively manufactured using pulps having a low shive count. Shives in wood pulp to be used for direct application to electrical conductors is potentially detrimental to the insulating characteristics and strength of the insulating wall. This test is useful for control purposes, specifications, and the comparison of different pulps.

35. Apparatus

35.1 *Disintegrator, Sheet Machine, Press, Blotters, and so forth*, in accordance with TAPPI T 205.

35.2 *Steel Rule*, graduated in 0.5 mm.

35.3 *Balance*, to weigh up to 100 g with 0.1-g accuracy.

35.4 *Specimen Viewer* with white opaque glass and a fluorescent or incandescent light source.

35.5 *Transparent Cylinder*, 0.6 L.

36. Procedure

36.1 From the sample obtained as specified in Section 6, take a quantity of pulp equivalent to 30 g of moisture-free pulp. Soak this pulp in 0.5 L of water for 4 h at a temperature of 20 to 30°C.

36.2 Tear the pulp into smaller pieces (approximately 1 in. or 25 mm square) and dilute to 2.0 L. **Warning**—*Tear*, do not cut the pulp.

36.3 Using the TAPPI disintegrator, disintegrate for 10 minute minimum. This time is likely to be sufficient to disperse the pulp completely. A technique for checking the dispersion is as follows:

36.3.1 Take a small sample of the slurry from the disintegrator (about 2 or 3 mL) and dilute to 0.6 L in a clear cylinder. Stopper the cylinder and mix the suspension by rotating the cylinder end over end. Observe the suspension by looking through it toward a strong light source. The suspension shall be free of clumps or agglomerates of fibers, but is allowed to contain shives. If the suspension contains clumps or agglomerates, subject the pulp to additional 5-min periods of disintegration until it is free of clumps and agglomerates.

36.4 Dilute the disintegrated pulp with water to result in a consistency of 0.3 % or 3 g/L.

36.5 Clean the sheet machine thoroughly.

36.6 Form handsheets in accordance with TAPPI T 205 and couch but do not dry the sheets.

36.7 Make at least five handsheets for viewing.

36.8 On each of five handsheets, mark out six viewing areas. Each viewing area shall be 625 mm². Facilitate this step by making a transparent plastic overlay grid with these areas cut out or other suitable method.

36.9 With the viewer and the steel rule, count the shives that exceed 1.5 mm in length that are viewed within each of the six areas. Record the total number of shives in each handsheet.

37. Calculation

37.1 Add the total shives found in all five handsheets. This sum, multiplied by 53, yields the shive count expressed as shives per square metre.

37.2 Calculate the shive count as shives per kilogram if the handsheet area is 0.02 m². Shives per kilogram is the product of total shives counted times 888. This multiplier is valid only for the standard handsheets in accordance with TAPPI T 205, with a grammage of 60 ± 1.2 g/m² and an area of 0.02 m².

38. Report

38.1 Report the disintegration time if more than 10 min.

38.2 Report the shive count as shives per square metre or as shives per kilogram as agreed upon between the supplier and the purchaser.

39. Precision and Bias

39.1 *Precision*—From a round-robin test involving three laboratories, a coefficient of variation between laboratories in the order of 300 was obtained, at a level of 5000 to 8000 shives/m².

39.2 *Bias*—No statement of bias can be made because of the unavailability of standard reference material.

DIRT IN PULP

40. Significance and Use

40.1 Dirt content is one indication of the quality of the pulp. This measure gives only a visual indication of contamination. The nature of foreign particles is very significant in determining whether the contamination is detrimental to the end-product use. TAPPI T 445 is likely to be appropriate for identification of the particulate contamination. This test is useful for control purposes and the comparison of different pulps.

41. Procedure

41.1 Follow TAPPI T 213 .

FIBER LENGTH OF PULP

42. Significance and Use

42.1 The fiber length is a means of comparing pulps. It is possible that the fiber length distribution will affect the forming characteristics, which in turn influence the physical characteristics of the end-product. This method is useful for control purposes, the comparison of different pulps, and research.

43. Procedure

43.1 Follow TAPPI T 232, T 233.

RESISTANCE OF PULP TO DISINTEGRATION (STANDARD RPG)

NOTE 6—The method described herein is essentially an adaptation of TAPPI UM 252, with several significant changes. The method is complete and no reference to UM 252 is required in its use.

44. Significance and Use

44.1 Resistance to disintegration is important in that it is a measure of repulpability. The method is useful for control purposes and the comparison of different pulps.

45. Apparatus

45.1 *Disintegrator*—TAPPI standard disintegrator in accordance with T 205; equipped with a 2-L standard vessel, timer/timer controlled power source, 1-s maximum time division.

45.2 *Handsheet Machine*—British Standard sheet machine in accordance with T 205, with couch roll, couch plate, 8 by 8-in. (200 by 200-mm) blotters, and a hot plate.

45.3 *Beakers*—Set of twelve numbered 50-mL beakers and set of twelve numbered 600-mL beakers.

45.4 *Graduated Cylinder*, 500-mL, transparent.

45.5 *Vessel*, to contain 1500 mL or more pulp, calibrated at 1500 mL.

45.6 *Sample Cup*, to hold 50 mL of pulp slurry.

45.7 *Oven*, drying, controlled at 105 ± 3°C.

45.8 *Balance*, to weigh up to 100 g with 0.1-g accuracy.

45.9 *Weighing Bottle*, to hold 10 g of pulp.

45.10 *Light Box*—Source of uniform illumination (incandescent or fluorescent) with surface sufficiently large to hold two handsheets (160-mm diameter disks).

46. Test Specimens

46.1 From the sample obtained as specified in Section 6, weigh out three specimens each equivalent to 60 g of moisture-free pulp. Determine the moisture content in accordance with Sections 31 – 33. Tear, do not cut, the test specimen from the test unit.

47. Procedure

47.1 Connect the disintegrator to the timed power outlet, and fill the disintegrator vessel with 2 L of water (25 ± 5°C). Select a disintegration period appropriate to the resistance of the pulp to disintegration.

NOTE 7—The times shown below are a guide for selecting the appropriate disintegration period.

<u>Resistance of Pulp to Dispersion</u>	<u>Disintegration Period</u>
slight	15
moderate	30
high	45

47.1.1 Take one specimen and briefly immerse it in the water in the disintegrator vessel to wet it thoroughly (for example, for 15 s) in water at 25 ± 5°C. Tear the specimen into pieces about 20 mm square. If the pulp is flash dried, it is acceptable to split it so that the specimen pieces are about 2.5 mm thick.

47.1.2 Quickly put the torn specimen into the disintegrator vessel and start the disintegration/sampling sequence. Disintegrate the specimen for one period, stop the disintegrator, remove 50 mL of the pulp slurry, and put it into beaker No. 1