

# INTERNATIONAL STANDARD

# NORME INTERNATIONALE



Optical fibres – **STANDARD PREVIEW**  
Part 2-10: Product specifications – Sectional specification for category A1  
multimode fibres  
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/b85d8886-7454-46ed-b3e5-606000000000/iec-60793-2-10-2019>  
Fibres optiques –  
Partie 2-10: Spécifications de produits – Spécification intermédiaire pour les  
fibres multimodales de catégorie A1



## THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2019 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office  
3, rue de Varembe  
CH-1211 Geneva 20  
Switzerland

Tel.: +41 22 919 02 11  
[info@iec.ch](mailto:info@iec.ch)  
[www.iec.ch](http://www.iec.ch)

### About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

### About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

#### IEC publications search - [webstore.iec.ch/advsearchform](http://webstore.iec.ch/advsearchform)

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

#### IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

#### IEC Customer Service Centre - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: [sales@iec.ch](mailto:sales@iec.ch).

#### Electropedia - [www.electropedia.org](http://www.electropedia.org)

The world's leading online dictionary on electrotechnology, containing more than 22,000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

#### IEC Glossary - [std.iec.ch/glossary](http://std.iec.ch/glossary)

67,000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

### A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

### A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

#### Recherche de publications IEC -

##### [webstore.iec.ch/advsearchform](http://webstore.iec.ch/advsearchform)

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

#### IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

#### Service Clients - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: [sales@iec.ch](mailto:sales@iec.ch).

#### Electropedia - [www.electropedia.org](http://www.electropedia.org)

Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 000 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 16 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

#### Glossaire IEC - [std.iec.ch/glossary](http://std.iec.ch/glossary)

67 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

# INTERNATIONAL STANDARD

## NORME INTERNATIONALE



**Optical fibres –** iTeh STANDARD PREVIEW  
**Part 2-10: Product specifications – Sectional specification for category A1**  
**multimode fibres** (standards.iteh.ai)

**Fibres optiques –** <https://standards.iteh.ai/catalog/standards/sist/b85d8886-7454-46ed-b3e5-60793-2-10>  
**Partie 2-10: Spécifications de produits – Spécification intermédiaire pour les**  
**fibres multimodales de catégorie A1**

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

COMMISSION  
ELECTROTECHNIQUE  
INTERNATIONALE

ICS 33.180.10

ISBN 978-2-8322-6920-6

**Warning! Make sure that you obtained this publication from an authorized distributor.**  
**Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

## CONTENTS

FOREWORD .....	5
1 Scope .....	7
2 Normative references .....	8
3 Terms and definitions .....	9
4 Abbreviated terms .....	10
5 Specifications .....	10
5.1 General .....	10
5.2 Dimensional requirements .....	10
5.3 Mechanical requirements .....	12
5.4 Transmission requirements .....	12
5.5 Environmental requirements .....	14
5.5.1 General .....	14
5.5.2 Mechanical environmental requirements (common to all fibres in category A1) .....	15
5.5.3 Transmission environmental requirements .....	16
Annex A (normative) Specifications for sub-categories A1-OM2, A1-OM3, A1-OM4 and A1-OM5 multimode fibres .....	17
A.1 General .....	17
A.2 Dimensional requirements .....	17
A.3 Mechanical requirements .....	18
A.4 Transmission requirements .....	18
A.5 Environmental requirements .....	20
Annex B (normative) Specifications for sub-category A1-OM1 multimode fibres .....	21
B.1 General .....	21
B.2 Dimensional requirements .....	21
B.3 Mechanical requirements .....	21
B.4 Transmission requirements .....	22
B.5 Environmental requirements .....	22
Annex C (normative) Specifications for sub-category A1d multimode fibres .....	23
C.1 General .....	23
C.2 Dimensional requirements .....	23
C.3 Mechanical requirements .....	23
C.4 Transmission requirements .....	24
C.5 Environmental requirements .....	24
Annex D (normative) Fibre differential mode delay (DMD), calculated effective modal bandwidth (EMB <sub>c</sub> ) and calculated overfilled modal bandwidth (OMB <sub>c</sub> ) requirements .....	25
D.1 A1-OM3 fibre DMD requirements .....	25
D.1.1 General .....	25
D.1.2 DMD templates .....	25
D.1.3 DMD interval masks .....	26
D.2 A1-OM3 fibre EMB <sub>c</sub> requirements .....	27
D.2.1 General .....	27
D.2.2 Calculated effective bandwidth .....	27
D.3 A1-OM4 DMD requirements .....	29
D.3.1 General .....	29

D.3.2	DMD templates .....	29
D.3.3	DMD interval masks .....	30
D.4	A1-OM4 fibre EMB <sub>C</sub> requirements .....	30
D.4.1	General .....	30
D.4.2	Calculated effective bandwidth .....	30
D.5	A1-OM5 fibre modal bandwidth requirements .....	30
D.5.1	General .....	30
D.5.2	Calculated effective modal bandwidth .....	31
D.6	A1-OM2, A1-OM3, A1-OM4 and A1-OM5 calculated overfilled modal bandwidth .....	31
Annex E (informative)	System, modal bandwidth, and transmitter considerations .....	33
E.1	Background .....	33
E.2	System considerations .....	33
E.2.1	A1-OM3 and A1-OM4 fibres .....	33
E.2.2	A1-OM5 fibre .....	33
E.3	Effective modal bandwidth (EMB) .....	34
E.4	Transmitter encircled flux (EF) and centre wavelength requirements .....	37
E.4.1	Encircled flux .....	37
E.4.2	Centre wavelength for A1-OM3 and A1-OM4 fibres .....	38
E.4.3	Centre wavelength for A1-OM5 fibre .....	38
Annex F (informative)	Bandwidth nomenclature explanation .....	40
Annex G (informative)	Preliminary indications for items needing further study .....	41
G.1	Effective modal bandwidth (EMB) at 1 300 nm .....	41
G.2	Scaling of EMB with DMD .....	41
Annex H (informative)	Applications and cabling categories supported by A1 fibres .....	43
Annex I (informative)	1-Gigabit, 10-Gigabit, 25-Gigabit, 40-Gigabit and 100-Gigabit Ethernet applications .....	44
Bibliography	.....	50
Figure 1	– Relation between bandwidths at 850 nm and 1 300 nm .....	14
Figure D.1	– DMD template requirements .....	26
Figure E.1	– Estimated minimum wide band EMB versus wavelength for A1-OM3 .....	35
Figure E.2	– Estimated minimum wide band EMB versus wavelength for A1-OM4 .....	36
Figure E.3	– Estimated minimum wide band EMB versus wavelength for A1-OM5 .....	37
Figure E.4	– Approximate position of DMD weightings relative to the EF boundaries of Equations (E.10) and (E.11) .....	38
Table 1	– Cross reference IEC A1 multimode fibre designations to IEC 60793-2-10:2017 .....	8
Table 2	– Dimensional attributes and measurement methods .....	11
Table 3	– Dimensional requirements common to category A1 fibres .....	11
Table 4	– Additional dimensional attributes required in sub-category specifications .....	11
Table 5	– Mechanical attributes and measurement methods .....	12
Table 6	– Mechanical requirements common to category A1 fibres .....	12
Table 7	– Transmission attributes and measurement methods .....	13
Table 8	– Additional transmission attributes required in sub-category specifications .....	13
Table 9	– Environmental exposure tests .....	15

Table 10 – Attributes measured for environmental tests .....	15
Table 11 – Strip force for environmental tests .....	15
Table 12 – Tensile strength for environmental tests .....	16
Table 13 – Stress corrosion susceptibility for environmental tests .....	16
Table 14 – Change in attenuation for environmental tests .....	16
Table A.1 – Dimensional requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres .....	18
Table A.2 – Mechanical requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres .....	18
Table A.3 – Transmission requirements specific to A1-OM2, A1-OM3, A1-OM4 and A1-OM5 fibres .....	19
Table B.1 – Dimensional requirements specific to A1-OM1 fibres .....	21
Table B.2 – Mechanical requirements specific to A1-OM1 fibres .....	21
Table B.3 – Transmission requirements specific to A1-OM1 fibres .....	22
Table C.1 – Dimensional requirements specific to A1d fibres .....	23
Table C.2 – Mechanical requirements specific to A1d fibres .....	23
Table C.3 – Transmission requirements specific to A1d fibres .....	24
Table D.1 – DMD templates for A1-OM3 fibres .....	25
Table D.2 – DMD interval masks for A1-OM3 fibres .....	27
Table D.3 – DMD weightings .....	28
Table D.4 – DMD templates for A1-OM4 fibres .....	30
Table D.5 – DMD interval masks for A1-OM4 fibres .....	30
Table D.6 – DMD weighting for OMB <sub>c</sub> .....	32
Table F.1 – Bandwidth nomenclature explanation .....	40
Table H.1 – Some standardised applications supported by A1-OM2, A1-OM3, A1-OM4, A1-OM5 fibres and in some cases A1-OM1 fibres .....	43
Table I.1 – Summary of 1 Gb/s, 10 Gb/s, 25 Gb/s, 40 Gb/s and 100 Gb/s Ethernet requirements and capabilities .....	45

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

## OPTICAL FIBRES –

**Part 2-10: Product specifications –  
Sectional specification for category A1 multimode fibres**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60793-2-10 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This seventh edition cancels and replaces the sixth edition published in 2017. This edition constitutes a technical revision.

This edition includes the following significant change with respect to the previous edition: revision of the naming convention for A1 multimode fibres, which better matches with those found in ISO/IEC standards. These changes are outlined in the scope of this document along with a cross reference table for the new names.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
86A/1932/FDIS	86A/1939/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60793 series, published under the general title *Optical fibres*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

## iTeh STANDARD PREVIEW

(standards.iteh.ai)

**IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.**

<https://standards.iteh.ai/catalog/standards/sist/b85d8886-7454-46ed-b3e5-a2cc5ef12952/iec-60793-2-10-2019>



## OPTICAL FIBRES –

### Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres

#### 1 Scope

This part of IEC 60793 is applicable to optical fibre sub-categories A1-OM1, A1-OM2, A1-OM3, A1-OM4, A1-OM5, and A1d. These fibres are used or can be incorporated in information transmission equipment and optical fibre cables.

Sub-categories A1-OM2, A1-OM3, A1-OM4 and A1-OM5 apply to 50/125  $\mu\text{m}$  graded index fibre in four bandwidth grades. Each of these bandwidth grades is defined for two levels of macrobend loss performance that are distinguished by "a" or "b" suffix. Those sub-categories with suffix "a" are specified to meet traditional macrobend loss performance levels. Those sub-categories with suffix "b" are specified to meet enhanced macrobend loss (i.e. lower loss) performance levels.

Sub-category A1-OM5 is specified to support single wavelength or multi-wavelength transmission systems in the vicinity of 850 nm to 950 nm. Although not normatively specified, bandwidth information covering this wavelength range is also included for A1-OM3 and A1-OM4.

(standards.iteh.ai)

Sub-category A1-OM1 applies to 62,5/125  $\mu\text{m}$  graded index fibre and sub-category A1d applies to 100/140  $\mu\text{m}$  graded index fibre.

[IEC 60793-2-10:2019](https://standards.iteh.ai/catalog/standards/sist/b85d8886-7454-46ed-b3e5-a2cc5ef72952/iec-60793-2-10-2019)

[https://standards.iteh.ai/catalog/standards/sist/b85d8886-7454-46ed-b3e5-](https://standards.iteh.ai/catalog/standards/sist/b85d8886-7454-46ed-b3e5-a2cc5ef72952/iec-60793-2-10-2019)

Other applications include, but are not restricted to, the following: short reach, high bit-rate systems in telephony, distribution and local networks carrying data, voice and/or video services; on-premises intra-building and inter-building fibre installations including data centres, local area networks (LANs), storage area networks (SANs), private branch exchanges (PBXs), video, various multiplexing uses, outside telephone cable plant use, and miscellaneous related uses.

Three types of requirements apply to these fibres:

- general requirements, as defined in IEC 60793-2;
- specific requirements common to the category A1 multimode fibres covered in this document and which are given in Clause 5;
- particular requirements applicable to individual fibre sub-categories and models, or specific applications, which are defined in the normative specification Annexes A to D.

Table 1 shows the cross reference between the IEC A1 multimode optical fibre designations used in this document compared to those used in IEC 60793-2-10:2017. The table also refers to the normative annexes A, B and C for the A1 sub-category multimode fibres in this document that contains the detailed specification.

**Table 1 – Cross reference IEC A1 multimode fibre designations to IEC 60793-2-10:2017**

Annex	Sub-category	Sub-category/Model	Core diameter (nominal)	ISO/IEC 11801-1:2017
	This document designations	IEC 60793-2-10:2017 designations		Usage of cabled OMx fibres
A	A1-OM2	A1a.1	50 µm <sup>a</sup>	OM2 <sup>b</sup>
	A1-OM3	A1a.2	50 µm	OM3
	A1-OM4	A1a.3	50 µm	OM4
	A1-OM5	A1a.4	50 µm	OM5
B	A1-OM1	A1b	62,5 µm <sup>c</sup>	OM1 <sup>d</sup>
C	A1d	A1d	100 µm	-
<sup>a</sup> Historically, ISO/IEC 11801:2002 also defined OM2 cables made with 62,5/125 µm fibres having a minimum overfilled launch bandwidth of 500 MHz·km at 850 nm and 500 MHz·km at 1 300 nm. This specific bandwidth combination of 62,5/125 µm fibre is not part of this document. <sup>b</sup> OM2 cables are not supported for new installations within ISO/IEC 11801-1:2017. <sup>c</sup> Historically, ISO/IEC 11801:2002 also defined OM1 cables made with 50/125 µm fibres having a minimum overfilled launch bandwidth of 200 MHz·km at 850 nm and 500 MHz·km at 1 300 nm. This specific bandwidth combination of 50/125 µm fibre is not part of this document. <sup>d</sup> OM1 cables are not supported for new installations within ISO/IEC 11801-1:2017.				

<https://standards.iteh.ai/catalog/standards/sist/b85d8886-7454-46ed-b3e5-a2cc5ef12952/iec-60793-2-10-2019>

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60793-1-20, *Optical fibres – Part 1-20: Measurement methods and test procedures – Fibre geometry*

IEC 60793-1-21, *Optical fibres – Part 1-21: Measurement methods and test procedures – Coating geometry*

IEC 60793-1-22, *Optical fibres – Part 1-22: Measurement methods and test procedures – Length measurement*

IEC 60793-1-30, *Optical fibres – Part 1-30: Measurement methods and test procedures – Fibre proof test*

IEC 60793-1-31, *Optical fibres – Part 1-31: Measurement methods and test procedures – Tensile strength*

IEC 60793-1-32, *Optical fibres – Part 1-32: Measurement methods and test procedures – Coating strippability*

IEC 60793-1-33, *Optical fibres – Part 1-33: Measurement methods and test procedures – Stress corrosion susceptibility*

IEC 60793-1-40, *Optical fibres – Part 1-40: Measurement methods and test procedures – Attenuation*

IEC 60793-1-41, *Optical fibres – Part 1-41: Measurement methods and test procedures – Bandwidth*

IEC 60793-1-42, *Optical fibres – Part 1-42: Measurement methods and test procedures – Chromatic dispersion*

IEC 60793-1-43, *Optical fibres – Part 1-43: Measurement methods and test procedures – Numerical aperture measurement*

IEC 60793-1-46, *Optical fibres – Part 1-46: Measurement methods and test procedures – Monitoring of changes in optical transmittance*

IEC 60793-1-47, *Optical fibres – Part 1-47: Measurement methods and test procedures – Macrobending loss*

IEC 60793-1-49, *Optical fibres – Part 1-49: Measurement methods and test procedures – Differential mode delay*

IEC 60793-1-50, *Optical fibres – Part 1-50: Measurement methods and test procedures – Damp heat (steady state) tests*

IEC 60793-1-51, *Optical fibres – Part 1-51: Measurement methods and test procedures – Dry heat (steady state) tests*

IEC 60793-1-52, *Optical fibres – Part 1-52: Measurement methods and test procedures – Change of temperature tests*

IEC 60793-1-53, *Optical fibres – Part 1-53: Measurement methods and test procedures – Water immersion tests*

IEC 60793-2, *Optical fibres – Part 2: Product specifications – General*

IEC 61280-4-1:2009, *Fibre-optic communication subsystem test procedures – Part 4-1: Installed cable plant – Multimode attenuation measurement*

### 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

## 4 Abbreviated terms

CPR	coupled power ratio
DMD	differential mode delay
EF	encircled flux
EMB	effective modal bandwidth
EMB <sub>c</sub>	calculated effective modal bandwidth
LAN	local area network
MMF	multimode fibre
NA	numerical aperture
OFL	overfilled launch
OMB <sub>c</sub>	overfilled launch modal bandwidth calculated from differential mode delay (also known as OFL <sub>c</sub> )
PBX	private branch exchange
PMD	physical medium dependent
ROFL	radial overfilled launch
SAN	storage area network

## 5 Specifications

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)

### 5.1 General

The fibre consists of a glass core with a graded index profile and a glass cladding in accordance with IEC 60793-2.

<https://standards.iteh.ai/catalog/standards/sist/b85d8886-7454-46ed-b3e5-a2cc5ef12952/iec-60793-2-10-2019>

The term "glass" usually refers to material consisting of non-metallic oxides.

### 5.2 Dimensional requirements

Dimensional attributes and measurement methods are given in Table 2.

Requirements common to all fibres in category A1 are indicated in Table 3.

Table 4 lists additional attributes that shall be specified by each sub-category specification.

**Table 2 – Dimensional attributes and measurement methods**

Attributes	Measurement methods
Cladding diameter	IEC 60793-1-20
Core diameter <sup>a, b</sup>	IEC 60793-1-20
Cladding non-circularity	IEC 60793-1-20
Core non-circularity	IEC 60793-1-20
Core-cladding concentricity error	IEC 60793-1-20
Primary coating diameter	IEC 60793-1-21
Primary coating non-circularity	IEC 60793-1-21
Primary coating-cladding concentricity error	IEC 60793-1-21
Fibre length	IEC 60793-1-22
<sup>a</sup> Core diameter is specified at $850 \text{ nm} \pm 10 \text{ nm}$ with a test specimen length of $2,0 \text{ m} \pm 0,2 \text{ m}$ and a threshold value, $k_{\text{CORE}}$ , of 0,025 for A1 fibres except A1-OM2b, A1-OM3b, A1-OM4b, A1-OM5b fibres.	
<sup>b</sup> Core diameter is specified at $850 \text{ nm} \pm 10 \text{ nm}$ with a test specimen length of $100 \text{ m} \pm 5 \%$ and a threshold value, $k_{\text{CORE}}$ , of 0,025 for A1-OM2b, A1-OM3b, A1-OM4b, A1-OM5b fibres.	

**Table 3 – Dimensional requirements common to category A1 fibres**

Attributes	Unit	Limits
Core non-circularity	%	$\leq 6$
Primary coating diameter – uncoloured <sup>a</sup>	$\mu\text{m}$	$245 \pm 10$
Primary coating diameter – coloured <sup>a</sup>	$\mu\text{m}$	$250 \pm 15$
Primary coating-cladding concentricity error	$\mu\text{m}$	$\leq 12,5$
Fibre length	km	<sup>b</sup>
<sup>a</sup> The limits on primary coating diameter are most commonly used in telecommunications cables. There are other applications, which use other primary coating diameters, several of which are listed below. Alternative nominal primary coating diameters and tolerance ( $\mu\text{m}$ ): $400 \pm 40$ $500 \pm 50$ $700 \pm 100$ $900 \pm 100$		
<sup>b</sup> Length requirements vary and should be agreed between supplier and customer.		

**Table 4 – Additional dimensional attributes required in sub-category specifications**

Attributes
Cladding diameter
Cladding non-circularity
Core diameter
Core-cladding concentricity error

### 5.3 Mechanical requirements

Mechanical attributes and measurement methods are given in Table 5.

Requirements common to all fibres in category A1 are in Table 6.

**Table 5 – Mechanical attributes and measurement methods**

Attributes	Test methods
Proof test	IEC 60793-1-30
Tensile strength	IEC 60793-1-31
Primary coating strippability	IEC 60793-1-32
Stress corrosion susceptibility	IEC 60793-1-33

**Table 6 – Mechanical requirements common to category A1 fibres**

Attributes	Unit	Limits
Proof stress level	GPa	$\geq 0,69^a$
Average strip force <sup>b</sup>	N	$1,0 \leq F_{\text{avg}} \leq 5,0$
Peak strip force <sup>b</sup>	N	$1,0 \leq F_{\text{peak}} \leq 8,9$
Tensile strength (median) for 0,5 m specimen length	GPa	$\geq 3,8$
Stress corrosion susceptibility constant, $n_d$		$\geq 18$

<sup>a</sup> The proof test value of 0,69 GPa equals about 1 % strain or about 8,8 N force, for A1-OM1 to A1-OM5 fibres. For the relation between these different units, see IEC TR 62048:2014, 8.4.

<sup>b</sup> Either average strip force or peak strip force, which are defined in the test procedure, may be specified by agreement between supplier and customer.

### 5.4 Transmission requirements

Transmission attributes and measurement methods are given in Table 7.

Table 8 lists additional attributes that shall be specified by each sub-category specification.

**Table 7 – Transmission attributes and measurement methods**

Attributes	Measurement methods
Attenuation coefficient	IEC 60793-1-40
Modal bandwidth <sup>a,b</sup>	IEC 60793-1-41
Numerical aperture <sup>c,d</sup>	IEC 60793-1-43
Chromatic dispersion	IEC 60793-1-42
Change of optical transmission	IEC 60793-1-46
Macrobending loss	IEC 60793-1-47
Differential mode delay <sup>e</sup>	IEC 60793-1-49
<p><sup>a</sup> For modal bandwidth, either overfilled launch (OFL) or overfilled launch modal bandwidth calculated from differential mode delay (OMB<sub>c</sub>) can be used. OMB<sub>c</sub> is the reference test method for A1-OM2, A1-OM3 and A1-OM4 fibres at 850 nm and is the required method for A1-OM5 fibres at 850 nm and 953 nm.</p> <p><sup>b</sup> 850 nm modal bandwidth is specified with a test specimen length of 1 000 m ± 5 % for A1-OM3 to A1-OM5 fibres. For A1-OM3 fibres, the 850 nm modal bandwidth is measured at 850 nm ± 10 nm. For A1-OM4 and A1-OM5 fibres, the 850 nm modal bandwidth is measured at 850 nm ± 2 nm. For A1-OM5 fibre, the modal bandwidth is also measured at 953 nm ± 6 nm.</p> <p><sup>c</sup> Numerical aperture is specified at 850 nm ± 10 nm with a test specimen length of 2 m ± 0,2 m and a threshold value, <math>k_{NA}</math>, of 0,05 for A1 fibres except A1-OM2b, A1-OM3b, A1-OM4b, A1-OM5b fibres.</p> <p><sup>d</sup> Numerical aperture is specified at 850 nm ± 10 nm with a test specimen length of 100 m ± 5 % and a threshold value, <math>k_{NA}</math>, of 0,05 for A1-OM2b, A1-OM3b, A1-OM4b and A1-OM5b fibres.</p> <p><sup>e</sup> Differential mode delay is specified with a test specimen length of 1 000 m ± 5 % for A1-OM3, A1-OM4 and A1-OM5 fibres. For A1-OM3 fibres, the DMD is measured at 850 nm ± 10 nm. For A1-OM4 and A1-OM5 fibres, the DMD is measured at 850 nm ± 2 nm. For A1-OM5 fibre, the DMD is also measured at 953 nm ± 6 nm.</p>	

(standards.iteh.ai)

Specification compliance of chromatic dispersion can be assured by compliance to the numerical aperture (NA) specification for A1 fibre.

**Table 8 – Additional transmission attributes  
required in sub-category specifications**

Attributes
Attenuation coefficient
Modal bandwidth
Chromatic dispersion
Numerical aperture
Macrobending loss

For attenuation coefficient and modal bandwidth, the sub-category specifications may contain ranges of specifiable values instead of fixed limits. In this case, the actual values of the maximum attenuation coefficient and minimum modal bandwidth, at both 850 nm and 1 300 nm (or just at one of these wavelengths) shall be agreed between supplier and customer. For commercial purposes, the modal bandwidth is linearly normalized to 1 km.

For guidance purposes, Annex H shows a number of standardised applications supported by A1 fibres and Annex I shows transmission capabilities for these fibres.

The indicated maximum attenuation coefficients apply to uncabled optical fibres; for the maximum cabled attenuation coefficients, reference is made to IEC 60794-1-1, which can be used in conjunction with this document. Tighter specifications for the fibre may be requested to account for added attenuation in the cabling process.

Remarks on the specification of modal bandwidth: