



Designation: ~~D2647~~—~~10~~ **D2647** – 18

Standard Specification for Crosslinkable Ethylene Plastics¹

This standard is issued under the fixed designation D2647; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This specification covers a general classification system for crosslinkable ethylene plastics compounds (**Note 1**). The requirements specified herein are not necessarily applicable for use as criteria in determining suitability for the end use of a fabricated product.

NOTE 1—It is to be noted that this specification describes materials that are available commercially in their uncrosslinked form. Therefore, they are crosslinkable compounds despite the fact that measurement of the parameters used for their classification and specification will usually be carried out after curing has been effected.

1.2 Two types of compounds are covered, namely, mechanical types in which mechanical strength properties are of prime importance in applications, and electrical types in which electrical insulating or conducting properties also are of prime importance in applications.

1.3 The parameters used to classify and specify the mechanical types are ultimate elongation, elongation retention after aging, apparent modulus of rigidity, and brittleness temperature.

1.4 The parameters used to classify and specify the electrical types are ultimate elongation, elongation retention after aging, apparent modulus of rigidity, brittleness temperature, dielectric constant, dissipation factor, and volume resistivity.

1.5 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.6 The following safety hazards caveat pertains only to the test methods portion, Section 7, of this specification: *This specification standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this specification standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

NOTE 2—There is no known ISO equivalent to this standard.

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D150 Test Methods for AC Loss Characteristics and Permittivity \(Dielectric Constant\) of Solid Electrical Insulation](#)

[D257 Test Methods for DC Resistance or Conductance of Insulating Materials](#)

[D573 Test Method for Rubber—Deterioration in an Air Oven](#)

[D618 Practice for Conditioning Plastics for Testing](#)

[D638 Test Method for Tensile Properties of Plastics](#)

[D746 Test Method for Brittleness Temperature of Plastics and Elastomers by Impact](#)

[D883 Terminology Relating to Plastics](#)

[D991 Test Method for Rubber Property—Volume Resistivity Of Electrically Conductive and Antistatic Products](#)

[D1043 Test Method for Stiffness Properties of Plastics as a Function of Temperature by Means of a Torsion Test](#)

[D2765 Test Methods for Determination of Gel Content and Swell Ratio of Crosslinked Ethylene Plastics](#)

[D3892 Practice for Packaging/Packing of Plastics](#)

¹ This specification is under the jurisdiction of ASTM Committee [D20](#) on Plastics and is the direct responsibility of Subcommittee [D20.15](#) on Thermoplastic Materials. Current edition approved April 1, 2010/Nov. 1, 2018. Published May 2010/November 2018. Originally approved in 1967. Last previous edition approved in 2005/2010 as [D2647 – 05](#)/[D2647 - 10](#). A. DOI: [10.1520/D2647-10](#)/[10.1520/D2647-18](#).

² For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

IEEE/ASTM SI-10 Standard for Use of the International System of Units (SI): (The Modernized Metric System)

2.2 Military Standard:

MIL-STD-105 Sampling Procedures and Tables for Inspection by Attributes³(Obsolete 1995)

3. Terminology

3.1 *Definitions:—Definitions—*For definitions of plastics terms used in this specification, see Terminology **D883**.

3.2 *Abbreviations:—Abbreviations—*Units, Symbols, and Abbreviations—For units, symbols, and abbreviations used in this specification see **IEEE/ASTM SI-10**.

4. Classification

4.1 *Classification System—***Table 1** and **Table 2** provide a classification system for these compounds so that the relations among them can be delineated and those that are commercially available can be readily specified. It is not the intent to indicate that all the combinations of properties possible are represented by commercial products or that they are technically possible at the present state of knowledge.

4.2 *Types—*This specification covers two general types of compounds: *Type I—*Mechanical types (**Table 1**), and *Type II—*Electrical types (**Table 2**).

4.3 *Grades—*A grade is designated by first indicating the type (I or II) followed by cell numbers for each property in the order in which they are listed in the tables. Where there is no interest in a property, a “0” is entered in place of a cell number.

5. General Requirements

5.1 The compound shall be in powder, pellet or granular form, as agreed upon between the seller and the purchaser.

5.2 The compound, after crosslinking, shall conform to the requirements given in **Table 1** or **Table 2**, whichever is applicable, for the type and grade specified when tested in accordance with the procedures given in Sections 6, 7, and 8.

6. Sampling

6.1 Sampling shall be statistically adequate to satisfy the requirements of 9.4.

6.2 A batch or lot shall be constituted as a unit of manufacture as prepared for shipment and can consist of sometimes is a blend of two or more “production runs.”

7. Specimen Preparation

7.1 Unless otherwise agreed upon between the seller and the purchaser, the test specimens shall be formed and cured in accordance with the compound manufacturer’s recommendations.

8. Test Methods

8.1 *Conditioning—*Condition the test specimen at $23 \pm 2^\circ\text{C}$ ($73.4 \pm 3.6^\circ\text{F}$) and $50 \pm 10\%$ relative humidity for not less than 40 h prior to test in accordance with Procedure A of Practice **D618**, for those tests where conditioning is required and in all cases of disagreement.

8.2 *Test Conditions—*Conduct tests in the standard laboratory atmosphere of $23 \pm 2^\circ\text{C}$ ($73.4 \pm 3.6^\circ\text{F}$) and $50 \pm 10\%$ relative humidity, unless otherwise specified in the test methods or in this specification.

TABLE 1 Type I, Mechanical Compound Requirements

Designation Order No.	Property	Cell Limits					
		0	1	2	3	4	5
1	Ultimate elongation, %	unspecified	<25	≥25	≥150	≥250	≥450
2	Minimum of 75 % retention of elongation after aging at the specified temperature for 168 h, °C (°F)	unspecified	121 (250)	150 (302)			
3	Apparent modulus of rigidity, MPa (psi)	unspecified	<70 (10 000)	≥70 (10 000)	≥275 (40 000)		
4	Brittleness temperature, °C (°F)	unspecified	<-75 (-103)	≤-54 (-65)	≤-40 (-40)	≤-29 (-20)	
5	Percent extract (measure of degree of cross-linking)	unspecified	<10	≥10	≥20	≥30	

³ Available from Defense Automation and Production Service, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.