This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.



Designation: D3275 - 08 (Reapproved 2013) D3275 - 18

Standard Classification System for E-CTFE-Fluoroplastic Molding, Extrusion, and Coating Materials¹

This standard is issued under the fixed designation D3275; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope Scope*

1.1 This classification system covers melt processible molding, extrusion, and coating materials of ethylenechlorotrifluoroethylene (E-CTFE) fluoroplastics. The resin is a copolymer of ethylene and chlorotrifluoroethylene containing approximately 80 weight % of chlorotrifluoroethylene.

1.2 The values stated in SI units, as detailed in IEEE/ASTM SI-10, are to be regarded as standard.

1.3 The following precautionary statement pertains only to the test methods portion, Section 11 of this classification system. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety safety, health, and healthenvironmental practices and determine the applicability of regulatory limitations prior to use.

NOTE 1—Although this classification system and ISO 12086-11SO 20568-1 and ISO 12086-21SO 20568-2 differ in approach or detail, data obtained using either are technically equivalent.

<u>1.4 This international standard was developed in accordance with internationally recognized principles on standardization</u> established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

D150 Test Methods for AC Loss Characteristics and Permittivity (Dielectric Constant) of Solid Electrical Insulation

D618 Practice for Conditioning Plastics for Testing ASTM D3275-18

D638 Test Method for Tensile Properties of Plastics

D792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement 0.43275-18 D883 Terminology Relating to Plastics

D1238 Test Method for Melt Flow Rates of Thermoplastics by Extrusion Plastometer

D1600 Terminology for Abbreviated Terms Relating to Plastics

D1708 Test Method for Tensile Properties of Plastics by Use of Microtensile Specimens

D2863 Test Method for Measuring the Minimum Oxygen Concentration to Support Candle-Like Combustion of Plastics (Oxygen Index)

D3892 Practice for Packaging/Packing of Plastics

D4591 Test Method for Determining Temperatures and Heats of Transitions of Fluoropolymers by Differential Scanning Calorimetry

IEEE/ASTM SI-10 Use of the International System of Units (SI): The Modern Metric System

2.2 ISO Standards:³

ISO 12086-HISO 20568-1 Plastics—Fluoropolymer Dispersion and Moulding and Extrusion Materials—Part 1: Designation and Basis for Specification

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959. United States

¹ This classification system is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials

Current edition approved May 1, 2013 Nov. 1, 2018. Published May 2013 November 2018. Originally approved in 1973. Last previous edition approved in 2008 2013 as $\frac{10275 - 08:D3275 - 08:$

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

ISO 12086-2ISO 20568-2 Plastics—Fluoropolymer Dispersion and Moulding and Extrusion Materials—Part 2: Preparation of Test Specimens and Determination of Properties

3. Terminology

3.1 *Definitions:*

3.1.1 Definitions of terms used in this classification system shall be in accordance with Terminology D883.

3.1.2 lot, n-one production run or a uniform blend of two or more production runs.

3.2 *Abbreviations:*

3.2.1 Abbreviations are in accordance with Terminology D1600.

4. Classification

4.1 ECTFE materials are classified into groups in accordance with their physical appearance. The groups are further divided into classes based on melt flow rate. These classes are subdivided into grades as shown in the Table E-CTFE. An example of a material of this classification system is given as follows: ECTFE 01 1 1

TABLE E-CTFE											
Group	Class	Description	Grade	Melt Flow Rate, ^{A,B} g/10 min	Specific Gravity, ^C 23/23°C	Tensile Strength, ^{D,E} min, MPa	Elongation, ^{<i>E</i>,} min, %	Melting Point, °C, ^G min	Oxygen Index, ^H min, %	Dielectric Constant, ⁷ max, 10 ⁶ Hz	Dissipation Factor, ^J max, 10 ⁶ Hz
01 powder	1	Low melt flow rate	1	0.05-1.50	1.65–1.71	40	200	240	52	2.6	0.015
	2	Medium melt flow rate	1	1.51–6.0	1.65–1.71	40	200	240	52	2.6	0.015
	3	High melt flow rate	1	6.1–25	1.65–1.71	40	200	240	52	2.6	0.015
	0	Other	0								
02 pellet	1	Low melt flow rate	1	0.05-1.50	1.65–1.71	40 2	200	240	52	2.6	0.015
	2	Medium melt flow rate	1	1.51–6.0	1.65–1.71	40	200	240	52	2.6	0.015
	3	High melt flow rate		6.1–25	1.65–1.71	40	200	240	52	2.6	0.015
	4	Ultra Low melt flow rate	1	0.8–1.3	1.65–1.71	40	ev ²⁰⁰ ev	220	52	2.6	0.015
	0	Other	0								
00	0	Other	0								

^A See 11.2 for test method for above parameters. /standards/sist/459a7cdf-c807-4dfd-9555-97682758c600/astm-d3275-18 ^BSee 11.2 for test method for group 2 class 4 grade 1 replace 2.16 kg mass with 5 kg mass.

^C See 11.4 for test method for above parameters.

^D See 11.5 for test method for above parameters.

^E At 23 ± 2°C (73.4 ± 3.6°F).

^FSee 11.5 for test method for above parameters.

^G See 11.3 for test method for above parameters.

^{*H*} See 11.7 for test method for above parameters.

¹ See <u>11.6</u> for test method for above parameters.

^J See 11.6 for test method for above parameters.

where:

- 01 = ECTFE powder
- 1 = low melt flow

2 = properties in accordance with Table E-CTFE (Grade 1)

4.1.1 To facilitate incorporation of future material, the other category for Group (00), Class (0) and Grade (0) are shown in Table E-CTFE.

5. Ordering Information

5.1 The purchase order or inquiry for these materials shall state the classification callout. For example, D3275 ECTFE 01 1 2.

6. General Requirements

6.1 The material covered by this classification system shall conform to the requirements prescribed in Table E-CTFE when tested by the procedures specified herein.

7. Detail Requirements

7.1 Test specimens prepared in accordance with Section 10 shall conform to the requirements prescribed for the particular class.