



## Designation: **B717–96 (Reapproved 2012) B717 – 96 (Reapproved 2018)**

# Standard Specification for Refined Ruthenium<sup>1</sup>

This standard is issued under the fixed designation B717; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers refined ruthenium as sponge and powder in one grade as follows:

1.1.1 *Grade 99.80*—Ruthenium having a purity of 99.80 %.

1.1.2 *Grade 99.90*—Ruthenium having a purity of 99.90 %.

NOTE 1—For the purposes of determining conformance with this specification, an observed value obtained from analysis shall be rounded to the nearest unit in the last right-hand place of figures used in expressing the limiting value in accordance with the rounding method of Practice E29.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS)(SDS) for this product/material as provided by the manufacturer, to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

## 3. Manufacture

3.1 The material may be produced by any refining process that yields a product capable of meeting the chemical requirements of this specification. The purchaser, upon request, shall be informed of the refining process used.

## 4. Chemical Composition

4.1 The material should conform to the requirements for chemical composition as prescribed in Table 1.

4.2 Analysis shall be made using the manufacturer's standard methods. In the event of disagreement as to the chemical composition of the metal, methods of chemical analysis for reference purposes shall be determined by a mutually acceptable laboratory.

## 5. Sampling

5.1 The value of this material is such that special attention must be paid to the sampling procedures. The purchaser and manufacturer shall agree upon the sampling procedures used.

5.2 *Lot Size*—Sampling lots shall consist of the following:

5.2.1 *Sponge*—A single refining lot.

5.2.2 *Powder*—A single refining lot.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.05 on Precious Metals and Electrical Contact Materials.

Current edition approved May 1, 2012; Nov. 1, 2018. Published May 2012; November 2018. Originally approved in 1983. Last previous edition approved in 2006 as B717 – 96 (2006); (2012). DOI: 10.1520/B0717-96R12; 10.1520/B0717-96R18.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.