

TECHNICAL SPECIFICATION

Piezoelectric, dielectric and electrostatic devices and associated materials for frequency control, selection and detection – Glossary –
Part 4-1: Piezoelectric materials – Synthetic quartz crystal

[IEC TS 61994-4-1:2018](https://standards.iteh.ai/catalog/standards/sist/407d9a04-80e8-4255-b49b-99d4e7fe78cc/iec-ts-61994-4-1-2018)

<https://standards.iteh.ai/catalog/standards/sist/407d9a04-80e8-4255-b49b-99d4e7fe78cc/iec-ts-61994-4-1-2018>



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2018 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing 21 000 terms and definitions in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC STANDARD PREVIEW
(standards@iec.ch)
IEC TS 61994-4:2018
IEC TS 61994-4:2018
99d4e7fe78cc/iec-ts-61994-4-1-2018

TECHNICAL SPECIFICATION

Piezoelectric, dielectric and electrostatic devices and associated materials for frequency control, selection and detection – Glossary – Part 4-1: Piezoelectric materials – Synthetic quartz crystal

[IEC TS 61994-4-1:2018](https://standards.iteh.ai/catalog/standards/sist/407d9a04-80e8-4255-b49b-99d4e7fe78cc/iec-ts-61994-4-1-2018)

<https://standards.iteh.ai/catalog/standards/sist/407d9a04-80e8-4255-b49b-99d4e7fe78cc/iec-ts-61994-4-1-2018>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 01.040.31; 31.140

ISBN 978-2-8322-6186-6

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	3
1 Scope.....	5
2 Normative references	5
3 Terms and definitions	5
Bibliography.....	11

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[IEC TS 61994-4-1:2018](https://standards.iteh.ai/catalog/standards/sist/407d9a04-80e8-4255-b49b-99d4e7fe78cc/iec-ts-61994-4-1-2018)

<https://standards.iteh.ai/catalog/standards/sist/407d9a04-80e8-4255-b49b-99d4e7fe78cc/iec-ts-61994-4-1-2018>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**PIEZOELECTRIC, DIELECTRIC AND ELECTROSTATIC DEVICES
AND ASSOCIATED MATERIALS FOR FREQUENCY CONTROL,
SELECTION AND DETECTION – GLOSSARY –****Part 4-1: Piezoelectric materials – Synthetic quartz crystal**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. In exceptional circumstances, a technical committee may propose the publication of a technical specification when

- the required support cannot be obtained for the publication of an International Standard, despite repeated efforts, or
- the subject is still under technical development or where, for any other reason, there is the future but no immediate possibility of an agreement on an International Standard.

Technical specifications are subject to review within three years of publication to decide whether they can be transformed into International Standards.

IEC TS 61944-4-1, which is a technical specification, has been prepared by IEC technical committee 49: Piezoelectric, dielectric and electrostatic devices and associated materials for frequency control, selection and detection.

This third edition of IEC 61994-4-1 cancels and replaces the second edition published in 2007. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) The new terms and definitions given in IEC 60758:2016 have been taken into account;
- b) The general title has been changed according to the change in the title of TC 49 in 2009.

The text of this technical specification is based on the following documents:

Enquiry draft	Report on voting
49/1282/DTS	49/1286/RVDTS

Full information on the voting for the approval of this technical specification can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 61994 series, published under the general title *Piezoelectric, dielectric and electrostatic devices and associated materials for frequency control, selection and detection – Glossary*, can be found on the IEC website.

Future standards in this series will carry the new general title as cited above. Titles of existing standards in this series will be updated at the time of the next edition.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- transformed into an International standard,
- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

PIEZOELECTRIC, DIELECTRIC AND ELECTROSTATIC DEVICES AND ASSOCIATED MATERIALS FOR FREQUENCY CONTROL, SELECTION AND DETECTION – GLOSSARY –

Part 4-1: Piezoelectric materials – Synthetic quartz crystal

1 Scope

This part of IEC 61994 gives the terms and definition for synthetic quartz crystals representing the state of the art, which are intended for manufacturing piezoelectric and optical elements.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

There are no normative references in this document.

3 Terms and definitions (standards.iteh.ai)

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1

AT-cut plate

rotated Y-cut crystal plate oriented at an angle of about $+35^\circ$ around the X-axis or about -3° from the z (minor rhombohedral)-face

[SOURCE: IEC 60758:2016, 3.11, modified – the reference to Figure 3 has been removed.]

3.2

as-grown Y-bar

crystals which are grown by using long stick seed in the Y-direction

[SOURCE: IEC 60758:2016, 3.4]

3.3

as-grown Z-bar

crystals which are grown by using Z-cut seed

[SOURCE: IEC 60758:2016, 3.5]

3.4

as-grown synthetic quartz crystal

state of synthetic quartz crystal prior to grinding or cutting

[SOURCE: IEC 60758:2016, 3.3]

3.5 autoclave

vessel for the high-pressure and high-temperature condition required for growth of a synthetic quartz crystal

[SOURCE: IEC 60758:2016, 3.26]

3.6 dimensions

dimensions pertaining to growth on Z-cut seed rotated less than 20° from the Y-axis

[SOURCE: IEC 60758:2016, 3.16]

3.7 dislocations

linear defects in the crystal due to misplaced planes of atoms

[SOURCE: IEC 60758:2016, 3.25]

3.8 dopant

additive used in the growth process which may change the crystal habit, chemical composition, physical or electrical properties of the synthetic quartz batch

[SOURCE: IEC 60758:2016, 3.22]

3.9 effective Z-dimension

minimum measure in the Z ($\theta = 0^\circ$) or Z' direction in usable Y or Y' area of an as-grown crystal and described by Z_{eff}

[SOURCE: IEC 60758:2016, 3.17 modified – The definition has been shortened and the reference to Figure 2 has been removed.]

3.10 etch channel

roughly cylindrical void that is present along the dislocation line after etching a quartz crystal

[SOURCE: IEC 60758:2016, 3.21]

3.11 growth band

contrasting density band that can be observed in the Y-cut crystal by Schlieren and similar optical method

[SOURCE: IEC 60758:2016, 3.35, modified – The four notes to entry have been removed.]

3.12 growth zones

regions of a synthetic quartz crystal resulting from growth along different crystallographic directions

[SOURCE: IEC 60758:2016, 3.8, modified – The reference to Figure 2 has been removed.]

3.13**hydrothermal crystal growth**

crystal growth in the presence of water of elevated temperature and pressure

[SOURCE: IEC 60758:2016, 3.1 modified – The definition has been shortened.]

3.14**impurity concentration**

concentration of impurities relative to silicon atoms

[SOURCE: IEC 60758:2016, 3.24]

3.15**inclusions**

any foreign material within a synthetic quartz crystal, visible by examination of scattered light from a bright source with the crystal immersed in a refractive index-matching liquid

[SOURCE: IEC 60758:2016, 3.19, modified – Note 1 to entry has been removed.]

3.16**infrared absorption coefficient α value**

coefficient (referred to as the α value) established by determining the relationship between absorption of two wave numbers

Note 1 to entry: One wave number is minimal absorption due to OH impurity, the other with high absorption due to the presence of OH impurities in the crystal lattice. The OH impurity creates mechanical loss in resonators and its presence is correlated to the presence of other loss-inducing impurities. The α value is a measure of OH concentration and is correlated with expected mechanical losses due to material impurities.

Note 2 to entry: For the coefficient defined here, the logarithm base 10 is used. The infrared absorption coefficient value α is determined using the following equation:

$$\alpha = \frac{1}{t} \log_{10} \left(\frac{T_1}{T_2} \right)$$

where

α is the infrared absorption coefficient;

t is the thickness of Y-cut sample, in cm;

T_1 is the per cent transmission at a wave number of 3 800 cm^{-1} or 3 979 cm^{-1} ;

T_2 is the per cent transmission at a wave number of 3 500 cm^{-1} , or 3 585 cm^{-1} .

[SOURCE: IEC 60758:2016, 3.29]

3.17**internal transmittance**

transmittance which does not include loss of surface refraction

[SOURCE: IEC 60758:2016, 3.33, modified – Note 1 to entry has been removed.]

3.18**lumbered synthetic quartz crystal**

synthetic quartz crystal whose X- and Z- or Z'- surfaces in the as-grown condition have been processed flat and parallel by sawing, grinding, lapping, etc., to meet specified dimensions and orientation

[SOURCE: IEC 60758:2016, 3.30]