



# Standard Specification for Nickel-Chromium-Aluminum Alloys (UNS N06699), Nickel- Chromium-Iron Alloys (UNS N06600, N06601, N06603, N06690, N06693, N06025, N06045, and N06696), Nickel- Chromium-Cobalt-Molybdenum Alloy (UNS N06617), Nickel- Iron-Chromium-Tungsten Alloy (UNS N06674), Plate, Sheet, and Strip<sup>1</sup>

This standard is issued under the fixed designation B168; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope\*

1.1 This specification<sup>2</sup> covers rolled nickel-chromium-aluminum alloys (UNS N06699), nickel-chromium-iron alloys (UNS N06600, N06601, N06603, N06690, N06693, N06025, N06045, and N06696),<sup>3</sup> nickel-chromium-cobalt-molybdenum alloy (UNS N06617), and nickel-iron-chromium-tungsten alloy (UNS N06674) plate, sheet, and strip.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 The following precautionary caveat pertains only to the test methods portion, Section 13, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Safety Data Sheet (SDS) for this product/material as provided by the manufacturer; to establish appropriate safety, health, and environmental practices, and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recom-*

*mendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>4</sup>

- B166 Specification for Nickel-Chromium-Iron Alloys (UNS N06600, N06601, N06603, N06690, N06693, N06025, N06045, and N06696), Nickel-Chromium-Cobalt-Molybdenum Alloy (UNS N06617), and Nickel-Iron-Chromium-Tungsten Alloy (UNS N06674) Rod, Bar, and Wire
- B880 Specification for General Requirements for Chemical Check Analysis Limits for Nickel, Nickel Alloys and Cobalt Alloys
- E8/E8M Test Methods for Tension Testing of Metallic Materials
- E10 Test Method for Brinell Hardness of Metallic Materials
- E18 Test Methods for Rockwell Hardness of Metallic Materials
- E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E38 Methods for Chemical Analysis of Nickel-Chromium and Nickel-Chromium-Iron Alloys (Withdrawn 1989)<sup>5</sup>
- E112 Test Methods for Determining Average Grain Size
- E140 Hardness Conversion Tables for Metals Relationship Among Brinell Hardness, Vickers Hardness, Rockwell Hardness, Superficial Hardness, Knoop Hardness, Scleroscope Hardness, and Leeb Hardness
- E527 Practice for Numbering Metals and Alloys in the

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Nov. 1, 2018. Published November 2018. Originally approved in 1941. Last previous edition approved in 2011 as B168 – 11 (2016). DOI: 10.1520/B0168-18.

<sup>2</sup> For ASME Boiler and Pressure Code applications, see related Specification SB-168 in Section II of that Code.

<sup>3</sup> New designation established in accordance with Practice E527 and SAE J1086, Practice for Numbering Metals and Alloys (UNS).

<sup>4</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>5</sup> The last approved version of this historical standard is referenced on www.astm.org.

\*A Summary of Changes section appears at the end of this standard

**Unified Numbering System (UNS)**
**E1473 Test Methods for Chemical Analysis of Nickel, Cobalt and High-Temperature Alloys**
**F155 Method of Test for Temper of Strip and Sheet Metals for Electronic Devices (Spring-Back Method) (Withdrawn 1982)<sup>5</sup>**
**2.2 Federal Standards:<sup>6</sup>**
**Fed. Std. No. 102 Preservation, Packaging and Packing Levels**
**Fed. Std. No. 123 Marking for Shipment (Civil Agencies)**
**Fed. Std. No. 182 Continuous Identification Marking of Nickel and Nickel-Base Alloys**
**2.3 Military Standard:<sup>6</sup>**
**MIL-STD-129 Marking for Shipment and Storage**
**3. Terminology**
**3.1 Descriptions of Terms Specific to This Standard**—The terms given in **Table 1** shall apply.

**4. Ordering Information**

4.1 It is the responsibility of the purchaser to specify all requirements that are necessary for the safe and satisfactory performance of material ordered under this specification. Examples of such requirements include, but are not limited to, the following:

**4.1.1 Alloy**—Name or UNS number (see **Table 2**),

**4.1.2 ASTM designation**, including year of issue,

**4.1.3 Condition**—See **7.1** and **7.2** and **Appendix X1**,

**4.1.4 Finish**—**Appendix X1**,

**4.1.5 Dimensions**—Thickness, width, and length,

**4.1.6 Quantity**,

**4.1.7 Optional Requirements:**
**4.1.7.1 Sheet and Strip**—Whether to be furnished in coil, in cut straight lengths, or in random straight lengths,

**4.1.7.2 Strip**—Whether to be furnished with commercial slit edge, square edge, or round edge,

**4.1.7.3 Plate**—Whether to be furnished specially flattened (see **8.7.2**); also how plate is to be cut (see **8.2.1** and **8.3.2**),

**4.1.8 Certification**—State if certification or a report of test results is required (Section **16**),

**4.1.9 Samples for Product (Check) Analysis**—Whether samples for product (check) analysis should be furnished (see **5.2**), and

<sup>6</sup> Available from DLA Document Services, Building 4/D, 700 Robbins Ave., Philadelphia, PA 19111-5094, <http://quicksearch.dla.mil>.

**4.1.10 Purchaser Inspection**—If the purchaser wishes to witness tests or inspection of material at the place of manufacture, the purchase order must so state indicating which tests or inspections are to be witnessed (Section **14**).

**5. Chemical Composition**

5.1 The material shall conform to the requirements as to chemical composition prescribed in **Table 2**.

5.2 If a product (check) analysis is performed by the purchaser, the material shall conform to the product (check) analysis variations prescribed in Specification **B880**.

**6. Heat Treatment**

6.1 Material of N06674 shall be solution annealed after cold-working or hot-working by heating to 2150°F (1175°C) minimum, followed by quenching in water or rapidly cooling by other means.

**7. Mechanical Properties and Other Requirements**

**7.1 Mechanical Properties**—The material shall conform to the mechanical properties prescribed in **Table 3**.

**7.2 Deep Drawing and Spinning Quality Sheet and Strip**—The material shall conform to the grain size and hardness requirements as prescribed in **Table 4**.

**7.2.1** The mechanical properties of **Table 3** do not apply to deep drawing and spinning quality sheet and strip.

**7.3 Grain Size**—Except as prescribed in **7.2**, the grain size for N06674 shall be 7 or coarser, as determined in accordance with Test Methods **E112**.

**8. Dimensions and Permissible Variations**

**8.1 Thickness and Weight:**

**8.1.1 Plate**—For plate up to 2 in. (50.8 mm), inclusive, in thickness, the permissible variation under the specified thickness and permissible excess in overweight shall not exceed the amounts prescribed in **Table 5**.

**8.1.1.1** For use with **Table 5**, plate shall be assumed to weigh 0.304 lb/in.<sup>3</sup> (8.415 g/cm<sup>3</sup>).

**8.1.2 Plate**—For plate over 2 in. (50.8 mm) in thickness, the permissible variations over the specified thickness shall not exceed the amounts prescribed in **Table 6**.

**8.1.3 Sheet and Strip**—The permissible variations in thickness of sheet and strip shall be as prescribed in **Table 7**. The thickness of strip and sheet shall be measured with the micrometer spindle  $\frac{3}{8}$  in. (9.5 mm) or more from either edge

**TABLE 1 Product Description**

Product	Thickness, in. (mm)	Width, in. (mm)
Hot-rolled plate <sup>A</sup>	$\frac{3}{16}$ and over ( <b>Table 5</b> and <b>Table 6</b> )	( <b>Table 8</b> ) <sup>B</sup>
Hot-rolled sheet <sup>A</sup>	0.018 to 0.250 (0.46 to 6.4), incl ( <b>Table 7</b> )	( <b>Table 10</b> )
Cold-rolled sheet <sup>C</sup>	0.018 to 0.250 (0.46 to 6.4), incl ( <b>Table 7</b> )	( <b>Table 10</b> )
Cold-rolled strip <sup>C</sup>	0.005 to 0.250 (0.13 to 6.4), incl ( <b>Table 7</b> )	( <b>Table 10</b> )

<sup>A</sup> Material  $\frac{3}{16}$  to  $\frac{1}{4}$  in. (4.8 to 6.4 mm), incl, in thickness may be furnished as sheet or plate provided the material meets the specification requirements for the condition ordered.

<sup>B</sup> Hot-rolled plate, in widths 10 in. (254 mm) and under, may be furnished as hot-finished rectangles with sheared or cut edges in accordance with Specification **B166**, provided the mechanical property requirements of this specification are met.

<sup>C</sup> Material under 48 in. (1219 mm) in width may be furnished as sheet or strip provided the material meets the specification requirements for the condition ordered.

**TABLE 2 Chemical Requirements<sup>A</sup>**

Element	Composition Limits, %										
	Alloy N06600	Alloy N06601	Alloy N06617	Alloy N06674	Alloy N06690	Alloy N06693	Alloy N06025	Alloy N06045	Alloy N06603	Alloy N06696	Alloy N06699
Nickel	72.0 min	58.0-63.0	44.5 min	remainder <sup>B</sup>	58.0 min	remainder <sup>B</sup>	remainder <sup>B</sup>	45.0 min	remainder <sup>B</sup>	remainder <sup>B</sup>	remainder <sup>B</sup>
Chromium	14.0-17.0	21.0-25.0	20.0-24.0	21.5-24.5	27.0-31.0	27.0-31.0	24.0-26.0	26.0-29.0	24.0-26.0	28.0-32.0	26.0-30.0
Cobalt	...	...	10.0-15.0	...	...	...	...	...	...	...	...
Molybdenum	...	...	8.0-10.0	...	...	...	...	...	...	...	...
Niobium	...	...	...	0.10-0.35	...	0.5-2.5	...	...	...	1.0-3.0	...
Iron	6.0-10.0	remainder <sup>B</sup>	3.0 max	20.0-27.0	7.0-11.0	2.5-6.0	8.0-11.0	21.0-25.0	8.0-11.0	2.0-6.0	0.50 max
Manganese	1.0 max	1.0 max	1.0 max	1.50 max	0.5 max	1.0 max	0.15 max	1.0 max	0.15 max	1.0 max	2.5 max
Aluminum	...	1.0-1.7	0.8-1.5	...	...	2.5-4.0	1.8-2.4	...	2.4-3.0	...	1.9-3.0
Carbon	0.15 max	0.10 max	0.05-0.15	0.10 max	0.05 max	0.15 max	0.15-0.25	0.05-0.12	0.20-0.40	0.15 max	0.005-0.10
Copper	0.5 max	1.0 max	0.5 max	...	0.5 max	0.5 max	0.1 max	0.3 max	0.50 max	1.5-3.0	0.50 max
Silicon	0.5 max	0.5 max	1.0 max	1.0 max	0.5 max	0.5 max	0.5 max	2.5-3.0	0.50 max	1.0-2.5	0.50 max
Sulfur	0.015 max	0.015 max	0.015 max	0.015 max	0.015 max	0.01 max	0.010 max	0.010 max	0.010 max	0.010 max	0.01 max
Titanium	...	...	0.6 max	0.05-0.20	...	1.0 max	0.1-0.2	...	0.01-0.25	1.0 max	0.60 max
Phosphorus	...	...	...	0.030 max	...	...	0.020 max	0.020 max	0.020 max	...	0.02 max
Zirconium	...	...	...	...	...	...	0.01-0.10	...	0.01-0.10	...	0.10 max
Yttrium	...	...	...	...	...	...	0.05-0.12	...	0.01-0.15	...	...
Boron	...	...	0.006 max	0.0005-0.006	...	...	...	...	...	...	...
Nitrogen	...	...	...	0.02 max	...	...	...	...	...	...	0.008 max
Cerium	...	...	...	...	...	...	...	...	...	...	0.05 max
Tungsten	...	...	...	6.0-8.0	...	...	...	0.03-0.09	...	...	...

<sup>A</sup> Where ellipses (...) appear in this table there is no requirement and the element need neither be analyzed for nor reported.

<sup>B</sup> Element shall be determined arithmetically by difference.

**TABLE 3 Mechanical Properties for Plate, Sheet, and Strip (All Thicknesses and Sizes Unless Otherwise Indicated)**

Condition (Temper)	Tensile Strength, min, psi (MPa)	Yield Strength <sup>A</sup> (0.2 % offset), min, psi (MPa)	Elongation in 2 in. or 50 mm (or 4D), min, %	Rockwell Hardness <sup>B,C</sup>
Hot-Rolled Plate				
UNS N06600:				
Annealed	80 000 (550)	35 000 (240)	30	...
As-rolled <sup>D,E</sup>	85 000 (586)	35 000 (240)	30	...
UNS N06601:				
Annealed	80 000 (550)	30 000 (205)	30	...
UNS N06603:				
Annealed	94 000 (650)	43 000 (300)	25	...
UNS N06617:				
Annealed	95 000 (655)	35 000 (240)	35	...
UNS N06674:				
Annealed	86 000 (590)	34 000 (235)	30	...
UNS N06690:				
Annealed	85 000 (586)	35 000 (240)	30	...
As-rolled <sup>D,E</sup>	85 000 (586)	35 000 (240)	30	...
Annealed <sup>F</sup>	75 000 (514)	30 000 (206)	30	...
UNS N06693:				
Annealed	100 000 (690)	50 000 (345)	30	...
UNS N06025:				
Annealed	98 000 (680)	39 000 (270)	30	...
UNS N06045:				
Annealed	90 000 (620)	35 000 (240)	35	...
UNS N06699				
Annealed	89 000 (610)	35 000 (240)	40	...
Hot-Rolled Sheet				
UNS N06600:				
Annealed	80 000 (550)	35 000 (240)	30	...
UNS N06601:				
Annealed	80 000 (550)	30 000 (205)	30	...
UNS N06603:				
Annealed	94 000 (650)	43 000 (300)	25	...
UNS N06617:				
Annealed	95 000 (655)	35 000 (240)	30	...
UNS N06674:				
Annealed	86 000 (590)	34 000 (235)	30	...
UNS N06690:				
Annealed	85 000 (586)	35 000 (240)	30	...
UNS N06693:				
Annealed	100 000 (690)	50 000 (345)	30	...
UNS N06025:				
Annealed	98 000 (680)	39 000 (270)	30	...
UNS N06045:				
Annealed	90 000 (620)	35 000 (240)	35	...
UNS N06699				
Annealed	89 000 (610)	35 000 (240)	40	...
Cold-Rolled Plate				
UNS N06603:				
Annealed	94 000 (650)	43 000 (300)	25	...
UNS N06674:				
Annealed	86 000 (590)	34 000 (235)	30	...
UNS N06025:				
Annealed	98 000 (680)	39 000 (270)	30	...
UNS N06045:				
Annealed	90 000 (620)	35 000 (240)	35	...
UNS N06699				
Annealed	89 000 (610)	35 000 (240)	40	...
Cold-Rolled Sheet				
UNS N06600:				
Annealed	80 000 (550) <sup>G</sup>	35 000 (240)	30 <sup>G</sup>	...
Hard	125 000 (860) <sup>G</sup>	90 000 (620)	2 <sup>G</sup>	...
UNS N06601:				
Annealed	80 000 (550) <sup>G</sup>	30 000 (205)	30 <sup>G</sup>	...
UNS N06603:				
Annealed	94 000 (650)	43 000 (300)	25 <sup>G</sup>	...
UNS N06674:				
Annealed	86 000 (590)	34 000 (235)	30	...
UNS N06617:				
Annealed	95 000 (655) <sup>G</sup>	35 000 (240)	25 <sup>G</sup>	...
UNS N06690:				
Annealed	85 000 (586) <sup>G</sup>	35 000 (240)	30 <sup>G</sup>	...
Hard	125 000 (860) <sup>G</sup>	90 000 (620)	2 <sup>G</sup>	...
UNS N06693:				
Annealed	100 000 (690)	50 000 (345)	30	...

**TABLE 3** *Continued*

Condition (Temper)	Tensile Strength, min, psi (MPa)	Yield Strength <sup>A</sup> (0.2 % offset), min, psi (MPa)	Elongation in 2 in. or 50 mm (or 4D), min,%	Rockwell Hardness <sup>B,C</sup>
UNS N06025: Annealed	98 000 (680)	39 000 (270)	30	...
UNS N06045: Annealed	90 000 (620)	35 000 (240)	35	...
UNS N06699 Annealed	89 000 (610)	35 000 (240)	40	...
Cold-Rolled Strip				
UNS N06600: Annealed	80 000 (550) <sup>G</sup>	35 000 (240)	30 <sup>G</sup>	...
Skin-hard	...	...	...	B85 to B88
Quarter-hard	...	...	...	B88 to B94
Half-hard	...	...	...	B93 to B98
Three-quarter-hard	...	...	...	B97 to C25
Hard	125 000 (860) <sup>G</sup>	90 000 (620)	2 <sup>G</sup>	...
Spring	...	...	...	C30 min
UNS N06601: Annealed	80 000 (550) <sup>G</sup>	30 000 (205)	30 <sup>G</sup>	...
UNS N06603: Annealed	94 000 (650)	43 000 (300)	25 <sup>G</sup>	...
UNS N06617: Annealed	95 000 (655) <sup>G</sup>	35 000 (240)	30 <sup>G</sup>	...
UNS N06674: Annealed	86 000 (590)	34 000 (235)	30	...
UNS N06690: Annealed	85 000 (586) <sup>G</sup>	35 000 (240)	30 <sup>G</sup>	...
Skin-hard	...	...	...	B85 to B88
Quarter-hard	...	...	...	B88 to B94
Half-hard	...	...	...	B93 to B98
Three-quarter-hard	...	...	...	B97 to C25
Hard	125 000 (860) <sup>G</sup>	90 000 (620)	2 <sup>G</sup>	...
Spring	...	...	...	C30 min
UNS N06693: Annealed	100 000 (690)	50 000 (345)	30	...
UNS N06025: Annealed	98 000 (680)	39 000 (270)	30	...
UNS N06045: Annealed	90 000 (620)	35 000 (240)	35	...
UNS N06696: Annealed	85 000 (586)	35 000 (240)	30	...
UNS N06699 Annealed	89 000 (610)	35 000 (210)	40	...

<sup>A</sup> Yield strength requirements do not apply to material under 0.020 in. (0.51 mm) in thickness.

<sup>B</sup> For Rockwell or equivalent hardness conversions, see Hardness Conversion Tables E140.

<sup>C</sup> Caution should be served in using the Rockwell test on thin material, as the results may be affected by specimen thickness. For thicknesses under 0.050 in. (1.3 mm), the use of the Rockwell superficial or the Vickers hardness test is suggested.

<sup>D</sup> As-rolled plate may be given a stress relieving heat treatment subsequent to final rolling.

<sup>E</sup> As-rolled plate specified "suitable for hot forming" shall be furnished from heats of known good hot-malleability characteristics (see X1.2.2). There are no applicable tensile or hardness requirements for such material.

<sup>F</sup> Annealed at 1850°F (1010°C) minimum.

<sup>G</sup> Not applicable for thickness under 0.010 in. (0.25 mm).

for material 1 in. (25.4 mm) or over in width and at any place on the strip under 1 in. in width.

## 8.2 Width or Diameter:

8.2.1 *Plate*—The permissible variations in width of rectangular plates and diameter of circular plates shall be as prescribed in Table 8 and Table 9.

8.2.2 *Sheet and Strip*—The permissible variations in width for sheet and strip shall be as prescribed in Table 10.

## 8.3 Length:

8.3.1 Sheet and strip of all sizes may be ordered to cut lengths, in which case a variation of 1/8 in. (3.2 mm) over the specified length shall be permitted.

8.3.2 Permissible variations in length of rectangular plate shall be as prescribed in Table 11.

## 8.4 Straightness:

8.4.1 The edgewise curvature (depth of chord) of flat sheet, strip, and plate shall not exceed 0.05 in. multiplied by the length in feet (0.04 mm multiplied by the length in centimetres).

8.4.2 Straightness for coiled material is subject to agreement between the manufacturer and the purchaser.

## 8.5 Edges:

8.5.1 When finished edges of strip are specified in the contract or order, the following descriptions shall apply:

**TABLE 4 Grain Size and Hardness for Cold-Rolled, Deep-Drawing, and Spinning-Quality Sheet and Strip**

Thickness, in. (mm)	Calculated Diameter of Average Grain Section, max. in. (mm)	Corresponding ASTM MicroGrain Size No.	Rockwell B <sup>A,B</sup> Hardness, max
<b>Sheet (56 in. (1.42 m) Wide and Under)</b>			
0.050 (1.3) and less	0.0030 (0.075)	4.5	86
Over 0.050 to 0.250 (1.3 to 6.4), incl	0.0043 (0.110)	3.5	86
<b>Strip (12 in. (305 mm) Wide and Under)<sup>C</sup></b>			
0.005 <sup>D</sup> to 0.010 (0.13 to 0.25), incl	0.0009 (0.022)	8 <sup>E</sup>	88 <sup>E</sup>
Over 0.010 to 0.125 (0.25 to 3.2), incl	0.0030 (0.075)	4.5	86

<sup>A</sup> For Rockwell or equivalent hardness conversions, see Hardness Conversion Tables E140.

<sup>B</sup> Caution should be observed in using the Rockwell test on thin material, as the results may be affected by specimen thickness. For thicknesses under 0.050 in. (1.3 mm), the use of the Rockwell superficial or the Vickers hardness test is suggested.

<sup>C</sup> Sheet requirements (above) apply to strip thicknesses over 0.125 in. (3.2 mm), and for all thicknesses of strip over 12 in. (305 mm) in width.

<sup>D</sup> For ductility evaluations for strip under 0.005 in. (0.13 mm) in thickness, the springback test, such as described in Test Method F155, is often used and the manufacturer should be consulted.

<sup>E</sup> Accurate grain size and hardness determinations are difficult to make on strip under 0.005 in. (0.13 mm) in thickness and are not recommended.

**TABLE 5 Permissible Variations in Thickness and Overweight of Rectangular Plates**

NOTE 1—All plates shall be ordered to thickness and not to weight per square foot (cm). No plates shall vary more than 0.01 in. (0.3 mm) under the thickness ordered, and the overweight of each lot<sup>A</sup> in each shipment shall not exceed the amount in the table. Spot grinding is permitted to remove surface imperfections, such spots not to exceed 0.01 in. under the specified thickness.

Specified Thickness, in. (mm)	Permissible Excess in Average Weight <sup>B,C</sup> per Square Foot of Plates for Widths Given in Inches (Millimetres) Expressed in Percentage of Nominal Weights									
	Under 48 (1220)	48 to 60 (1220 to 1520), excl	60 to 72 (1520 to 1830), excl	72 to 84 (1830 to 2130), excl	84 to 96 (2130 to 2440), excl	96 to 108 (2440 to 2740), excl	108 to 120 (2740 to 3050), excl	120 to 132 (3050 to 3350), excl	132 to 144 (3350 to 3660), excl	144 to 160 (3660 to 4070), excl
3/16 to 5/16 (4.8 to 7.9), excl	9.0	10.5	12.0	13.5	15.0	16.5	18.0	...	...	...
5/16 to 3/8 (7.9 to 9.5), excl	7.5	9.0	10.5	12.0	13.5	15.0	16.5	18.0	...	...
3/8 to 7/16 (9.5 to 11.1), excl	7.0	7.5	9.0	10.5	12.0	13.5	15.0	16.5	18.0	19.5
7/16 to 1/2 (11.1 to 12.7), excl	6.0	7.0	7.5	9.0	10.5	12.0	13.5	15.0	16.5	18.0
1/2 to 5/8 (12.7 to 15.9), excl	5.0	6.0	7.0	7.5	9.0	10.5	12.0	13.5	15.0	16.5
5/8 to 3/4 (15.9 to 19.1), excl	4.5	5.5	6.0	7.0	7.5	9.0	10.5	12.0	13.5	15.0
3/4 to 1 (19.1 to 25.4), excl	4.0	4.5	5.5	6.0	7.0	7.5	9.0	10.5	12.0	13.5
1 to 2 (25.4 to 50.8), incl	4.0	4.0	4.5	5.5	6.0	7.0	7.5	9.0	10.5	12.0

<sup>A</sup> The term "lot" applied to this table means all of the plates of each group width and each group thickness.

<sup>B</sup> The permissible overweight for lots of circular and sketch plates shall be 25 % greater than the amounts given in this table.

<sup>C</sup> The weight of individual plates shall not exceed the nominal weight by more than 1 1/4 times the amount given in the table and Footnote B.

**TABLE 6 Permissible Variations in Thickness for Rectangular Plates Over 2 in. (51 mm) in Thickness**

NOTE 1—Permissible variation under specified thickness, 0.01 in. (0.3 mm).

Specified Thickness, in. (mm)	Permissible Variations, in. (mm), over Specified Thickness for Widths Given, in. (mm)					
	To 36 (915), excl	36 to 60 (915 to 1520), excl	60 to 84 (1520 to 2130), excl	84 to 120 (2130 to 3050), excl	120 to 132 (3050 to 3350), excl	132 (3350) and over
Over 2 to 3 (51 to 76), excl	1/16 (1.6)	3/32 (2.4)	7/64 (2.8)	1/8 (3.2)	1/8 (3.2)	3/64 (3.6)
3 to 4 (76 to 102), incl	3/64 (2.0)	3/32 (2.4)	7/64 (2.8)	1/8 (3.2)	1/8 (3.2)	3/64 (3.6)

8.5.1.1 Square-edge strip shall be supplied with finished edges, with sharp, square corners, without bevel or rounding.