

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Ferrite cores – Guidelines on dimensions and the limits of surface irregularities –
Part 12: Ring-cores**

(standards.iteh.ai)

**Noyaux ferrites – Lignes directrices relatives aux dimensions et aux limites des
irrégularités de surface –**

Partie 12: Noyaux toriques



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2019 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22,000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67,000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Recherche de publications IEC -

webstore.iec.ch/advsearchform

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: sales@iec.ch.

Electropedia - www.electropedia.org

Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 000 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 16 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

Glossaire IEC - std.iec.ch/glossary

67 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Ferrite cores – Guidelines on dimensions and the limits of surface irregularities –
Part 12: Ring-cores**

(standards.iteh.ai)

**Noyaux ferrites – Lignes directrices relatives aux dimensions et aux limites des
irrégularités de surface –**

Partie 12: Noyaux toriques

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 29.100.10

ISBN 978-2-8322-6715-8

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

FOREWORD.....	3
1 Scope.....	5
2 Normative references	5
3 Terms and definitions	5
4 Primary dimensions	5
4.1 General.....	5
4.2 Dimensions of ring-cores	6
4.2.1 Designation of dimensions	6
4.2.2 Identification of standard sizes.....	6
4.2.3 Effective parameter values.....	6
4.2.4 Dimensional limits for standard sizes	7
4.3 Coating	13
5 Limits of surface irregularities.....	13
5.1 Uncoated ring-cores.....	13
5.1.1 General.....	13
5.1.2 Chips and ragged edges	13
5.1.3 Cracks and pull-outs	14
5.1.4 Crystallites.....	14
5.1.5 Pores.....	15
5.2 Coated ring-cores	15
5.2.1 General.....	15
5.2.2 Coating features	15
5.2.3 Coating performance	16
5.3 Area and length reference for visual inspection.....	16
Bibliography.....	18
Figure 1 – Dimensions of ring-cores.....	6
Figure 2 – Location of chips and ragged edges.....	14
Figure 3 – Location of cracks and pull-out on ring-cores	14
Figure 4 – Location of crystallite on ring-cores	15
Figure 5 – Location of pore on ring-cores.....	15
Table 1 – Ring-core dimension designations.....	6
Table 2 – Standard ring-cores.....	7
Table 3 – Effective parameters of ring-cores.....	9
Table 4 – Recommended dimensional limits for uncoated ring-cores.....	11
Table 5 – Area and length reference for visual inspection	17

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**FERRITE CORES – GUIDELINES ON DIMENSIONS
AND THE LIMITS OF SURFACE IRREGULARITIES –****Part 12: Ring-cores**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 63093-12 has been prepared by IEC technical committee 51: Magnetic components, ferrite and magnetic powder materials.

This first edition cancels and replaces the first edition of IEC 62317-12 published in 2016 and the second edition of IEC 60424-4 published in 2015. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to IEC 62317-12:2016 and IEC 60424-4:2015:

- a) IEC 63093-12 integrates the contents of IEC 62317-12:2016 and IEC 60424-4:2015.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
51/1271/FDIS	51/1284/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 63093 series, published under the general title *Ferrite cores – Guidelines on dimensions and the limits of surface irregularities*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[IEC 63093-12:2019](#)

<https://standards.iteh.ai/catalog/standards/sist/6cb4f7f3-39fa-4f5b-a164-b0703598aeba/iec-63093-12-2019>

FERRITE CORES – GUIDELINES ON DIMENSIONS AND THE LIMITS OF SURFACE IRREGULARITIES –

Part 12: Ring-cores

1 Scope

This part of IEC 63093 specifies the dimensions that are of importance for mechanical interchangeability for a preferred range of ring-cores, also called toroid cores, and the effective parameter values to be used in calculations involving them. It also gives guidelines on allowable limits of surface irregularities applicable to ring-cores.

This document is a specification useful in the negotiations between ferrite core manufacturers and users about surface irregularities.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60205, *Calculation of the effective parameters of magnetic piece parts*

[IEC 63093-12:2019](#)

IEC 60401-1, *Terms and nomenclature for cores made of magnetically soft ferrites – Part 1: Terms used for physical irregularities*

IEC 60424-1, *Ferrite cores – Guidelines on the limits of surface irregularities – Part 1: General specification*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60401-1 and IEC 60424-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Primary dimensions

4.1 General

Compliance with the following requirements ensures mechanical interchangeability of complete assemblies and wound coils.

4.2 Dimensions of ring-cores

4.2.1 Designation of dimensions

Figure 1 and Table 1 describe the alphabetic character assignments for the dimensions of ferrite ring-cores.




Figure 1 – Dimensions of ring-cores

Table 1 – Ring-core dimension designations

Letter	Dimension description
A	Outside diameter
B	Inside diameter
C	Height

4.2.2 Identification of standard sizes

Table 2 shows the nominal dimensions for the range of standard ring-cores. Table 2 also shows, where applicable, the origin and regional name of each standard size, whether from historical European sizes, historical Japanese sizes, or historical USA sizes. The previous IEC TR 61604 (now withdrawn) detailed the different ring sizes that were tooled and commonly used in the three distinct geographic regions. IEC TR 61604 laid the groundwork for the present document, which reflects the more global nature of the industry, compared to the time when ferrite standards were evolving in different parts of the world. Manufacturers tend to have more globally complete offerings of ring sizes than before, leading to a profusion of different sizes.

The number of different ring sizes used in total is quite large, far in excess of the 82 commonly known standard sizes shown here, for a couple of reasons: ring-cores are relatively inexpensive to build tooling for, nor does a new ring-core require an expensive new coil former to be assembled, meaning that custom ring-cores are often commercially practical. Ferrite rings, which lack a residual air gap, that E-cores and other shapes have at their mating surfaces, exhibit directly the full magnetic performance possible in the ferrite material, meaning that assembling precisely optimal new dimensions can give a significant advantage to a designer that is optimizing for best possible performance.

4.2.3 Effective parameter values

The effective parameter values for the standard ring-cores are given in Table 3. For global practicality and simplicity the effective parameters in this document are calculated from the nominal dimensions, assuming cores of a rectangular cross section, and are useful for reference and comparison of cores. For cores having a cross section with an appreciable average rounding radius, more precise values shall be calculated from the method given in IEC 60205, if required.

4.2.4 Dimensional limits for standard sizes

The standard tolerance limits for uncoated ring-cores are given in Table 4. Manufacturers can choose to offer looser standard limits for ferrite materials that exhibit greater process variability, or tighter limits for applications that justify higher processing and yield costs to achieve a narrower dimensional range.

The limits take account of shrinkage variation and warping during firing. The specification for the out-of-round condition of the inner or outer circumference is that the inside diameter (B) and outside diameter (A) shall stay within the indicated limits, measured at any point. Similarly, the specification for the non-flat condition of the sides of a ring is that the height minimum and maximum shall be achieved at all points.

Table 2 – Standard ring-cores

Nominal uncoated dimensions			Size reference
A (mm)	B (mm)	C (mm)	
2,5	1,3	1,3	
2,5	1,5	0,8	
2,5	1,5	1,0	Europe R2,5
3,1	1,3	1,3	
3,1	1,8	2,0	
3,5	1,8	1,3	
3,9	1,8	1,8	
3,94	2,24	1,27	USA T3,9
4,0	2,0	2,0	
4,0	2,2	1,6	Europe R4
4,83	2,29	1,27	USA T4,8
5,84	3,05	1,52	USA T5,8
6,0	3,0	2,0	
6,0	4,0	2,0	
6,3	3,8	2,5	Europe R6,3
7,62	3,18	4,78	USA T7,6
8,0	4,0	2,0	
8,2	3,7	4,0	
9,0	6,0	3,0	
9,53	4,75	3,18	USA T9,5
10,0	5,0	4,0	
10,0	5,0	5,0	Japan FOR 10
10,0	6,0	4,0	Europe R10
12,0	6,0	4,0	Japan FOR12
12,7	7,1	5,1	
12,7	7,92	6,35	USA T12,7
13,2	7,4	4,0	
13,6	7,0	3,5	
14,0	8,0	7,0	
14,0	9,0	5,0	
15,88	8,89	4,7	USA T15,9
16,0	9,0	5,0	

Nominal uncoated dimensions			Size reference
A (mm)	B (mm)	C (mm)	
16,0	9,6	6,3	Europe R16
16,0	12,0	8,0	
18,0	10,0	10,0	Japan FOR 18
18,5	9,8	10,3	Japan FOR 19
20,0	10,0	7,0	Europe R20
20,0	12,0	10,0	Japan FOR 20
22,0	14,0	10,0	Japan FOR 22
22,1	13,72	6,35	USA T22,1
25,0	15,0	10,0	Europe R25
25,0	15,0	12,0	Japan FOR 25
25,4	15,49	9,53	USA T25,4
26,9	14,2	12,2	
28,0	16,0	13,0	Japan FOR 28
29,0	19,0	7,49	USA T29,0
30,8	19,1	12,7	
31,0	19,0	13,0	Japan FOR 31
32,0	19,0	13,0	
36,0	23,0	10,0	USA T36,0
36,0	23,0	15,0	Europe R36
38,0	19,0	13,0	Japan FOR 38
38,0	22,0	13,0	
38,1	19,0	6,35	USA T38,1
40,0	24,0	16,0	Europe R40
40,0	24,0	20,0	
41,8	26,2	18,0	
44,5	30,0	13,0	Japan FOR 45
47,0	27,0	15,0	Japan FOR 47
49,1	31,8	15,9	
49,1	33,8	15,9	
50,0	30,0	20,0	Europe R50
51,0	32,0	19,0	
55,0	32,0	19,0	
58,0	41,0	18,0	
61,0	35,6	12,7	
63,0	38,0	25,0	Europe R63
68,0	48,0	13,0	
72,0	48,0	20,0	
73,7	38,9	12,7	USA T73,7
80,0	40,0	15,0	
80,0	50,0	20,0	
85,7	55,5	12,7	
96,0	70,0	20,0	
102,0	65,0	15,0	

Nominal uncoated dimensions			Size reference
A (mm)	B (mm)	C (mm)	
104,0	80,0	20,0	
107,0	65,0	18,0	
127,0	89,0	20,0	
140,0	106,0	25,0	
152,0	104,0	19,0	
202,0	153,0	25,0	
305,0	207,0	30,0	

Table 3 – Effective parameters of ring-cores

A mm	B mm	C mm	C_1 mm ⁻¹	C_2 mm ⁻³	A_e mm ²	l_e mm	V_e mm ³
2,5	1,3	1,3	7,391 1	9,818 3	0,753	5,56	4,19
2,5	1,5	0,8	15,375	39,281	0,391	6,02	2,36
2,5	1,5	1,0	12,300	25,140	0,489	6,02	2,94
3,1	1,3	1,3	5,561 6	5,060 3	1,10	6,11	6,72
3,1	1,8	2,0	5,779 1	4,556 0	1,27	7,33	9,30
3,5	1,8	1,3	7,268 3	6,823 6	1,07	7,74	8,25
3,9	1,8	1,8	4,514 6	2,510 1	1,80	8,12	14,6
3,94	2,24	1,27	8,761 0	8,333 8	1,05	9,21	9,68
4,0	2,0	2,0	4,532 4	2,358 4	1,92	8,71	16,7
4,0	2,2	1,6	6,568 7	4,699 1	1,40	9,18	12,8
4,83	2,29	1,27	6,629 3	4,304 5	1,54	10,2	15,7
5,84	3,05	1,52	6,363 5	3,108 1	2,05	13,0	26,7
6,0	3,0	2,0	4,532 4	1,572 3	2,88	13,1	37,7
6,0	4,0	2,0	7,748 1	3,927 4	1,97	15,3	30,2
6,3	3,8	2,5	4,971 4	1,625 0	3,06	15,2	46,5
7,62	3,18	4,78	1,504 2	0,151 00	9,96	15,0	149
8,0	4,0	2,0	4,532 4	1,179 2	3,84	17,4	67,0
8,2	3,7	4,0	1,973 9	0,231 14	8,54	16,9	144
9,0	6,0	3,0	5,165 4	1,163 7	4,44	22,9	102
9,53	4,75	3,18	2,837 6	0,388 69	7,30	20,7	151
10,0	5,0	4,0	2,266 2	0,235 84	9,61	21,8	209
10,0	5,0	5,0	1,812 9	0,150 94	12,0	21,8	262
10,0	6,0	4,0	3,075 0	0,392 81	7,83	24,1	188
12,0	6,0	4,0	2,266 2	0,196 53	11,5	26,1	301
12,7	7,1	5,1	2,118 6	0,152 59	13,9	29,4	408
12,7	7,92	6,35	2,095 4	0,140 65	14,9	31,2	465
13,2	7,4	4,0	2,714 2	0,240 59	11,3	30,6	345
13,6	7,0	3,5	2,703 0	0,242 75	11,1	30,1	335
14,0	8,0	7,0	1,604 0	0,078 393	20,5	32,8	671
14,0	9,0	5,0	2,844 1	0,231 26	12,3	35,0	430
15,88	8,89	4,7	2,304 4	0,144 26	16,0	36,8	588

A mm	B mm	C mm	C ₁ mm ⁻¹	C ₂ mm ⁻³	A _e mm ²	l _e mm	V _e mm ³
16,0	9,0	5,0	2,184 1	0,128 29	17,0	37,2	633
16,0	9,6	6,3	1,952 4	0,098 969	19,7	38,5	760
16,0	12,0	8,0	2,730 1	0,171 81	15,9	43,4	689
18,0	10,0	10,0	1,069 0	0,027 502	38,9	41,5	1610
18,5	9,8	10,3	0,960 07	0,022 158	43,3	41,6	1800
20,0	10,0	7,0	1,295 0	0,038 504	33,6	43,6	1460
20,0	12,0	10,0	1,230 0	0,031 425	39,1	48,1	1880
22,0	14,0	10,0	1,390 1	0,035 349	39,3	54,7	2150
22,1	13,72	6,35	2,075 6	0,079 499	26,1	54,2	1410
25,0	15,0	10,0	1,230 0	0,025 140	48,9	60,2	2940
25,0	15,0	12,0	1,025 0	0,017 458	58,7	60,2	3530
25,4	15,49	9,53	1,333 1	0,028 812	46,3	61,7	2850
26,9	14,2	12,2	0,806 12	0,010 764	74,9	60,4	4520
28,0	16,0	13,0	0,863 67	0,011 365	76,0	65,6	4990
29,0	19,0	7,49	1,983 8	0,053 767	36,9	73,2	2700
30,8	19,1	12,7	1,035 4	0,014 203	72,9	75,5	5500
31,0	19,0	13,0	0,987 28	0,012 912	76,5	75,5	5770
32,0	19,0	13,0	0,927 15	0,011 223	82,6	76,6	6330
36,0	23,0	10,0	1,402 4	0,021 939	63,9	89,6	5730
36,0	23,0	15,0	0,934 95	0,009 7507	95,9	89,6	8600
38,0	19,0	13,0	0,697 29	0,005 8757	119	82,7	9820
38,0	22,0	13,0	0,884 32	0,008 7169	101	89,7	9100
38,1	19,0	6,35	1.422 1	0,024 412	58,3	8,8	4830
40,0	24,0	16,0	0,768 75	0,006 1376	125	96,3	12100
40,0	24,0	20,0	0,615 00	0,003 9281	157	96,3	15100
41,8	26,2	18,0	0,747 25	0,005 4198	138	103	14200
44,5	30,0	13,0	1,225 8	0,013 175	93,0	114	10600
47,0	27,0	15,0	0,755 68	0,005 1682	146	110	16200
49,1	31,8	15,9	0,909 70	0,006 7190	135	123	16700
49,1	33,8	15,9	1,058 3	0,008 8022	120	127	15300
50,0	30,0	20,0	0,615 00	0,003 1425	196	120	23600
51,0	32,0	19,0	0,709 51	0,004 0025	177	126	22300
55,0	32,0	19,0	0,610 59	0,002 8634	213	130	27800
58,0	41,0	18,0	1,006 3	0,006 6435	151	152	23100
61,0	35,6	12,7	0,918 69	0,005 8349	157	145	22800
63,0	38,0	25,0	0,497 14	0,001 6250	306	152	46500
68,0	48,0	13,0	1,387 6	0,010 782	129	179	23000
72,0	48,0	20,0	0,774 81	0,003 2729	237	183	43400
73,7	38,9	12,7	0,774 23	0,003 6245	214	165	35300
80,0	40,0	15,0	0,604 31	0,002 0963	288	174	50200
80,0	50,0	20,0	0,668 42	0,002 2694	295	197	58000
85,7	55,5	12,7	1,138 7	0,006 0319	189	215	40600
96,0	70,0	20,0	0,994 64	0,003 8574	258	256	66100

A mm	B mm	C mm	C_1 mm ⁻¹	C_2 mm ⁻³	A_e mm ²	l_e mm	V_e mm ³
102,0	65,0	15,0	0,929 63	0,003 407 1	273	254	69 200
104,0	80,0	20,0	1,197 4	0,005 017 9	239	286	68 200
107,0	65,0	18,0	0,700 31	0,001 891 4	370	259	96 000
127,0	89,0	20,0	0,883 58	0,002 349 8	376	332	125 000
140,0	106,0	25,0	0,903 39	0,002 139 4	422	381	161 000
152,0	104,0	19,0	0,871 42	0,001 934 0	451	393	177 000
202,0	153,0	25,0	0,904 61	0,001 486 4	609	551	335 000
305,0	207,0	30,0	0,540 36	0,000 372 22	1450	784	1 140 000

Table 4 – Recommended dimensional limits for uncoated ring-cores

A mm	Min. mm	Max. mm	B mm	Min. mm	Max. mm	C mm	Min. mm	Max. mm
2,5	2,35	2,65	1,3	1,15	1,45	1,3	1,15	1,45
2,5	2,35	2,65	1,5	1,35	1,65	0,8	0,65	0,95
2,5	2,35	2,65	1,5	1,35	1,65	1,0	0,85	1,15
3,1	2,95	3,25	1,3	1,15	1,45	1,3	1,15	1,45
3,1	2,95	3,25	1,8	1,65	1,95	2,0	1,85	2,15
3,5	3,35	3,65	1,8	1,65	1,95	1,3	1,15	1,45
3,9	3,75	4,05	1,8	1,65	1,95	1,8	1,65	1,95
3,94	3,79	4,09	2,24	2,09	2,39	1,27	1,12	1,42
4,0	3,80	4,20	2,0	1,85	2,15	2,0	1,85	2,15
4,0	3,80	4,20	2,2	2,05	2,35	1,6	1,45	1,75
4,83	4,63	5,03	2,29	2,14	2,44	1,27	1,12	1,42
5,84	5,64	6,04	3,05	2,90	3,20	1,52	1,37	1,67
6,0	5,80	6,20	3,0	2,85	3,15	2,0	1,85	2,15
6,0	5,80	6,20	4,0	3,85	4,15	2,0	1,85	2,15
6,3	6,10	6,50	3,8	3,65	3,95	2,5	2,35	2,65
7,62	7,42	7,82	3,18	3,03	3,33	4,78	4,48	5,08
8,0	7,80	8,20	4,0	3,85	4,15	2,0	1,85	2,15
8,2	8,00	8,40	3,7	3,55	3,85	4,0	3,75	4,25
9,0	8,70	9,30	6,0	5,80	6,20	3,0	2,80	3,20
9,53	9,23	9,83	4,75	4,55	4,95	3,18	3,03	3,33
10,0	9,70	10,30	5,0	4,80	5,20	4,0	3,85	4,15
10,0	9,70	10,30	5,0	4,80	5,20	5,0	4,85	5,15
10,0	9,70	10,30	6,0	5,80	6,20	4,0	3,85	4,15
12,0	11,60	12,40	6,0	5,75	6,25	4,0	3,85	4,15
12,7	12,30	13,10	7,1	6,85	7,35	5,1	4,90	5,30
12,7	12,30	13,10	7,92	7,67	8,17	6,35	6,15	6,55
13,2	12,80	13,60	7,4	7,15	7,65	4,0	3,85	4,15
13,6	13,20	14,00	7,0	6,75	7,25	3,5	3,35	3,65
14,0	13,50	14,50	8,0	7,70	8,30	7,0	6,80	7,20
14,0	13,50	14,50	9,0	8,70	9,30	5,0	4,80	5,20