



Designation: D4559 – 99 (Reapproved 2018)

Standard Test Method for Volatile Matter in Silicone Fluid¹

This standard is issued under the fixed designation D4559; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method describes a procedure for determining the volatile matter in silicone fluids used for electrical insulation.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D923 Practices for Sampling Electrical Insulating Liquids](#)

[D5423 Specification for Forced-Convection Laboratory Ovens for Evaluation of Electrical Insulation](#)

3. Summary of Test Method

3.1 Specimens are weighed before and after heating for a specific time in a forced air oven to determine weight loss.

4. Significance and Use

4.1 High values may indicate contamination of the silicone with other materials, inadequate removal of volatile components by the producer, or the presence of a depolymerization catalyst.

¹ This test method is under the jurisdiction of ASTM Committee D27 on Electrical Insulating Liquids and Gases and is the direct responsibility of Subcommittee D27.07 on Physical Test.

Current edition approved Dec. 1, 2018. Published December 2018. Originally approved in 1986. Last previous edition approved in 2010 as D4559 – 99 (2010). DOI: 10.1520/D4559-99R18.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4.2 The outcome will be affected directly by the presence of any high vapor pressure material in the sample, such as solvents or low molecular weight silicones.

4.3 A high volatile content could also indicate the presence of a depolymerization catalyst in the fluid. The time and temperature specified in this test method are ideal for detecting the effect of such a material, as the depolymerization takes place at a highly accelerated rate and the low molecular weight components are rapidly evaporated. The result is a very significant weight loss during the test period. The exact amount depends on the type and amount of catalyst present. The conditions specified in the method should not cause measurable depolymerization of silicone if such a catalyst is not present.

5. Apparatus

5.1 *Air-circulating Oven*, capable of meeting the requirements of Specification [D5423](#).

5.2 *Griffin Pyrex Beakers*, 50-mL, with the following dimensions:

5.2.1 *Outside Diameter*— 42 ± 0.6 mm.

5.2.2 *Wall Thickness*—0.14 to 0.165 mm.

5.3 *Analytical Balance*, capable of measuring to 1 mg.

6. Sampling

6.1 Obtain a sample of the silicone fluid to be tested using appropriate ASTM sampling apparatus in accordance with Test Methods [D923](#).

7. Procedure

7.1 Clean two 50-mL beakers by washing in toluene, followed by a rinse in acetone or other appropriate cleaning method.

7.2 Bake two 50-mL beakers at $150 \pm 5^\circ\text{C}$ for a minimum of 1 h, transfer to a desiccator using clean, dry gloves or crucible tongs and cool the beakers to ambient temperatures. Use clean, dry gloves or crucible tongs to handle beakers from this point forward. Weigh each beaker to the nearest mg (T).

7.3 Weigh a 2.0 ± 0.2 g sample to the nearest mg in each beaker (W_1).

7.4 Heat at $150 \pm 5^\circ\text{C}$ in an air circulating oven for 24 ± 0.25 h, cool in a desiccator, and reweigh (W_2).