



Designation: **D2746 – 07 (Reapproved 2013) D2746/D2746M – 18**

Standard Test Method for Staining Tendency of Asphalt (Stain Index)¹

This standard is issued under the fixed designation ~~D2746~~**D2746/D2746M**; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the staining tendency of asphalt and the assignment of a stain index proportional to the extent of staining observed.

1.2 This test method is applicable to asphalts having ring-and-ball softening points of 85°C (185°F)[185°F] or greater.

NOTE 1—This test method may be modified for use with other bituminous materials with softening points less than 85°C (185°F)[185°F] by using a different temperature than specified in Section 7 by agreement of the interested parties. The report of results from such a test may cite this method but must clearly state the temperature employed in the exception and acknowledge that the interpretation of results in Section 9 and the precision and bias stated in Section 10 may not apply.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as the standard. The values in parentheses are for information only. ~~Values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.~~

1.4 ~~This standard does not purport to address the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.~~

1.5 ~~This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.~~

2. Referenced Documents

2.1 ASTM Standards:²

~~D36~~**D36/D36M** Test Method for Softening Point of Bitumen (Ring-and-Ball Apparatus)

~~D140~~**D140/D140M** Practice for Sampling Asphalt Materials

~~E230~~**E230M** Specification for Temperature-Electromotive Force (emf) Tables for Standardized Thermocouples

~~E1137~~**E1137M** Specification for Industrial Platinum Resistance Thermometers

~~E2251~~ Specification for Liquid-in-Glass ASTM Thermometers with Low-Hazard Precision Liquids

3. Summary of Test Method

3.1 A horizontal disc of asphalt, cast in a brass retaining ring, is placed on a sheet of filter paper supported on a flat plate and heated at 80°C (175°F)[175°F] for 120 h. The diameter of the resulting stained circle on the paper is compared to the inside diameter of the brass ring to determine the staining characteristic of the asphalt. The stain index is the difference between the diameter of the stained circle and the initial disc diameter measured to the nearest 0.5 mm ($\frac{1}{64}$ in.).

4. Significance and Use

4.1 This test method measures the tendency for oil components to separate spontaneously from asphalt. The separation of oil components can cause staining in asphalt roofing products and adjacent materials in storage and use.

4.2 The stain index is related to the thermal stability of the asphalt. Higher stain index values indicate lower stability and greater tendency for staining.

¹ This test method is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.02 on Steep Roofing Products and Assemblies.

Current edition approved May 1, 2013; Nov. 1, 2018. Published May 2013; December 2018. Originally approved in 1991. Last previous edition approved in 2007 as D2746 – 07-07 (2013). DOI: 10.1520/D2746-07R13; 10.1520/D2746_D2746M-18.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.