

SLOVENSKI STANDARD

SIST EN 1360:2005

01-julij-2005

Nadomešča:
SIST EN 1360:2000

Gumene in polimerne cevi in cevni priključki za merjeno točenje goriv - Specifikacija

Rubber and plastic hoses and hose assemblies for measured fuel dispensing systems -
Specification

Zapfstellenschläuche und -schlauchleitungen aus Gummi und Kunststoff -
Anforderungen

Tuyaux et flexibles en caoutchouc pour distribution mesurée de carburants -
Spécification

<https://standards.iteh.ai/catalog/standards/sist/5edb1a1f-d2a3-4166-a0ae-13b36d9d2741/sist-en-1360-2005>

Ta slovenski standard je istoveten z: EN 1360:2005

ICS:

75.200	Oprema za skladiščenje nafte, naftnih proizvodov in zemeljskega plina	Petroleum products and natural gas handling equipment
83.140.40	Gumene cevi	Hoses

SIST EN 1360:2005

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1360:2005

<https://standards.iteh.ai/catalog/standards/sist/5edb1a1f-d2a3-4166-a0ae-13b36d9d2741/sist-en-1360-2005>

EUROPEAN STANDARD

EN 1360

NORME EUROPÉENNE

EUROPÄISCHE NORM

May 2005

ICS 75.200; 23.040.70

Supersedes EN 1360:1996

English version

Rubber and plastic hoses and hose assemblies for measured fuel dispensing systems - Specification

Tuyaux et flexibles en caoutchouc pour distribution
mesurée de carburants - Spécification

Zapfstellenschläuche und -schlauchleitungen aus Gummi
und Kunststoff - Anforderungen

This European Standard was approved by CEN on 15 March 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

SIST EN 1360:2005

<https://standards.iteh.ai/catalog/standards/sist/5edb1a1f-d2a3-4166-a0ae-13b36d9d2741/sist-en-1360-2005>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

page

Foreword.....	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	6
4 Classification.....	6
5 Materials and construction	6
6 Pressure requirements.....	6
7 Dimensions and tolerances	7
7.1 Internal diameters and bend radii	7
7.2 Minimum thickness of lining and cover	7
7.3 Concentricity	7
7.4 Tolerance on cut lengths	7
8 Physical properties.....	7
8.1 Compounds	7
8.2 Finished hose.....	9
8.3 Hose assembly.....	10
9 End fittings	10
10 Type tests	11
11 Frequency of testing	11
12 Marking	11
12.1 Hoses	11
12.2 End fittings	12
12.3 Hose assemblies.....	12
Annex A (normative) Test method for determination of low temperature resistance at –30 °C (for normal temperature class) and –40 °C (for low temperature class)	13
A.1 Test piece	13
A.2 Apparatus	13
A.3 Test method.....	13
Annex B (normative) Method for the determination of adhesion between components	15
B.1 Dry adhesion	15
B.2 Adhesion after contact with fuel	15
Annex C (normative) Test method for the determination of low temperature flexibility	16
C.1 Test piece	16
C.2 Apparatus	16
C.3 Test method.....	16
Annex D (normative) Test method for the determination of fuel permeation.....	18
D.1 Test piece	18
D.2 Apparatus	18

D.3	Test method	18
Annex E (normative) Test method for flammability		19
E.1	Test pieces	19
E.2	Apparatus	19
E.3	Test method	19
Annex F (normative) End-fitting pull-off test		21
F.1	Test piece	21
F.2	Apparatus	21
F.3	Test method	21
Annex G (normative) Test method for the determination of leakage (leak test).....		22
Annex H (normative) Test method for fatigue strength under reversed bending stress (flex test).....		23
H.1	Apparatus and test pieces	23
H.2	Test method	24
H.3	Test observations and report	24
Annex I (normative) Test frequency for type tests and routine tests		25
Annex J (informative) Test frequency for production acceptance tests		27

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 1360:2005

<https://standards.iteh.ai/catalog/standards/sist/5edb1a1f-d2a3-4166-a0ae-13b36d9d2741/sist-en-1360-2005>

Foreword

This document (EN 1360:2005) has been prepared by Technical Committee CEN/TC 218 “Rubber and plastics hoses and hose assemblies”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2005, and conflicting national standards shall be withdrawn at the latest by November 2005.

This document supersedes EN 1360:1996.

WARNING – Persons using this European Standard should be familiar with normal laboratory practice. This standard does not purport to address all of the safety problems, if any associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 1360:2005](https://standards.iteh.ai/catalog/standards/sist/5edb1a1f-d2a3-4166-a0ae-13b36d9d2741/sist-en-1360-2005)

<https://standards.iteh.ai/catalog/standards/sist/5edb1a1f-d2a3-4166-a0ae-13b36d9d2741/sist-en-1360-2005>

1 Scope

This European Standard specifies minimum requirements for three types of hoses in two categories and two classes of hose assemblies used for measured fuel dispensing, including oxygenated fuels (up to a maximum of 15 % oxygenated compounds).

The assemblies are intended for use at ambient temperatures between $-30\text{ }^{\circ}\text{C}$ and $+55\text{ }^{\circ}\text{C}$ for normal temperature class and $-40\text{ }^{\circ}\text{C}$ and $+55\text{ }^{\circ}\text{C}$ for low temperature class at a working pressure $\leq 16\text{ bar}^{1)}$.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 26801, *Rubber or plastics hoses — Determination of volumetric expansion* (ISO 6801:1983).

EN 27326, *Rubber and plastics hoses — Assessment of ozone resistance under static conditions* (ISO 7326:1991).

EN 28033, *Rubber and plastics hose — Determination of adhesion between components* (ISO 8033:1991).

EN ISO 1307, *Rubber and plastics hoses for general-purpose industrial applications — Bore diameters and tolerances, and tolerances on length* (ISO 1307:1992).

EN ISO 1402, *Rubber and plastics hoses and hose assemblies — Hydrostatic testing* (ISO 1402:1994).

EN ISO 1746, *Rubber or plastics hoses and tubing — Bending tests* (ISO 1746:1998, including technical corrigendum 1:1999).

EN ISO 4671, *Rubber and plastics hose and hose assemblies — Methods of measurement of dimensions* (ISO 4671:1999).

EN ISO 8031, *Rubber and plastics hoses and hose assemblies — Determination of electrical resistance* (ISO 8031:1993).

EN ISO 8330:2000, *Rubber and plastics hoses and hose assemblies — Vocabulary* (ISO 8330:1998).

ISO 37, *Rubber, vulcanised or thermoplastic — Determination of tensile stress-strain properties*.

ISO 188, *Rubber, vulcanised or thermoplastic — Accelerated ageing and heat-resistance tests*.

ISO 554, *Standard atmospheres for conditioning and/or testing — Specifications*.

ISO 1817, *Rubber, vulcanised — Determination of the effect of liquids*.

ISO 4649, *Rubber, vulcanised or thermoplastic — Determination of abrasion resistance using a rotating cylindrical drum device*.

1) 1 bar = 0,1 MPa

EN 1360:2005 (E)**3 Terms and definitions**

For the purposes of this document, the terms and definitions given in EN ISO 8330:2000 apply.

4 Classification

Hoses for this application shall be divided into three types:

- a) Type 1: textile reinforced;
- b) Type 2: textile and helical wire reinforced;
- c) Type 3: fine wire reinforced.

Hoses for this application shall be divided into two categories:

- d) Category M: electrically bonded
- e) Category Ω : electrically conductive

Hoses for this application shall be divided into two temperature classes:

Normal temperature class with an ambient working temperature of $-30\text{ }^{\circ}\text{C}$ to $+55\text{ }^{\circ}\text{C}$

Low temperature class (LT) with an ambient working temperature of $-40\text{ }^{\circ}\text{C}$ to $+55\text{ }^{\circ}\text{C}$

5 Materials and construction

The hose shall consist of the following:

- a smooth, fuel resistant lining of rubber or thermoplastic elastomer (TPE);
- a suitable reinforcement; related to type;
- a non-corrugated, fuel and weather-resistant rubber or TPE cover.

Hose assemblies shall be capable of conducting an electrical charge from coupling to coupling.

When this capability is provided by means of metallic bonding wires, not less than two (metallic) bonding wires shall be embedded in the hose and the metal used shall have a high resistance to fatigue and corrosion.

Hoses with metallic wires for electrical conductivity shall be designated 'M' and those using conductive compounds shall be designated ' Ω ', the relevant mark being branded on the hose (see clause 12).

6 Pressure requirements

For all types of hoses the following shall apply:

- a) - maximum working pressure: 16 bar
- b) - proof pressure: 24 bar
- c) - minimum bursting pressure: 48 bar

7 Dimensions and tolerances

7.1 Internal diameters and bend radii

When measured in accordance with EN ISO 4671 the internal diameter of the hose shall comply with the values given in Table 1.

When measured in accordance with EN ISO 1746 the minimum bend radii for each diameter of hose shall comply with the values given in Table 1.

Table 1 — Nominal bore, internal diameter, tolerance and bend radii

Nominal bore	Internal diameter mm	Tolerance mm	Bend radius mm
12	12,5	$\pm 0,8$	60
16	16,0		80
19	19,0		100
21	21,0	$\pm 1,25$	130
25	25,0		150
32	32,0		175
38	38,0		225
40	40,0		225

iTeh STANDARD PREVIEW
(standards.iteh.ai)

7.2 Minimum thickness of lining and cover

When measured in accordance with EN ISO 4671 the thickness of the lining shall not be less than 1,6 mm. The thickness of the cover shall not be less than 1,0 mm.

[SIST EN 1360:2005](https://standards.iteh.ai/catalog/standards/sist/5edb1a1f-d2a3-4166-a0ae-13b36d9d2741/sist-en-1360-2005)

<https://standards.iteh.ai/catalog/standards/sist/5edb1a1f-d2a3-4166-a0ae-13b36d9d2741/sist-en-1360-2005>

7.3 Concentricity

When determined in accordance with EN ISO 4671, the concentricity, based on a total indicator reading between the internal diameter and the outside surface of the cover, shall not exceed 1,0 mm.

7.4 Tolerance on cut lengths

For cut lengths, the tolerances on length shall be according to EN ISO 1307. The length of a hose assembly shall be measured from sealing face to sealing face of the end fittings with a tolerance from the nominal length of $\pm 1\%$.

8 Physical properties

8.1 Compounds

When tested in accordance with the methods in Table 2, the physical properties of the compounds used for the lining and cover shall comply with the values given in Table 2. Tests shall be carried out either on samples taken from the hose or from moulded vulcanised sheets at a thickness of 2 mm or moulded test pieces, vulcanised to the same cured state as the production hoses.

Table 2 — Physical properties of compounds

Property	Unit	Requirement		Test piece ^a	Test method
		Rubber	TPE		
Tensile strength Lining and cover, min.	MPa	9	12	Test piece cut from hose or from test sheet	ISO 37
Elongation at break Lining and cover, min.	%	250	350		
Accelerated ageing - Tensile strength change max. Lining and cover,	%	20	10		ISO 188 (air oven method) 14 days at (70 ± 1) °C
- Elongation at break change max. Lining and cover,	%	−35	−20		
Resistance to liquids	%				
Lining swell max.		+70			ISO 1817 70 h at 40 °C in oxygenated fuel type 3
		+25			ISO 1817 70 h at 100 °C in oil No 3
Lining extracted matter Normal temperature class max.		+10			ISO 1817 70 h at 40 °C in oxygenated fuel type 3 then dry 24 h at 100 °C
Lining extracted matter Low temperature class max.		+15			
Cover swell max.		+100			ISO 1817 70 h at 23 °C in Liquid B
Low temperature resistance of lining and cover at −30 °C (or −40 °C if required)	–	No cracks under × 10 magnification			Annex A
Abrasion resistance Cover compound max.	mm ³	500		Test piece from moulded test sheet of cover compound	ISO 4649 Method A

^a It is necessary that the test report indicates the source of the test piece.

8.2 Finished hose

When tested in accordance with the methods in Table 3, the physical properties of the finished hose shall comply with the values given in Table 3.

Table 3 — Physical properties of hoses

Property	Unit	Requirement	Test piece	Test method
Proof pressure at 24 bar	—	No leakage or other signs of weakness nor abrupt twisting	Full length of hose	EN ISO 1402 Proof test pressure
Burst pressure, min.	bar	48	Short length cut from hose	EN ISO 1402 Burst pressure
Volumetric expansion, max. Type 1 and Type 2 Type 3	%	2 1	At least 1 m cut from hose	EN 26801 Test pressure 3 bar
Adhesion between components on Un-aged hose, min. Aged hose, min.	N/mm	2,4 1,8	Short length cut from hose	Annex B
Ambient temperature bending	—	$\frac{T}{D} \geq 0,8$		EN ISO 1746 Nominal diameter $C = 10 \times \text{nominal bore}$
Low temperature flexibility		No cracks or breaks Maximum bending force 180 N	Annex C, Reference hose with nominal bore 16, 19 or 21	Annex C
Change in length at proof pressure	%	0 to +5	Full length of hose	EN ISO 1402
Ozone resistance of cover	—	No cracks under X 2 magnification	Short length cut from hose	EN 27326 168 h at 40 °C, 50 ppmh, relative humidity (55 ± 10) % and elongation 20 %
Fuel permeation of hose max. Normal temperature class Low temperature class	ml/(m·day)	12 18	2 m test piece cut from hose Reference hose with nominal bore 16, 19 or 21	Annex D
Electrical resistance max. Category Ω Category M	Ω	1×10^6 1×10^2	Equivalent to the length of hose assembly	EN ISO 8031 Method 3.4, 3.5 or 3.6 EN ISO 8031 Method 4

Table 3 (continued)

Property	Unit	Requirement	Test piece	Test method
Flammability	—	a) Burning with a naked flame to cease within 20 s of removal of the burner; b) no further glowing visible 2 min after removal of the burner; c) hose shall show no sign of leakage	Length of assembly to suit test rig	Annex E

8.3 Hose assembly

When tested in accordance with the methods in Table 4, the physical properties of the hose assembly shall comply with the values given in Table 4.

Table 4 — Physical properties of hose assembly

Property	Unit	Requirement	Test piece	Test method
Pull-off test	—	No movement of end fitting after removal of force	Short length of hose assembly	Annex F
Proof pressure at 24 bar	—	No leakage or other signs of weakness	Full length of hose assembly	EN ISO 1402 Proof test pressure
Electrical resistance max. Category M	Ω /assembly	1×10^2	Full length of hose assembly	EN ISO 8031 Method 4
Category Ω		1×10^6		EN ISO 8031, Method 3.4, 3.5 or 3.6
Leak test	—	No leakage	Full length of hose assembly	Annex G
Flex test	—	No defects after 18000 cycles No leakage after 50000 cycles max. electrical resistance		Annex H

9 End fittings

The following requirements shall be fulfilled:

- end fittings shall be designed for the pressure ratings according to clause 6;
- end fittings shall be designed so that, where used for their intended purpose, they do not adversely affect in-service reliability of the hose due to sharp edges or burrs;
- parallel thread
- end fittings with thread sealing (e.g. with PTFE-band) are not permitted;
- materials of the thread-bearing parts: corrosion-resistant metallic materials at the option of the manufacturer; control screw threads shall not be made from aluminium;