



Designation: ~~C126~~—~~17~~ **C126** – **18**

Standard Specification for Ceramic Glazed Structural Clay Facing Tile, Facing Brick, and Solid Masonry Units¹

This standard is issued under the fixed designation C126; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers structural clay load-bearing facing tile and facing brick and other “solid masonry units” made from clay, shale, fire-clay, or mixtures thereof, with or without the addition of grog or other mixtures, having a finish consisting of a ceramic glaze fused to the body at above 1500°F (655°C) making them inseparable, excluding natural salt-glazed ware. ~~Two grades, based on permissible variation in face dimensions, and two types are covered, as follows:~~

~~1.1.1 Grade S (select), for use with comparatively narrow mortar joints.~~

~~1.1.2 Grade SS (select sized or ground edge), for use where variation of face dimension must be very small.~~

~~1.1.3 Type I (single-faced units), for general use where only one finished face will be exposed.~~

~~1.1.4 Type II (two-faced units), for use where two opposite finished faces will be exposed.~~

1.2 The property requirements of this specification apply at the time of purchase. The use of results from testing of brick and tile extracted from masonry structures for determining conformance or nonconformance to the property requirements (Section [56](#)) of this standard is beyond the scope of this specification.

1.3 Brick and tile covered by this specification are manufactured from clay, shale, or similar naturally occurring substances and subjected to a heat treatment at elevated temperatures (firing). The heat treatment must develop sufficient fired bond between the particulate constituents to provide the strength requirements of this specification. (See firing and fired bond in Terminology [C1232](#).)

1.4 Two grades and two types of ceramic glazed units are covered.

1.5 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

1.6 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.7 The following precautionary caveat pertains only to the test portion of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.8 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

~~E67C67/C67M~~ Test Methods for Sampling and Testing Brick and Structural Clay Tile

C1232 Terminology for Masonry

E84 Test Method for Surface Burning Characteristics of Building Materials

E2105 Practice for General Techniques of Thermogravimetric Analysis (TGA) Coupled With Infrared Analysis (TGA/IR)

¹ This specification is under the jurisdiction of ASTM Committee C15 on Manufactured Masonry Units and is the direct responsibility of Subcommittee C15.02 on Brick and Structural Clay Tile.

Current edition approved Dec. 1, 2017/Dec. 1, 2018. Published January 2018/December 2018. Originally approved in 1936. Last previous edition approved in 2016/2017 as ~~C126—16~~C126 – 17. DOI: ~~10.1520/C0126-17~~10.1520/C0126-18.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

2.2 *National Fire Protection Association Standard*.³

NFPA No. 255 Test for Surface Burning Characteristics of Building Materials

2.3 *Underwriters Laboratories, Inc. Standard*.⁴

UL No. 723 Flammability Studies of Cellular Plastics and other Building Materials used for Interior Finishes

3. Terminology

3.1 *Definitions*—For definitions relating to ceramic glazed structural clay facing tile, facing brick, and solid masonry units, refer to Terminology **C1232**.

4. Classification

4.1 *Grades*—Grades classify units according to their permissible variation in face dimensions. Two grades of ceramic glazed facing tile, brick, and solid masonry units are covered. The requirements are given in Section 7.

4.1.1 *Grade S (select)*, for use with comparatively narrow mortar joints.

4.1.2 *Grade SS (select sized or ground edge)*, for use where variation of face dimension must be very small.

4.1.3 When the grade is not specified, the requirements for Grade S shall govern.

4.2 *Types*—Two types of ceramic glazed facing tile, brick, and solid masonry units are covered. The requirements are given in Section 7.

4.2.1 *Type I (single-faced units)*, for general use where only one finished face will be exposed.

4.2.2 *Type II (two-faced units)*, for use where two opposite finished faces will be exposed.

4.2.3 When the type is not specified, the requirements for Type I shall govern.

5. Ordering Information

5.1 Orders for material under this specification shall include the following information:

5.1.1 *Grade*—When the grade is not specified, the requirements for Grade S shall govern.

5.1.2 *Type*—When the type is not specified, the requirements for Type I shall govern.

5.1.3 *Sizes and Shapes*—The sizes and shapes shall be specified in accordance with Section **6-17.1**.

5.1.4 *Color and Texture of Finish*—The color and texture of the finish shall be specified in accordance with Section **7-68.6**.

5.1.5 *Back Surfaces*—Unless otherwise specified, smooth, scored, combed, or roughened unglazed backs and smooth unselected glazed backs or a mixture thereof, are furnished. When plaster is to be applied, the back surface shall be specified in accordance with Section **7-58.5**.

5.1.6 *Coring*—Unless otherwise specified, either standard or special duty units as prescribed in Section **109** are furnished.

5.1.7 *Opacity*—Where ceramic glazed units are not specified as opaque, they need not meet the requirements for opacity prescribed in **7-4.28.4.2**.

5.1.8 *Exterior Use*—Where ceramic glazed units are required for exterior use, the manufacturers shall be consulted for material suitable for this purpose.

NOTE 1—The requirements included in this specification do not cover minimum criteria for durability of units exposed to exterior environments.

6. Physical Properties

6.1 The compressive strengths (based on gross area) of the units shall be not less than the values prescribed in **Table 1**.

NOTE 2—Special duty units may be available from various manufacturers where higher compressive strengths are required.

7. Dimensions and Permissible Variations

7.1 The face sizes of ceramic glazed units and fittings therefore shall be as specified.

NOTE 3—The sizes shown in **Table 2** are standard in the industry for single-faced units (Type I).

7.2 *Face Dimension Tolerances*—The total variation in the finished face dimensions of units shall be not more than the values shown in **Table 3**.

TABLE 1 Compressive Strengths of Units

| Direction of Coring | Minimum Average of Five Tests, psi (MPa) | Individual Minimum, psi (MPa) |
|---------------------|--|-------------------------------|
| Vertical | 3 000 (20.7) | 2 500 (17.2) |
| Horizontal | 2 000 (13.8) | 1 500 (10.3) |

³ Available from National Fire Protection Association (NFPA), 1 Batterymarch Park, Quincy, MA 02169-7471, <http://www.nfpa.org>.

⁴ Available from Underwriters Laboratories (UL), 333 Pfingsten Rd., Northbrook, IL 60062-2096, <http://www.ul.com>.

TABLE 2 Size of Single-Faced Units

| Series Designation | Specified Face Dimensions | | Specified Thickness, in. (mm) |
|--------------------|---------------------------|------------------|---|
| | Height, in. (mm) | Length, in. (mm) | |
| 4S | 2¼ (57.2) | 7⅝ (193.7) | 1¾, 3⅝, 5⅝, or 7⅝ (44.5, 92.1, 142.9, or 193.7) |
| 4W | 7⅝ (193.7) | 7⅝ (193.7) | 1¾, 3⅝, 5⅝, or 7⅝ (44.5, 92.1, 142.9, or 193.7) |
| 6P | 3⅝ (92.1) | 11⅝ (295.3) | 1¾, 3⅝, 5⅝, or 7⅝ (44.5, 92.1, 142.9, or 193.7) |
| 6T | 5 (127) | 11⅞ (296.9) | 1¾, 3⅝, 5⅝, or 7⅝ (44.5, 92.1, 142.9, or 193.7) |
| 8W | 7⅝ (193.7) | 15⅝ (396.9) | 1¾, 3⅝, 5⅝, or 7⅝ (44.5, 92.1, 142.9, or 193.7) |

TABLE 3 Permissible Variations in Face Dimensions

NOTE 1—Permissible variations for units having specified dimensions more than ¼ in. (6.4 mm) greater than shown in this table shall be the same as for the next larger dimension.

| Specified Face Dimension, Return or Reveal (Height, Length), in. (mm) | Maximum Difference Between Dimension of Any Unit and the Specified Dimension | | Maximum Difference Between Largest and Smallest Unit in One Lot, ^A in. (mm) |
|---|--|----------------------|--|
| | If Larger, in. (mm) | If Smaller, in. (mm) | |
| Grade S Units | | | |
| 6 (152.4) and Under | ⅛ (1.6) | ⅜ (2.4) | ⅜ (2.4) |
| Over 6 to 8 (152.4 to 203.2) | ⅛ (1.6) | ½ (3.2) | ⅝ (4.0) |
| Over 8 to 16 (203.2 to 406.4) | ⅛ (1.6) | ⅝ (4.0) | ⅜ (4.8) |
| Grade SS—Select Sized or Ground-Edge Units Only | | | |
| Any dimension | ⅛ (1.6) | ⅛ (1.6) | ⅛ (3.2) |

^ASize of lot shall be determined by agreement between the purchaser and the seller.

7.3 *Bed-Depth Dimension Tolerances*—The total variation in the bed-depth (through the wall) dimension of units shall be not more than the value shown in **Table 4**.

7.4 *Warpage Tolerances*—The maximum permissible deviation of the plane and the edges of the face of individual units from a plane surface and from a straight line, respectively, shall not exceed the value shown in **Table 5**.

NOTE 4—When convex units are laid upon a plane surface, the apparent variation is greater than the actual variation from the plane of the unit.

<https://standards.iteh.ai/catalog/standards/sist/0a6d7890-75a5-436d-9da8-e16e4881e8c9/astm-c126-18>

TABLE 4 Permissible Variation in Bed Depth Dimensions

NOTE 1—Permissible variations for units having specified dimensions more than ¼ in. (6.4 mm) greater than shown in this table shall be the same as for the next larger dimension.

NOTE 2—Variation in the bed depth of individual units is controlled by the limitations on warpage. The thickness of a unit shall be considered either the maximum or minimum thickness, whichever is the farther from the specified dimension.

| Specified Bed Depth Dimension (Wall Thickness), in. (mm) | Maximum Difference Between Dimension of Any Unit and the Specified Dimension | | Maximum Difference Between Largest and Smallest Unit in One Lot, in. (mm) ^A |
|--|--|----------------------|--|
| | If Larger, in. (mm) | If Smaller, in. (mm) | |
| Type I—Single-Faced Units | | | |
| 2 (50.8) and Under | ⅛ (3.2) | ⅛ (3.2) | ⅛ (3.2) |
| Over 2 to 4 (50.8 to 101.6) | ⅛ (3.2) | ⅜ (4.7) | ⅜ (4.7) |
| Over 4 to 6 (101.6 to 152.4) | ⅛ (3.2) | ¼ (6.4) | ¼ (6.4) |
| Over 6 to 8 (152.4 to 203.2) | ⅛ (3.2) | ⅝ (7.9) | ⅝ (7.9) |
| Type II—Two-Faced Units | | | |
| 8 (203.2) and Under | ⅛ (3.2) | ⅛ (3.2) | ⅛ (3.2) |

^ASize of lot shall be determined by agreement between the purchaser and the seller.