

Designation: D3251 - 04 (Reapproved 2013) D3251 - 19

Standard Test Method for Thermal Endurance Characteristics of Electrical Insulating Varnishes Applied Over Film-Insulated Magnet Wire¹

This standard is issued under the fixed designation D3251; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope-Scope*

- 1.1 This test method covers the determination of the thermal endurance characteristics of electrical insulating varnishes and film-insulated magnet wire in combination.
 - 1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.
- 1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety safety, health, and health environmental practices and determine the applicability of regulatory limitations prior to use.

Note 1—This test method is equivalent to IEC 60172.

1.4 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

2. Referenced Documents

2.1 ASTM Standards:²

D115 Test Methods for Testing Solvent Containing Varnishes Used for Electrical Insulation

D1711 Terminology Relating to Electrical Insulation

D2307 Test Method for Thermal Endurance of Film-Insulated Round Magnet Wire

2.2 IEC Standard:

IEC 60172 Test Procedure for the determination of the temperature index of enameled winding wires³

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms used in this test method refer to Terminology D1711.

4. Summary of Test Method

4.1 A varnish is applied to twisted pairs of film-insulated magnet wire and exposed to elevated temperatures. Life test results are compared to those of unvarnished twisted pairs.

5. Significance and Use

- 5.1 Different combinations of varnishes and film-insulated magnet wire behave differently when exposed to elevated temperatures. This includes different varnishes tested with the same film-insulated magnet wire and a single varnish tested with different film-insulated magnet wire.
- 5.2 This test method is used to determine the effect on the electrical properties of a varnish applied to film-insulated magnet wire when the combination is exposed to prescribed elevated temperatures.

¹ This test method is under the jurisdiction of ASTM Committee D09 on Electrical and Electronic Insulating Materials and is the direct responsibility of Subcommittee D09.01 on Electrical Insulating Varnishes, Powders and Encapsulating Compounds Products.

Current edition approved April 1, 2013Jan. 1, 2019. Published April 2013January 2019. Originally approved in 1973. Last previous edition approved in 20092013 as D3251 – 04 (2009),(2013). DOI: 10.1520/D3251-04R13.10.1520/D3251-19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Association, 25 W. 43rd St., 4th Floor, New York, NY 10036.