



Designation: D6531 – 00 (Reapproved 2019)

Standard Test Method for Relative Tinting Strength of Aqueous Ink Systems by Instrumental Measurement¹

This standard is issued under the fixed designation D6531; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the procedure for determining the relative tinting strength of waterbased ink systems using a computer-aided spectrophotometer.

1.2 This test method is applicable to waterbased printing inks and bases to be used primarily in flexographic and gravure printing applications.

1.3 This test method applies only to single, non-fluorescent pigmented colors and black ink systems for which there is a reference standard containing a pigment of the identical color index name and number.

1.4 The procedure in this test method specifies placing tinted samples in a cuvette for spectrophotometric measurements. The use of thick wet drawdowns as in Test Methods D2066 are inappropriate due to severe floating problems with aqueous systems.

1.5 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.7 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.56 on Printing Inks.

Current edition approved Jan. 1, 2019. Published January 2019. Originally approved in 2000. Last previous edition approved in 2010 as D6531 – 00 (2010). DOI: 10.1520/D6531-00R19.

2. Referenced Documents

2.1 *ASTM Standards:*²

D2066 Test Methods for Relative Tinting Strength of Paste-Type Printing Ink Dispersions

D2244 Practice for Calculation of Color Tolerances and Color Differences from Instrumentally Measured Color Coordinates

E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

E1331 Test Method for Reflectance Factor and Color by Spectrophotometry Using Hemispherical Geometry

E1347 Test Method for Color and Color-Difference Measurement by Tristimulus Colorimetry

E1349 Test Method for Reflectance Factor and Color by Spectrophotometry Using Bidirectional (45°:0° or 0°:45°) Geometry

3. Terminology

3.1 Definitions related to color differences are covered in Practice D2244. The definitions of tinting strength terms are given in Test Methods D2066.

4. Summary of Test Method

4.1 A standard and unknown samples are each reduced to the same concentration in a white tinting base then dispersed on a paint shaker.

4.2 The dispersed samples are transferred to cuvettes for reflectance measurements on a spectrophotometer. Hue and strength relative to the standard tint are computed.

NOTE 1—The hue readings indicate the closeness of the unknown sample to that of the standard.

5. Significance and Use

5.1 Tinting strength is an essential property of printing ink dispersions. Although results on bulk tints do not guarantee

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.