



Designation: B830 – 18

Standard Specification for Uniform Test Methods and Frequency¹

This standard is issued under the fixed designation B830; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers a standard basis for uniform testing and frequency to determine physical and electrical compliance for aluminum and copper drawing stock, and aluminum and copper conductors.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.2.1 *Exception*—Resistivity is measured in SI units.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 The following documents, of the date issued, form a part of this specification to the extent referenced herein.

2.2 *ASTM Standards*:²

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

2.3 *National Bureau of Standards*:³

NBS Handbook 100—Copper Wire Tables

2.4 *ANSI Standards*:⁴

ANSI/ISO/ASQ 9001-2015 Quality Management Systems—Requirements

ANSI/ISO/ASQ Q9004-2009 Managing for the Sustained

Success of an Organization—A Quality Management Approach⁵

ANSI/ASQC S1-2012 An Attribute Skip-Lot Sampling Program

ANSI/ASQ Z1.4-2003 (R2013) Sampling Procedures and Tables for Inspection by Attributes

3. Terminology

3.1 *Definitions of Terms Specific to This Standard*:

3.1.1 *acceptable quality level (AQL)*—the maximum percent nonconforming (or the maximum number of nonconformities per hundred units) that, for purposes of sampling inspection, can be considered as a process average.

3.1.2 *average outgoing quality (AOQ)*—the average quality of outgoing product, including all accepted lots or batches, plus all lots or batches not accepted after such lots or batches have been effectively 100 % inspected and all nonconforming units replaced by conforming units.

3.1.3 *CPK*—Process Performance Index.

Discussion:

Capability in Relation to Spec Mean:

USL	=	5.0
LSL	=	1.0
MEAN	=	2.0
Standard deviation (σ)	=	0.5

CPK tells the capability of a process based upon the worst case view of the data.

The equation is:

CPK = the lesser of:

$$\frac{(USL - MEAN)}{3\sigma} \text{ or } \frac{(MEAN - LSL)}{3\sigma} \tag{1}$$

For example:

$$\begin{aligned}
 CPK &= \frac{(5.0 - 2.0)}{1.5} \text{ or } \frac{(2.0 - 1.0)}{1.5} \tag{2} \\
 &= 2.0 \text{ or } 0.67 \\
 &= 0.67
 \end{aligned}$$

A negative value for CPK indicates that the mean is outside the specification limits. A CPK of zero indicates that the mean is equal to one of the specification limits. A CPK between 0 and 1.0 means that part of the 6 sigma limits falls

¹ This specification is under the jurisdiction of ASTM Committee B01 on Electrical Conductors and is the direct responsibility of Subcommittee B01.02 on Methods of Test and Sampling Procedure.

Current edition approved June 15, 2018. Published January 2019. Originally approved in 1993. Last previous edition approved in 2011 as B830 – 11. DOI: 10.1520/B0830-18.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from National Technical Information Service (NTIS), 5301 Shawnee Rd., Alexandria, VA 22312, http://www.ntis.gov.

⁴ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

⁵ This ANSI standard is an identical adoption of ISO 9001:2015 and the text does not differ in any way from ISO 9001:2015.

outside the specification limits. A CPK of 1.0 means that one end of the 6 sigma limits falls on a specification limit. A CPK larger than 1.0 means that the 6 sigma limits fall completely within the specification limits. See Explanatory **Note 1** for an example interpretation of CPK values and actions to follow.

Capability indices are useful tools in the analysis of capability data. The most useful index is CPK, since it formulates capability in a manner that relates to shifts in the mean of the distribution away from the midpoint.

3.1.4 *lot*—a group of production units of one type and size of wire, which were produced during the same time period under similar production conditions, and are presented for acceptance at the same time. The mass will be defined in the ASTM document for the specific product to be tested.

3.1.5 *process average*—the average percent nonconforming or average number of nonconformities per hundred units (whichever is applicable) of product submitted by the supplier for original inspection. Original inspection is the first inspection of a particular quantity of product as distinguished from the inspection of product that has been resubmitted after prior rejection. When double or multiple sampling is used, only the first sample results shall be included in the process average calculation.

3.1.6 *production unit*—a coil, reel, spool, or other package of drawing stock/wire that represents a single usable length.

3.1.7 *sample*—the production unit or units from which a test specimen or specimens have been removed and which are considered to have properties representative of the lot.

3.1.8 *specimen*—a length of drawing stock/wire removed for test purposes.

4. Methods for Ensuring Product Compliance

4.1 Acceptance Sampling:

4.1.1 When acceptance sampling is used, statistical sampling of each lot shall be presented for inspection in accordance with ANSI/ASQ Z1.4-2003 (R2013). Sampling of each lot shall be presented for normal inspection in accordance with the sampling system described by ANSI/ASQ Z1.4-2003 (R2013).

4.1.2 Diameter and tensile shall be tested using General Inspection Level 1 with an AQL (acceptable quality level) of 4.0 %. (See **Table 1**.)

4.1.3 Resistivity shall be tested using Special Inspection Level S-4 with an AQL of 4.0 %. (See **Table 2**.)

4.1.4 All other material properties shall be tested per the specific level and AQL in ANSI/ASQ Z1.4-2003 (R2013) as required in the ASTM specification for the specific product.

4.1.5 Test records shall meet the requirements of ANSI/ASQ 9001-2015, Section 7.5.1.

4.2 Conformance Criteria:

4.2.1 Failure of a specimen to conform to the applicable requirements of ASTM shall constitute failure of the production unit from which the specimen was taken. Sampling of each lot shall be switched according to the rules described in ANSI/ASQ Z1.4-2003 (R2013). (See **Fig. 1**.)

4.2.2 Any lot of drawing stock/wire that has been sampled in accordance with 4.1.2, 4.1.3, or 4.1.4, and from which the number of specimens failing to comply with the requirements does not equal or exceed the appropriate reject number of the sampling **Table 1** used, shall be considered as complying with the requirements of ASTM.

4.2.3 Rejected lots may be screened to remove nonconforming production units by testing one specimen from each production unit in the lot for the failing characteristic.

4.2.4 *Sample Size*—The sample size shall be the number of production units selected.

4.3 Provisions for Skip-lot Inspection:

4.3.1 When reduced inspection is in effect (see 4.2), skip-lot inspection shall be allowed when the preceding ten lots have been accepted in accordance with ANSI/ASQ Z1.4-2003 (R2013). Skip-lot testing shall be in accordance with ANSI/ASQC S1-2012.

4.3.2 When skip-lot inspection is in effect, normal inspection (see 4.1) shall be instituted if any lot is found unacceptable.

4.4 When skip-lot inspection (see 4.3) is in effect, and the preceding ten inspected lots have been accepted, audit inspection shall be instituted by the manufacturer in accordance with the following statistical process control (SPC) program requirements.

4.4.1 CPK >1.0 for 10 lots in control with less than 2 out-of-control indications.

TABLE 1 Sampling for Diameter and Tensile Properties Except Joints

NOTE 1—This sampling plan was taken from ANSI/ASQ Z1.4-2003 (R2013). General Inspection Level I, normal sampling was used, with an AQL (Acceptance Quality Level) of 4.0 %.

Number of Units in Lot	Sample	Sample Size	Cumulative Sample Size	Acceptance Number	Reject Number
1 to 3	first ^A	all	all	0	1
4 to 90	first ^A	3	3	0	1
91 to 280	first	8	8	0	2
	second	8	16	1	2
281 to 500	first	13	13	0	3
	second	13	26	3	4
501 to 1200	first	20	20	1	4
	second	20	40	4	5

^A Single sampling only.