

# INTERNATIONAL STANDARD

## NORME INTERNATIONALE

Optical fibres – **iTeh STANDARD PREVIEW**  
Part 2: Product specifications – General  
(standards.iteh.ai)

Fibres optiques –  
Partie 2: Spécifications de produits – Généralités  
<https://standards.iteh.ai/catalog/standards/sist/c762cde8-904e-4af6-85f2-f611bf43e17d/iec-60793-2-2019>



## THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2019 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office  
3, rue de Varembe  
CH-1211 Geneva 20  
Switzerland

Tel.: +41 22 919 02 11  
[info@iec.ch](mailto:info@iec.ch)  
[www.iec.ch](http://www.iec.ch)

### About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

### About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

#### IEC publications search - [webstore.iec.ch/advsearchform](http://webstore.iec.ch/advsearchform)

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

#### IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

#### IEC Customer Service Centre - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: [sales@iec.ch](mailto:sales@iec.ch).

#### Electropedia - [www.electropedia.org](http://www.electropedia.org)

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

#### IEC Glossary - [std.iec.ch/glossary](http://std.iec.ch/glossary)

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

### A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

### A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

#### Recherche de publications IEC -

[webstore.iec.ch/advsearchform](http://webstore.iec.ch/advsearchform)

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études,...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

#### IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

#### Service Clients - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: [sales@iec.ch](mailto:sales@iec.ch).

#### Electropedia - [www.electropedia.org](http://www.electropedia.org)

Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 000 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 16 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

#### Glossaire IEC - [std.iec.ch/glossary](http://std.iec.ch/glossary)

67 000 entrées terminologiques électrotechniques, en anglais et en français, extraites des articles Termes et Définitions des publications IEC parues depuis 2002. Plus certaines entrées antérieures extraites des publications des CE 37, 77, 86 et CISPR de l'IEC.



## CONTENTS

FOREWORD .....	3
1 Scope .....	5
2 Normative references .....	6
3 Terms and definitions .....	6
4 Quality assurance .....	7
5 Construction of optical fibres .....	7
5.1 Class A – Multimode fibres .....	7
5.2 Class B – Single-mode fibres .....	9
5.3 Class C – Single-mode fibres for intraconnection .....	10
5.4 Class D – Polarization-maintaining fibres .....	11
6 General requirements .....	11
6.1 Coating .....	11
6.2 Interface with the coating .....	11
6.3 Colours of the coating .....	12
Annex A (normative) Existing multimode fibres .....	13
Annex B (normative) Existing single-mode fibres .....	14
B.1 Existing single-mode fibres .....	14
B.2 Existing fibres for intraconnection .....	15
B.3 Existing polarization-maintaining fibres .....	15
Bibliography .....	16
<p style="text-align: center;"><a href="https://standards.iteh.ai/catalog/standards/sist/e762ede8-904e-4af6-85f2-161fb43e17d/iec-60793-2-2019">https://standards.iteh.ai/catalog/standards/sist/e762ede8-904e-4af6-85f2-161fb43e17d/iec-60793-2-2019</a></p>	
Table 1 – Sectional specifications .....	5
Table 2 – Main categories of multimode fibres .....	8
Table 3 – Sub-categories of multimode fibres .....	8
Table 4 – Categories of glass core/glass clad single-mode fibres .....	10
Table 5 – Categories of glass core/glass clad single-mode fibres for intraconnection .....	11
Table 6 – Categories of glass core/glass clad polarization-maintaining fibres .....	11
Table A.1 – Existing multimode fibres .....	13
Table B.1 – Existing single-mode fibres .....	14
Table B.2 – Existing fibres for intraconnection .....	15
Table B.3 – Existing polarization-maintaining fibres .....	15

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

## OPTICAL FIBRES –

**Part 2: Product specifications –  
General**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60793-2 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This ninth edition cancels and replaces the eighth edition published in 2015. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) introduction of the revised fibre designations for most A1 sub-category fibres and all class B single-mode fibres;
- b) addition of the new fibre model (A1-OM5) defined for A1 category;
- c) addition of class D polarization maintaining fibres.

This document is to be read in conjunction with those parts of the IEC 60793-1 series that address individual measurements and tests for attributes of optical fibres.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
86A/1964/FDIS	86A/1974/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60793 series, published under the general title *Optical fibres*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

**ITeH STANDARD PREVIEW**  
**(standards.iteh.ai)**

IEC 60793-2:2019  
<https://standards.iteh.ai/catalog/standards/sist/e762ede8-904e-4af6-85f2-f611bf43e17d/iec-60793-2-2019>

## OPTICAL FIBRES –

### Part 2: Product specifications – General

#### 1 Scope

This part of IEC 60793 contains the general specifications for both multimode and single-mode optical fibres.

Sectional specifications for each of the four categories of multimode fibres: A1, A2, A3, and A4 (part of the multimode fibre class A) contain requirements specific to each category.

Sectional specifications for each of the three single-mode fibre classes, B, C and D contain requirements common to each class.

Each sectional specification includes family specifications (in normative annexes) that contain requirements for the applicable category or sub-categories. These sub-categories are distinguished on the basis of different fibre types or applications.

The requirements of this document apply to all classes.

Each sectional specification contains the requirements that are common to all the family specifications that are within it. These common requirements are copied to the family specification for ease of reference.

Tests or measurement methods are defined for each specified attribute. Where possible, these definitions are by reference to an IEC International Standard (see IEC 60793-1 series) – otherwise the test or measurement method is outlined in the relevant sectional specification.

Table 1 defines the sectional specifications. The relevant family specifications are defined within the sectional specifications as normative annexes (see Tables 2 to 5).

Annexes A and B summarize the existing fibre specifications.

**Table 1 – Sectional specifications**

Document ID	Fibre category/class	Cladding material	Core material	Index profile
IEC 60793-2-10	A1 multimode	Glass	Glass	Graded
IEC 60793-2-20	A2 multimode	Glass	Glass	Quasi-step or step
IEC 60793-2-30	A3 multimode	Plastic	Glass	Step or graded (under consideration)
IEC 60793-2-40	A4 multimode	Plastic	Plastic	Step, multi-step or graded
IEC 60793-2-50	B single-mode	Glass	Glass	Not applicable
IEC 60793-2-60	C single-mode	Glass	Glass	Not applicable
IEC 60793-2-70	D polarization-maintaining	Glass	Glass	Not applicable

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60304, *Standard colours for insulation for low-frequency cables and wires*

IEC 60793-1 (all parts), *Optical fibres – Part 1: Measurement methods and test procedures*

IEC 60793-2-10:2019, *Optical fibres – Part 2-10: Product specifications – Sectional specification for category A1 multimode fibres*

IEC 60793-2-20:2015, *Optical fibres – Part 2-20: Product specifications – Sectional specification for category A2 multimode fibres*

IEC 60793-2-30:2015, *Optical fibres – Part 2-30: Product specifications – Sectional specification for category A3 multimode fibres*

IEC 60793-2-40:2015, *Optical fibres – Part 2-40: Product specifications – Sectional specification for category A4 multimode fibres*

IEC 60793-2-50:2018, *Optical fibres – Part 2-50: Product specifications – Sectional specification for class B single-mode fibres*

IEC 60793-2-60:2008, *Optical fibres – Part 2-60: Product specifications – Sectional specification for category C single-mode intraconnection fibres*

IEC 60793-2-70:2017, *Optical fibres – Part 2-70: Product specifications – Sectional specification for polarization-maintaining fibres*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 3.1

#### **multimode fibre**

optical fibre in the core of which the radiation of two or more bound modes can propagate at the wavelength of interest

[SOURCE: IEC 60050-731:1991, 731-02-03]

### 3.2

#### **single-mode fibre**

optical fibre in which the radiation of only one bound mode can propagate at the wavelength of interest

[SOURCE: IEC 60050-731:1991, 731-02-02, modified – Note deleted.]



**3.3****core**

central region of an optical fibre through which most of the optical power is transmitted

[SOURCE: IEC 60050-731:1991, 731-02-04]

**3.4****cladding**

dielectric material of an optical fibre surrounding the core

[SOURCE: IEC 60050-731:1991, 731-02-05]

**3.5****primary coating**

thin coating applied directly to the cladding, usually at the time of the fibre drawing, in one or more layers, to preserve integrity of the cladding surface

Note 1 to entry A secondary coating may be applied directly to the primary coating of one or more fibres, to reinforce the protection of the optical fibre during handling and cabling.

[SOURCE: IEC 60050-731:1991, 731-02-57, modified – The wording "usually at the time of the fibre drawing, in one or more layers," and Note 1 have been added.]

**3.6****fibre buffer**

material or assembly of materials used to protect the optical fibre against physical damage

[SOURCE: IEC 60050-731:1991, 731-02-56]

**3.7****coloured coating**

thin coating applied on the primary coating or on the secondary coating in order to make each fibre distinguishable by its colour

**3.8****coloured buffer**

buffer applied on the primary coating and/or secondary coating in order to make each fibre distinguishable by its colour

**4 Quality assurance**

It is the responsibility of the supplier to establish quality assurance by quality control procedures which ensures that the product meets the requirements of this document and the related sectional specifications and family specifications. It is not intended that a complete testing programme be carried out on every length of fibre. When the customer wishes to specify acceptance tests or other quality procedures, it is essential that an agreement be reached between the supplier and the customer at the time of ordering.

**5 Construction of optical fibres****5.1 Class A – Multimode fibres**

The main fibre categories are based on  $g$ , the refractive index profile parameter, see Table 2.

The normalized index profile is expressed as:

$$\delta(x) = 1 - x^g \quad (1)$$

where

$$\delta(x) = \frac{n(x) - n(1)}{n(0) - n(1)} \quad (2)$$

$$x = \frac{r}{a} \quad (0 \leq r \leq a) \text{ is the normalized radial position;} \quad (3)$$

$a$  is the core radius;

$n(x)$  is the refractive index at normalized position  $x$ .

**Table 2 – Main categories of multimode fibres**

Category	Material	Type	Limits
<b>A1</b>	Glass core/glass cladding	Graded index fibre	$1 \leq g < 3$
<b>A2</b>	Glass core/glass cladding	Step and quasi-step index fibre	$3 \leq g < \infty$
<b>A3</b>	Glass core/plastic cladding	Step index fibre or graded index fibre (under consideration)	$10 \leq g < \infty$ $1 \leq g \leq 3$
<b>A4</b>	Plastic core/plastic cladding	Step, multi-step, or graded index fibre	$1 \leq g < \infty$

NOTE Attention is drawn to the index profile as stated in the detail specification. The fibre category is determined on the basis of the material type and the  $g$  value which best fits the normalized refractive index profile, falling within the category defined above.

IEC 60793-2:2019

<https://standards.iteh.ai/catalog/standards/sist/e762ede8-904e-4af6-85f2-81b1bf23e745/iec-60793-2-2019>

A further differentiation of sub-categories (and models) inside the main categories is given in Table 3.

**Table 3 – Sub-categories of multimode fibres**

Category	Sub-category	Model	Nominal core diameter $\mu\text{m}$	Nominal cladding diameter $\mu\text{m}$	Nominal coating diameter $\mu\text{m}$	Nominal numerical aperture ( $NA_{ff}$ )
<b>A1</b>						
	A1-OM2	A1-OM2a (traditional macrobend loss)	50	125	245	0,20
		A1-OM2b (enhanced macrobend loss)				
	A1-OM3	A1-OM3a (traditional macrobend loss)				
		A1-OM3b (enhanced macrobend loss)				
	A1-OM4	A1-OM4a (traditional macrobend loss)				
		A1-OM4b (enhanced macrobend loss)				
	A1-OM5	A1-OM5a (traditional macrobend loss)				
		A1-OM5b (enhanced macrobend loss)				
	A1-OM1		62,5	125	245	0,275

Category	Sub-category	Model	Nominal core diameter $\mu\text{m}$	Nominal cladding diameter $\mu\text{m}$	Nominal coating diameter $\mu\text{m}$	Nominal numerical aperture ( $\text{NA}_{\text{ff}}$ )
	A1d		100	140	245	0,26 or 0,29
<b>A2</b>						
	A2a		100	140	NS	0,23 or 0,26
	A2b		200	240	NS	0,23 or 0,26
	A2c		200	280	NS	0,23 or 0,26
<b>A3</b>						
	A3a		200	300	900	0,40
	A3b		200	380	600	0,40
	A3c		200	230	500	0,40
	A3d		200	230	500	0,35
	A3e		200	230	500	0,37
	A3f		50	230	500	0,20
	A3g		62,5	230	500	0,275
<b>A4</b>						
	A4a	A4a.1	NS	1 000	NA	(A4a.1): 0,50
		A4a.2				(A4a.2): 0,485
	A4b		NS	750	NA	0,50
	A4c		NS	500	NA	0,50
	A4d		NS	1 000	NA	0,30
	A4e		$\geq 500$	750	NA	0,25
	A4f		200	490	NA	0,19
	A4g		120	490	NA	0,19
	A4h		62,5	245	NA	0,19
NOTE 1 NA = not applicable; NS = not specified.						
NOTE 2 All five A1-OMx sub-categories indicated differ in bandwidth (or DMD) requirements.						
NOTE 3 Most A1 sub-categories have been changed in terms of fibre designation, starting from IEC 60793-2-10:2019 (edition 7). See Table 1 of IEC 60793-2-10:2019 for cross-references to former fibre designations.						

## 5.2 Class B – Single-mode fibres

The categories of single-mode fibres currently in use are given in Table 4.

**Table 4 – Categories of glass core/glass clad single-mode fibres**

Category	Type	Description
<b>B-652</b>	Dispersion unshifted	Dispersion unshifted single-mode fibre.  Two sub-categories are recognized: B-652.B is optimised for use in the 1 310 nm region but can be used in the 1 550 nm and 1 625 nm regions. Depending on link length and bit rates, dispersion may need accommodation in the 1 550 nm region.  B-652.D can be used over the extended wavelength range from 1 260 nm up to 1 625 nm. Chromatic dispersion in this band may impose requirements either on the maximum link length or the need for accommodation.
<b>B-653</b>	Dispersion shifted	This dispersion-shifted single-mode fibre is optimised for single-channel transmission in the 1 550 nm region. Multiple channels can only be transmitted if care is taken to avoid the effects of four-wave mixing by, for example, moderating the power levels or appropriate spacing or placement of the channels.  Two sub-categories are recognized (B-653.A and B-653.B) differing in chromatic dispersion characteristics.
<b>B-654</b>	Cut-off shifted	This category of dispersion unshifted single-mode fibre is optimised for low loss in the 1 550 nm region.  Five sub-categories are recognized (B-654.A, B-654.B, B-654.C, B-654.D and B-654.E) differing in chromatic dispersion and mode field characteristics.
<b>B-655</b>	Non-zero dispersion shifted	This dispersion-shifted single-mode fibre is optimised for multiple channel transmission in the 1 550 nm region. The dispersion coefficient is required to be non-zero throughout the band from 1 530 nm to 1 565 nm, but may be either positive or negative. Depending on the dispersion characteristics, multiple channel transmission may be possible at bands either above or below the normal 1 550 nm region. Three sub-categories are recognized (B-655.C, B-655.D and B-655.E), differing in chromatic dispersion characteristics.
<b>B-656</b>	Wideband non-zero dispersion-shifted	This wideband non-zero dispersion-shifted single-mode fibre is optimised for multiple channel transmission in the wavelength range of 1 460 nm to 1 625 nm with the positive value of the chromatic dispersion coefficient that is greater than some non-zero value. This fibre can be used for both CWDM and DWDM systems throughout the wavelength region between 1 460 nm and 1 625 nm.
<b>B-657</b>	Bending loss insensitive	This category of single-mode fibre is optimised for improved bending performance.  Four sub-categories are recognized: B-657.A1 and B-657.A2 fibres are a subset of category B-652.D fibres and therefore are compliant with B-652.D fibres and have the same transmission properties. Sub-category B-657.A1 fibres are appropriate for a minimum bend radius of 10 mm; sub-category B-657.A2 fibres for a minimum bend radius of 7,5 mm.  B-657.B2 and B-657.B3 fibres are intended to be used for restricted distances (less than 1 000 m) at the end of access networks, in particular inside buildings or near buildings (e.g. outside building riser cabling). Application length of B-657.B fibre, however, depends on the deployment strategy of each network operator. Sub-category B-657.B fibres are not necessarily compliant with category B-652.D fibres in terms of chromatic dispersion coefficient specifications. These fibres, however, are system compatible with B-657.A (and B-652.D) fibres in access networks. Sub-category B-657.B2 fibres are appropriate for a minimum bend radius of 7,5 mm; sub category B-657.B3 fibres for a minimum bend radius of 5 mm.
NOTE The Class B categories have been changed in fibre designation, starting from IEC 60793-2-50:2018 (edition 6). See Table 1 of IEC 60793-2-50:2018 for cross-references to former fibre designations.		

### 5.3 Class C – Single-mode fibres for intraconnection

The categories of single-mode fibres for intraconnection currently in use are given in Table 5.