
Katodna zaščita za plavajoče jeklene priobalne konstrukcije

Cathodic protection for steel offshore floating structures

Kathodischer Korrosionsschutz für schwimmende Offshore-Anlagen aus Stahl

Protection cathodique des structures en acier flottant en mer

Ta slovenski standard je istoveten z: EN 13173:2001[SIST EN 13173:2003](https://standards.iteh.ai/catalog/standards/sist/ac728662-4cb0-4eaf-84da-bc9408aa4a64/sist-en-13173-2003)<https://standards.iteh.ai/catalog/standards/sist/ac728662-4cb0-4eaf-84da-bc9408aa4a64/sist-en-13173-2003>**ICS:**

25.220.40	Kovinske prevleke	Metallic coatings
47.020.01	Splošni standardi v zvezi z ladjedelništvom in konstrukcijami na morju	General standards related to shipbuilding and marine structures

SIST EN 13173:2003**en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13173:2003

<https://standards.iteh.ai/catalog/standards/sist/ac728662-4cb0-4eaf-84da-bc9408aa4a64/sist-en-13173-2003>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 13173

January 2001

ICS 47.020.01; 77.060

English version

Cathodic protection for steel offshore floating structures

Protection cathodique des structures en acier flottant en
mer

Kathodischer Korrosionsschutz für schwimmende Offshore-
Anlagen aus Stahl

This European Standard was approved by CEN on 6 July 2000.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

(standards.iteh.ai)

SIST EN 13173:2003

<https://standards.iteh.ai/catalog/standards/sist/ac728662-4cb0-4eaf-84da-bc9408aa4a64/sist-en-13173-2003>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Foreword.....	4
Introduction	4
1 Scope	5
1.1 Structures	5
1.2 Materials.....	5
1.3 Environment	5
1.4 Safety and environment protection.....	6
2 Normative references	6
3 Terms and definitions.....	6
4 Design basis.....	7
4.1 Objectives	7
4.2 Cathodic protection criteria	7
4.3 Design parameters.....	7
4.4 Electrical current demand	8
4.5 Cathodic protection systems.....	10
4.6 Electrical continuity	11
4.7 Interactions.....	11
5 Impressed current system design.....	11
5.1 Objectives	11
5.2 Design considerations.....	12
5.3 Equipment considerations	12
6 Galvanic anode system design.....	14
6.1 Objectives	14
6.2 Design considerations.....	14
6.3 Factors determining the anode current output and operating life.....	15
6.4 Location of anodes	16

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13173:2003

<https://standards.iteh.ai/catalog/standards/sist/ac728662-4cb0-4eaf-84da-bc9408aa4a04/sist-en-13173-2003>

7 Cathodic protection system monitoring	16
7.1 Objectives	16
7.2 Potential measurements	16
7.3 Measurement of the impressed current anode electrical current output	17
7.4 Impressed current power source control	17
7.5 Additional monitoring methods	17
8 Documentation	18
8.1 Objectives	18
8.2 Impressed current system	18
8.3 Galvanic anode systems	19
Annex A (informative) Guidance for current requirements for cathodic protection of offshore floating structures	20
Annex B (informative) Anode resistance and life determination	21
Annex C (informative) Typical electrochemical characteristics of impressed current anodes	23
Annex D (informative) Typical cofferdam arrangements	24

SIST EN 13173:2003

<https://standards.iteh.ai/catalog/standards/sist/ac728662-4cb0-4eaf-84da-bc9408aa4a64/sist-en-13173-2003>

Foreword

This European Standard has been prepared by Technical Committee CEN/TC 219 "Cathodic protection", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2001, and conflicting national standards shall be withdrawn at the latest by July 2001.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13173:2003

<https://standards.iteh.ai/catalog/standards/sist/ac728662-4cb0-4eaf-84da-bc9408aa4a64/sist-en-13173-2003>

Introduction

Cathodic protection is usually applied, mostly as a complement to protective coating or paint, to protect the external surfaces of steel offshore floating structures and appurtenances from corrosion due to sea water or saline mud.

Cathodic protection works by supplying sufficient direct current to the immersed surface of the structure in order to change the steel to electrolyte potential to values where corrosion is insignificant.

The general principles of cathodic protection are detailed in EN 12473.

1 Scope

This European Standard defines the means to be used to cathodically protect the submerged metallic surfaces of steel offshore floating structures and appurtenances in sea water and saline mud.

1.1 Structures

This European Standard covers the cathodic protection of the external surface of offshore floating structures which are static during their usual operating conditions. This essentially includes: barges, jack-ups, semi-submersible platforms, storage tankers, buoys, etc.

It also covers the submerged areas of appurtenances, such as chains, attached to the structure, when these are not electrically isolated from the structure.

It does not cover the cathodic protection of ships, fixed offshore structures, elongated structures (pipelines, cables) or harbour installations, which are covered by other standards.

This European Standard concerns only the cathodic protection of external surfaces immersed in sea water, including sea chests and water intakes up to the first valve.

This European Standard does not include the internal protection of surfaces of any components such as ballast tanks and hull internals of floating structures.

1.2 Materials

This European Standard covers the cathodic protection of structures fabricated principally from bare or coated carbon manganese steels

As some parts of the structure may be made of metallic materials other than carbon manganese steels, the cathodic protection system should be designed to ensure that there is a complete control over any galvanic coupling and minimise risks due to hydrogen embrittlement or hydrogen induced cracking (see EN 12473).

This European Standard does not cover concrete structures.

1.3 Environment

This European Standard is applicable for the whole submerged zone in sea water, brackish waters, saline mud which can normally be found where the floating structure is anchored, moored or moving.

This European Standard is also applicable to appurtenances which may be in contact with muds (e.g. chains).

For surfaces which are alternately immersed and exposed to the atmosphere, the cathodic protection is only effective when the immersion time is sufficiently long for the steel to become polarised.

1.4 Safety and environment protection

This European Standard does not cover safety and environmental protection aspects associated with cathodic protection. The relevant national or international regulations shall apply.

2 Normative references

This European Standard incorporates, by dated or undated references, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 12473, *General principles of cathodic protection in sea water.*

prEN 12496, *Galvanic anodes for cathodic protection in sea water.*

3 Terms and definitions

For the purposes of this European Standard the terms and definitions in EN 12473 and the following apply:

3.1 atmospheric zone

zone located above the wetted zone; that means above the level reached by the normal swell, whether the structure is moving or not

3.2 boot topping

section of the hull between light and fully loaded conditions, which may be intermittently immersed

3.3 Cathodic Protection zone

that part of the structure which can be considered independently with respect to cathodic protection design

3.4 immersed zone

zone located below the water line at draught corresponding to normal working conditions

3.5 submerged zone

zone including the immersed and the buried zones

3.6 underwater hull

part of the hull vital for its stability and buoyancy of a floating structure, i.e. below the light water line

4 Design basis

4.1 Objectives

The major objective of a cathodic protection system is to deliver sufficient current to protect each part of the structure and appurtenances and distribute this current so that the potential of each part of the structure is within the limits given by the protection criteria (see 4.2).

Potentials should be as uniform as possible over the whole structure. This objective may only be approached by an adequate distribution of the protective current over the structure during its normal service conditions. However, it may be difficult to achieve in some areas such as chains, water intakes, sea chests, when supplementary cathodic protection systems should be considered.

The cathodic protection system for a floating structure is generally combined with a coating system, even though some appurtenances, such as chains, may not benefit from a coating protection.

Dielectric shields may be used in conjunction with anodes to minimise the risk of local over-protection.

The cathodic protection system should be designed either for the life of the structure or for a period corresponding to the maintenance dry-docking interval.

The above objectives should be achieved by the design of a cathodic protection system using galvanic anodes or impressed current systems or a combination of both.

4.2 Cathodic protection criteria

The criteria for cathodic protection are detailed in EN 12473.

To achieve an adequate cathodic protection level, steel structures should have potentials as indicated hereafter.

The accepted criterion for protection of steel in aerated sea water is a potential more negative than -0,80 V measured with respect to Ag/AgCl/sea water reference electrode.

A negative limit of -1,10 V (Ag/AgCl/sea water reference electrode) is generally recommended.

Where there is a possibility of coating disbondment and corrosion fatigue, the negative limit should be more positive. This negative limit should be documented.

4.3 Design parameters

The design of a cathodic protection system should be made in accordance with the following parameters: structure subdivision, components description and service conditions.

4.3.1 Structure subdivision

A floating structure can be divided into different Cathodic Protection zones, (CP zones), which are then considered independently with respect to cathodic protection design, although they may not necessarily be electrically isolated.

EXAMPLE 1 For a storage tanker, some specific components may not be included in the underwater hull CP zone and therefore constitute a CP zone by themselves (e.g. : seachests).

EXAMPLE 2 For buoys, a single zone is generally considered, including two components: the body of the buoy and the influenced part of the mooring chain(s).

4.3.2 Description of CP zones

Each C.P. zone may consist of several components which should be fully described including material, surface area and coating characteristics (type, lifetime and coating breakdown factor).

4.3.3 Service conditions

The design of the cathodic protection system(s) will depend on service conditions which include: expected life time, environment and operating conditions.

- Life time: either the whole design life or dry-docking interval(s) should be considered.
- Environment: the sea water properties should be established (see EN 12473).
- Operating conditions: the cathodic protection design normally considers only the static conditions of the structure because the durations when dynamic conditions prevail are generally negligible.

4.4 Electrical current demand

4.4.1 General

To achieve the criteria for protection for the conditions outlined in 4.3, it is necessary to select the appropriate current density for each component.

The current demand of each metallic component of the structure is the result of the product of its surface area multiplied by the required current density.

4.4.2 Protection current density for bare steel

The current density required may not be the same for all components of the structure as the environmental and service conditions are variable.

The selection of design current densities may be based on experience gained from similar structures in a similar environment or from specific tests and measurements.

The current density depends on the kinetics of electrochemical reactions and varies with parameters such as the protection potential, surface condition, dissolved oxygen content in sea water, sea water velocity at the steel surface, temperature.

The following should be evaluated for each design:

- initial current density required to achieve the initial polarisation of the structure;
- maintenance current density required to maintain polarisation of the structure;
- final current density for possible repolarisation of the structure, e.g. after severe storms or cleaning operations.

As the initial polarisation preceding steady state conditions is normally short compared to the design life, the average current density over the lifetime of the structure is usually very close to the maintenance current density.

The (average) maintenance current density is used to calculate the minimum mass of anode material necessary to maintain cathodic protection throughout the design life.

Typical values of current densities as used for bare steel are given in annex A.

4.4.3 Protection current density for coated steel

The cathodic protection system is generally combined with suitable coating systems. The coating reduces current density and improves the current distribution over the surface.

The reduction of current density may be in a ratio of 100 to 1 or even more. However the current density will increase with time as the coating deteriorates.

An initial coating breakdown factor related mainly to mechanical damage occurring during the fabrication of the structure should be considered. A coating deterioration rate (i.e. an increase of the coating breakdown factor) should be selected in order to take into account the coating ageing and possible mechanical damage occurring to the coating during the life time of the structure or a period corresponding to the dry-docking interval.

These values are strongly dependent on the actual construction and operational conditions.

Guidelines for the values of coating breakdown factors (f_c) are given in annex A.

The protection current density needed for the protection of coated steel is equal to the product of the current density for bare steel and the coating breakdown factor.

$$J_c = J_b \cdot f_c$$

where:

J_c is the protection current density for coated steel in amperes per square metre,

J_b is the protection current density for bare steel in amperes per square metre,

f_c is the coating breakdown factor which varies with time due to ageing and mechanical damage:

$f_c = 0$ for a perfectly insulating coating,

$f_c = 1$ for a coating with no insulation property (equivalent to bare steel structure).

This formula should be applied for each individual component or zone as defined in 4.3 where the coating, or the current density for bare steel, may be different.

4.4.4 Protection current demand

An evaluation of the current demand required should be carried out to optimise the mass and size of galvanic anodes, or the capacity of impressed current systems.

The protection current demand I_e of each component of the structure to be cathodically protected is equal to:

$$I_e = A_e \cdot J_{ce}$$

where:

A_e is the surface area of the individual component in square metres,

J_{ce} is the individual protection current density for the component considered, in amperes per square metre.

The protection current demand I_z of each CP zone is therefore equal to the sum of current demands for each component included in the CP zone:

$$I_z = \sum_z (I_e)$$