



SLOVENSKI STANDARD
SIST-TS CEN/TS 14038-1:2005

01-februar-2005

**Elektrokemična realkalizacija in postopki kloridne ekstrakcije za armiran beton – 1.
del: Realkalizacija**

Electrochemical realkalization and chloride extraction treatments for reinforced concrete -
Part 1: Realkalization

Elektrochemische Realkalisierung und Chloridextraktionsbehandlungen für Stahlbeton -
Teil 1: Realkalisierung

Ré-alkalinisation électrochimique et traitements d'extraction des chlorures applicables au
béton armé - Partie 1 : Ré-alkalinisation

iTeh STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/78588f0c-bfd6-4a72-b2c7-fb0b44309a1e/sist-ts-cen-ts-14038-1-2005>

Ta slovenski standard je istoveten z: CEN/TS 14038-1:2004

ICS:

91.100.30	Beton in betonski izdelki	Concrete and concrete products
-----------	---------------------------	--------------------------------

SIST-TS CEN/TS 14038-1:2005	en
------------------------------------	-----------

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST-TS CEN/TS 14038-1:2005](#)

<https://standards.iteh.ai/catalog/standards/sist/78588f0c-bfd6-4a72-b2c7-fb0b44309a1e/sist-ts-cen-ts-14038-1-2005>

TECHNICAL SPECIFICATION
SPÉCIFICATION TECHNIQUE
TECHNISCHE SPEZIFIKATION

CEN/TS 14038-1

November 2004

ICS 91.080.40

English version

**Electrochemical realkalization and chloride extraction treatments
for reinforced concrete - Part 1: Realkalization**

Ré-alkalination électrochimique et traitements d'extraction
des chlorures applicables au béton armé - Partie 1 : Ré-
alkalination

Elektrochemische Realkalisierung und
Chloridextraktionsbehandlungen für Stahlbeton - Teil 1:
Realkalisierung

This Technical Specification (CEN/TS) was approved by CEN on 9 September 2004 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST-TS CEN/TS 14038-1:2005](https://standards.iteh.ai/catalog/standards/sist/78588f0c-bfd6-4a72-b2c7-fb0b44309a1e/sist-ts-cen-ts-14038-1-2005)

<https://standards.iteh.ai/catalog/standards/sist/78588f0c-bfd6-4a72-b2c7-fb0b44309a1e/sist-ts-cen-ts-14038-1-2005>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....	3
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Principle.....	6
5 Assessment and repair of the structure.....	6
5.1 General.....	6
5.2 Review of records	6
5.3 Inspection	6
5.4 Carbonation depth measurement	6
5.5 Determination of chloride content	7
5.6 Concrete cover thickness and reinforcement location measurements	7
5.7 Alkali aggregate reaction	7
5.8 Reinforcement continuity and size	7
5.9 Repair.....	7
5.9.1 General.....	7
5.9.2 Concrete removal.....	7
5.9.3 Reinforcement preparation.....	8
6 Materials and apparatus.....	8
6.1 Calibration of instrumentation	8
6.2 Anode system	8
6.2.1 General.....	8
6.2.2 Anode.....	8
6.2.3 Anode zone.....	8
6.2.4 Alkaline electrolyte solution	8
6.3 Electric cables.....	8
6.4 Power supply.....	9
7 Installation procedures	9
7.1 Electrical continuity.....	9
7.2 Performance monitoring	9
7.3 Installation of anode system	9
7.4 Protection of electrolyte solution.....	9
7.5 Electrical installation	10
7.6 Preliminary testing and documentation	10
8 Commissioning, operation and termination of treatment	10
8.1 Visual inspection	10
8.2 Energizing and adjustment of current output.....	10
8.3 Routine inspection and maintenance	10
8.4 Realkalization process monitoring	11
8.5 Termination of treatment	11
9 Final report	11
10 Post-treatment coating and monitoring	12
Bibliography.....	13

iTech STANDARD PREVIEW
(standards.iteh.ai)

SIST-TS CEN/TS 14038-1:2005

<https://standards.iteh.ai/catalog/standards/sist/7858810c-01d6-4a72-b2c7->

[1b0b44309a1c/sist-ts-cen-ts-14038-1-2005](https://standards.iteh.ai/catalog/standards/sist/7858810c-01d6-4a72-b2c7-1b0b44309a1c/sist-ts-cen-ts-14038-1-2005)

Foreword

This document (CEN/TS 14038-1:2004) has been prepared by Technical Committee CEN/TC 219 “Cathodic protection”, the secretariat of which is held by BSI.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST-TS CEN/TS 14038-1:2005](https://standards.iteh.ai/catalog/standards/sist/78588f0c-bfd6-4a72-b2c7-fb0b44309a1e/sist-ts-cen-ts-14038-1-2005)

<https://standards.iteh.ai/catalog/standards/sist/78588f0c-bfd6-4a72-b2c7-fb0b44309a1e/sist-ts-cen-ts-14038-1-2005>

Introduction

The purpose of realkalization is to provide long-term corrosion protection of steel reinforcement in concrete, which has become carbonated.

There are other electrochemical procedures, which can be used to provide corrosion protection of steel in concrete structures. These include cathodic protection and chloride extraction. There is a European Standard for cathodic protection of steel in concrete (EN 12696).

It is assumed in the drafting of this document that the execution of its provisions is entrusted to appropriately qualified and competent people, for whose use it has been prepared.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST-TS CEN/TS 14038-1:2005](https://standards.iteh.ai/catalog/standards/sist/78588f0c-bfd6-4a72-b2c7-fb0b44309a1e/sist-ts-cen-ts-14038-1-2005)

<https://standards.iteh.ai/catalog/standards/sist/78588f0c-bfd6-4a72-b2c7-fb0b44309a1e/sist-ts-cen-ts-14038-1-2005>

1 Scope

This document specifies a procedure for carrying out impressed current electrochemical realkalization of carbonated reinforced concrete in existing structures. It is applicable to atmospherically exposed parts of structures with ordinary reinforcement embedded in concrete.

This document does not apply to concrete containing prestressing steel which can suffer hydrogen embrittlement during realkalization, or to concrete containing epoxy-coated or galvanized reinforcement, or if chloride contamination is contributing to reinforcement corrosion.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

prEN 14629:2003, *Products and systems for the protection and repair of concrete structures — Test methods — Determination of chloride content in hardened concrete*

prEN 14630:2003, *Products and systems for the protection and repair of concrete structures - Test methods - Determination of carbonation depth in hardened concrete by the phenolphthalein method*

EN 12696:2000, *Cathodic protection of steel in concrete*

ENV 1504-9, *Products and systems for the protection and repair of concrete structures — Definitions, requirements, quality control and evaluation of conformity — Part 9: General principles for use of products and systems.*

EN ISO 8044:1999, *Corrosion of metals and alloys — Basic terms and definitions (ISO 8044:1999).*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN ISO 8044:1999 and the following apply.

3.1

realkalization

electrochemical treatment for restoring to concrete, which surrounds reinforcing bars, a high pH value corresponding to sound, non-carbonated concrete

CEN/TS 14038-1:2004 (E)**4 Principle**

Realkalization of reinforced concrete is performed by applying an electric field between the steel reinforcement embedded in the concrete and an anode surrounded by an alkaline electrolyte solution containing carbonate or hydroxyl ions temporarily placed on the concrete surface.

NOTE 1 The carbonated area treated by realkalization lies beneath the anode.

NOTE 2 Details of the principle underlying this process are given in the European Federation of Corrosion report [1].

NOTE 3 Electrolyte solutions of sodium, potassium and lithium may be used.

5 Assessment and repair of the structure**5.1 General**

Prior to undertaking realkalization an assessment of the structure, including its physical condition, its structural integrity and the nature and extent of any repairs, which might be needed, shall be performed in accordance with ENV 1504-9.

The investigations specified in 5.2 to 5.8 shall be carried out in order to:

a) determine the suitability of the structure for realkalization;

b) provide information for design.

ITIH STANDARD PREVIEW
(standards.iteh.ai)

5.2 Review of records

SIST-TS CEN/TS 14038-1:2005

<https://standards.iteh.ai/catalog/standards/sist/78588f0c-bfd6-4a72-b2c7-10044309a1c3/sist-ts-cen-ts-14038-1-2005>

All available drawings, specifications, records and notes shall be reviewed for information on the location, quantity, nature (e.g. mild or high strength steel, smooth or deformed bar, galvanized, epoxy-coated) and continuity of the reinforcement, as well as the constituents and quality of the concrete.

NOTE The possible sensitivity to reduction of bond strength should be evaluated in the case of smooth reinforcement.

5.3 Inspection

An inspection shall be carried out to ascertain the type, causes and extent of defects and any features of the structure or of its surrounding environment, which could influence the application and effectiveness of realkalization. All areas of the structure, which require realkalization, shall be checked for delamination of the concrete cover. Defects such as delaminations, cracks, honeycombing or poor construction joints which could permit significant water penetration, or prevent current flow and thereby impair the effectiveness of the realkalization treatment, shall be recorded.

NOTE 1 In areas, which have been previously repaired, the repair methods and materials used should be identified, as far as possible. If the concrete behind the repair is to be realkalized, the electrical resistivity and porosity of the repair media should be considered.

The cause of any deterioration, which is not attributable to corroding reinforcement, shall be determined.

NOTE 2 If any signs of structural distress are evident, an assessment of both the load-bearing capacity of the structure and the need for temporary or permanent strengthening or support should be made.

5.4 Carbonation depth measurement

Carbonation depth shall be measured according to prEN 14630 at several locations to ascertain its distribution.

NOTE In selecting locations for concrete sampling, the objective is to identify areas with various carbonation depths for comparison with post-treatment data.

5.5 Determination of chloride content

The chloride content of the concrete shall be determined according to prEN 14629 as a proportion of the mass of cement or concrete.

Concrete samples shall be taken from areas expected to have the highest possible chloride content in order to ascertain whether chloride contamination is present.

If chloride contamination is found to be a cause of reinforcement corrosion, chloride content shall be determined in accordance with ENV 1504-9 or EN 12696.

5.6 Concrete cover thickness and reinforcement location measurements

Concrete cover thickness and reinforcement location measurements shall be carried out in order to enable a determination to be made of comparative current flow through areas of thick and thin cover, and to identify regions of varying reinforcement density. Any features that could impair the effectiveness of realkalization, such as shielding of the reinforcement, caused by embedded metal mesh, metal fibres, metal plates, plastic sheets or non-conductive repair materials shall be identified. Points at which short circuits between the reinforcing steel and the anodes could occur shall be noted.

5.7 Alkali aggregate reaction

If the concrete of the structure, which is to be realkalized, contains aggregates, which can be sensitive to alkali, the risk of provoking an alkali aggregate reaction (AAR) shall be considered prior to any treatment.

NOTE No case of induced AAR has been reported in connection with realkalization.

5.8 Reinforcement continuity and size

The reinforcement continuity shall be proven on site by measuring the electrical resistance between reinforcing bars in mutually remote locations across the structure and between all reinforcing bars exposed during concrete repairs (see 5.9.3) or other works following the method and acceptance criteria as specified in EN 12696:2000, 7.1. These measurements shall include the following:

- a) continuity between elements of the structure within each realkalization zone;
- b) continuity of metallic items, other than reinforcement, with the reinforcement itself.

Reinforcement size shall be identified from drawings when available and shall be verified by direct measurements.

5.9 Repair

5.9.1 General

All operations comprising repair shall be performed in accordance with ENV 1504-9, except where stated otherwise in 5.9.2 to 5.9.3 below.

5.9.2 Concrete removal

All delaminated and honeycombed concrete and repair materials with unacceptably high electrical resistivity (> 200 % of parent company resistivity) and/or containing any other materials that may impair the effects of realkalization shall be broken out to achieve a clean, physically sound concrete surface. Any tying wire, nails