



Designation: E2396/E2396M – 19

# Standard Test Method for Saturated Water Permeability of Granular Drainage Media [Falling-Head Method] for Vegetative (Green) Roof Systems<sup>1</sup>

This standard is issued under the fixed designation E2396/E2396M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This test method covers a procedure for determining the water permeability of coarse granular materials used in the drainage layers of vegetative (green) roof systems.

1.2 This test method addresses water permeability under the low-head conditions that typify horizontal flow in vegetative (green) roof applications.

1.3 This test method is suitable for coarse-grained materials with 100 % of the material retained on the U.S. #8 [2.25 mm] sieve. It is not suitable for finer-grained materials.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and to determine the applicability of regulatory limitations prior to use.*

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.24 on Sustainability.

Current edition approved Feb. 1, 2019. Published February 2019. Originally approved in 2005. Last previous edition approved in 2015 as E2396/E2396M – 15. DOI: 10.1520/E2396\_E2396M-19.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- [C29/C29M Test Method for Bulk Density \(“Unit Weight”\) and Voids in Aggregate](#)
- [C130 Specification for Lightweight Aggregates for Concrete \(Withdrawn 1954\)<sup>3</sup>](#)
- [E631 Terminology of Building Constructions](#)
- [E2114 Terminology for Sustainability Relative to the Performance of Buildings](#)

## 3. Terminology

### 3.1 Definitions:

3.1.1 For terms related to building construction, refer to Terminology E631.

3.1.2 For terms related to sustainability relative to the performance of buildings, refer to Terminology E2114.

### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *water permeability*—the coefficient which when multiplied by the hydraulic gradient will yield the apparent velocity with which water (at 68°F) will move through a cross-section of media.

3.2.2 *wet density*—the density of coarse granular drainage course materials determined after immersion for 24 hours.

## 4. Summary of Test Method

4.1 This procedure involves measuring the water permeability of coarse granular materials under the low-head conditions that characterize the environment in vegetative (green) roof systems. A falling-head technique is used. Incidental to the procedure is the measurement of the wet density of the medium.

## 5. Significance and Use

5.1 This test method addresses performance characteristics for vegetative (green) roof systems with respect to the water permeability of the drainage media.

5.1.1 Water permeability of coarse materials is highly influenced by the head conditions under which it is measured. In vegetative (green) roofs, coarse materials are frequently used to create drainage zones for percolated rainfall.

<sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.