

INTERNATIONAL STANDARD



**Flexible insulating sleeving –
Part 3: Specifications for individual types of sleeving –
Sheet 280: Heat-shrinkable, polyolefin sleeving, anti-tracking**

Document Preview

[IEC 60684-3-280:2019](#)

<https://standards.iteh.ai/catalog/standards/iec/606dd13c-ccd4-4f6a-a2ba-cea74657278e/iec-60684-3-280-2019>



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2019 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

International
Standards
IEC Standards
Document Preview

[IEC 60684-3-280:2019](https://standards.iteh.ai/catalog/standards/iec/606dd13c-ccd4-4f6a-a2ba-cea74657278e/iec-60684-3-280-2019)

<https://standards.iteh.ai/catalog/standards/iec/606dd13c-ccd4-4f6a-a2ba-cea74657278e/iec-60684-3-280-2019>



IEC 60684-3-280

Edition 2.0 2019-08
REDLINE VERSION

INTERNATIONAL STANDARD



**Flexible insulating sleeving –
Part 3: Specifications for individual types of sleeving –
Sheet 280: Heat-shrinkable, polyolefin sleeving, anti-tracking**

Document Preview

[IEC 60684-3-280:2019](https://standards.iteh.ai/catalog/standards/iec/606dd13c-ccd4-4f6a-a2ba-cea74657278e/iec-60684-3-280-2019)

<https://standards.iteh.ai/catalog/standards/iec/606dd13c-ccd4-4f6a-a2ba-cea74657278e/iec-60684-3-280-2019>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.035.20

ISBN 978-2-8322-7326-5

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD	3
INTRODUCTION	5
1 Scope	6
2 Normative references	6
3 Terms and definitions	7
4 Designation	7
5 Conditions of test	7
6 Requirements	7
7 Sleeving conformance	7
Annex A (informative) Guidance on the available sizes and wall thicknesses	12
Bibliography	13
Table 1 – Property requirements	8
Table 2 – Requirements for dielectric strength	9
Table 3 – Resistance to selected fluids	10
Table 4 – Additional property requirements	10
Table A.1 – Guidance on the available sizes and wall thicknesses	12

iteh Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC 60684-3-280:2019](#)

<https://standards.iteh.ai/catalog/standards/iec/606dd13c-ccd4-4f6a-a2ba-cea74657278e/iec-60684-3-280-2019>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

FLEXIBLE INSULATING SLEEVING –

Part 3: Specifications for individual types of sleeving – Sheet 280: Heat-shrinkable, polyolefin sleeving, anti-tracking

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

International Standard IEC 60684-3-280 has been prepared by IEC technical committee 15: Solid electrical insulating materials.

This second edition cancels and replaces the first edition published in 2010 and Amendment 1:2013. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) change of moulded plaque thickness for resistance to tracking and weathering tests to $(6 \pm 0,5)$ mm.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
15/891/FDIS	15/898/RVD

Full information on the voting for the approval of this International Standard can be found in the report

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60684 series, published under the general title *Flexible insulating sleeving*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

INTRODUCTION

This document is one of a series of standards which deals with flexible insulating sleeving for electrical purposes.

The series consists of three parts:

Part 1: Definitions and general requirements (IEC 60684-1)

Part 2: Methods of test (IEC 60684-2)

Part 3: Specifications for individual types of sleeving (IEC 60684-3)

This document comprises one of the sheets of Part 3 as follows:

Sheet 280: Heat-shrinkable, polyolefin sleeving, anti-tracking

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

[IEC 60684-3-280:2019](https://standards.itih.ai/catalog/standards/iec/606dd13c-ccd4-4f6a-a2ba-cea74657278e/iec-60684-3-280-2019)

<https://standards.itih.ai/catalog/standards/iec/606dd13c-ccd4-4f6a-a2ba-cea74657278e/iec-60684-3-280-2019>

FLEXIBLE INSULATING SLEEVING –

Part 3: Specifications for individual types of sleeving – Sheet 280: Heat-shrinkable, polyolefin sleeving, anti-tracking

1 Scope

This part of IEC 60684 gives the requirements for heat-shrinkable, polyolefin sleeving, anti-tracking with a nominal shrink ratio of 3:1.

This sleeving has been found suitable for use at temperatures up to 100 °C.

Typically: medium wall, internal diameter up to 110 mm.

~~These sleeveings are~~ This sleeving is normally supplied in the colours red or brown.

Since these types of sleeveings cover a significantly large range of sizes and wall thicknesses, Annex A (Table A.1) provides guidance on the range of sizes available. The actual size ~~shall~~ will be agreed between the user and the supplier.

Materials which conform to this specification meet established levels of performance. However, the selection of a material by a user for a specific application ~~should~~ will be based on the actual requirements necessary for adequate performance in that application and not based on this specification alone.

This sleeving is designed to be used in medium voltage cable accessories and as such electrical performance ~~must~~ will be proven as part of the assembly. Examples of this are described in HD 629.1 and IEC 60502 (all parts).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60296:2003/2012, *Fluids for electrotechnical applications – Unused mineral insulating oils for transformers and switchgear*

~~IEC 60502 (all parts), Power cables with extruded insulation and their accessories for rated voltages from 1 kV ($U_m = 1,2$ kV) up to 30 kV ($U_m = 36$ kV)~~

IEC 60684-1:2003, *Flexible insulating sleeving – Part 1: Definitions and general requirements*

IEC 60684-2:1997/2011, *Flexible insulating sleeving – Part 2: Methods of test*
~~Amendment 1 (2003)~~
~~Amendment 2 (2005)~~

IEC 60757:1983, *Code for designation of colours*

ISO 846:1997/2019, *Plastics – Evaluation of the action of micro-organisms*

ISO 4892-3:2006/2016, *Plastics – Methods of exposure to laboratory light sources – Part 3: Fluorescent UV lamps*

~~HD 629, Test requirements on accessories for use on power cables of rated voltages from 3,6/6(7,2)kV up to 20,8/36 (42)kV – Part 1: Cables with extruded insulation~~

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Designation

The sleeving shall be identified by the following designation:

Description	IEC publication number	IEC part number	IEC sheet number	Size (expanded and recovered internal diameter in millimetres)	Colour	Table 4 ^a code
↓	↓	↓	↓	↓	↓	↓
Sleeving	IEC 60684	- 3	-280	- 60,0/19,0	- Red	X

^a NOTE 1 The addition of "X" at the end of the designation indicates that the properties contained in Table 4 have been agreed upon between the user and supplier.

Any colour abbreviation shall comply with IEC 60757, where applicable. Non-standard colours shall be written out in full.

NOTE 2 This information is for labelling only, in accordance with IEC 60684-1.

5 Conditions of test

Unless otherwise specified, the sleeving shall be shrunk in a forced air circulation oven for (10 ± 1) min at $200 \text{ °C} \pm 3 \text{ K}$ prior to testing.

6 Requirements

In addition to the general requirements given in IEC 60684-1, the sleeving shall comply with the requirements of Tables 1, 2, 3, and 4 where applicable.

7 Sleeving conformance

Conformance to the requirements of this specification shall normally be based on the results from typical sizes:

- Recovered ID 20 mm to 30 mm

Table 1 – Property requirements

Property	IEC 60684-2: 2011 clause or subclause	Units	Max. or min.	Requirements	Remarks
Dimensions Internal diameter Wall thickness Concentricity expanded recovered	3 3.1.2 3.3.2 3.3.3	mm mm %	Min. Min.	To be agreed between the purchaser and the supplier 60 85	
Heat shock Tensile strength Elongation at break	6 19.12 and 19.23 19.12 and 19.23	MPa %	Min. Min.	8 200	Heat at 150 °C ± 5 K Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb-bell samples cut from the sleeving
Longitudinal change	9	%	Max.	+5 -10	Heat expanded sleeving at 150 °C ± 3 K for (10 ± 1) min
Bending at low temperature	14	–	–	No cracking shall be visible.	Test at – 40 °C. For strips, the mandrel shall be between 20 times and 22 times the wall thickness. Full section sleeving is tested unfilled and the mandrel shall be between 20 times and 22 times the outer diameter
Dimensional stability on storage	16	–	–	The dimensions shall remain as agreed.	See Clause 1
Tensile strength Elongation at break	19.12 and 19.23 19.12 and 19.23	MPa %	Min. Min.	10 300	Use a jaw separation rate of 100 mm/min. Below 6,5 mm Ø as sleeving. At 6,5 mm Ø and above as dumbbells. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb-bell samples cut from the sleeving
Secant modulus at 2 % elongation	19.45	MPa MPa	Min. Max.	80 160	
Dielectric strength	See Table 2 of this document.	kV/m m	Min.	Table 2	
Breakdown voltage	21.2	kV/m m	Min.	See Table 2	
Volume resistivity at room temperature	23 23.45.2	Ω·m	Min.	10 ¹²	

Property	IEC 60684-2: 2011 clause or subclause	Units	Max. or min.	Requirements	Remarks
Resistance to tracking	25	–	Min.	Class 2A 2,5 kV – 1 h 2,75 kV – 1h 3,0 kV – 1 h 3,25 kV – 20 min	Specimens shall be prepared from cross-linked moulded plaques of thickness $(6 \pm 0,5)$ mm Specimens should not be abraded but cleaned with an appropriate solvent. The method of cleaning shall be recorded.
Resistance to selected fluids Tensile strength Elongation at break	36 19.12 and 19.23 19.12 and 19.23	MPa %	Min. Min.	8 200	Use the fluids and test temperatures specified in Table 3. Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb-bell samples cut from the sleeving Immersion (24 ± 1) h
Heat ageing Tensile strength Elongation at break	39 19.12 and 19.23 19.12 and 19.23	MPa %	Min. Min.	8 200	Heat at $150 \text{ °C} \pm 3 \text{ K}$ Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb-bell samples cut from the sleeving
Long term ageing Elongation at break	50 19.2 and 19.3	%	Min.	150	The ageing temperature shall be $100 \text{ °C} \pm 3 \text{ K}$ Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb-bell samples cut from the sleeving

Table 2 – Requirements for dielectric strength

Expanded wall thickness mm	Dielectric strength ^a Min.	
	Expanded ID	Dielectric strength kV/mm
All dimensions	10 to 25	14
	26 to 59	12
	60 to 120	10
^a Measure the expanded wall thickness and calculate the dielectric strength by dividing the breakdown voltage by this value.		

~~The breakdown voltage shall be determined by the method described in 21.4 of IEC 60684-2.~~

The sleeving shall be tested in the expanded condition.

The rate of application of the voltage shall be 500 V/s.

NOTE Care should be taken on selection of sizes based on these values. Refer to the manufacturer for actual values on installed condition.

Table 3 – Resistance to selected fluids

Test fluid No.	Fluids	Type	Standard or symbol	Immersion temperature °C ± 2 K
1	Insulating oil	Mineral based	IEC 60296	23
2			Isopropyl alcohol	23
3	-	Water	De-ionized	85

Other fluids and/or temperatures may be specified for customers with specific needs. These additional fluids and/or temperatures shall be applicable when incorporated into agreements between the supplier and the customer.

Table 4 – Additional property requirements

Property	IEC 60684-2:2011 clause or subclause	Units	Max. or min.	Requirements	Remarks
Fungus resistance Tensile strength Elongation	19.42 and 19.23	MPa %	Min. Min.	8 250	The test method shall be ISO 846, Method B. 56 days exposure Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb-bell samples cut from the sleeving