



Edition 2.0 2019-08 REDLINE VERSION

# INTERNATIONAL STANDARD



Flexible insulating sleeving - h Standards

Part 3: Specifications for individual types of sleeving -

Sheet 283: Heat-shrinkable, polyolefin sleeving for bus-bar insulation

### **Document Preview**

IEC 60684-3-283:2019

https://standards.iteh.ai/catalog/standards/iec/20782dd8-efbh-49e7-a584-ad1ac75c38bb/iec-60684-3-283-2019





### THIS PUBLICATION IS COPYRIGHT PROTECTED Copyright © 2019 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office 3, rue de Varembé CH-1211 Geneva 20 Switzerland

Tel.: +41 22 919 02 11

info@iec.ch www.iec.ch

#### About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

#### IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

**IEC Just Published - webstore.iec.ch/justpublished**Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

#### IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

#### Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

#### IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.





Edition 2.0 2019-08 REDLINE VERSION

# INTERNATIONAL STANDARD



Flexible insulating sleeving -eh Standards

Part 3: Specifications for individual types of sleeving -

Sheet 283: Heat-shrinkable, polyolefin sleeving for bus-bar insulation

### **Document Preview**

EC 60684-3-283:2019

https://standards.iteh.ai/catalog/standards/iec/20782dd8-efbb-49e7-a584-ad1ac75c38bb/iec-60684-3-283-2019

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ICS 29.035.20 ISBN 978-2-8322-7327-2

Warning! Make sure that you obtained this publication from an authorized distributor.

### **CONTENTS**

FΟ	)REWORD	3
IN٦	TRODUCTION	2
1	Scope	6
2	Normative references	ε
3	Terms and definitions	7
4	Designation	7
5	Conditions of test	7
6	Requirements	7
7	Sleeving conformance	7
An	nex A (informative) Guidance to the available sizes and wall thicknesses	12
Bib	bliography	13
		_
Tal	ble 1 – Property requirements	8
Tal	ble 2 – Requirements for dielectric strength	10
Tal	ble 3 – Resistance to selected fluids	10
Tal	ble 4 – Additional property requirements	11
	ble A.1 – Type A, medium wall	
Tal	ble A.2 – Type B, thick wall	12

## **Document Preview**

IEC 60684-3-283:2019

https://standards.iteh.ai/catalog/standards/iec/20782dd8-efbb-49e7-a584-ad1ac75c38bb/iec-60684-3-283-2019

#### INTERNATIONAL ELECTROTECHNICAL COMMISSION

#### FLEXIBLE INSULATING SLEEVING -

# Part 3: Specifications for individual types of sleeving – Sheet 283: Heat-shrinkable, polyolefin sleeving for bus-bar insulation

#### **FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

International Standard IEC 60684-3-283 has been prepared by IEC technical committee 15: Solid electrical insulating materials.

This second edition cancels and replaces the first edition published in 2010 and Amendment 1:2013. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

a) change of moulded plaque thickness for resistance to tracking and weathering tests to  $(6 \pm 0.5)$  mm.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
15/892/FDIS	15/901/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60684 series, published under the general title *Flexible insulating* sleeving, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,

IEC 60684-3-283:2019

- replaced by a revised edition, or 20782dd8-efbb-49e7-a584-ad1ac75c38bb/iec-60684-3-283-2019
- amended.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

#### INTRODUCTION

This document is one of a series of standards which deals with flexible insulating sleeving for electrical purposes.

The series consists of three parts:

Part 1: Definitions and general requirements (IEC 60684-1)

Part 2: Methods of test (IEC 60684-2)

Part 3: Specifications for individual types of sleeving (IEC 60684-3)

This document comprises one of the sheets of Part 3 as follows:

Sheet 283: Heat-shrinkable, polyolefin sleeving for bus-bar insulation.

## iTeh Standards (https://standards.iteh.ai) Document Preview

IEC 60684-3-283:2019

https://standards.iteh.ai/catalog/standards/iec/20782dd8-efbb-49e7-a584-ad1ac75c38bb/iec-60684-3-283-2019

#### FLEXIBLE INSULATING SLEEVING -

# Part 3: Specifications for individual types of sleeving – Sheet 283: Heat-shrinkable, polyolefin sleeving for bus-bar insulation

#### 1 Scope

This part of IEC 60684 gives the requirements for two types of heat-shrinkable, polyolefin sleeving for bus-bar insulation, with a nominal shrink ratio of 2,5:1.

This sleeving has been found suitable up to temperatures of 100 °C.

- Type A: Medium wall internal diameter up to 170,0 mm typically
- Type B: Thick wall internal diameter up to 165,0 mm typically

These sleevings are normally supplied in colour, red or brown.

Since these types of sleevings cover a significantly large range of sizes and wall thicknesses, Annex A (Tables A.1 and A.2) provides guidance to the range of sizes available. The actual size and wall thickness—shall will be agreed between the user and supplier depending on the electric strength of the installed tubing offered and the requirements of the user.

Materials which conform to this specification meet established levels of performance. However, the selection of a material by a user for a specific application—should will be based on the actual requirements necessary for adequate performance in that application and not based on this specification alone.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60296:<del>2003</del>2012, Fluids for electrotechnical applications – Unused mineral insulating oils for transformers and switchgear

IEC 60684-1:2003, Flexible insulating sleeving – Part 1: Definitions and general requirements

IEC 60684-2:<del>1997</del>2011, Flexible insulating sleeving – Part 2: Methods of test Amendment 1 (2003) Amendment 2 (2005)

IEC 60757:1983, Code for designation of colours

ISO 846:<del>1997</del>2019, Plastics – Evaluation of the action of microorganisms

ISO 4892-3:<del>2006</del>2016, Plastics – Methods of exposure to laboratory light sources – Part 3: Fluorescent UV lamps

#### 3 Terms and definitions


No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at http://www.iso.org/obp

### 4 Designation

The sleeving shall be identified by the following designation:



\* NOTE 1 The addition of "X" at the end of the designation indicates that the properties contained in Table 4 have been agreed upon between the user and the supplier.

Any colour abbreviation shall comply with IEC 60757, where applicable. Non-standard colours shall be written out in full.

NOTE 2 This is for package labelling only in accordance with IEC 60684-1.

#### 5 Conditions of test

Unless otherwise specified, the sleeving shall be shrunk in a forced air circulation oven for (10  $\pm$  1) min at 200 °C  $\pm$  3 K prior to testing.

#### 6 Requirements

In addition to the general requirements given in IEC 60684-1, the sleeving shall comply with the requirements of Tables 1, 2, 3, and 4 where applicable.

#### 7 Sleeving conformance

Conformance to the requirements of this specification shall normally be based on the results from typical sizes:

- Type A: Recovered ID 25 mm to 30 mm
- Type B: Recovered ID 25 mm to 40 mm

Table 1 – Property requirements

Property	IEC 60684-2: 2011 clause or subclause	Units	Max. or min.	Requirements	Remarks
Dimensions Internal diameter Wall thickness Concentricity – expanded – recovered	3 3.1.2 3.3.2 3.3.3	mm mm %	Min. Min.	To be agreed between the purchaser and the supplier 60 85	
Heat shock Tensile strength Elongation at break	6 19. <del>1</del> 2 and 19. <del>2</del> 3 19. <del>1</del> 2 and 19. <del>2</del> 3	MPa %	Min. Min.	5 200	Heat at 150 °C ± 5 K  Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumbbell samples cut from the sleeving
Longitudinal change	9	%	Max.	-10 +5	
Bending at low temperature				No cracking shall be visible.  A constant of the constant of t	Test at -40 °C  For strips, the mandrel shall be between 20 times and 22 times the wall thickness. Full section sleeving is tested unfilled and the mandrel shall be between 20 times and 22 times the outer diameter.
Dimensional stability on storage	16 alog/standards/ie	<u>IEC 60</u> c/20782c	<u>684-3-283</u> ld8-efbb-4	The dimensions shall remain as agreed	See Clause 1 8bb/jec-60684-3-28
Tensile strength Elongation at break	19.42 and 19.23 19.42 and 19.23	MPa %	Min. Min.	8 400	Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumbbell samples cut from the sleeving
Secant modulus at 2 % elongation	19.45	MPa	Max.	160	
Dielectric strength	21	kV/mm	Min.	See Table 2.	
Breakdown voltage	21.2	kV/mm	Min.	See Table 2	
Volume resistivity at room temperature	23 23. <b>4</b> 5.2	Ω·m	Min.	10 <sup>11</sup>	

https://s

-2019

Property	IEC 60684-2: 2011 clause or subclause	Units	Max. or min.	Requirements	Remarks
Flame propagation	26 Method C	s mm	Max. Max.	60 100	Burning includes flaming and glowing
Corrosion resistance Elongation	32 19. <mark>4</mark> 2 and 19. <mark>2</mark> 3	%	Min.	No chemical interaction	Heat at 150 °C ± 3 K  Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumbbell samples cut from the sleeving
Resistance to selected fluids Tensile strength Elongation at break	36 19.42 and 19.23 19.42 and 19.23	MPa %	Min. Min.	5 200	Use the fluids and test temperatures specified in Table 3  Immersion (24 ± 1) h  Use a jaw separation rate of 100 mm/min. For internal diameters
		Teh S //sta	Stano ndan	lards ds.iteh.ai	< 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumb- bell samples cut from the sleeving
Heat ageing Tensile strength Elongation at break standards.iteh.ai/eat	39 19.42 and 19.23 19.42 and 19.23 alog/standards/id	MPa % IEC 60 c/207826	Min. 684-3-283 d8-efbb-4	200 2019 9e7-a584-ad1ac75c3	Heat at 150 °C ± 3 K  Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm -28 and larger diameter sleeving, use dumbbell samples cut from
Long term ageing Elongation at break	50 19.2 and 19.3	%	Min.	150	The ageing temperature shall be 100 °C ± 3 K
					Use a jaw separation rate of 100 mm/min. For internal diameters < 6,5 mm, use sleeving samples for testing. On 6,5 mm and larger diameter sleeving, use dumbbell samples cut from the sleeving

https://st

Table 2 - Requirements for dielectric strength

Expanded wall thickness	Dielectric strength <sup>a</sup>			
mm	Min.			
	Expanded ID	Dielectric strength kV/mm		
All dimensions	Types A+B			
	All sizes	12		

NOTE Care should be taken on selection of sizes based on these values. Refer to the manufacturer for actual values on installed conditions.

The breakdown voltage shall be determined by the method described in 21 of IEC 60684-2. All values shall comply with the minimum value in this table.

The sleeving shall be tested in the expanded condition.

The rate of application of the voltage shall be 500 V/s.

Table 3 - Resistance to selected fluids

Test fluid	Fluids	Type Standard or symbol		Immersion temperature
No.	(httr	s.//standa	rds itch ai	°C ± 2 K
1	Insulating oil	Mineral based	IEC 60296	23
2	Cleaning fluid	Solvent	Isopropyl alcohol	23
3	-	Water	De-ionized	85

IEC 60684-3-283:2019

Other fluids and/or temperatures may be specified for customers with specific needs. These additional fluids and/or temperatures shall be applicable when incorporated into agreements between the supplier and the customer.

<sup>&</sup>lt;sup>a</sup> Measure the expanded wall thickness and calculate the electric strength by dividing the breakdown voltage by this value.