



Designation: **A995/A995M – 18a A995/A995M – 19**

Standard Specification for Castings, Austenitic-Ferritic (Duplex) Stainless Steel, for Pressure-Containing Parts¹

This standard is issued under the fixed designation A995/A995M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers austenitic-ferritic (duplex) stainless steel castings for valves, flanges, fittings, and other pressure-containing parts.

1.2 The duplex stainless steels offer a combination of enhanced mechanical properties and corrosion resistance when properly balanced in composition and properly heat treated. Ferrite levels are not specified, but these grades will develop a range of approximately 30 to 60 % ferrite with the balance austenite. It is the responsibility of the purchaser to determine which grade shall be furnished depending on design and service conditions, mechanical properties, and corrosion-resistant characteristics.

NOTE 1—Because of the possibility of precipitation of embrittling phases, the grades included in this specification are not recommended for service at temperatures above 600 °F [315 °C].

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[A488/A488M Practice for Steel Castings, Welding, Qualifications of Procedures and Personnel](#)

[A703/A703M Specification for Steel Castings, General Requirements, for Pressure-Containing Parts](#)

[E125 Reference Photographs for Magnetic Particle Indications on Ferrous Castings](#)

[E165/E165M Practice for Liquid Penetrant Testing for General Industry](#)

[E562 Test Method for Determining Volume Fraction by Systematic Manual Point Count](#)

[G48 Test Methods for Pitting and Crevice Corrosion Resistance of Stainless Steels and Related Alloys by Use of Ferric Chloride Solution](#)

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *duplex stainless steel*—an iron-chromium-nickel-molybdenum alloy that, when properly heat treated, consists of approximately 30 to 60 % ferrite with the balance austenite.

4. General Conditions for Delivery

4.1 Material furnished to this specification shall conform to the applicable requirements of Specification [A703/A703M](#), including the supplementary requirements that are indicated on the purchaser order. Failure to comply with the general requirements of Specification [A703/A703M](#) constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification [A703/A703M](#), this specification shall prevail.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved Sept. 1, 2018/March 1, 2019. Published October 2018/March 2019. Originally approved in 1998. Last previous edition approved in 2018 as [A995/A995M – 18](#)/[A995/A995M – 18a](#). DOI: [10.1520/A0995_A0995M-18A](#); [10.1520/A0995_A0995M-19](#).

² For referenced ASTM standards, visit the ASTM website, [www.astm.org](#), or contact ASTM Customer Service at [service@astm.org](#). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard



TABLE 1 Heat Treatment Requirements

Grade	Heat Treatment
1B	Heat to 1900 °F [1040 °C] minimum, hold for sufficient time to heat casting uniformly to temperature, quench in water or rapid cool by other means.
2A	Heat to 2050 °F [1120 °C] minimum, hold for sufficient time to heat casting uniformly to temperature, quench in water or rapid cool by other means.
3A	Heat to 1950 °F [1070 °C] minimum, hold for sufficient time to heat casting uniformly to temperature, quench in water or rapid cool by other means.
4A	Heat to 2050 °F [1120 °C] minimum for sufficient time to heat casting uniformly to temperature and water quench, or the casting may be furnace cooled to 1850 °F [1010 °C] minimum, hold for 15 min minimum and then water quench. A rapid cool by other means may be employed in lieu of water quench.
5A	Heat to 2050 °F [1120 °C] minimum, hold for sufficient time to heat casting to temperature, furnace cool to 1910 °F [1045 °C] minimum, quench in water or rapid cool by other means.
6A	Heat to 2010 °F [1100 °C] minimum, hold for sufficient time to heat casting uniformly to temperature, quench in water or rapid cool by other means, or the casting may be furnace cooled to a temperature no lower than 1925 °F [1050 °C], hold for 15 min minimum, and then quench in water or rapid cool by other means.
7A	Heat to 2065 °F [1130 °C] minimum, hold for sufficient time to heat casting to temperature, furnace cool to 1940 °F [1060 °C] minimum, quench in water or rapid cool by other means.

5. Ordering Information

5.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Such requirements may include, but are not limited to, the following:

5.1.1 A description of the casting by pattern number or drawing (dimensional tolerances shall be included on the casting drawing),

5.1.2 Quantity (weight and number of castings),

5.1.3 Specification designation and date of issue,

5.1.4 Grade of steel,

5.1.5 Supplementary requirements including acceptance criteria, and

5.1.6 Additional requirements.

6. Process

6.1 The steel shall be made by the electric furnace process with or without separate refining.

7. Heat Treatment

7.1 All castings shall be heat treated in accordance with **Table 1**.

8. Chemical Composition

8.1 The steel shall conform to the requirements as to chemical composition prescribed in **Table 2**.

9. Tensile Properties

9.1 One tension test shall be made from each heat and shall conform to the requirements as to tensile properties prescribed in **Table 3**.

10. Quality

10.1 When additional inspection is desired, Supplementary Requirements S5, S6, and S10 may be ordered.

11. Repair by Welding

11.1 Repairs shall be made using procedures and welders qualified under Practice **A488/A488M**.

11.2 The composition of the deposited weld metal may be similar to that of the casting or may be suitably alloyed to achieve the desired corrosion resistance and mechanical properties.

11.3 Weld repairs shall be subject to the same quality standards as used to inspect the castings.



TABLE 2 Chemical Requirements

2A3A4A5A4

Grade	1B							
	Type	25Cr-5Ni- Mo-Cu-N	24Cr- 10Ni- Mo-N	25Cr- 5Ni- Mo-N	22Cr- 5Ni- Mo-N	25Cr-7Ni- Mo-N	25Cr-7Ni- Mo-N	27Cr-7Ni- Mo-W-N
UNS	J93372	J93345	J93371	J92205	J93404	J93380	J93379	
ACI	GD4MCuNCE8MN		GD6MN	GD3MN	GE3MN	GD3MWCuN	GD3MWN	
Composition:								
Carbon, max	0.040	0.080	0.060	0.030	0.030	0.030	0.030	
Manganese, max	1.00	1.00	1.00	1.50	1.50	1.00	1.00–3.00	
Silicon, max	1.00	1.50	1.00	1.00	1.00	1.00	1.00	
Phosphorus, max	0.040	0.040	0.040	0.040	0.040	0.030	0.030	
Sulfur, max	0.040	0.040	0.040	0.020	0.040	0.025	0.020	
Chromium	24.5–26.5	22.5–25.5	24.0–27.0	21.0–23.5	24.0–26.0	24.0–26.0	26.0–28.0	
Nickel	4.7–6.0	8.0–11.0	4.0–6.0	4.5–6.5	6.0–8.0	6.5–8.5	6.0–8.0	
Molybdenum	1.70–2.30	3.0–4.5	1.75–2.50	2.5–3.5	4.0–5.0	3.0–4.0	2.0–3.5	
Copper	2.7–3.3	1.00, max	...	0.50–1.00	1.00 max	
Tungsten	0.50–1.00	3.0–4.0	
Nitrogen	0.10–0.25	0.10–0.30	0.15–0.25	0.10–0.30	0.10–0.30	0.20–0.30	0.30–0.40	
Boron	0.0010–0.0100	
Barium	0.0002–0.0100	
Ce + La	0.005–0.030	

TABLE 2 Chemical Requirements^{A,B}

Material Grade	Element, %												
	Type UNS	Carbon	Manganese	Phosphorus	Sulfur	Silicon	Chromium	Nickel	Molybdenum	Nitrogen	Copper	Tungsten	Other
CD4MCuN (1B) 25Cr-5Ni-Mo- Cu-N J93372		0.040	1.00	0.040	0.040	1.00	24.5–26.5	4.7–6.0	1.70–2.30	0.10–0.25	2.7–3.3
CE8MN (2A) 24Cr-10Ni-Mo-N J93345		0.080	1.00	0.040	0.040	1.50	22.5–25.5	8.0–11.0	3.0–4.5	0.10–0.30
CD6MN (3A) 25Cr-5Ni-Mo-N J93371		0.060	1.00	0.040	0.040	1.00	24.0–27.0	4.0–6.0	1.75–2.50	0.15–0.25
CD3MN (4A) 22Cr-5Ni-Mo-N J92205		0.030	1.50	0.040	0.040	1.00	21.0–23.5	4.5–6.5	2.5–3.5	0.10–0.30	1.00
GE3MN (5A) ^C 25Cr-7Ni-Mo-N J93404		0.030	1.50	0.040	0.040	1.00	24.0–26.0	6.0–8.0	4.0–5.0	0.10–0.30
CD3MWCuN (6A) ^D 25Cr-7Ni-Mo-N J93380		0.030	1.00	0.030	0.025	1.00	24.0–26.0	6.5–8.5	3.0–4.0	0.20–0.30	0.50–1.00	0.50–1.00	...
CD3MWN (7A) ^E 27Cr-7Ni-Mo- W-N J93379		0.030	1.00–3.00	0.030	0.020	1.00	26.0–28.0	6.0–8.0	2.0–3.5	0.30–0.40	1.00	3.0–4.0	B: 0.0010–0.0100 Ba: 0.0002–0.0100 Ce + La: 0.005–0.030

^A All values are maximums, except where a range is provided.^B Where ellipses (...) appear in this table, there is no requirement, and the element need not be analyzed for or reported.^C % Cr + 3.3 % Mo + 16 % N ≥ 40.^D % Cr + 3.3 (% Mo + 0.5 % W) + 16 % N ≥ 45.40.^E % Cr + 3.3 (% Mo + 0.5 % W) + 16 % N ≥ 45.