



Designation: A949/A949M – 01 (Reapproved 2019)

# Standard Specification for Spray-Formed Seamless Ferritic/Austenitic Stainless Steel Pipe<sup>1</sup>

This standard is issued under the fixed designation A949/A949M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers spray-formed seamless ferritic/austenitic stainless steel pipe intended for general corrosive service, with particular emphasis on resistance to stress corrosion cracking. These steels are susceptible to embrittlement if used for prolonged periods at elevated temperatures.

1.2 Optional supplementary requirements are provided for pipe where a greater degree of testing is desired. These supplementary requirements call for additional tests to be made and when desired, one or more of these may be specified in the order.

1.3 **Appendix X1** of this specification lists the dimensions of seamless stainless steel pipe as shown in ANSI B 36.19. Pipe having other dimensions may be furnished provided such pipe complies with all other requirements of this specification.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4.1 Within the text, the SI units are shown in brackets.

1.4.2 The inch-pound units shall apply unless the “M” designation of this specification is specified in the order.

NOTE 1—The dimensionless designator NPS (nominal pipe size) has been substituted in this standard for such traditional terms as “nominal diameter,” “size,” and “nominal size.”

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.10 on Stainless and Alloy Steel Tubular Products.

Current edition approved March 1, 2019. Published March 2019. Originally approved in 1995. Last previous edition approved in 2014 as A949/A949M – 01 (2014). DOI: 10.1520/A0949\_A0949M-01R19.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

A450/A450M Specification for General Requirements for Carbon and Low Alloy Steel Tubes

A941 Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys

A999/A999M Specification for General Requirements for Alloy and Stainless Steel Pipe

E381 Method of Macroetch Testing Steel Bars, Billets, Blooms, and Forgings

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

### 2.2 ANSI/ASME Standards:

B 1.20.1 Pipe Threads, General Purpose<sup>3</sup>

B 36.10M-1995 Welded and Seamless Wrought Steel Pipe<sup>3</sup>

B 36.19 Stainless Steel Pipe

### 2.3 Other Standard:

SAE J1086 Practice for Numbering Metals and Alloys (UNS)<sup>4</sup>

## 3. Terminology

### 3.1 Definitions:

3.1.1 For definitions of terms used in this specification, refer to Terminology A941.

### 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *spray-formed*—denotes the fabrication of different shapes of a metallic material by deposition of a spray, consisting of droplets, solid particles, and particles that are partially solid, onto a moving substrate.

3.2.1.1 *Discussion*—The spray is produced by gas atomization of the liquid metal or alloy. On impingement with the substrate, the species of the spray consolidate and solidify completely to produce a product that is essentially free of porosity. The metallurgical characteristics of the spray-formed

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

<sup>4</sup> Available from SAE International (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, http://www.sae.org.

product are controlled primarily by the thermal condition of the spray, and that of the surface of the metallic deposit formed on the substrate.

#### 4. Ordering Information

4.1 Orders for material under this specification should include the following, as required, to describe the desired material adequately:

- 4.1.1 Quantity (feet, metres, or number of lengths),
- 4.1.2 Name of material (ferritic/austenitic steel pipe),
- 4.1.3 Grade (**Table 1**),
- 4.1.4 Size (NPS designator or outside diameter and schedule number of average wall thickness, or other),
- 4.1.5 Length (specific or random) (**Section 10**),
- 4.1.6 End finish (section on Ends of Specification **A999/A999M**),
- 4.1.7 Optional requirements (**Section 9**), Supplementary Requirements S1 to S4,
- 4.1.8 Test report required (section on Certification of Specification **A999/A999M**),
- 4.1.9 Specification designation, and
- 4.1.10 Special requirements or exceptions to the specification.

#### 5. General Requirements

5.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification **A999/A999M** unless otherwise provided herein.

#### 6. Materials and Manufacture

6.1 *Melting*—The steel shall be made by the electric-furnace process or other primary processes approved by the purchaser.

##### 6.2 Pipe Manufacture:

6.2.1 The pipe shall be made by the spray forming process using the melt from the primary melting as noted in **7.1**.

6.2.2 The pipe shall be made by spraying the melt on to a thin-walled collector tube. The as spray formed tube shall be machined on both the inner and outer surfaces. The remaining metal shall be homogeneous, sound, and meet the requirements of **Section 11**.

6.2.3 Unless specified by the purchaser, pipe may be furnished as spray formed or as spray-formed and cold-finished.

6.2.4 All pipe shall be furnished in the heat-treated condition as shown in **Table 1**.

6.2.5 All pipe shall be furnished in the descaled condition and be free of contaminating iron particles. Pickling, blasting or surface finishing is not mandatory when pipe is bright annealed. The purchaser may request that a passivating treatment be applied.

#### 7. Chemical Composition

7.1 The steel shall conform to the chemical requirements as prescribed in **Table 2**.

#### 8. Product Analysis

8.1 At the request of the purchaser, an analysis of two pipes from each lot shall be made by the manufacturer. A lot of pipe shall consist of the following number of lengths of the same size and wall thickness from any one heat of stainless steel:

| NPS Designator | Lengths of Pipe in Lot  |
|----------------|-------------------------|
| Under 2        | 400 or fraction thereof |
| 2 to 5, incl   | 200 or fraction thereof |
| 6 and over     | 100 or fraction thereof |

8.2 The results of these analyses shall be reported to the purchaser or the purchaser's representative, and shall conform to the requirements specified in **Section 5**.

8.3 If the analysis of one of the tests specified in **8.1** does not conform to the requirements specified in **Section 5**, an analysis of each pipe from the same heat or lot may be made, and all pipes conforming to the requirements shall be accepted.

#### 9. Tensile and Hardness Properties

9.1 The material shall conform to the tensile and hardness properties prescribed in **Table 3**.

#### 10. Lengths

10.1 Pipe lengths shall be in accordance with the following regular practice:

10.1.1 Unless otherwise agreed upon, all sizes from NPS ½ to and including NPS 8 are available in a length up to 24 ft (**Note 2**) with the permissible range of 15 to 24 ft (**Note 2**). Short lengths are acceptable and the number and minimum length shall be agreed upon between the manufacturer and the purchaser.

**NOTE 2**—This value applies when the inch-pound designation of this specification is the basis of purchase. When the "M" designation of this specification is the basis of purchase, the corresponding metric value(s) shall be agreed upon between the manufacturer and the purchaser.

10.1.2 If definite cut lengths are desired, the lengths required shall be specified in the order. No pipe shall be less than the specified length and no more than ¼ in. [6 mm] over it.

#### 11. Workmanship, Finish, and Appearance

11.1 The finished pipes shall be reasonably straight and shall have a workmanlike finish. Imperfections may be removed by grinding, provided the wall thicknesses are not decreased to less than that permitted, in the Permissible Variations in Wall Thickness Section of Specification **A999/A999M**.

**TABLE 1 Heat Treatment**

| UNS Designation | Temperature               | Quench                        |
|-----------------|---------------------------|-------------------------------|
| S31803          | 1870–2010°F [1020–1100°C] | rapid cooling in air or water |
| S31500          | 1800–1900°F [980–1040°C]  | rapid cooling in air or water |
| S31200          | 1920–2010°F [1050–1100°C] | rapid cooling in water        |
| S32550          | 1900°F [1040°C] min       | rapid cooling in air or water |
| S31260          | 1870–2010°F [1020–1100°C] | rapid cooling in water        |
| S32304          | 1700–1920°F [925–1050°C]  | rapid cooling in air or water |
| S32750          | 1880–2060°F [1025–1125°C] | rapid cooling in air or water |
| S32900          | 1700–1750°F [925–955°C]   | rapid cooling in air or water |
| S32950          | 1820–1880°F [995–1025°C]  | air cool                      |