



Designation: B887 – 12 (Reapproved 2019)

Standard Test Method for Determination of Coercivity (H_{cs}) of Cemented Carbides¹

This standard is issued under the fixed designation B887; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of magnetization coercivity (H_{cs}) of cemented carbide materials and products using coercive force instrumentation. It is patterned after ISO 3326.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[A340 Terminology of Symbols and Definitions Relating to Magnetic Testing](#)

[B243 Terminology of Powder Metallurgy](#)

[E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods](#)

[E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method](#)

2.2 *ISO Standard:*³

[ISO 3326 Hardmetals - Determination of \(the Magnetization\) Coercivity](#)

¹ This test method is under the jurisdiction of ASTM Committee B09 on Metal Powders and Metal Powder Products and is the direct responsibility of Subcommittee B09.06 on Cemented Carbides.

Current edition approved April 1, 2019. Published April 2019. Originally approved in 1998. Last previous edition approved in 2012 as B887 – 12. DOI: 10.1520/B0887-12R19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

3. Terminology

3.1 *Definitions:*

3.1.1 For definition of terms used in this procedure refer to Terminology [A340](#) and Terminology [B243](#).

3.1.2 *dc*—direct current.

4. Summary of Test Method

4.1 A test sample is positioned in the dc magnetic field of the test apparatus and magnetized to technical saturation. The magnetic field polarity is then reversed and the test sample is demagnetized by increasing the energy of the reversed magnetic field until the test sample reaches zero magnetism. The coercive force (H_c) is the magnetizing force required to return the saturated magnetic induction to zero.

5. Significance and Use

5.1 Measurement of coercivity provides a relative comparison of carbide grain size, binder content, and possibly carbon deficiency for a given graded carbide material or product, and may be employed as a non-destructive measurement indicating deviation from a specified norm.

5.2 This test method allows the non-destructive estimate of average carbide grain size in sintered cemented carbide hardmetals. It is appropriate for a wide range of compositions and tungsten carbide (WC) WC grain sizes, and can be used for acceptance of material or product to specification.

6. Interferences

6.1 H_{cs} measurement is a non-destructive “bulk” measurement that is averaged over the specimen volume. Bi-modal grain size distributions will give approximately the same H_c value as would be obtained from a normal grain size distribution about the same mean value.

6.2 Large test specimens must be sized to fit within the magnetic field coil spacing available for the apparatus employed.

6.3 Small test specimens may be immeasurable if their size prohibits detection by the magnetic field coils for the apparatus employed.

6.4 Specimen shape, that is, symmetry and aspect ratio, influence H_c measurement values and repeatability of results. Test specimens should be positioned with their long axis in the