

## **IEC TS 61044**

Edition 1.0 2021-08

## TECHNICAL SPECIFICATION

# Opportunity charging of lead-acid traction batteries VIEW (standards.iteh.ai)

IEC TS 61044:2021 https://standards.iteh.ai/catalog/standards/sist/351c9c5b-8c7a-4ee7-a51b-5b2ec8cf57bb/iec-ts-61044-2021





#### THIS PUBLICATION IS COPYRIGHT PROTECTED Copyright © 2021 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

**IEC Central Office** 3, rue de Varembé CH-1211 Geneva 20 Switzerland

Tel.: +41 22 919 02 11 info@iec.ch www.iec.ch

#### About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

#### About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

#### IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email. 

IEC Customer Service Centre - webstore iec ch/csc If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch. IEC TS 61044:2021

#### IEC online collection - oc.iec.ch

Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

#### Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 18 additional languages. Also known as the International Electrotechnical Vocabulary



https://standards.iteh.ai/catalog/standards/sist/351c9c5b-8c7a-4ee7-a51b

5b2ec8cf57bb/iec-ts-61044-2021



## **IEC TS 61044**

Edition 1.0 2021-08

## TECHNICAL SPECIFICATION

## Opportunity charging of lead-acid traction batteries VIEW (standards.iteh.ai)

IEC TS 61044:2021 https://standards.iteh.ai/catalog/standards/sist/351c9c5b-8c7a-4ee7-a51b-5b2ec8cf57bb/iec-ts-61044-2021

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ICS 29.220.20; 29.220.99

ISBN 978-2-8322-1006-7

Warning! Make sure that you obtained this publication from an authorized distributor.

#### CONTENTS

3					
5					
6					
3					
5					
7					
3					
3					
3					
3					
)					
)					
)					
Bibliography12					

Figure 1 -	<ul> <li>Examples</li> </ul>	of discharge	and cha	rge profiles	of vented	lead-acid	batteries	10
		of discharge a						
batteries		iTeh S	T.A.NI	JARD.	DREV	/		

## (standards.iteh.ai)

IEC TS 61044:2021 https://standards.iteh.ai/catalog/standards/sist/351c9c5b-8c7a-4ee7-a51b-5b2ec8cf57bb/iec-ts-61044-2021

#### INTERNATIONAL ELECTROTECHNICAL COMMISSION

#### OPPORTUNITY CHARGING OF LEAD-ACID TRACTION BATTERIES

#### FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies. Stat/351c9c5b-8c7a-4ce7-a51b-
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

IEC TS 61044 has been prepared by IEC technical committee 21: Secondary cells and batteries. It is a Technical Specification.

This first edition cancels and replaces the second edition of IEC TR 61044 published in 2002. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) the recommended depth of discharge for opportunity charging has been adjusted;
- b) a distinction is made between valve regulated lead-acid batteries (VRLA) and vented leadacid batteries.

The text of this Technical Specification is based on the following documents:

Draft	Report on voting
21/1081/DTS	21/1088/RVDTS

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this Technical Specification is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members\_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/standardsdev/publications.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed, •
- withdrawn, •
- replaced by a revised edition, or **I CANDARD PREVIEW**
- amended.

IEC TS 61044:2021 https://standards.iteh.ai/catalog/standards/sist/351c9c5b-8c7a-4ee7-a51b-5b2ec8cf57bb/iec-ts-61044-2021

(standards.iteh.ai)

#### INTRODUCTION

Lead-acid traction batteries find a widespread application in industrial transportation vehicles because of their particular properties of providing a reliable power supply source with a very low environmental impact.

In such applications, both monitoring and power management by electronic means have made great strides not only on the discharge side of the energy balance but during charging as well.

This progress permits refuelling, i.e., charging of a lead-acid traction battery in a wellcontrolled manner during idle periods in the course of a working schedule.

As a result, the total capacity or ampere-hour output of the lead-acid battery increases per working day substantially beyond the manufacturer's maximum recommended value.

However, such opportunity charging will provide improved capital efficiency only if adequate precautions are taken to prevent premature deterioration of the state of the lead-acid traction battery caused by such a practice.

This document is intended to present requirements, derived from the field experience of battery manufacturers in general and from opportunity charging of lead-acid traction batteries in particular, with the aim of preventing detrimental effects on batteries and industrial equipment.

### iTeh STANDARD PREVIEW (standards.iteh.ai)

IEC TS 61044:2021 https://standards.iteh.ai/catalog/standards/sist/351c9c5b-8c7a-4ee7-a51b-5b2ec8cf57bb/iec-ts-61044-2021

#### OPPORTUNITY CHARGING OF LEAD-ACID TRACTION BATTERIES

#### 1 Scope

This document covers opportunity charging of lead-acid traction batteries, i.e., the use of idle time during a working period to increase the state of charge (SoC) so as to extend the daily working period of a lead-acid traction battery while at the same time avoiding an excessive depth of discharge.

This document specifies requirements for the use of opportunity charging of lead-acid traction batteries of vented and valve regulated types when the battery manufacturer has not provided alternative specific operating procedures.

This document is only applicable for lead-acid traction batteries of vented and valve regulated design for which the battery manufacturer has not provided specific operating procedures.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

#### IEC\_TS 61044:2021

IEC 62485-3:2014, Safety requirements for secondary batteries 4and battery installations – Part 3: Traction batteries 5b2ec8cf57bb/iec-ts-61044-2021

#### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at http://www.electropedia.org/
- ISO Online browsing platform: available at http://www.iso.org/obp

3.1

#### opportunity charging

use of periods of inactivity of a partially discharged battery to increase its state of charge

Note 1 to entry: Opportunity charging at a state of charge (SoC) of > 70 % is less effective and can result in a significant increase of battery temperature and water loss.

#### 3.2

#### regular charge

charge of a battery as specified by the manufacturer necessary to attain the state of maximum storage of electric energy

#### 3.3

#### self-compensating charger

device which supplies charge, monitors the state of charge, and terminates the charge of the battery when the correct amount of electric charge has been supplied

#### IEC TS 61044:2021 © IEC 2021

Note 1 to entry: The control logic of the self-compensating charger will prevent overcharging if a fully charged battery is connected to the charger.

#### 3.4

#### vented lead-acid battery

secondary battery in which cells have a cover provided with an opening through which products of electrolysis and evaporation are allowed to escape freely from the cell to the atmosphere

[SOURCE: IEC 60050-482:2004, 482-05-14, modified – the term "vented cell" has been replaced by "vented lead-acid battery" and the words "secondary cell having" have been replaced by "secondary battery in which cells have".]

#### 3.5

### valve regulated lead-acid battery VRLA

secondary battery in which cells are closed but have a valve which allows the escape of gas if the internal pressure exceeds a predetermined value

Note 1 to entry: The cell or battery cannot normally receive additions to the electrolyte.

[SOURCE: IEC 60050-482:2004, 482-05-15, modified – a hyphen has been added to the term.]

#### 3.6

### excessive discharge Teh STANDARD PREVIEW

discharge of a battery exceeding the maximum depth of discharge as declared by the manufacturer (standards.iteh.al)

Note 1 to entry: For purposes of this document the maximum depth of discharge is 80 % for vented lead-acid batteries and 60 % for valve regulated lead-acid batteries except when otherwise declared by the manufacturer.

#### 3.7 state of charge SoC

5b2ec8cf57bb/iec-ts-61044-2021

available capacity in a battery expressed as a percentage of a rated capacity

#### 4 Planning the implementation of opportunity charging

The following list items a) to c) shall be considered when planning to introduce opportunity charging.

- Indications that opportunity charging may be beneficial are:
  - a) when the maximum permissible physical size of the battery for the vehicle does not have enough capacity to complete the daily workload before a next complete recharge becomes necessary. This allows an undesirable physical change-out of the battery to be avoided.
  - b) when the operational requirements of the vehicle are such that it is impossible to predict when the battery will next be released for a complete recharge. This can occur for example in locations such as airports where 24 h per day working is a rule.
  - c) when a battery is close to the end of its operational life and the use of opportunity charging can be shown to maintain an acceptable performance of the vehicle.

An implementation of opportunity charging will result in an additional energy turnover in the battery beyond the 60 % or 80 % limit per cycle specified by the manufacturer. This change in operational mode is therefore to be cleared beforehand with the battery manufacturer as it is possible that this will have an impact on warranty terms and conditions.

NOTE 1 If the periods available for charging are of short duration and infrequent, then opportunity charging will be of little benefit.

NOTE 2 When opportunity charging enables the user to discharge substantially more than the recommended percentage of the rated capacity each day, the battery-life measured in years will be reduced as the battery-life measured in terms of cumulative ampere-hours discharged is approximately constant.

NOTE 3 Opportunity charging at a SoC > 70 % is less effective and can result in a significant increase of battery temperature, gassing, water loss or sudden failure of VRLA designs.

NOTE 4 Opportunity charging results in higher electrolyte working temperatures that accelerate battery ageing.

#### **5** Operational procedures

#### 5.1 General

The following information in 5.2 to 5.5 shall be considered when operational procedures are being established.

#### 5.2 Charging conditions

Self-compensating chargers are preferred when opportunity charging is carried out. A correctly sized battery and charger combination is essential for all batteries.

For opportunity charging of valve regulated lead-acid batteries it is essential that only chargers with a current-voltage-time characteristic in accordance with the battery manufacturer's recommendation are used.

In order to maximize the beneficial effects of opportunity charging, such an operation is preferably carried out only when the fully charged battery has been discharged by at least 30 % of its rated capacity. (standards.iteh.ai)

This limit is especially important when vented lead-acid batteries are charged with non-self-compensating chargers. Non-self-compensating chargers shall not be used for valve regulated lead-acid batteries. 5b2ec8ct57bb/jec-ts-61044-2021

For intensive energy throughput applications with expected high battery temperatures, opportunity charging shall be initiated only when at least 40 % of the rated capacity has been discharged from the fully charged battery.

An air agitation system of the electrolyte is highly recommended for vented lead-acid batteries in order to prevent acid stratification and to improve the efficiency of the opportunity charging.

Where a known duty cycle exists, a calculation of the energy balance or ampere-hour balance is recommended. The availability of adequate charging time and intervals for opportunity charging shall be verified beforehand.

#### 5.3 Regular charges

The frequency of a regular charge, whereby the battery is allowed to complete its charging cycle and thus prevent premature deterioration of the battery, is as follows:

- for standard vented lead-acid batteries and valve regulated lead-acid batteries, one regular charge every working day. It is possible that this will not be applicable for the scenarios described under Clause 4, list item b) and if that is the case a compromise solution is to be found in discussions with the battery manufacturer.
- for vented lead-acid batteries with air agitation system and especially with valve regulated traction batteries, an interval of up to 1 week between complete recharges may be feasible.