



Designation: D6686 – 01 (Reapproved 2019)

Standard Test Method for Evaluation of Tannin Stain Resistance of Coatings¹

This standard is issued under the fixed designation D6686; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method is an accelerated procedure to determine the effectiveness of latex coatings at preventing the migration of tannin stains from wood substrates.

1.2 The values in SI units are to be regarded as the standard. The values in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D1475 Test Method for Density of Liquid Coatings, Inks, and Related Products

D4585 Practice for Testing Water Resistance of Coatings Using Controlled Condensation

D5068 Practice for Preparation of Paint Brushes for Evaluation

3. Terminology

3.1 *Definitions:*

3.1.1 *tannin stain resistance, n*—the ability of a coating to prevent the migration of tannins or other wood-based chromospheres to the surface of a film.

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.42 on Architectural Coatings.

Current edition approved April 1, 2019. Published April 2019. Originally approved in 2001. Last previous edition approved in 2013 as D6686 – 01 (2013). DOI: 10.1520/D6686-01R19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Summary of Test Method

4.1 This test method utilizes a condensation test chamber to determine the tannin stain resistance of latex paints. The test paints are applied to substrates that contain tannin extractives and are placed on or in the test chamber. CIELAB L* and b* values as well as subjective ratings are recorded after exposure.

5. Significance and Use

5.1 Tannins and other chromophoric extractives are naturally occurring materials in wood and wood-based substrates. Tannins are prevalent to a high degree in cedar, redwood, oak, and to a lesser degree in white and yellow pine. Tannins are also present in varying amounts in wood composition products. These extractives are solubilized and darkened in color by aqueous coatings, resulting in unsightly yellow or brown discolorations. This test method is designed to show the relative ability of paints to prevent tannin bleed-through. Typically, cedar or redwood panels are used for this test.

6. Apparatus

6.1 *Test Chamber*, as described in Practice **D4585**.

6.2 *Test Substrate*, 15.2 by 121.9 cm (6 by 48 in.) substrate or of a size agreed upon by the purchaser and seller of the coating being tested.

6.3 *Paint Brush*, nylon/polyester brush of good quality.

6.4 *Spectrophotometer*.

6.5 *Electronic Balance*.

6.6 *Conditioned Room*, at 18 to 29.5 °C (65 to 85 °F) and 40 to 60 % relative humidity.

7. Reagents and Materials

7.1 *Wood Panels*—Such as cedar, redwood, oak, white pine, yellow pine, or other substrate as agreed upon between the purchaser and the seller of the coating being tested.

7.2 *Control Paint*—An agreed-upon paint of known tannin stain resistance.

7.3 *Test Paints*—Since there are no standard panels, photographs, or paints for this test method, an agreed-upon control paint (7.2) should be included as one of the test paints.