



Designation: D7072 – 04 (Reapproved 2019)

Standard Practice for Evaluating Accelerated Efflorescence of Latex Coatings¹

This standard is issued under the fixed designation D7072; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers the evaluation of the degree to which a latex paint resists the formation of efflorescence and alkali burnout on the exposed paint surface.

1.2 This practice is designed primarily to relate efflorescence originating in the substrate to the deposit appearing on the surface of latex paints. This practice relates chiefly to the painting of masonry-type substrates such as concrete block, brick, mortar, stucco, poured concrete, and similar materials.

1.3 The values in SI units are to be regarded as the standard. The values in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety, health, and environmental practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 ASTM Standards:²

D1475 Test Method for Density of Liquid Coatings, Inks, and Related Products

D1734 Practice for Making Cementitious Panels for Testing Coatings

D4585 Practice for Testing Water Resistance of Coatings Using Controlled Condensation

D5068 Practice for Preparation of Paint Brushes for Evaluation

¹ This practice is under the jurisdiction of Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.42 on Architectural Coatings.

Current edition approved on April 1, 2019. Published April 2019. Originally approved in 2004. Last previous edition approved in 2013 as D7072 – 04 (2013). DOI: 10.1520/D7072-04R19.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. Terminology (Specific to This Practice)

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *alkali burnout, n*—the premature fading or decomposition of paints that are sensitive to the high pH of the substrate. The high alkaline content of the substrate can alter the color.

3.1.2 *efflorescence, n*—the deposition of soluble salts on the exposed paint surface. Efflorescence is characterized by a light-colored, nonuniform, powdery incrustation which detracts from the paint film appearance. The discoloration occurs when soluble salts in the substrate or paint migrate to the surface by the leaching and evaporating action of the water carrier. The efflorescence originating within the substrate is that with which this method is concerned.

4. Summary of Practice

4.1 Panels known to have a level of salts capable of being easily and quickly transported to the paint surface are used. Since tinted paints show the efflorescence most clearly, all white paints should be tinted before application. The panel is placed face down over the surface of the test chamber which contains heated water, so that moisture condenses and remains on the painted surface of the panel for a period of 48 h. After drying at ambient conditions, the panels are rated for the degree of efflorescence which has formed.

5. Significance and Use

5.1 Latex paints are sometimes applied over substrates that contain a high level of water-soluble salts that results in efflorescence. This practice evaluates a coating's vulnerability to efflorescence.

6. Apparatus

6.1 *Condensation Test Chamber*—As described in Practice **D4585**.

6.2 *Test Substrate*—Fiber-cement siding³ or a substrate agreed upon by the purchaser and seller. The substrate size would depend on the number of test paints.

6.3 *White Portland Cement and Graded Standard Sand* (as described in Practice **D1734**).

³ Hardieplank, a registered trademark of James Hardie, was found to be acceptable but others may be used.