

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Plastic films for electrical purposes –
Part 3: Specifications for individual materials – Sheet 1: Biaxially oriented
polypropylene (PP) films for capacitors**

**Films plastiques à usages électriques –
Partie 3: Spécifications pour matériaux particuliers – Feuille 1: Films de
polypropylène biorienté (PP) pour condensateurs**



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2021 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC online collection - oc.iec.ch

Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 18 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Recherche de publications IEC -

webstore.iec.ch/advsearchform

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études, ...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: sales@iec.ch.

IEC online collection - oc.iec.ch

Découvrez notre puissant moteur de recherche et consultez gratuitement tous les aperçus des publications. Avec un abonnement, vous aurez toujours accès à un contenu à jour adapté à vos besoins.

Electropedia - www.electropedia.org

Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 000 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 16 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Plastic films for electrical purposes –
Part 3: Specifications for individual materials – Sheet 1: Biaxially oriented
polypropylene (PP) films for capacitors**

**Films plastiques à usages électriques –
Partie 3: Spécifications pour matériaux particuliers – Feuille 1: Films de
polypropylène biorienté (PP) pour condensateurs**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

ICS 29.035.20

ISBN 978-2-8322-1017-4

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions	6
4 Classification.....	6
5 Designation	7
6 General requirements	7
7 Dimensions	7
7.1 Thickness	7
7.2 Width	8
7.3 Length/diameter	8
8 Properties.....	8
8.1 Physical properties.....	8
8.2 Electric strength (DC test)	9
8.3 Electrical weak spots.....	9
8.4 Thermal endurance	10
8.5 Wetting tension (types 1b + 1c, 2b + 2c and 3b + 3c only).....	10
8.6 Liquid absorption.....	10
8.7 Compatibility with impregnants	10
8.8 Dissipation factor under impregnated conditions	10
8.9 Space factor	11
9 Roll characteristics	11
9.1 Windability	11
9.2 Joins.....	11
9.3 Roll width (overall width)	12
9.4 Core	12
9.5 Labelling	12
Bibliography	13
Table 1 – Physical properties	8
Table 2 – Electric strength (DC test) for types 1, 2 and 3	9
Table 3 – Electrical weak spots for types 1, 2 and 3.....	10
Table 4 – Maximum number of joins within a roll (types 1, 2 and 3).....	11

INTERNATIONAL ELECTROTECHNICAL COMMISSION

PLASTIC FILMS FOR ELECTRICAL PURPOSES –**Part 3: Specifications for individual materials –
Sheet 1: Biaxially oriented polypropylene (PP) films for capacitors****FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

IEC 60674-3-1 has been prepared by IEC technical committee 15: Solid electrical insulating materials.

This second edition cancels and replaces the first edition published in 1998 and Amendment 1:2011. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) this document has been completely revised editorially and technically and included in the IEC 60674 series of standards;
- b) the test methods have been updated to reflect today's state of the art.

The text of this International Standard is based on the following documents:

Draft	Report on voting
15/909/CDV	15/925/RVC

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/standardsdev/publications.

A list of all parts in the IEC 60674 series, published under the general title *Plastic films for electrical purposes*, can be found on the IEC website.

Future standards in this series will carry the new general title as cited above. Titles of existing standards in this series will be updated at the time of the next edition.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

[IEC 60674-3-1:2021](http://www.iec.ch)

<https://standards.iteh.ai/catalog/standards/sist/b4b3940e-a928-4215-bb3a-043bc0883407/iec-60674-3-1-2021>

INTRODUCTION

This standard is one of a series which deals with plastic films for electrical purposes. The series will consist of three parts:

Part 1: Definitions and general requirements (IEC 60674-1);

Part 2: Methods of test (IEC 60674-2);

Part 3: Specifications for individual materials (IEC 60674-3).

This standard contains one of the sheets comprising Part 3, as follows:

Sheet 1: Biaxially oriented (PP) polypropylene films for capacitors.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[IEC 60674-3-1:2021](https://standards.iteh.ai/catalog/standards/sist/b4b3940e-a928-4215-bb3a-043bc0883407/iec-60674-3-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/b4b3940e-a928-4215-bb3a-043bc0883407/iec-60674-3-1-2021>

PLASTIC FILMS FOR ELECTRICAL PURPOSES –

Part 3: Specifications for individual materials – Sheet 1: Biaxially oriented polypropylene (PP) films for capacitors

1 Scope

This sheet of IEC 60674-3 gives the requirements for biaxially oriented polypropylene film having a smooth or rough surface, corona treated when required for vacuum metallization. The films are for use as dielectric in capacitors.

Materials which conform to this specification meet established levels of performance. However, the selection of a material by a user for a specific application is based on the actual requirements necessary for adequate performance in that application and not based on this specification alone.

Safety warning: It is the responsibility of the user of the methods contained or referred to in this document to ensure that they are used in a safe manner.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

<https://standards.iteh.ai/catalog/standards/sist/b4b3940e-a928-4215-bb3a-043bc0883407/iec-60674-3-1-2021>

IEC 60674-1:1980, *Specification for plastic films for electrical purposes – Part 1: Definitions and general requirements*

IEC 60674-2:2016, *Specification for plastic films for electrical purposes – Part 2: Methods of test*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Classification

The polypropylene film shall be of the following types:

- Type 1: having smooth surfaces (space factor <5 %, see 8.9);
- Type 1a: not corona treated;
- Type 1b: one side pre-treated to facilitate the vacuum deposition of metal;
- Type 1c: both sides pre-treated;

- Type 2: having at least one rough surface (space factor ≥ 5 %, see 8.9);
- Type 2a: not corona treated;
- Type 2b: one side pre-treated to facilitate the vacuum deposition of metal;
- Type 2c: both sides pre-treated.
- Type 3: having high electric strength for thin film (film thickness $\leq 3,5$ μm);
- Type 3a: not corona treated;
- Type 3b: one side pre-treated to facilitate the vacuum deposition of metal;
- Type 3c: both sides pre-treated.

5 Designation

The plastic film shall be identified by the following designation:

Designation of the film – IEC 60674-3-1 – PP – type – thickness in micrometres – width in millimetres – length in metres.

EXAMPLE

Polypropylene film – IEC 60674-3-1 – PP – 1a – 6 – 100 – 3000.

6 General requirements

The materials shall be made essentially from isotactic type polypropylene homopolymer and shall conform to the requirements laid down in IEC 60674-1.

7 Dimensions

<https://standards.iteh.ai/catalog/standards/sist/b4b3940e-a928-4215-bb3a-043bc0883407/iec-60674-3-1-2021>

7.1 Thickness

The film thickness shall be measured in accordance with the requirements of 4.3.2 of IEC 60674-2:2016. This is in general the gravimetric thickness, but for type 2 distinction shall be made between thickness determined by weighing (t_g = gravimetric thickness) and thickness measured by micrometer method (t_b = bulking thickness).

Gravimetric thickness shall be measured in accordance with the requirements of 4.3.2 of IEC 60674-2:2016.

Bulking (micrometric) thickness shall be measured according to 4.2.3 of IEC 60674-2:2016.

There are no requirements for thickness in this document, but preferred gravimetric thicknesses are as follows:

- Type 1: 4,0 μm ; 5,0 μm ; 6,0 μm ; 7,0 μm ; 8,0 μm ; 10,0 μm ; 12,0 μm ; 15,0 μm ; 18,0 μm ; 20,0 μm and 25 μm .
- Type 2: 7,4 μm ; 9,0 μm ; 10,1; 11,0 μm ; 12,0 μm ; 12,7 μm ; 13,6 μm ; 14,4 μm ; 15,2 μm ; 16,2 μm and 17,8 μm .
- Type 3: 2,5 μm ; 2,8 μm ; 3,0 μm and 3,5 μm .

The thickness tolerance shall comply with the requirements of 4.1 of IEC 60674-1:1980 unless otherwise specified.

7.2 Width

The film width shall be measured in accordance with the requirements of Clause 6 of IEC 60674-2:2016.

Preferred widths cannot be given on account of the great variety of applications and different requirements throughout the capacitor industry.

The tolerance on the width shall comply with the requirements of 4.2 of IEC 60674-1:1980.

7.3 Length/diameter

There are no requirements in this document for length or diameters of rolls. These should be subject to purchase contract.

8 Properties

8.1 Physical properties

See Table 1.

Table 1 – Physical properties

Property	Test method	Unit	Requirement	Remarks
Density	ISO 1183-2:2019	kg/dm ³ (g/cm ³)	0.91 ± 0.01	This method is only suitable for film thickness > 12 µm. The recommended mixture is methanol/ethylene glycol
Melting point	ISO 11357-3:2018	°C	165 to 175	DSC method
Tensile strength (either direction)	IEC 60674-2:2016, Clause 12	MPa	Minimum Type 1: 120 Type 2: 90 Type 3: 120	Specimen width (15 ± 3) mm, rate of extension (100 ± 2) mm/min, reference lines with the initial grip separation (100 ± 2) mm apart
Elongation at break (either direction)		%	Minimum Type 1: 40 Type 2: 30 Type 3: 30	
Surface resistivity	IEC 60674-2:2016, Clause 16 ^a	Ω	≥ 10 ¹⁴	The test voltages are 100 V for thicknesses > 10 µm and 10 V for thicknesses ≤ 10 µm
Volume resistivity	IEC 60674-2:2016, Clause 17 ^a	Ωm	> 10 ¹⁵	
Dissipation factor at 23 °C and 48 Hz – 62 Hz: 1 kHz:	IEC 60674-2:2016, 18.2 or 18.3		≤ 3 × 10 ⁻⁴ ≤ 3 × 10 ⁻⁴	Use evaporated metal electrodes or non-contacting electrodes (18.2.4 or 18.2.5)
Permittivity	IEC 60674-2:2016, 18.2		2,2 ± 0,1	Use evaporated metal electrodes or non-contacting electrodes (18.2.4 or 18.2.5)
Dimensional change for shrinkage: – Machine direction – Transverse direction	IEC 60674-2:2016, Clause 25	% %		Shrinkage shall be agreed between supplier and purchaser
NOTE Although the potential effects of certain properties such as crystallinity, orientation and isotactic/ atactic content on the performance of the film are recognized, no recommendations regarding the determination of these parameters have been made, particularly as no suitable test methods are available in IEC 60674-2.				
^a Measurement conditions: (23 ± 2) °C and (50 ± 5) % relative humidity after at least 24 h exposure.				

8.2 Electric strength (DC test)

Electric strength shall be measured according to 20.2 of IEC 60674-2:2016. The central value shall be not less than the value given in Table 2. The winding tension shall $2,5 \text{ N/mm}^2 \pm 0,5 \text{ N/mm}^2$.

Table 2 – Electric strength (DC test) for types 1, 2 and 3

Nominal film thickness μm	Type	Electric strength (central value) $\text{V}/\mu\text{m}$		Not more than 1 of 21 results shall be below $\text{V}/\mu\text{m}$	
		23 °C	105 °C	23 °C	105 °C
2,5	3	250	125	150	75
2,8		250	125	150	75
3,0		250	125	150	75
3,5		250	125	150	75
4	1 and 2	120	-	40	-
5		150	-	60	-
6		190	-	80	-
7 and 7,4		230	-	100	-
8		250	-	120	-
9		270	-	145	-
10 and 10,1		290	-	165	-
11		300	-	175	-
12		310	-	185	-
12,7		315	-	195	-
>12,7 to 25		320	-	200	-

8.3 Electrical weak spots

Electrical weak spots shall be measured according to 21.4 of IEC 60674-2:2016.

The number of faults counted shall not exceed the numbers given in Table 3. A minimum surface area of 5 m^2 is to be tested.

Compliance with any one of two method criteria shall constitute compliance with this document.

Table 3 – Electrical weak spots for types 1, 2 and 3

Nominal thickness μm	Type	Method C1 (Aluminium foil electrodes) 21.4.2.2 of IEC 60674-2:2016		Method C3 (Metal electrode with air gap) 21.4.2.4 of IEC 60674-2:2016	
		Fault count/ m^2	Test voltage $\text{V}/\mu\text{m}$	Fault count/ m^2	Test voltage $\text{V}/\mu\text{m}$
2,5 2,8 3,0 3,5	3	2,6	250	2,0	200
4 5 6 7 and 7,4 8 9 10 and 10,1 11 ≥ 12	1 and 2	2,6 2,3 1,8 1,7 1,5 1,3 1,2 1,1 1,0	150	1,0 0,5	350 300 300 250 250 230 230 220 200

8.4 Thermal endurance

There is no requirement in this document for thermal endurance.

8.5 Wetting tension (types 1b + 1c, 2b + 2c and 3b + 3c only)

When tested in accordance with Clause 11 of IEC 60674-2:2016, the wetting tension of the tested surface shall not be less than $35 \text{ mN}\cdot\text{m}^{-1}$.

8.6 Liquid absorption

For satisfactory construction of impregnated capacitors, the absorption of the impregnant by the film may need to be controlled within certain limits. If required, the method of measurement, the time and the temperature used and the absorption limits shall be agreed between supplier and purchaser¹.

The preferred method shall conform with Clause 33 of IEC 60674-2:2016.

8.7 Compatibility with impregnants

The compatibility of the film with selected dielectric fluids shall be determined using a method agreed upon between the supplier and the purchaser. This method may, for example, be based on swelling or solubility of the film in the fluid, or on contamination of the fluid or the film¹.

8.8 Dissipation factor under impregnated conditions

The impregnants and the methods of testing used throughout the capacitor industry vary widely and many of the materials and procedures are proprietary. Where the dissipation factor of the

¹ In view of the wide variety of impregnants available today and under development for capacitor application, no specific tests and/or limits can be given in this document for liquid absorption (8.6), compatibility with dielectric fluids (8.7) and dissipation factor under impregnated conditions (8.8).